MILITARY SPECIFICATION

TAPE, TEXTILE, NYLON, PARACHUTE CONSTRUCTION

This amendment forms a part of Military Specification MIL-T-6134C, dated 23 February 1971, and is approved for use by all Departments and Agencies of the Department of Defense.

Page 1

1.1: Delete "two types" and substitute "three types."

1.2: Type I, delete "525 pounds breaking strength"
Type II, delete "300 pounds breaking strength"
Add "Type III"

Page 2

3.2.1: Last sentence, delete "442° Centigrade (C)" and substitute "472" Fahrenheit (F)."

3.2.2: First sentence, delete "both" and substitute "all."

3.2.3: Delete a and b and substitute:

"a. Type I - spun nylon of 20/4 or 10/2 yarn number ±5 percent (cotton system), spun polyester of 12/4 yarn number ±5 percent (cotton system), or 985 denier bulked nylon. The filling yarn breaking strength shall be a minimum of 4.75 pounds when tested as specified in 4.3.1.

"b. Type II - Spun nylon or polyester of 60/2 or 30/1 yarn number ±5 percent (cotton system). The filling yarn breaking strength shall be a minimum of 0.90 pounds when tested as specified in 4.3.1.

"c. Type III - Nylon filament 840/140 denier. The filling yarn breaking strength shall be a minimum of 4.75 pounds when tested as specified in 4.3.1.

3.2.4: At end of last sentence add "in the 60/1 single yarn."

3.3a: First sentence, delete "Type I - Woven" and substitute "Type I and III Woven."

3.5 Delete first sentence and substitute: "Unless otherwise specified by the processing activity, the color of the tapes shall be natural except for the identification yarn for type I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:38Z
Check the source to verify that this is the current version before use.

Tables I and II: Delete and substitute:

TABLE I. Construction and Physical Properties

Property	Type I	Type II	Type III
Width, Inch ±1/16	1	1	1
Yarn ply:			
Warp	Single	Single	Single
Filling	2 or 4	Single or 2	Continuous Filament
Yarns (Minimum):			
Warp (total)	206	104	206
Filling (per inch)	48	58	44
Weight, oz/linear yard (maximum)	0.40	0.145	0.40
Thickness, inch	0.025-0.045	0.010-0.030	0.025-0.045
Breaking strength, pounds, minimum	525	300	525
Elongation, percent, minimum	16	14	16

TABLE II. Testing of Components

Characteristic	Requirement Reference	Test Method
Warp Yarn:		
Nylon Identification	3.2.1	1/
Nylon Melting Point	3.2.1	1534 1/
Luster	3.2.2	Visual 1/
Denier	3.2.2	4021.1
Tenacity	3.2.2	4001.1 1/
Identification yarn, Type I	3.5.1	Visual 1/
Turns per Inch	3.2.4	4052
Filling Yarn:		
Yarn Identification	3.2.1	1/
Nylon Melting Point	3.2.1	1534 1/
Yarn Number	3.2.3	4021 1/
Breaking Strength	3.2.3	4100.1 2/
Ply	3.2.3	Visual 3/
Turns per Inch	3.2.4	4054.1
Colorfastness to Crocking	3.5.1.1	5651 1/

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:38Z
Check the source to verify that this is the current version before use.

Concluding Material: Delete and substitute:

"Custodians:
Army - GL
Navy - AS
Air Force - 99

Review Activity:
DSPC - CT"

Preparing Activity
Air Force - 99

Custodians:
Army - GL
Navy - AS
Air Force - 99

Review Activity:
DSPC - CT

Preparing Activity:
Air Force - 99

Project No. 8315-0250

Source: https://assist.dla.mil -- Downloaded: 202610-17T06:38Z
Check the source to verify that this is the currentversion before use.