ZZ-C-450a
October 18, 1962

SUPERSEDING
Fed. Spec. ZZ-C-450
June 19, 1957

FEDERAL SPECIFICATION

CLOTH, COATED (RUBBER AND PLASTIC) AND PLASTIC SHEETING FOR HOSPITAL USE

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. The coated cloth and plastic sheeting covered by this specification is intended for the protection of mattresses on hospital beds.

1.2 Classification.

1.2.1 *Types, classes, and colors.* The coated cloth and plastic sheeting shall be of the following types, classes, and colors as specified (see 6.1).

Type I. — Cotton or synthetic cloth (rubber coated both sides).

Type II. — Cotton or synthetic cloth (vinyl coated both sides).

Type III. — Plastic unsupported film (sheeting).

Class 1.—0.004 inch thick. Applicable to type III only.

Class 2.—0.006 inch thick. Applicable to type III only.

Color 1.—Natural (applicable to types II and III only).

Color 2.—Black. Applicable to all types.

Color 3.—White. Applicable to all types.

Color 4. — Maroon. Applicable to all types.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS.

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification to the extent specified herein.

Federal Specifications:

L-P-375—Plastic Film, Flexible, Vinyl Chloride.

L-P-406—Plastics; Organic; General Specifications, Test Methods.

TT-I-735—Isopropyl Alcohol, Technical.

CCC-T-191—Textile Test Methods.

PPP-P-51—Packaging, Packing, and Marking of Textile Fabrics (Woolens, Worsteds, Cottons, Silks, and Synthetics).

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging and Packing Levels.

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

Fed. Test Method Std. No. 601—Rubber; Sampling and Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents,

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

TABLE I. *Physical and chemical requirements*

Characteristic	Type I	Type I	Type II	Type II	Type III	Type III
	Min.	*Max.*	*Min.*	*Min.*	*Min.*	*Max.*
Thickness-inches	0.013	0.018	0.013	0.018	—	—
Breaking strength-pounds						
Warp	55	—	55	—	—	—
Filling	50	—	50	—	—	—
Resistance to phenol	Note 1	—	Note 1	—	Note 2	—
Resistance to cracking after resistance to phenol	Note 3	—	Note 3	—	—	—
Fastness to crocking after resistance to phenol	Good	—	Good	—	Good	—
Resistance to alcohol	Note 1	—	Note 1	—	Note 2	—
Resistance to cracking after resistance to alcohol	Note 3	—	Note 3	—	Note 3	—
Fastness to crocking after resistance to alcohol	Good	—	Good	—	Good	—
Resistance to accelerated aging	Note 1	—	—	—	—	—
Resistance to cracking after resistance to accelerated aging	Note 3	—	—	—	—	—
Fastness to crocking after resistance to accelerated aging	Good	—	—	—	—	—
Hydrostatic resistance	Note 4	—	Note 4	—	—	—
Volatility—percent	—	—	—	Note 1 5.0	Note 1	Note 5
Steam sterilization	Note 1	—	Note 1	—	—	—
Resistance to cracking after steam sterilization	Note 3	—	Note 3	—	—	—
Resistance to crocking after steam sterilization	Good	—	Good	—	—	—
Adhesion of coating lbs/2 inch width	7.0	—	7.0	—	—	—

[1]The coated cloth and plastic sheeting shall show no evidence of softening, tackiness, hardening, peeling or blistering.

[2]The coated cloth and plastic sheeting shall show no evidence of softening, tackiness, hardening or blistering and shall not decrease in weight more than 4%

[3]Shall not crack at the fold.

[4]The cloth shall withstand a pressure of 25 lb/sq inch for a period of 5 minutes.

[5]9.0 percent maximum loss for 0.006 inch film; 7.5 percent maximum loss for 0.004 inch film.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, and Auburn, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 — Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Material.

3.1.1. *Base fabric* The base fabric for types I and II hospital sheeting shall be woven from either cotton or a synthetic fiber. The cloth shall have closely woven selvage edges not less than 1/8 inch in width.

3.1.2 *Rubber coating compound (applicable to type I coated cloth)*. The coating compound shall be natural rubber, synthetic rubber, or a mixture of natural and synthetic rubber suitably formulated and pigmented to meet the requirements of this specification.

3.1.3 *Vinyl coating compound applicable to type II coated cloth.* The coating compound shall be vinyl-chloride polymer or copolymer suitably plasticized and pigmented to meet the requirements of this specification.

3.1.4 *Unsupported plastic film (applicable to type III sheeting).* The unsupported plastic film used in type III sheeting shall conform to type I, class 2 of L-P-375 except that plasticizers, other than phosphate and phthalate, may be used and the tearing strength of the film shall be not less than 200 pounds per inch of thickness when tested as specified in L-P-375.

3.1.5 *Dusting powder* The dusting powder for application to type I coated cloth shall be talc.

3.1.6 *Toxicity.* The coating compounds and the unsupported films referenced in 3.1.2 through 3.1.4 shall not contain any ingredients that may have an irritating effect on the skin (see 6.6). The contractor shall submit a certificate of compliance with each lot stating that no materials known to be toxic were used in the manufacture of the coating compound of unsupported film.

3.2 Construction.

3.2.1. *Type I coated cloth.* Type I coated cloth shall be constructed by uniformly coating the base fabric specified in 3.1.1, on both sides, with approximately equal amounts of the coating compound specified in 3.1.2 and dusting with talc. The coated cloth shall conform to all applicable requirements in table I when tested as specified in 4.3.

3.2.2 *Type II coated cloth.* Type II coated cloth shall be constructed by uniformly coating the base fabric specified in 3.1.1, on both sides, with approximately equal amounts of the coating compound specified in 3.1.3. The coated cloth shall conform to all applicable requirements in table I when tested as specified in 4.3.

3.2.3 *Type III sheeting.* Type III sheeting shall be constructed from the unsupported plastic film specified in 3.1.4. In addition, the sheeting shall conform to all applicable requirements in table I when tested as specified in 4.3.

3.3 Length.

3.3.1 *Types I and II.* Unless otherwise specified in the invitation for bids, types I and II coated cloth shall be furnished in rolls

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

containing 50 to 60 yards (see 6.1). The rolls shall contain not more than three pieces and no piece shall be less than 6 yards in length.

3.3.2 *Type III.* Type III sheeting shall be furnished in continuous rolls of the length specified in the invitation for bids, (see 6.1). No individual roll shall exceed 125 pounds in weight.

3.4 **Width.** The minimum width for all types of sheeting shall be as specified in the contract or order (see 6.1).

3.5 **Workmanship.** The finished sheeting shall have a uniform, smooth, soft finish; the surface shall be free from perforations, uncoated areas (as applicable), pits, pinholes, and blisters. The sheeting shall conform to the quality of product established by this specification and the occurrence of defects shall not exceed the levels set by the applicable quality levels.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 **Contractor's inspection responsibility.** The supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. Inspection records of the examination and tests shall be kept complete and available to the Government as specified in the contract or order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 **Inspection for acceptance.** Inspection shall be in accordance with the provisions of MIL-STD-105 except where otherwise indicated.

4.2.1 *Testing of components.* In addition to the quality assurance provisions of the subsidiary specifications, the coating compounds specified in 3.1.2 and 3.1.3 and the toxicity requirements specified in 3.1.6 shall be accepted on the basis of a contractor's certificate of compliance with the requirements specified for such characteristics.

4.2.2 *Inspection of the end item.*

4.2.2.1 *Examination of the end item.* Defects found during the examination shall be classified in accordance with list shown in 4.2.2.1.1, 4.2.2.1.2 and 4.2.2.1.3.

4.2.2.1.1 *Yard-by-yard examination.* The required yardage of each roll shall be inspected on one side only (however, the sample shall be alternated on every other piece examined) and visual defects classified as listed. The same yardage shall be given a through-lighting inspection, for pinholes only. The defects found shall be counted regardless of their proximity to each other except where two or more defects represent a single local condition of the cloth, in which case only the more serious defects shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The unit of product shall be 1 linear yard. The acceptable quality level (AQL) for this examination shall be 4.0 defects per 100 units (one class). The sample size shall be based upon Inspection Level II, table III of MIL-STD-105. The sample size shall be expressed in units of 1 yard each. The number of rolls from which the sample is to be selected shall be in accordance with table II. An approximately equal number of yards shall be examined in each roll of the sample.

Defects

Pinhole—any
Hole or tear—any
Uncoated area—any
Thinly coated area—any
Separation of coating from base fabric—any
Cracked or checked coating
Blister or lump—any
Non-uniform coating—clearly visible
Crease or wrinkle—resulting in doubling, adhesion or surfaces against each other, poorly coated area of embedded creases that cannot be corrected by manual pressure.
Width—less than minimum specified

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

TABLE II. *Sample size*

Lot size in yards	Sample size in rolls	Acceptance number
Up to 1,300[1]	3	0
1,301 to 3,200 ...	5	0
3,201 to 8,000 ...	7	0
8,001 to 22,000 ..	10	0
22,0001 to 110,000	15	0
110,001 and up ..	25	1

[1]If lot contains fewer than 3 rolls, each roll in the lot shall be examined.

4.2.2.1.2 *Overall examination.* Each defect listed below shall be counted not more than once in each roll examined. The unit of product shall be one roll. The sample size and acceptance number for this examination shall be as shown in table II.

Defects

Overall uncleanliness
Offensive odor

(Note: Normal aromatic odors usually associated with specified types of coating shall not be classified as offensive.)

Not uniformly coated—both sides
Color not as specified
Raised edges resulting in noticeable build-up in the roll

4.2.2.1.3 *Examination for length.*

4.2.2.1.3.1 *Individual rolls.* The unit of product shall be one roll. The number of rolls to be examined and the acceptance number shall be in accordance with table II. The following shall be considered a defect:

Any roll (gross length) less than 50 yards or more than 60 yards.

Any roll (gross length) more than 2 yards below gross length marked on ticket.

Any piece in roll less than 6 gross yards.

Any roll containing more than 3 pieces.

4.2.2.1.3.2 *Total yardage in sample.* The lot shall be unacceptable if the total of the gross lengths of the rolls in the sample is less than the total of the gross lengths marked on the tickets.

4.2.2.1.4 *Examination of preparation for delivery.* An examination will be made to determine that packaging, packing, and marking requirements of Section 5 of the specification are compiled with. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be L-4 and the AQL shall be 4.0 defects per one hundred units.

Examination	*Defect*
Markings (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence or method of application.
Materials	Any component missing. Any component damaged, affecting serviceability.
Workmanship	Inadequate application of component such as incomplete closure of case liners, container flaps, loose strapping, inadequate stapling. Bulging or distortion of containers.
Weight	Gross weight exceeds requirements.

4.3 Tests. The methods of testing specified herein and in CCC-T--191 and Fed. Test Method Std. No. 601, wherever applicable, and as listed in table IV shall be followed. The physical and chemical values specified in Section 3 apply to each unit of product tested and reported as specified in the applicable test provisions of table IV. The unit of product for test purposes shall be 3 continuous yards, full width of material. The sample size (number of such units of product) shall be as shown in table III. The lot will be unacceptable if any unit fails to meet any requirement specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

TABLE III.

Lot size (yards)	Sample size
800 or less	2
801 to 22,000	3
Over 22,000	5

4.4 Test methods.

4.4.1 *Resistance to phenol (types I and II).* Resistance to phenol shall be determined by method 6711 of Fed. Test Method Std. No. 601 with the following exceptions:

(a) Test specimens shall be 8 by 4 inches.

(b) Two specimens with the long dimension parallel to the length and two specimens with the long dimension parallel to the width of the coated cloth shall be tested from each test unit.

(c) The specimen shall be examined for evidence of softening, tackiness, stiffening, peeling, or blistering.

4.4.1.1 *Resistance to phenol (type III).* The resistance to phenol of type III sheeting shall be determined as specified in 4.4.1 except that the test specimens shall be weighed before immersion. After immersion, the test specimens shall be wiped with a soft absorbent and the specimens shall be reweighed. The difference in weight shall be calculated as the percent loss in weight.

4.4.2 *Resistance to cracking after resistance to phenol (types I and II).* Twenty-four hours after the end of the test specified in 4.4.1, one specimen from each direction of each test unit shall be tested for cracking as follows: The test specimen shall be folded double and placed on a hard, smooth, flat surface. The folded edge shall be rolled 10 times, 5 in each direction along its full length with a metal roller approximately 1 inch in diameter, under a load of five pounds. Each specimen shall be examined immediately for any cracking.

4.4.3 *Resistance to isopropyl alcohol (types I and II).* The resistance to isopropyl alcohol shall be determined as specified in 4.4.1 except that the immersion media shall be 70 percent isopropyl alcohol conforming to grade A of TT-I-735. The time of immersion shall be 22 ± 1/4 hours.

4.4.3.1 *Resistance to isopropyl alcohol (type III).* The resistance of type III sheeting to isopropyl alcohol shall be determined as specified in 4.4.1.1 except that the immersion media shall be 70 percent isopropyl alcohol conforming to grade A of TT-I-735. The time of immersion shall be 22 ± 1/4 hours.

4.4.4 *Resistance to cracking after resistance to isopropyl alcohol (types I and II).* Twenty-four hours after the end of the test specified in 4.4.3, one specimen from each direction of each test unit shall be tested for cracking as follows: The test specimen shall be folded double and placed on a hard, smooth, flat surface. The folded edge shall be rolled 10 times, 5 in each direction along its full length with a metal roller approximately 1 inch in diameter, under a load of five pounds. Each specimen shall be examined immediately for any cracking.

4.4.5 *Resistance to accelerated aging (type I).* The coated cloth shall be exposed to circulating air as specified in method 7221 or 7231 of Fed. Test Method Std. No. 601 with the following exceptions:

(a) Test specimens shall be 8 by 4 inches.

(b) Two specimens with the long dimension parallel to the length and two specimens with the long dimensions parallel to the width of the coated cloth shall be tested from each test unit.

(c) The specimens shall be examined for evidence of softening, tackiness, hardening, peeling, or blistering of of the coating.

4.4.6 *Resistance to cracking after resistance to accelerated aging (type I).* Twenty-four hours after the test specified in 4.4.5, one test specimen from each direction shall be tested for resistance to cracking as follows: The test specimen shall be folded double and placed on a hard, smooth, flat sur-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

TABLE IV. *Instructions for testing sheeting*

Characteristic	Requirement reference	Test method	Determinations per sample unit	Results reported as	
				Pass or Fail	Numerically to nearest
Thickness	Table I	5030 of CCC-T-191	5		0.001 inch
Breaking strength:					
Warp	Table I	5100 of CCC-T-191	5 each direction	—	1.0 pound
Filling	Table I				
Resistance to phenol:					
Warp	Table I	4.4.1	2 each direction	X	—
Filling	Table I				
Resistance to cracking after resistance to phenol:					
Warp	Table 1	4.4.2	1 each direction	X	—
Filling	Table 1				
Fastness to crocking after resistance to phenol	Table 1	5651 of CCC-T-191	1	—	Adjective rating
Resistance to alcohol:					
Warp	Table I	4.4.3	2 each direction	X	—
Filling	Table I				
Resistance to cracking after resistance to alcohol:					
Warp	Table I	4.4.4	1 each direction	X	—
Filling	Table I				
Fastness to crocking after resistance to alcohol	Table I	5651 of CCC-T-191	1	—	Adjective rating
Resistance to accelerated aging:					
Warp	Table I	4.4.5	2 each direction	X	—
Filling	Table I				
Resistance to cracking after accelerated aging:					
Warp	Table I	4.4.6	1 each direction	X	—
Filling	Table I				
Resistance to crocking after accelerated aging	Table I	5651 of CCC-T-191	1	—	Adjective rating
Hydrostatic resistance	Table I	4.4.7	5	X	—
Volatility	Table I	4.4.8	1	X	1.0 percent
Steam sterilization	Table I	4.4.9	1	X	—
Resistance to cracking after sterilization	Table I	4.4.10	1	X	—
Fastness to crocking after sterilization	Table I	5651 of CCC-T-191	1	X	—
Adhesion of coating	Table I	4.4.11	3	—	0.5 pound

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

face. The folded edge shall be rolled 10 times, 5 in each direction along its full length with a metal roller approximately 1 inch in diameter, under a load of five pounds. Each specimen shall be examined immediately for any cracking.

4.4.7 *Hydrostatic resistance, types I and II.*

4.4.7.1 *Testing apparatus (see* 6.5). The machine shall be a motor-driven hydrostatic tester wherein the specimen is held between two annular, plane clamping surfaces. The upper clamping surface shall have a circular opening 1.240 ± 0.010 inch in diameter. The lower clamping surface shall have an opening 1.240 ± 0.010 inch in diameter, and shall have concentric to it a recession with an inside diameter of 2.00 ± 0.01 inch, and outside diameter of 2.375 ± 0.010 inch, and a depth of 0.094 ± 0.002 inch. Into this recession shall be fitted a rubber gasket having a cross-sectional diameter equal to the width of the concentric recession. The machine shall be fitted with a pressure gauge of the Bourdon tube, maximum-reading type, having a dial 4.5 inch in diameter, with the scale divided to read 2.0-pound units. The range of the gauge shall normally be 0 to 300 pounds, and its accuracy shall be ± 2.0 pounds. Prior to each determination, the pump shall be backed to normal starting position and the water level in the pressure chamber brought flush with the top of the rubber gasket.

4.4.7.2 *Test procedure.* Test specimens of the coated cloth measuring 4 by 4 inches that are free from coating defects shall be conditioned as specified in section 4 of CCC-T-191. The specimen shall be clamped in the machine and the pressure raised to 25 pounds per square inch. The specimen shall remain at the required pressure within ± 2 pounds per square inch for five minutes. At the end of the five-minute period, the specimen shall be examined for leakage. Five specimens shall be tested and all specimens shall pass the test.

4.4.8 *Volatility (type II).* The volatility of the plasticizers shall be determined as specified in method 6081 of L-P-406 with the following exceptions:

(a) The specimen shall be preconditioned for 40 hours at 73° ± 2°F. and 50 ± 4 percent relative humidity. Adequate air circulation shall be provided on all sides of the specimen, by placing them on suitable racks, hanging them by metal clips, or laying them on wide mesh wire screen frames with at least one inch between the screen and the surface of the bevels.

(b) Reconditioning time shall be 40 hours.

(c) After the specimen has been weighed, it shall be examined for evidence of softening, tackiness, stiffening, peeling, or blistering.

4.4.9 *Steam sterilization (types I and II).* The coated cloth shall be subjected to steam sterilization as specified in method 7411 of the Fed. Test Method Std. No. 601 except as follows:

(a) The specimen shall be a piece of coated cloth 12 by 12 inches folded once to give a rectangle 12 by 6 inches and folded again to give a square 6 by 6 inches.

(b) Tensile strength and elongation tests shall not apply.

(c) One specimen shall be tested from each test unit and after testing it shall be examined for softening, hardening, tackiness, peeling, and blistering.

4.4.10 *Resistance to cracking after steam sterilization (types I and II).* Twenty-four hours after the fifth period of sterilization, one piece 8 by 6 inches shall be cut from each direction of the sterilized specimen and tested for resistance to cracking as specified in 4.4.6.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

4.4.11 *Adhesion of coating.* The adhesion of coating shall be determined by method 5970 of CCC-T-191 with the following exceptions:

The cement or solvent used in preparing test specimens shall be one of the following:

(*a*) A solventless adhesive (Eastman 910 cement) (see 6.4.1).

(*b*) Boxer, Liquid Plastic No. 700 (see 6.4.2).

(*c*) A mixture of 50 percent methyl-ethyl-ketone and 50 percent cyclohexanone. If a proper adhesive bond is not obtained with (*a*) above, (*b*) shall be used. If a proper adhesive bond is not obtained with (*a*) or (*b*) above, (*c*) shall be used.

When preparing test specimens, the coating shall be cut through to the cloth with a razor or knife to facilitate the initial separation of the coating from the cloth.

When specimens are removed from between the plates they shall be cooled for a maximum of twenty-four hours in lieu of one hour.

When reporting results, if the coating is separated from the cloth at an average force greater than that specified in table I, or if the average force necessary to separate the the cemented sample at the cement line is greater than that specified in table I, the adhesion of coating requirement shall be considered as passing. If a proper adhesive bond is not obtained with one of the above methods of sample preparation, the coated cloth shall be unacceptable and shall be reported as failing with respect to bonding of coating to coating. The test report shall show which method of sample preparation was used and shall indicate separation of coating or separation at the adhesive line.

5. PREPARATION FOR DELIVERY

(Fed. Std. No. 102 shall be referred to for definition and application of the various levels of packaging and packing for civilian procurements).

5.1 Packaging. Packaging shall be levels A, B, and C as specified (see 6.1).

5.1.1 *Levels A, B, and C.* The coated cloth and plastic sheeting, put up on rolls, shall be wrapped in accordance with method A and packaged in accordance with the applicable requirements for class 3 fabrics of PPP-P-51.

5.2 Packing. Packing shall be levels A, B, and C as specified (see 6.1).

5.2.1 *Levels A, B,* and C. The coated cloth and plastic sheeting shall be packed in accordance with the applicable requirements of PPP-P-51, except that fiberboard or rigid type shipping containers shall be used.

5.3 Marking.

5.3.1 *Civil agencies.* In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the applicable requirements of Fed. Std. No. 123.

5.3.2 *Military requirements.* In addition to any special marking required by the contract or order, shipments shall be marked in according with the applicable requirements of PPP-P-51.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(*a*) Title, number, and date of this specification.

(*b*) Type, class, and color (see 1.2).

(*c*) Width required (see 3.4).

(*d*) Length of rolls (see 3.3.1 and 3.3.2).

(*e*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

(*f*) Inspection methods and tests (see 4.1).

6.2 It is not intended that type III sheeting be exposed to steam sterilization.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

6.3 Transportation description. Transportation description and minimum weights applicable to this commodity are:

Rail:

Cloth, coated with synthetic plastic or rubber.
Carload minimum weight 30,000 pounds.

Motor:

Cloth, cotton coated with plastic or rubber.
Truckload minimum weight 30,000 pounds, subject to Rule 34, National Motor Freight Classification.

6.4 Adhesives.

6.4.1 Eastman 910 manufactured by Tennessee Eastman Company is available from the Armstrong Cork Co., Lancaster, Pennsylvania (see 4.4.11).

6.4.2 Boxer, Liquid Plastic No. 700 is made by Union Laboratories Incorporated, Morganville, New Jersey (see 4.4.11).

6.5 A hydrostatic testing machine of the type described in 4.4.7.1 is similar to the Model A Hydrostatic Tester manufactured by B. F. Perkins and Sons, Inc., Holyoke, Mass.

6.6 Toxicity. Any questions raised regarding toxicity should be referred by the procuring activity through channels to the departmental medical agency. In case of Army procurement, the Surgeon General will act as advisor to the procuring activity (see 3. 1.6).

Notice. When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:

Army—M Q
Navy—S Md
Air Force—MAA

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.