ZZ-C-450b
May 24, 1966
SUPERSEDING
Fed. Spec. ZZ-C-450a
October 18, 1962

FEDERAL SPECIFICATION

CLOTH, COATED (RUBBER AND PLASTIC) AND PLASTIC SHEETING FOR HOSPITAL USE

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. The coated cloth and plastic sheeting covered by this specification is intended for the protection of mattresses on hospital beds.

1.2 Classification.

1.2.1 *Types, classes, and colors.* The coated cloth and plastic sheeting shall be of the following types, classes, and colors, as specified (see 6.1).

Type I—Cotton or synthetic cloth (rubber coated both sides).
Type II—Cotton or synthetic cloth (vinyl coated both sides).
Type III—Plastic unsupported film (sheeting).
Class 1—0.004 inch thick. Applicable to to type III only.
Class 2—0.006 inch thick. Applicable to type III only.
Color 1—Clear (applicable to types II and III only).
Color 2—Black (applicable to all types).
Color 3—White (applicable to all types).
Color 4—Maroon (applicable to all types).

2. APPLICABLE DOCUMENTS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

L-P-375—Plastic Film, Flexible, Vinyl Chloride.
TT-I-735—Isopropyl Alcohol.
CCC-T-191—Textile Test Methods.
PPP-P-51—Packaging, Packing, and Marking of Textile Fabrics (Woolens, Worsteds, Cotton, Silks, and Synthetics).

Federal Standards:

Fed. Test Method Std. No. 406—Plastics: Methods of Testing.
Fed. Std. No. 595—Colors.
Fed. Test Method Std. No. 601—Rubber: Sampling and Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standard:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

FSC 8305/9330

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Samples.

3.1.1 *Preproduction sample.* When specified (see 6.1), before production is commenced, a 3-yard sample of the type, class, and color of the coated cloth or plastic sheeting specified in the contract or order shall be submitted to the contracting officer or his authorized representative for inspection as specified in 4.2. The approval of the preproduction sample authorizes the commencement of production but does not relieve the supplier of the responsibility for compliance with all provisions of this specification. The preproduction sample shall be manufactured by the supplier in the same facilities to be used for the manufacture of the production items.

3.1.2 *Standard samples.* Unless otherwise specified, a standard sample for color shall apply (see 6.2).

3.2 Materials.

3.2.1 *Base cloth.* The base cloth for types I and II hospital sheeting shall be woven from either cotton or synthetic fiber.

3.2.2 *Rubber coating compound (applicable to type I coated cloth).* The coating compound shall be natural rubber, synthetic rubber, or a mixture of natural and synthetic rubber suitably formulated and pigmented to meet the requirements of this specification.

3.2.3 *Vinyl coating compound (applicable to type II coated cloth).* The coating compound shall be vinyl-chloride polymer or copolymer suitably plasticized and pigmented to meet the requirements of this specification.

3.2.4 *Unsupported plastic film (applicable to type III sheeting).* The unsupported plastic film used in type III sheeting shall conform to type I, class 2 of L-P-375 except that plasticizers other than phosphate and phthalate may be used and the tearing strength of the film shall be not less than 200 pounds per inch of thickness when tested as specified in L-P-375.

3.2.5 *Dusting powder.* The dusting powder for application to type I coated cloth shall be talc.

3.3 Construction.

3.3.1 *Type I coated cloth.* Type I coated cloth shall be constructed by uniformly coating the base cloth specified in 3.2.1 on both sides, with approximately equal amounts of the coating compound specified in 3.2.2 and dusting with talc. The coated cloth shall be vulcanized and shall conform to all applicable requirements in table I when tested as specified in 4.3.3.

3.3.2 *Type II coated cloth.* Type II coated cloth shall be constructed by uniformly coating the base cloth specified in 3.2.1 on both sides, with approximately equal amounts of the coating compound specified in 3.2.3. The coated cloth shall conform to all applicable requirements in table I when tested as specified in 4.3.3.

TABLE I. *Physical and chemical requirements*

Characteristic	Type I	Type II	Type III
Thickness (inch):			
Minimum	0.013	0.013	—
Maximum	0.018	0.018	—
Breaking strength, pounds, minimum:			
Warp	50	50	—
Filling	50	50	—
Resistance to phenol	1	1	1 & 2
Resistance to cracking after resistance to phenol	3	3	—
Fastness to crocking after resistance to phenol, minimum ..	Good	Good	Good
Resistance to alcohol	1	1	1 & 2
Resistance to cracking after resistance to alcohol	3	3	3

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

TABLE I. *Physical and chemical requirements (cont'd)*

Characteristic	Type I	Type II	Type III
Fastness to crocking after resistance to alcohol, minimum	Good	Good	Good
Resistance to accelerated aging	1	—	—
Resistance to cracking after resistance to accelerated aging	3	—	—
Fastness to crocking after resistance to accelerated aging, minimum	Good	—	—
Hydrostatic resistance	4	4	—
Volatility—percent maximum	—	5.0[1]	1 & 5
Steam sterilization ..	1	1	—
Resistance to cracking after steam sterilization	3	3	—
Fastness to crocking after steam sterilization, minimum	Good	Good	—
Adhesion of coating lbs./2 inch width, minimum	7.0	7.0	—

Notes: [1] The coated cloth and plastic sheeting shall show no evidence of softening, tackiness, hardening, peeling, or blistering, when compared to an unexposed specimen of the same material.
[2] The plastic sheeting shall not decrease in weight more than 4.0 percent.
[3] The specimen shall not crack at the fold.
[4] The coated cloth shall withstand a pressure maintained at 25 lbs./sq. in. for 5 minutes.
[5] The maximum loss shall be 7.5 percent for class 1 film and 9.0 percent for class 2 film.

3.3.3 *Type III sheeting.* Type III sheeting shall be constructed from the unsupported plastic film specified in 3.2.4. In addition, the sheeting shall conform to all applicable requirements in table I when tested as specified in 4.3.3.

3.4 Put-up and length.

3.4.1 *Types I and II.* Types I and II coated cloth shall be put up on rolls as specified in PPP-P-51. The rolls shall be 50 to 60 yards in length, shall contain not more than three pieces and no piece shall be less than 6 yards in length.

3.4.2 *Type III.* Type III sheeting shall be furnished in continuous rolls. Total length shall be such that no roll weighs more than 125 pounds. No roll shall be less than 40 yards long.

3.5 Width. The minimum width for all types of sheeting shall be as specified in the contract or order (see 6.1).

3.6 Color. The color shall match the applicable color number of Fed. Std. No. 595 or shall match the approved color standard for the color specified where such a standard is applicable.

3.6.1 *Matching.* The color and shade shall match the standard sample (see 6.2) under natural (north sky) daylight or artificial daylight having a color temperature of 7500° Kelvin, and shall be a good approximation to the standard sample under incandescent lamplight at 2800° Kelvin.

3.7 Workmanship. The finished product shall be clean, shall have a uniform smooth surface, and shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels (AQLs).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

4.2 **Preproduction sample inspection.** The preproduction sample submitted in accordance with 3.1 shall be visually inspected for appearance and color. The sample shall be tested for physical and chemical properties in accordance with 4.3.3 to the extent applicable.

4.3 **Inspection.** Inspection shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated.

4.3.1 *Inspection of components.* In accordance with 4.1, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document. In addition, the supplier shall submit a certificate of compliance with each shipment or lot citing conformance to the requirements in 3.2.2 and 3.2.3 for coating compounds and to the requirement in 3.2.5 for dusting powder.

4.3.2 *Inspection of the end item.*

4.3.2.1 *Examination of the end item.* The end item shall be examined for the defects listed in 4.3.2.1.1 and 4.3.2.1.2.

4.3.2.1.1 *Yard-by-yard examination.* The required yardage of each roll shall be inspected on one side only; however, the sample shall be alternated on every other piece examined and visual defects classified as listed. The same yardage shall be given a thorough lighting inspection, for pinholes only. The defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the cloth, in which case, only one defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The sample unit shall be 1 linear yard. The sample size shall be in accordance with inspection level II of MIL-STD-105. The AQL shall be 4.0 defects per 100 units (yards). The lot size shall be expressed in units of one yard each. An approximate equal number of yards shall be examined from each roll selected. The number of rolls from which the sample is to be selected shall be in accordance with table II.

Defects
Any cut, tear, hole (including pinhole), scratch, or abrasion mark.
Any uncoated area.
Any thinly coated area.
Any separation of coating from base cloth.
Any cracked or checked area.
Any tacky area.
Any heavily coated area.
Any lump or blister.
Any crease or wrinkle, resulting in doubling or adhesion of surfaces.
Width—less than minimum specified.
Color not as specified.
Curled, folded, doubled, or rolled edges resulting in noticeable build up in roll.
Any dirt, spot, stain, or foreign matter.
Offensive odor.

Note: Normal aromatic odors usually associated with specified types of coating shall not be classified as offensive.

TABLE II. *Sample size, rolls*

Lot size (yards)	Sample size in rolls	Maximum number of defects acceptable in sample
1,300 or less	3	0
1,301 up to and including 3,200	5	0
3,201 up to and including 8,000	7	0
8,001 up to and including 22,000	10	0
22,001 up to and including 110,000	15	1
110,001 and over	25	1

4.3.2.1.2 *Examination for length.*

4.3.2.1.2.1 *Individual rolls.* Each individual roll in the sample shall be examined for the defects listed below. The sample unit for this examination shall be one roll. The sample size and acceptance number shall be as shown in table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

Defects
Any roll (gross length) less than 50 yards or more than 60 yards (types I & II).
Any roll (gross length) less than 40 yards (type III).
Any roll (gross length) more than 2 yards below gross length marked on ticket.
Any piece in roll less than 6 yards (types I & II).
Any roll containing more than 3 pieces (types I & II).
Any roll not one continuous piece (type III).

4.3.2.1.2.2 *Total yardage in sample.* The lot shall be unacceptable if the total of the gross lengths of the rolls in the sample is less than the total of the gross lengths marked on the tickets.

4.3.2.1.3 *Examination of preparation for delivery.* An examination shall be made to determine that packaging, packing, and marking requirements of section 5 of this specification are complied with. The examination shall be conducted as specified in PPP-P-51.

4.3.3 *Testing of the end item.* The methods of testing contained in CCC-T-191, whenever applicable, and as listed in table IV, shall be followed. The requirements for all tests are referenced in table I. The physical values specified apply to the average of determinations made on a sample unit for test purposes as specified in the applicable test methods. All test reports shall contain the individual values utilized in expressing the final result. The sample unit for test purposes shall be 3 yards full width of finished cloth. The sample size (number of sample units) shall be as shown in table III. The lot shall be unacceptable if one or more units fail to meet any requirement specified. For those characteristics where test results are reported as "pass" or "fail", there shall be no evidence of failure of any test specimen to meet the requirements as specified.

TABLE III. *Sample size (units)*

Lot size (yards)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE IV. *Instructions for testing*

Characteristic	Test method	Number of determinations per sample unit	Results reported as	
			Pass or fail	Numerically to nearest
Thickness	5030	5	—	0.001 inch
Breaking strength:				
Warp	5100	5	—	1 pound
Filling	5100	5	—	1 pound
Resistance to phenol:				
Types I and II	4.4.2	2	X	
Type III	4.4.2.1	2	X	0.1 percent
Resistance to cracking after resistance to phenol:				
Warp	4.4.3	1	X	
Filling	4.4.3	1	X	
Fastness to crocking after resistance to phenol[1]	5651	1	—	Adjective rating
Resistance to alcohol:				
Types I and II	4.4.4	2	X	
Type III	4.4.4.1	2	X	0.1 percent
Resistance to cracking after resistance to alcohol:				
Warp	4.4.5	1	X	
Filling	4.4.5	1	X	
Fastness to crocking after resistance to alcohol[1]	5651	1	—	Adjective rating

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

TABLE IV. *Instructions for testing (cont'd)*

Characteristic	Test method	Number of determinations per sample unit	Results reported as	
			Pass or fail	Numerically to nearest
Resistance to accelerated aging:				
Warp	4.4.6	2	X	—
Filling	4.4.6	2	X	—
Resistance to cracking after accelerated aging:		1	X	—
Warp	4.4.7	1	X	—
Filling	4.4.7	1	X	—
Fastness to crocking after accelerated aging[1]	5651	1	—	Adjective rating
Hydrostatic resistance	4.4.8	5	X	—
Volatility	4.4.9	3	X	0.1 percent
Steam sterilization	4.4.10	1	X	—
Resistance to cracking after sterilization	4.4.11	1	X	—
Fastness to crocking after sterilization[1]	5651	1	—	Adjective rating
Adhesion of coating (types 1 and 2)	4.4.12	3	—	0.1 pound

[1] Not applicable to color 1.

4.4 Test methods.

4.4.1 *Test conditions.* Results of physical tests obtained under testing conditions defined in Fed. Test Method Std. No. 406, Fed. Test Method Std. No. 601, or CCC-T-191, will be acceptable except in case of dispute; in dispute cases, tests shall be conducted with both the specimen and test apparatus under standard conditions as defined in CCC-T-191

4.4.2 *Resistance to phenol (types I and II).* Resistance to phenol shall be determined by method 6711 of Fed. Test Method Std. No. 601 with the following exceptions:

(a) Test specimens shall be 8 by 6 inches.

(b) Two specimens with the long dimension parallel to the length and two specimens with the long dimension parallel to the width of the coated cloth shall be tested from each test unit.

(c) The specimen shall be examined for evidence of softening, tackiness, hardening, peeling, or blistering.

4.4.2.1 *Resistance to phenol (type III).* The resistance to phenol of type III sheeting shall be determined as specified in 4.4.2 except that the test specimens shall be weighed to the nearest milligram before immersion. After immersion, the test specimens shall be wiped with a soft absorbent cloth and the specimens shall be reweighed. The difference in weight shall be used to calculate the percent loss in weight.

4.4.3 *Resistance to cracking after resistance to phenol (types I and II).* Twenty-four hours after the end of the test specified in 4.4.2, one specimen from each direction of each test unit shall be tested for cracking as follows: The test specimen shall be folded double and placed on a hard, smooth, flat surface. The folded edge shall be rolled 10 times, 5 in each direction along its full length with a metal roller approximately 1 inch in diameter, under a load of five pounds. Each specimen shall be examined immediately for any cracking.

4.4.4 *Resistance to isopropyl alcohol (types I and II).* The resistance to isopropyl alcohol shall be determined as specified in 4.4.2 except that the immersion media shall be 70 percent isopropyl alcohol conforming to grade A of TT-I-735. The time of immersion shall be 22 ± 1/4 hour.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

4.4.4.1 *Resistance to isopropyl alcohol (type III).* The resistance of type III sheeting to isopropyl alcohol shall be determined as specified in 4.4.2.1 except that the immersion media shall be 70 percent isopropyl alcohol conforming to grade A of TT-I-735. The time of immersion shall be 22 ± 1/4 hour.

4.4.5 *Resistance to cracking after resistance to isopropyl alcohol (types I and II).* Twenty-four hours after the end of the test specified in 4.4.4, one specimen from each direction of each test unit shall be tested for cracking as follows: The test specimen shall be folded double and placed on a hard, smooth, flat surface. The folded edge shall be rolled 10 times, 5 in each direction along its full length with a metal roller approximately 1 inch in diameter, under a load of five pounds. Each specimen shall be examined immediately for any cracking.

4.4.6 *Resistance to accelerated aging (type I).* The coated cloth shall be exposed to circulating air as specified in method 7221 of Fed. Test Method Std. No. 601 with the following exceptions:

(a) Test specimens shall be 8 by 4 inches.
(b) Two specimens with the long dimension parallel to the length and two specimens with the long dimensions parallel to the width of the coated cloth shall be tested from each test unit
(c) The specimens shall be examined for evidence of softening, tackiness, hardening, peeling, or blistering of the coating.

4.4.7 *Resistance to cracking after resistance to accelerated aging (type I).* Twenty-four hours after the test specified in 4.4.5, one test specimen from each direction shall be tested for resistance to cracking as follows: The test specimen shall be folded double and placed on a hard, smooth, flat surface. The folded edge shall be rolled 10 times, 5 in each direction along its full length with a metal roller approximately 1 inch in diameter, under a load of five pounds. Each specimen shall be examined immediately for any cracking.

4.4.8 *Hydrostatic resistance, types I and II.* The hydrostatic resistance shall be determined in accordance with method 5512 of CCC-T-191 except that the hydrostatic pressure shall be raised to 25 ± 2 p.s.i. and maintained at that pressure for 5 minutes and then examined for leakage. The range of the gage shall be 0 to 60 p.s.i. Leakage shall be defined as the appearance of water at one or more spots in the test area.

4.4.9 *Volatility (type II).* The volatility of the plasticizers shall be determined as specified in method 6081 of Fed. Test Method Std. No. 406 with the following exceptions:

(a) The specimen shall be preconditioned for 40 hours at 73° ± 2°F. and 50 ± 4 percent relative humidity. Adequate air circulation shall be provided on all sides of the specimen, by placing them on suitable racks, hanging them by metal clips, or laying them on wide mesh wire screen frames with at least one inch between the screen and the surface of the bevels.

(b) Reconditioning time shall be 40 hours.

(c) After the specimen has been weighed, it shall be examined for evidence of softening, tackiness, stiffening, peeling, or blistering.

4.4.10 *Steam sterilization (types I and II).* The coated cloth shall be subjected to steam sterilization as specified in method 7411 of the Fed. Test Method Std. No. 601 except as follows:

(a) The specimen shall be a piece of coated cloth 12 by 12 inches folded once to give a rectangle 12 by 6 inches and folded again to give a square 6 by 6 inches.
(b) Tensile strength and elongation tests shall not apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

(c) One specimen shall be tested from each test unit and after testing, it shall be examined for softening, hardening, tackiness, peeling, and blistering.

4.4.11 *Resistance to cracking after steam sterilization (types I and II).* Twenty-four hours after the fifth period of sterilization, one piece, 8 by 6 inches, shall be cut from each direction of the sterilized specimen and tested for resistance to cracking as specified in 4.4.7.

4.4.12 *Adhesion of coating.* The adhesion of coating shall be determined by method 5970 of CCC-T-191, except that if the coating is separated from the base cloth at an average force greater than that specified or if the average force necessary to separate the cemented sample at the cement line is greater than that specified, the adhesion of coating requirement shall be considered as passing.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.1).

5.1.1 *Levels A and C.* The coated cloth and sheeting, put up as specified, shall be packaged in accordance with the applicable requirements for class 5 fabrics of PPP-P-51 except that the roll shall not be secured from unwinding. Rolling of the material, except for type III, shall be done with the minimum tension practicable to produce a "soft roll".

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.1).

5.2.1 *Levels A, B, and C.* The coated cloth and sheeting shall be packed in accordance with the applicable requirements for class 5 fabrics of PPP-P-51. Not more than two rolls shall be packed per container, with the rolls positioned two in width.

5.3 Marking. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with PPP-P-51.

6. NOTES

6.1 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(*a*) Title, number, and date of this specification.
(*b*) Type, class and color required (see 1.2).
(*c*) When preproduction sample is required (see 3.1.1).
(*d*) Width required (see 3.5).
(*e*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.2 Samples. For access to standard shade samples, address the procuring office issuing the invitation for bids (see 3.6).

6.3 It is not intended that type III sheeting be exposed to steam sterilization.

6.4 Toxicity. Any questions raised regarding toxicity should be referred by the procuring activity through channels to the departmental medical agency. In case of Army procurement, the Surgeon General will act as advisor to the procuring activity.

6.5 Transportation descriptions. The transportation descriptions and minimum weights applicable to this commodity are:

Rail:

Cloth, coated with synthetic rubber or plastic.
Carload minimum weight 30,000 pounds.

Motor:

Cloth, cotton, coated with plastic or rubber.
Truckload minimum weight 30,000 pounds, subject to Rule 115, National Motor Freight Classification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

CUSTODIANS:

Army—GL
Navy—SA
Air Force—67

Review activities:

Army—MD
Navy—SA
Air Force—67

User activities:

Navy—CG
Air Force—69

Preparing activity:

Army—GL

Review and user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Standardization Documents.

Orders for this publication are to be placed with ation, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity.

SPECIFICATION

loth, Coated (Rubber and Plastic) and Plastic Sheeting for (ZZ-C-450b) Hospital Use

ORGANIZATION	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD FORM 1 OCT 64 1426

"to detach this form, cut along this line"

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01762

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRE-SS
Natick, Massachusetts 01762

FOLD

"to detach this form, cut along this line"

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:25Z
Check the source to verify that this is the current version before use.