ZZ-M-91e
INTERIM AMENDMENT-1(GSA-FSS)
March 20, 1968

INTERIM AMENDMENT

TO

FEDERAL SPECIFICATION

MATTRESS, BED, LATEX FOAM

This interim amendment was developed by Federal Supply Service, General Services Administration, Washington, D. C. 20405, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim amendment as a valid exception to Federal Specification ZZ-M-91e, dated February 28, 1963.

PAGE 1

Title: Delete "LATEX".

Paragraph 1.1, delete "latex".

Paragraph 1.2, add the following text: "The foam mattresses covered by this specification shall be of the following types (see 6.2):
Type I - Latex foam.
Type II - Polyurethane foam."

PAGE 2

Add the following new paragraph:

2.2. Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM) Standards:

D1564-64T, Tentative Methods of Test for Flexible Urethane Foam

(Application for copies should be addressed to the American Society for testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103).

Paragraph 3.1.1, delete "Latex" from heading and the first sentence entirely and substitute for the latter the following:

"The foam insert shall be made from latex foam in the case of type I, either natural or synthetic or a mixture of the two, or for type II, polyurethane foam."

Table I - Footnotes 1 and 2. Delete the word "latex".

Paragraph 3.1.1.1, delete "2" at end of first sentence and substitute "3".

Delete second sentence entirely, and substitute the following:

"For type II, polyurethane foam, the compression shall be determined after preflexing the samples to 25 percent of original thickness 10 times before the testing and there shall be a waiting period of 6 ± 1 minute after preflexing prior to testing."

FSC 7210

Add the following new paragraph:

3.1.1.2 **Density.** The type II foam insert shall have a density of not less than 1.8 pounds per cubic foot.

PAGE 3

Paragraph 3.2.1 (a), (b), (c), delete "latex" in first sentence.

Paragraph 3.2.3, line 2, delete "latex".

Paragraph 3.2.4.1, lines 2 and 7, delete "latex".

Paragraph 3.2.4.2, lines 2 and 4, delete "latex".

PAGE 4

Paragraph 3.2.4.3, lines 1 and 3, delete "latex".

Paragraph 3.2.5.1, lines 1, 8, and 21, delete "latex".

Paragraph 3.2.5.2, line 6, delete "latex".

PAGE 5

Table II, footnote 1, lines 1 and 3, delete "latex".

Paragraph 3.4.1, line 1, delete "latex" both places.

PAGE 6

Table III:
First column, delete "latex"
Fourth column, after "Test Method" insert "Type I".
Add new test method column as follows:

Test Method - Type II
Sections 12-18 of ASTM D1564-64T
Sections 45-56 of ASTM D1564-64T
Sections 45-56 of ASTM D1564-64T
4.4.1 and Sections 19-25 of ASTM D-1564-64T
4.4.2
Standard Commercial
Standard Commercial
Standard Commercial
Sections 19-25 of ASTM D1564-64T
4.4.4

PAGE 7

Table III, footnote 3, lines 1, 2, 3, and 4, delete "latex". Add sentence as follows:

"In any case, the minimum specimen size shall be 15 by 15 by 4 inches.

PAGE 8

Paragraph 4.3.1.1, line 7, delete "latex".

Paragraph 4.3.2.1, line 4, delete "latex".

Paragraph 4.3.2.1.1, line 1, delete "latex".

PAGE 9

Column titled "Defect":
First column, lines 11 and 14, delete "latex".
Second column, lines 11, 14 and 17, delete "latex".

PAGE 12

Paragraph 4.4.1, lines 1 and 2, delete "latex".

Paragraph 4.4.2, line 1, delete "latex".

Paragraph 4.4.4, line 3, delete "latex".

PAGE 13

Paragraph 6.2, line 7, insert before "size" the words "Type and".