MIL-I-22266C
24 June 1971

SUPERSEDING
MIL-S-22266B(ASG)
26 July 1961

MILITARY SPECIFICATION

INSULATING COMPOUND, ELECTRICAL (FOR FIELD SPLICING APPLICATIONS)

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers two component, room-temperature curing, insulating compounds for field-splicing applications.

1.2 Classification. The insulating compound shall be of the following types as specified (see 6.2 and 6.6):

Type I	Epoxy resin
Class A	Packaged in film bags
Class B	Packaged in metal containers
Type III	Polyurethane resin
Class A	Packaged in film bags
Class B	Packaged in metal containers

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

Federal

PPP-B-566	Boxes, Folding, Paperboard
PPP-B-601	Boxes, Wood, Cleated-Plywood

FSC 5970

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:46Z
Check the source to verify that this is the current version before use.

Federal (Cont'd)

PPP-B-621	Boxes, Wood, Nailed and Lock-Corner
PPP-B-636	Box, Fiberboard
PPP-B-665	Boxes, Paperboard, Metal-Stayed (Including Stay Material)
PPP-C-96	Cans, Metal, 28 Gage and Lighter

Military

MIL-B-117	Bag, Sleeve and Tubing, Interior Packaging
MIL-L-10547	Liners, Case, and Sheet, Overwrap, Water-Vaporproof or Waterproof, Flexible

STANDARDS

Federal

Fed. Test Method Std. No. 406	Plastics: Method of Testing

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	Marking for Shipment and Storage

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials

ASTM D 412	Tension Testing of Vulcanized Rubber
ASTM D 2240	Test for Indentation Hardness of Rubber and Plastics by Means of a Durometer

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:46Z
Check the source to verify that this is the current version before use.

(Copies of ASTM publications may be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

3. REQUIREMENTS

3.1 First article inspection. The insulating compound and curing agent furnished under this specification shall be a product(s) which has been inspected and has passed the first article inspection specified herein (see 4.3 and 6.2).

3.2 Materials. The insulating compound shall be a two-component system consisting of a thermosetting resin base of the room temperature curing epoxy type or elastomer of the polyurethane type and a curing agent. The component materials of the resin base and curing agent shall be such that the cured insulating compound(s) shall not be corrosive to the metals from which the electrical cables are made, nor shall the cured compound cause deterioration of the jacketing materials used in cable construction.

3.2.1 Primer. The use of a primer specified by the manufacturer to improve the adhesion of the compound to the substrate is permitted. The primer shall be available from the same manufacturer as the compound with which it is to be used and shall be applied in strict conformance with the manufacturer's recommendation. Primer, when specified by the manufacturer, shall not be corrosive to the electrical metal cable or cause deterioration to the jacketing materials and shall be used in all tests where required for the insulating compound to conform to specification requirements (see 6.4).

3.3 Suitability. The insulating compound shall be suitable for application and use on electrical cables, for insulating ends against moisture, and electrically insulating cable splices. It shall be so formulated to flow between conductors causing them to be sealed and insulated to preserve the electrical and physical properties of the cable against moisture, dirt, fumes, fungus, or other foreign materials.

3.4 Physical properties. The physical properties of the insulating compound shall be as specified in Table I.

3.5 Electrical properties. The electrical properties of the insulating compound shall be as specified in Table II.

3.6 Shelf storage life. Types I and III material furnished in either Class A or Class B packages shall be capable of being stored for 1 year from the date of manufacture and meet the requirements of Tables I and II , provided that the daily mean temperature of the ambient air at the storage location falls within the range of -40°C to 55°C (-40°F to 131°F) (see 4.5.13).

Source: https://assist.dla.mil -- Downloaded: 202610-19T11:46Z
Check the source to verify that this is the currentversion before use.

requirements of this MIL are met

TABLE I

PHYSICAL PROPERTIES

Test	Requirement		Test paragraph
	Type I	Type III	
Specific gravity (cured)	1.1 - 1.2	1.1 - 1.2	4.5.3
Viscosity (cps) (mixed) (max.)	3,600	1,500	4.5.4
Gel time (minutes) (100 gm. samples)	8.0 - 13.5	14.5 - 20.0	4.5.5
Tensile strength (psi) (min.)	2,500	400	4.5.6
Elongation (percent min.)	2	170	4.5.6
Water absorption (percent max.)	1	1	4.5.7
Shrinkage (percent max.)	1	1	4.5.8
Hardness	70 - 90 (Shore D)	60 - 70 (Shore A)	4.5.9

3.7 Stability test. After conditioning the specimens 28 days at 200 ±2°F at a minimum relative humidity of 95 percent as specified in 4.5.14, the insulating compound hardness shall not be less than 25 points and the volume resistivity shall not be less than 1 X 10^9 ohm-cm.

3.8 Corrosion. When tested as specified in 4.5.15, the cured resin shall not be corrosive to the metals from which the cable is manufactured.

3.9 Oil resistance. When tested as specified in 4.5.16, the cured resin shall show no evidence of warping, splitting, or softening.

3.10 Package strength (Class A packages only). When tested as specified in 4.5.17, the packages shall have strengths listed in Table III.

Source: https://assist.dla.mil -- Downloaded: 202610-19T11:46Z
Check the source to verify that this is the current version before use.

TABLE II

ELECTRICAL PROPERTIES

Test	Requirement		Test paragraph
	Type I	Type III	
Dielectric strength (volts/mil 1/8-inch sample)	300 (min.)	300 (min.)	4.5.10
Dielectric constant (max.) 100 Hertz			4.5.11
30°C	4.0	6.0	
60°C	5.0	7.5	
70°C	6.5	-	
Dissipation factor (max.) 100 Hertz			4.5.11
30°C	0.03	0.25	
60°C	0.08	0.15	
70°C	0.30	0.05	
Volume resistivity, (min.) (23.1 ±1.1°C) (ohm-cm)	3.3×10^{13}	4.0×10^{13}	4.5.12

TABLE III

TEST VALUES FOR UNIT PACKAGE INNER BAG

Tests (Types I and III, Class A)	Test value and tolerance
Package strength (4.5.17): Shall not leak	Pounds:
2-3/4 fl. oz. size	200 (min.)
6-1/4 fl. oz. size	250 (min.)
12-1/2 fl. oz. size	300 (min.)
Air inclusion (4.5.18):	Sq. inch:
2-3/4 fl. oz. size	0.25 (max.)
6-1/4 fl. oz. size	.35 (max.)
12-1/2 fl. oz. size	.50 (max.)

Source: https://assist.dla.mil -- Downloaded: 202610-19T11:46Z
Check the source to verify that this is the currentversion before use.

3.11 Air inclusion tests (Class A packages only). When tested as specified in 4.5.18, the air inclusion in the packages shall not exceed the values listed in Table III.

3.12 Workmanship. Workmanship shall be in accordance with high grade practice for this type of material.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services to prescribed requirements.

4.2 Classification of inspection. The inspection requirements of the insulating compound shall be classified as follows:

(a) First article inspection (see 4.3)
(b) Quality conformance inspection (see 4.4)

4.3 First article inspection. First article inspection shall consist of all the requirements (Section 3) and of all the tests (4.5) of this specification, and any additional inspections required by the contract or purchase order. The responsibility for the performance of first article inspection shall be as specified by the procuring activity (see 6.2).

4.3.1 First article samples. Samples for first article inspection shall be obtained from the materials to be furnished for each type and class. Samples for Type I or Type III insulating compound furnished as Class A shall consist of ten film bags, each containing not less than 6 fluid ounces. Samples for Type I or Type III insulating compound furnished as Class B shall consist of three one-quart metal containers of resin and sufficient catalyst for the resin system. Samples shall be selected at random from material which has been manufactured using the same production processes, procedures and equipment which will be used in filling the contract.

4.3.2 First article sample and inspection for a subsequent contract. If a contractor has previously furnished insulating compound in accordance with the requirements of this specification and his product has been found to be satisfactory, the requirements for a first article sample and its submittal for any subsequent contract or order may be waived at the discretion of the procuring activity (see 6.2.1).

Source: https://assist.dla.mil -- Downloaded: 20260-19T11:46Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection.

4.4.1 Lot formation. Unless otherwise specified, a lot shall consist of all insulating compound of the same type and class, manufactured at one time from one batch, forming part of one contract or order, and submitted for acceptance at the same time and place.

4.4.2 Sampling.

4.4.2.1 Sampling for quality conformance inspection. Two or more filled film bags (Class A), or metal containers (Class B), as applicable, sufficient to provide not less than 12-1/2 fluid ounces of admixed compound, shall be selected at random from each lot and shall be tested as specified in 4.4.3.1.

4.4.2.2 Sampling for preparation for delivery. A quantity of shipping containers prepared for delivery, just prior to closure, shall be selected in accordance with MIL-STD-105 and subjected to the examinations specified in 4.4.3.2.

4.4.3 Inspection procedure.

4.4.3.1 Inspection of sample for quality conformance. Test specimens shall be prepared from the samples selected in accordance with 4.4.2.1. The specimens shall be tested to the requirements of Table IV. In addition, the sample may be subjected to any other test specified herein, when considered necessary by the procuring activity, to insure conformance to the requirements of this specification. Nonconformance of test specimens to a single requirement (Table IV) shall be cause for rejection of the lot represented by the sample.

TABLE IV

QUALITY CONFORMANCE TESTS

Requirement	Test paragraph
Viscosity	4.5.4
Gel time	4.5.5
Dielectric strength	4.5.10
Package strength	4.5.17
Air inclusion	4.5.18

Source: https://assist.dla.mil -- Downloaded: 20260-19T11:46Z
Check the source to verify that this is the current version before use.

4.4.3.2 Examination of preparation for delivery. The samples selected in accordance with 4.4.2.2 shall be examined for proper filling or weight, markings, mixing instructions, and leakage, either external or between compartments of the container. Any package having one or more defects or under required fill shall be rejected. If the number of defective packages exceeds the Acceptable Quality Level (AQL) of 2.5 percent defective in accordance with Level S-2 of MIL-STD-105, the lot represented by the sample shall be rejected.

4.5 Tests.

4.5.1 Standard conditions. Unless otherwise specified herein, all mixing, curing, and tests shall be performed at 73 ±2°F (23 ±1°C) and a relative humidity of 50 ±4 percent.

4.5.2 Test specimens.

4.5.2.1 Molds.

4.5.2.1.1 Mold for sheet specimens. Unless otherwise specified in the contract or order, the mold shall consist of two highly polished plates, 3/8-inch thick, coated with a release agent and spaced by 1/8-inch thick U-shaped spacers of polytetrafluoroethylene or any suitable material to which the compound will not adhere. The mold assembly shall be clamped together with sufficient pressure to prevent leakage of the compound. A mold to produce 6-inch by 6-inch specimens is suggested. The resulting cast slabs shall then be cut into the test specimens required.

4.5.2.1.2 Mold for shrinkage tests. The mold for linear shrinkage shall be a mold which will cast a test specimen 4 inches long by 3/4 inch wide by 1-1/4 inches high. The tolerance for the dimensions of the length and width shall be 0.010 inch. There shall be no variations of the length and width of the cast specimen because of such causes as mold release, flashing not being removed, or other inaccuracies of the mold which would give false readings for these dimensions. A suitable mold release shall be used to assure that the test specimen will not adhere to the mold.

4.5.2.2 Casting. The compound ingredients shall be mixed in accordance with the manufacturer's directions, then poured into the molds. When the ingredients are mixed at temperatures above 23°C, the molds shall be preheated approximately 10°C above the mixing temperature before the mixture is poured into the molds. In pouring, precautions shall be taken to avoid the entrapping of air.

4.5.2.3 Curing of test specimens. Unless otherwise specified in the individual test method, specimens shall be cured for 48 ±2 hours at 73 ±2°F (23 ±1°C) at relative humidity of 50 ±4 percent. All specimens shall be removed from the molds in 24 ±2 hours, and total cure time shall

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:46Z
Check the source to verify that this is the current version before use.

include the time the specimen is in the mold. Unless otherwise specified, cured specimens shall be tested within 2 hours from the end of the cure period.

4.5.3 Specific gravity. The specific gravity of the cast resin shall be determined by Method 5011 of Fed. Test Method Std. No. 406. Three specimens shall be tested and the average of the three determinations shall be reported.

4.5.4 Viscosity. The viscosity of the mixed resin and hardener shall be determined by means of a Brookfield viscosimeter or equal, according to the directions supplied by the manufacturer of the instrument, at a temperature of 25° ±0.5°C. The viscosimeter spindle and speed shall be according to directions supplied by the manufacturer of the instrument consistent with viscosity of the material tested at a temperature of 25° ±0.5°C. The use of 25°C temperature allows a 2°C rise over the 23°C standard test temperature. This rise usually occurs as a result of stirring, mixing, and handling.

4.5.5 Gel time. Samples for the gel time shall be mixed in accordance with the manufacturer's instructions, except that immediately before mixing, the materials shall be stabilized at an ambient temperature of 25 ±0.5°C. The sample, consisting of a 100-gram mass, shall be poured into a 3-ounce paper cup immediately after mixing. The samples shall be placed in a suitable clear plastic box (approximately 9 inches by 9 inches by 9 inches) for reduction of drafts. The gel time shall be reported as the time required for the insulating compound to become stringy, as determined by the raising and lowering of a 1/16 inch applicator stick. The resin need not become completely solid for this gel point.

4.5.6 Tensile strength.

4.5.6.1 Type I. Tensile strength and elongation tests shall be performed in accordance with Method 1012 of Fed. Test Method Std. No. 406.

4.5.6.2 Type III. The test shall be performed in accordance with ASTM D 412.

4.5.7 Water absorption. Water absorption shall be determined in accordance with procedure A of Method 7031 of Fed. Test Method Std. No. 406.

4.5.8 Linear shrinkage. Three specimens 4 inches long by 3/4 inch wide by 1-1/4 inches high shall be cast in a mold as specified in 4.5.2.1.2 and 4.5.2.2.

4.5.8.1 Dimensions. The length and width of each specimen shall be determined by averaging three determinations of each dimension. The percent linear shrinkage shall be calculated as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:46Z
Check the source to verify that this is the current version before use.

$$\frac{\text{Mold dimension - average specimen dimension}}{\text{Mold dimension}} \times 100$$

This shall be done for both dimensions on each specimen. The percent of linear shrinkage shall be reported as the average of the six determinations.

4.5.9 Hardness. The hardness of each test specimen of 4.5.14.1 shall be determined in accordance with ASTM D 2240 after the specimens have been allowed to cure for a maximum of 7 days at standard laboratory conditions (4.5.1). The reading shall be taken after the durometer presser foot is in contact with the specimen for 15 seconds and checked for conformance to Table I.

4.5.10 Dielectric strength. Dielectric strength tests shall be performed in accordance with the procedures of Method 4031 of Fed. Test Method Std. No. 406.

4.5.11 Dissipation factor and dielectric constant. The test circuit in Method 4021 of Fed. Test Method Std. No. 406, or equivalent, shall be used.

4.5.11.1 Specimens. One specimen shall be cast as specified in 4.5.2.2. Three disks or squares of suitable size shall then be cut from the slab for measurement.

4.5.11.2 Electrodes. Metal foil electrodes of suitable size and without guard rings shall be applied to the specimen by using a very thin film of petrolatum. The electrodes so applied shall be thoroughly rolled to exclude air.

4.5.11.3 Procedure. Dissipation factor and capacitance measurements shall be made on each specimen at 100 Hertz at 30°C, 60°C and 70°C.

4.5.11.4 Report. The average of three measurements at each temperature shall be reported.

4.5.12 Volume resistivity. Volume resistivity tests shall be performed in accordance with the procedures of Method 4041 of Fed. Test Method Std. No. 406. Four disk specimens, 3 inches in diameter and 1/8 inch thick shall be prepared as specified in 4.5.2.1.1. Volume resistivity shall be conducted on two of the specimens for conformance to Table II. The remaining two specimens shall be cured with the six hardness test specimens of 4.5.14.1 and subjected to conditioning as specified in 4.5.14.2.

4.5.13 Shelf storage life. The manufacturer shall submit an affidavit signed by a responsible official of management attesting that the insulating compound and primer when applicable, are capable of being stored for one year and meet the physical and electrical requirements specified in 3.6.

Source: https://assist.dla.mil -- Downloaded: 20261O-19T11:46Z
Check the source to verify that this is the current version before use.

4.5.14 Stability test.

4.5.14.1 Specimens. Hardness test specimens of the compound shall be prepared as specified in 4.5.2.1.1 except that specimens shall be 3 inches by 3 inches and shall have a thickness of 0.30 ±0.05 inch. Casting shall be as in 4.5.2.2, except that specimens shall be allowed to cure for a maximum of 7 days at standard laboratory conditions. Six specimens are required. The two specimens of 4.5.12 shall also be cured for 7 days.

4.5.14.2 Procedure. The six hardness test specimens of 4.5.14.1 and the two volume resistivity specimens of 4.5.12 shall be subjected to conditioning at 200 ±2°F and a minimum relative humidity of 95 percent for a period of 28 days. The eight test specimens shall be placed on suitable metal trays and placed in a pyrex battery jar or desiccator containing a saturated solution of potassium sulfate (K_2SO_4) in the bottom section to provide the required relative humidity. The desiccator shall be sealed and placed in a forced air oven maintained at 200° ±2°F.

4.5.14.3 Report. The eight specimens shall be removed from the test apparatus and conditioned to standard conditions (4.5.1) for 4 hours. Immediately after conditioning, each of the six test specimens of 4.5.14.1 shall again be tested for hardness for conformance to 3.7. The hardness of any one test specimen shall not be less than 25 points. The readings shall be taken after the durometer presser foot is in contact with the specimen for 3 seconds. Failure of more than one of the six specimens shall constitute failure of the material. The volume resistivity test shall be conducted on the two specimens prepared in 4.5.12 and checked for conformance to 3.7. Failure of either specimen shall constitute failure of the material.

4.5.15 Corrosion. A polished pure copper strip approximately 1 inch wide by 3 inches long of a convenient thickness shall be covered on one side with the primer (if applicable) and insulating compound mixed in accordance with 4.5.2.2, and allowed to remain for 48 hours. At the end of this period, the compound shall be removed from the copper strip and the strip examined for evidence of corrosion. Primer, when specified, by the manufacturer shall be coated on a separate copper strip as noted above and allowed to remain for 48 hours. The primer shall be removed from the strip and the copper strip examined for evidence of corrosion. Pitting or corrosion of the copper shall be cause for rejection. Discoloration of the copper shall not be considered objectionable.

4.5.16 Oil resistance. A test specimen of the insulating compound shall be subjected to the hot oil bath test, Method 6061 of Fed. Test Method Std. No. 406. The temperature of the oil bath shall be a minimum of 75° ±2°C. Any evidence of warping, splitting, or softening of the specimen after the bath shall be cause for rejection.

4.5.17 Package strength test (Class A only). The filled inner bag enclosed in its outer bag (see 5.1.1.1) shall be placed between two flat

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:46Z
Check the source to verify that this is the current version before use.

steel plates, 6 inches by 12 inches by 0.25 inch thick. This assembly shall be placed in a suitable hydraulic press and loaded for not less than 1 minute to the load prescribed in Table III for the package size under test. Following this test, the inner bag shall be removed from its outer bag and examined for rupture. Any leakage from the inner bag or transfer of contents from one compartment to the other shall be cause for rejection of the lot represented.

4.5.18 Air inclusion test (Class A only). Following the test of 4.5.17, the inner bag shall be laid on a flat horizontal surface and allowed to rest until the included air bubbles, if any, float to the top surface of the bag. The combined area of the bubbles, as viewed through the top surface of the bag, shall not exceed the prescribed values of Table III for the applicable size package.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be Level A, or C as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Types I and III, Class A unit package. The unit package shall consist of a bag made of flexible transparent high strength film. The bag shall have two compartments with an internally rupturable barrier separating the two compartments and shall be rupturable by manipulation of the bag without the aid of tools. The inner bag shall permit mixing of the bag with the hands after rupture of the internal barrier. The physical properties of the bag shall conform to the values shown in Table III. Unless otherwise specified in the contract or order, the insulating compound shall be furnished in 2-3/4, 6-1/4, or 12-1/2 fluid ounce size, as specified (see 6.2).

5.1.1.1.1 The unit package specified in 5.1.1.1 shall be further protected by placing the bag in another bag conforming to Type III, Class B of MIL-B-117, and sealed. This bag is further protected by packaging in a box conforming to PPP-B-566 or PPP-B-665. Alternately, the unit package specified in 5.1.1.1 may be placed in a metal container conforming to Type I, II, III, or V of PPP-C-96. The protective coating shall conform to Plan A of PPP-C-96. The use of paper labels conforming to manufacturer's commercial practices are acceptable.

5.1.1.2 Types I and III, Class B unit package. Unless otherwise specified in the contract or order, the compound shall be furnished in one quart size (see 6.2). The unit package shall consist of 2 metal cans, one containing the resin and the other, the hardener. Cans shall conform to Type I, II, III or IV of PPP-C-96. When specified in the contract or order (see 6.2), the resin and hardener shall be furnished in preweighed containers.

Source: https://assist.dla.mil -- Downloaded: 202610-19T11:46Z
Check the source to verify that this is the current version before use.

The preweighed resin containers shall have sufficient room to allow a preweighed container of the hardener to be emptied into it and blended by stirring. The two cans (one resin and one hardener) shall be placed in a box conforming to PPP-B-566 or PPP-B-665. The box shall be securely closed to prevent accidental opening. In no instance will the hardener and the resin be packaged separately.

5.1.2 Level C. Types I and III unit packages shall be packaged in accordance with the manufacturer's commercial practice. Packaging shall be sufficient to afford adequate protection against deterioration and physical damage during shipment from supply source to the first receiving activity for immediate use.

5.2 Packing. Packing shall be Levels A, B, or C as specified (see 6.2).

5.2.1 Level A. Types I and III unit packages shall be packed in a fiberboard box conforming to Type SF or CF, Class Domestic and shall be sealed according to the appendix, Method I of PPP-B-636. When specified in the contract or order, the packages shall be further overpacked in cleated plywood boxes conforming to PPP-B-601 (Overseas Type) or Class 2, Style 2 or 4 nailed wood boxes conforming to PPP-B-621. The boxes shall have a case liner conforming to Type I or III, Class A of MIL-L-10547. Weight of contents shall conform to weight limitations of the applicable box specification and shall not exceed a total weight of 200 pounds.

5.2.2 Level B. Types I and III unit packages shall be packed in snug-fitting shipping containers conforming to Type CF or SF, Class Domestic in accordance with PPP-B-636. Closure shall be as specified for Method I. Contents of the boxes shall not exceed the weight and size of the type and class of the box selected.

5.2.3 Level C. Insulating compound packaged in accordance with 5.1.2 shall be packed to afford protection against damage during direct shipment from the supply source to the first receiving activity for immediate use. Containers shall conform to the carrier rules and regulations applicable to the mode of transportation.

5.3 Marking. In addition to any special marking required by the contract or order (see 5.3.1 and 6.2), packages and shipping containers shall be marked in accordance with MIL-STD-129.

5.3.1 Mixing instructions. Each unit package shall be permanently and legibly marked with the instructions for mixing and application of the insulating compound. The marking shall include the maximum storage life of the insulating compound and any other pertinent information, such as the storage conditions and precautions to be taken in handling the insulating compound to avoid any toxic effect (see 6.3).

Source: https://assist.dla.mil -- Downloaded: 202610-19T11:46Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use (Types I and III, Class A). Insulating compounds are intended primarily for field splicing applications with or without suitable preforms as required (see 6.5). Types I and III, Classes A and B, may also be used by original equipment manufacturers in like applications.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type and class required (see 1.2).
(c) Unit package size required (see 5.1.1.1 or 5.1.1.2).
(d) Special markings, if required (see 5.3).
(e) Level of packaging and packing (see 5.1 and 5.2).
(f) Preweighed containers required and size of containers.
(g) Responsibility for the performance of first article inspection (see 3.1 and 4.3).

6.2.1 Contracts or orders shall specify the following provisions for the first article inspection:

6.2.1.1 Whether first article inspection is required. When a contractor is in continuous production of the insulating compound from contract to contract, consideration should be given to waive the first article inspections. If inspection is required, indicate:

(a) Where the first article inspection is to be conducted (at the contractor's plant or Government or commercial laboratory).
(b) That the approval of first article samples or the waiving of the first article inspection shall not relieve the contractor of his obligation to fulfill all other requirements of the specification and contract.

6.3 Handling precautions.

6.3.1 Toxicology. Certain unreacted monomers and catalysts are known to cause some toxic effects if no precautions are taken. In general, the following precautions are suggested:

(a) Handle only in well-ventilated areas.
(b) Avoid skin contact.
(c) Wear protective clothing when contact is anticipated.
(d) Protect eyes from curing agent.
(e) Cleanse the skin regularly with a mild soap and water.
(f) Reassign employees allergic to these materials.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:46Z
Check the source to verify that this is the current version before use.

6.4 Primer. Manufacturer's instructions in cable preparation shall be followed to insure maximum adhesion to cable insulation and jacket.

6.5 Preforms. Preforms designed to fit various cable configurations may be employed for holding the cable ends during splicing. The preforms will produce greater uniformity in splicing thicknesses and will also reduce resin wastage.

6.6 Cross reference of classification. Type II material previously furnished under MIL-S-22266B(ASG) dated 26 July 1961 has been deleted. Former Types I and II items should be utilized until stocks are depleted. Type III is a new composition material, polyurethane resin.

6.7 Marginal indicia. Asterisks are not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Custodians:
Army - EL
Navy - AS
Air Force - 11

Review activities:
Army - EL
Navy - AS, SH
Air Force - 80, 84
DSA - GS

Preparing activity:
Navy - AS
(Project No. 5970-0377)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T11:46Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION MIL-I-22266C, INSULATING COMPOUND, ELECTRICAL (FOR FIELD SPLICING APPLICATIONS)

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 83 1426

REPLACES EDITION OF 1 OCT 84 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 202610-19T11:46Z
Check the source to verify that this is the current version before use.

be cut adjacent to the issue. Fold the latter securely as a pencil mailer to protect the

FOLD

DEPARTMENT OF THE NAVY

Naval Air Engineering Center
Philadelphia, Pennsylvania 19112

POSTAGE AND FEES PAID
NAVY DEPARTMENT

OFFICIAL BUSINESS

Weapons Engineering Scandardization Office (Code X)
Naval Air Engineering Center
Philadelphia, Pennsylvania 19112

FOLD

Source: https://assist.dla.mil -- Downloaded: 202610-19T11:46Z
Check the source to verify that this is the current version before use.