
FEDERAL SPECIFICATION SHEET

RUBBER, SILICONE; NONMETALLIC SPECIAL SHAPED SECTION

This specification is approved by the Assistant Administrator, Office of Federal Supply and Services, General Services Administration, for the use of all Federal agencies.

The complete requirements for procuring the sections described herein shall consist of this document and the latest issue of ZZ-R-765/GEN.



BUMPER STRIP

PART NO. ZZR765/32-	A Height	B Width	C Inside Radius	D Outside Radius	E Base Flange Thickness	Length	Minimum Tensile Strength P.S.I	Temperature Rating °F
001A5	0.380	1.000	0.135	0.210	0.075	96.00	700	-100 to 425
002E5*	0.500	1.250	0.210	0.250	0.060	A/A	1200	-130 to 400

*Special Features - 0.030 inch first fillet radius.

AMSC: N/A

/FSC 9320/

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited.


Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:27Z
Check the source to verify that this is the current version before use.

NOTES: 1. Dimensions are in inches.
2. Nonmetallic Hardness Rating: 45.0 minimum to 55.0 maximum. Shore Durometer A.
3. Color: Natural.
4. Minimum Tensile Strength psi.
5. A/A : Any Acceptable.
6. When metric units are required, units for inch, degree fahrenheit and psi may be converted to the metric equivalent as follows:

English	Multiply by	Equals	Metric unit
inch	2.54	=	centimeter (cm)
degree fahrenheit	(t°F-32)/1.8	=	degree Celsius (°C)
psi	6.894×10^{-3}	=	mega pascal (MPa)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:27Z
Check the source to verify that this is the current version before use.

PART NUMBERING SYSTEM FOR FEDERAL SPECIFICATION ZZ-R-765/GEN



MILITARY INTERESTS:

Custodians

Army -- MR
Navy -- AS
Air Force -- 20

Review activity

DLA -- GS

CIVIL AGENCY COORDINATING ACTIVITY:

GSA -- FSS

PREPARING ACTIVITY:

Army -- MR

Project No. 9320-0386

(KBWP# ID-7078A/DISK-0535A. FOR AMMRC USE ONLY).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:27Z
Check the source to verify that this is the current version before use.