INCH-POUND

MIL-C-48161B (AR)
AMENDMENT 3
27 March 2001
SUPERSEDING
AMENDMENT 2
06 September 1996

MILITARY SPECIFICATION

CARTRIDGE, IGNITION, M702 PARTS FOR

MIL-C-48161B was inactivated after 14 February 1997 for new design.

This amendment forms a part of MIL-C-48161B (AR), dated 12 August 1987, and is approved for use by the U.S. Army Armament, Research, Development and Engineering Center, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 7

* 4.4.2.1, Delete note (a) in its entirety and substitute:

"(a) Beginning with the first lot produced and continuing until three consecutive lots have complied with applicable requirements, the sampling plan shall be in accordance with MIL-STD-105, code letter J, AQL of 0.65%. After three consecutive lots have met the criteria, code letter F and AQL of 0.65% applies."

PAGE 9

4.4.2.3, Major category:

Major 112: Change "0.065%" AQL to read "(a)" and add note (a) which reads, "See 4.4.3.1."

Major 113: Delete in its entirety and substitute:

"113. Depth of pellet cavity ...0.40%...3.2...Gage"

Major 114: Delete in its entirety.

AMSC N/A **FSC 1310**

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

PAGE 11

4.4.2.4, Minor 206: Change “Depth of spanner holes” to read “Depth of spanner holes, min.”

PAGE 14

4.4.2.6, Body: Major category:

Major 121: Change “0.065%” AQL to read “(a)” and add note (a) which reads, “See 4.4.3.1.”

Major 122: Delete in its entirety.

Major 123: Delete in its entirety.

Minor category: Minor 201: Change “Gage” to read “Visual”.

PAGE 15

4.4.3.1, Delete in its entirety and substitute:

“4.4.3.1 Salt spray test. For purposes of the salt spray test, the lot size shall not exceed the number of parts anodized during one eight-hour production period. Sampling of flash tubes and bodies from the anodized lots shall be in accordance with MIL-STD-105, Table II A, Level S-3 at 0.65% AQL.

In performing the test, samples from more than one lot may be tested in the same salt spray chamber; however, identity of components and their representative test specimens must be maintained. After passing the test, anodized lots from which the samples were selected may be mixed together in accordance with normal procedures, and identity of the anodizing lot(s) is no longer required. (The test shall be performed as specified in paragraph 4.5.3.)”

PAGE 19

4.5.3, Line 6: Change “336” to read “96”.

6.3, Delete “AMSMC-QAT-I” and substitute “AMSTA-AR-QAA-C”.

The margins of this amendment are marked with an asterisk or vertical line to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1310-0626)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:15Z
Check the source to verify that this is the current version before use.