MIL-C-13664A (Ord)
30 January 1962
SUPERSEDING
MIL-C-13664 (Ord)
24 September 1954
(SEE SECTION 6.)

MILITARY SPECIFICATION

CLIP, CARTRIDGE (FOR U.S. RIFLES, CALIBER .30, M1, M1C, AND M1D)

1. SCOPE

1.1 This specification covers one type of eight-round cartridge clip for U. S. Rifles, Cal .30, M1, M1C, and M1D.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids, form a part of this specification to the extent specified herein:

SPECIFICATIONS

Military

MIL-P-116	- Preservation, Methods of.
MIL-W-13855	- Weapons, Small Arms, General Specification for.
MIL-I-45208	- Inspection Requirements, General Specification for.

FSC 1305

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:59Z
Check the source to verify that this is the current version before use.

STANDARDS

Military

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-109	- Inspection Terms and Definitions.

DRAWINGS

Ordnance Corps

F6528288	- Clip, Cartridge.
GL6528288	- List of Inspection Gages.

PUBLICATIONS

Ordnance Corps

P6528288	- Packaging Data Sheet for Clip, Cartridge.

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Production samples. A sample of 100 clips representing initial production, representative of the normal production process utilized by the contractor, and representative of materiel which has been inspected and determined to be acceptable by the inspector, exclusive of the functioning test (see 4.4.2) shall be commercially packaged and identified with drawing and specification numbers, revision numbers and dates, contract number, name of contractor, and District Office. Thereafter a sample of 50 clips representing each month's production shall be packaged and identified as specified above. Monthly samples shall be submitted until three consecutive samples have been determined satisfactory by the testing agency. Accompanied by copies of the required certifications of the chemical analysis, physical tests, etc., samples shall be forwarded prepaid by the contractor to Springfield Armory, Springfield 1, Massachusetts, Attn: ORDBD-IA.

3.2 Materials, construction, and design. Clips shall conform to the requirements specified on Drawing (Dwg.) F6528288, and the materials and construction shall be in accordance with the applicable provisions of Specification MIL-W-13855. Clips shall be free of cracks, dents, tears, laminated stock, or incomplete embossing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:59Z
Check the source to verify that this is the current version before use.

3.2.1 Supplementary coating weight. The weight of the supplementary coating of clips shall be as specified on the applicable drawing when tested as specified in 4.4.1.

3.2.2 Functioning. Clips shall be capable of being loaded with eight cartridges and after loading shall operate without malfunctioning when tested as specified in 4.4.2.

3.3 Marking. Each clip shall be clearly marked in accordance with the applicable drawing.

3.4 Workmanship. Workmanship shall be in accordance with the workmanship requirements of Specification MIL-W-13855.

4. QUALITY ASSURANCE PROVISIONS

4.1 General quality assurance provisions. The supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. Inspection records of the examination and tests shall be kept complete and available to the Government as specified in the contract or order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Contractor's inspection system. The contractor shall provide and maintain an inspection system in accordance with Specification MIL-I-45208.

4.1.2 Inspection terms and definitions. Inspection terms and definitions used herein are in accordance with Standard MIL-STD-109. Whenever the term "inspector" is used herein, it denotes Government inspector.

4.2 Production samples. The designated testing agency will subject production samples to the examination and tests specified herein and such other examination and tests as are necessary to determine compliance with the requirements of the contract. The contractor will be informed of the results of any tests which indicate failure of the clips to meet prescribed requirements.

4.3 Inspection provisions.

4.3.1 Inspection lot. The formation, size, and presentation of inspection lots shall be in accordance with Standard MIL-STD-105. The inspector shall insure that inspection lots are as large as practicable, in consideration

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:59Z
Check the source to verify that this is the current version before use.

of quality history, manufacturing conditions, and contractor's delivery schedule, and within the limitations of Specification MIL-W-13855.

4.3.2 Examination. Examination of clips and packaging shall be performed in accordance with 4.3.2.3 and with the applicable inspection provisions of Specification MIL-W-13855.

4.3.2.1 Clips. Sample size shall be in accordance with Standard MIL-STD-105, using inspection level II.

4.3.2.2 Packaging. Sample size shall be in accordance with Standard MIL-STD-105, using inspection level I.

4.3.2.3 Classification of defects. Classification of defects and acceptable quality levels (AQL's) for examination in accordance with Standard MIL-STD-105 shall be as specified herein and shall include the following provisions:

(a) The AQL listed for each defect shall be applied to the individual defect, not to a group of defects.
(b) Listings under "Zone on Dwg: F6528288" are given as an aid in locating applicable dimensions or values.
(c) The presence of nicks, burrs, scratches, tool marks, missing operations, or other signs of poor workmanship on important areas of parts should be carefully considered.
(d) The drawing number under "Inspection method" indicates the existence of a Government gage design (see List of Inspection Gages, GL6528288).
(e) Examination for packaging defects specified in 4.3.2.3.2 shall apply to each clip or container, as applicable.

4.3.2.3.1 Clip, cartridge (Dwg. F6528288). See 4.3.2.3.2 for examination of packaging.

Categories	Defect	AQL	Inspection method	Zone on Dwg. F6528288
Critical:	None defined.			
Major:				
101	Distorted or broken clips.	0.065	Visual	
102	Alignment.	1.0	C5520508	E3 and D4
103	Form of back plate, under min.	1.0	D6511396	B8
104	Location of clip latch slot, over max.	1.0	D6511392	C5

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:59Z
Check the source to verify that this is the current version before use.

Categories	Defect	AQL	Inspection method	Zone on Dwg. F6528288
105	Location of clip latch slot, under min.	1.0	D6511392	C5
106	Location of bolt clearance radius.	1.0	D6511392	C5
107	Width of front end, under min.	1.0	D6511363	D1
108	Width of sides, front, over max.	1.0	D6511397	E1
109	Width in front of interior ribs.	1.0	D6511398	B3
110	Width of clip latch slot, under min.	1.0	B6045892	C4
111	Depth of clip latch slot, under min.	1.0	B6045892	C4
112	Height of notches (underside of latch slot).	1.0	F7319247	E6
113	Width of interior ribs, over.	1.0	B6045900	B5
114	Radius, front end.	1.0	C5520513	E1
115	Width of front end, over max.	1.5	D6511363	D1
116	Width of sides, front, under min.	1.5	D6511397	E2
117	Relative height of sides.	1.5	D6511398	E2
118	Width between interior ribs, under min.	1.5	D6511398	B2 and B3
119	Cracks, dents, tears, laminated stock or incomplete embossing (see 3.2).	1.5	Visual	
Minor:				
201	Form of back plate, over max.	2.5	D6511396	B8
202	Width in front of exterior ribs, over max.	2.5	D6511398	E3
203	Width in front of exterior ribs, under min.	2.5	D6511398	E3
204	Width between interior ribs, over max.	2.5	D6511398	B2 and B3
205	Depth of clip latch slot, over max.	2.5	B6045892	C4

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:59Z
Check the source to verify that this is the current version before use.

Categories	Defect	AQL	Inspection method	Zone on Dwg. F6528288
206	Height of detent, over max.	2.5	A5076772	B4
207	Height of detent, under min.	2.5	A5076772	B4
208	Height of embossing, over max. (embossing plus metal thickness).	2.5	Micrometer	B2 and C3
209	Height of embossing, under min. (embossing plus metal thickness).	2.5	Micrometer	B2 and C3
210	Phosphate coating (missing or defective).	2.5	Visual	D8
211	Identification marking (missing or illegible).	2.5	Visual	B5 and B6
212	Workmanship (See 3.4).	4.0	Visual	

4.3.2.3.2 Packaging.

Categories	Defect	AQL
Critical:	None defined.	
Major:		
101	Incorrect or illegible marking (see Packaging Data Sheet P6528288).	1.0
102	Inadequate cleaning (see Packaging Data Sheet P6528288).	1.5
103	Improper preservative application (see Packaging Data Sheet P6528288).	1.5
104	Improper shipping container (see Packaging Data Sheet P6528288).	1.5
105	Improper closure of shipping container (see Packaging Data Sheet P6528288).	1.5
106	Incorrect quantity, weight count, of clips per shipping container (see Packaging Data Sheet P6528288).	1.5
Minor:		
201	Workmanship (see 5.4).	4.0

4.3.3 Testing. In addition to the applicable test provisions specified in Specification MIL-W-13855 and other tests required by applicable drawings and specification, the following tests shall apply. Unless otherwise specified herein, tests shall be performed on samples taken from each

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:59Z
Check the source to verify that this is the current version before use.

inspection lot. Test fixtures and equipment shall be in accordance with Government drawings, or in the absence of drawings, shall be approved by the procuring agency.

4.3.3.1 Material testing. Tests required by applicable drawings and specifications shall be performed on materials used in the manufacture of clips. The contractor shall furnish the inspector certified copies of chemical and check analysis and reports of physical tests as may be required for each lot of each material used. The contractor shall also furnish the inspector with certification that the materials used in packaging conform to the applicable specifications.

4.3.3.2 Hardness testing. Samples of clips taken from each heat-treat batch shall be tested by the contractor for the hardness requirements specified on the applicable drawing. The sample size shall be in accordance with Standard MIL-STD-105, using code letter I and an AQL of 1.5 percent defective of the double sampling plan. A heat-treat batch shall consist of clips heat-treated in a batch-type furnace at one charge or in a continuous type furnace during an uninterrupted period extending over not more than one day's production.

4.3.3.3 Protective finish testing.

4.3.3.3.1 Accelerated corrosion. Accelerated corrosion testing of clips shall be performed by the contractor in accordance with the applicable drawing and specifications. The sample size shall be in accordance with Standard MIL-STD-105, using code letter H and an AQL of 2.5 percent defective of the double sampling plan.

4.3.3.3.2 Supplementary coating weight. A sample of 7 clips with supplementary coating taken from each 8 hours of use from each processing system or from each inspection lot shall be tested by the contractor for supplementary coating weight using the test methods specified in 4.4.1. Failure of clips to meet the specified supplementary coating weight requirement shall cause rejection of the represented lot.

4.3.3.4 Functioning testing. A sample of 20 clips from each production sample (see 3.1) shall be tested by the testing agency for functioning using the test methods specified in 4.4.2. Clips failing to function properly shall be inspected as necessary to determine compliance with drawing requirements.

4.3.3.5 Determination of cleanliness testing. Clips shall be tested by the contractor for cleanliness using the test methods specified in 4.4.3. Sampling shall be in accordance with Specification MIL-P-116.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:59Z
Check the source to verify that this is the current version before use.

4.3.4 Inspection equipment. Unless otherwise specified in procurement documents (see 6.1), responsibilities for acquisition, maintenance, (including calibration of standards), and disposition of acceptance inspection equipment prescribed on List of Inspection Gages, Drawing GL6528288, shall be in accordance with Specification MIL-I-45208. Use of the contractor's or Government furnished inspection equipment, when desired by the inspector, shall be permitted without charge. Accelerated corrosion testing equipment and hardness testing equipment shall be provided by the contractor.

4.4 Test methods.

4.4.1 Supplementary coating weight test. The clips shall be tested for supplementary coating weight requirement (see 3.2.1) by conditioning the clips in an oven at 200° + 10° F. for at least 15 minutes to remove any remaining volatile solvent. After removal from the oven, the clips shall be cooled to room temperature and, using an analytical balance, individually weighed to the nearest milligram. The supplementary coating shall then be completely removed from the clips by chlorinated solvent vapor. Clips shall not be immersed in the liquid phase of the oil solvent to remove the supplementary coating. The clips shall then be cooled to room temperature and weighed in the manner of the first weighing. The difference in weight between the first and second weighing shall be calculated to determine compliance with the requirements specified on the applicable drawing.

4.4.2 Functioning firing test. The sample clips shall be tested for functioning requirement (see 3.2.2) by loading each clip with eight Government Standard caliber .30 cartridges and then firing the loaded clips in an M1, M1C, or M1D rifle.

4.4.3 Determination of cleanliness test. The clips shall be subjected to the determination of cleanliness test of Specification MIL-P-116.

5. PREPARATION FOR DELIVERY

5.1 Materials, methods, processes, and procedures. The materials, methods, processes, and procedures utilized in the preparation of clips for shipment shall be in accordance with the requirements specified herein and on Packaging Data Sheet P6528288.

5.2 Preservation, packaging, and packing. Clips shall be preserved, packaged, and packed in accordance with the requirements of Packaging Data Sheet P6528288.

5.3 Marking. Packages shall be clearly marked in accordance with Packaging Data Sheet P6528288.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:59Z
Check the source to verify that this is the current version before use.

5.4 Workmanship. Adequate controls shall be utilized to check for contamination of cleaning solvents and preservatives.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) List of applicable drawings and specifications pertinent to the clip showing applicable revision dates.
(c) List of inspection gages pertinent to the clip, showing applicable revision dates.
(d) Place of final inspection and acceptance (see "Notes" in Specification MIL-W-13855).
(e) Responsibilities for supply, maintenance, and disposition of acceptance inspection equipment if other than specified (see 4.3.4).
(f) Work programing for examination and testing of production samples should be effected with Springfield Armory at the earliest practicable date.

6.2 The methods and materials specified for level C on Packaging Data Sheet P6528288 are intended for use in the preparation for delivery of clips for domestic shipment from manufacturers to ammunition loading plants for immediate use.

6.3 This specification also supersedes Springfield Armory Purchase Description, SAPD-195, dated 20 September 1960, for Clip, Cartridge (For U. S. Rifles, Caliber .30, M1, M1C, and M1D).

NOTICE. When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Custodian:
Army - Ord

Preparing activity:
Army - Ord

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:59Z
Check the source to verify that this is the current version before use.