MIL-K-81576A(AS)
23 August 1983
SUPERSEDING
MIL-K-81576(AS)
27 June 1968

MILITARY SPECIFICATION

KIT - TOUCH-UP, FOR CORROSION CONTROL OF WEAPONS SYSTEMS

This specification has been approved by the Naval Air Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a touch-up kit containing materials that can be used in treating small areas of corrosion on weapons systems.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. Unless otherwise specified, the following specifications, standards, and handbooks of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation form a part of this specification to the extent specified herein.

SPECIFICATIONS

Federal

H-B-643	Brush, Acid Swabbing
H-B-695	Brush, Varnish, Flat
H-T-560	Toothbrush (For Adults and Children)
L-B-560	Bottle, Screw Cap (Polyethylene), 1.25 Ounces
L-P-390	Plastic, Molding and Extrusion Material, Polyethylene and Copolymers (Low, Medium, and High Density)

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commanding Officer, Naval Air Engineering Center, Lakehurst, NJ 08733) by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8010

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS (Continued)

Federal (Continued)

P-C-451	Coated Abrasive, Cloth, Aluminum Oxide and Silicon Carbide
GG-G-531	Goggles, Industrial and Spectacles, Industrial, Plastic
QQ-A-250/11	Aluminum Alloy 6061, Plate and Sheet
QQ-A-1876	Aluminum Foil
UU-T-595	Towel, Wiping, Paper, Industrial and Institutional
VV-L-800	Lubricating Oil, General Purpose, Preservative (Water-displacing, Low Temperatures)
ZZ-S-70	Scraper, Baker's (Plate and Bowl)
GGG-M-350	Mirror, Inspection
PPP-B-28	Bag, Plastic, (Sandwich)
PPP-B-636	Box, Shipping, Fiberboard
PPP-C-96	Can, Metal, 28 Gage and Lighter
PPP-P-1892	Paint, Varnish, Lacquer, and Related Materials, Packaging, Packing and Marking of

Military

MIL-P-116	Preservation, Methods of
MIL-C-5541	Chemical Conversion Coatings on Aluminum and Aluminum Alloys
MIL-A-8625	Anodic Coatings, for Aluminum and Aluminum Alloys
MIL-S-8802	Sealing Compound, Temperature Resistant, Integral Fuel Tanks and Fuel Cell Cavities, High Adhesion
MIL-A-9962	Abrasive Mats, Nonwoven, Nonmetallic
MIL-C-16173	Corrosion Preventive Compound, Solvent Cutback, Cold Application
MIL-P-17171	Plastic, Laminate, Decorative, High Pressure

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS (Continued)

Military (Continued)

MIL-T-21595	Tape, Pressure Sensitive, Plastic, Masking (For Paint Color Separation)
MIL-B-22191	Barrier Material, Transparent, Flexible, Heat Sealable
MIL-P-23377	Primer Coating, Epoxy Polyamide, Chemical and Solvent Resistant
MIL-C-43616	Cleaning Compound, Aircraft Surface
MIL-R-81294	Remover, Paint, Epoxy and Polyurethane Systems
MIL-C-81302	Cleaning Compound, Solvent, Trichlorotrifluoroethane
MIL-C-81309	Corrosion Preventive Compound, Water Displacing Ultra Thin Film
MIL-C-83286	Coating Urethane, Aliphatic Isocyanate, For Aerospace Applications
MIL-C-85054	Corrosion Preventive Compound, Water Displacing Clear (AMLGUARD)

STANDARDS

Federal

FED-STD-595	Colors

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	Marking for Shipment and Storage
MIL-STD-794	Parts and Equipment, Procedures for Packaging of
MS18012	Handle, Metal, Spring Bail Type
MS20257	Hinge, Continuous (Asg)
MS27971	Hasp, Hinged, Double Safety, with Fixed Staple, Steel

(Copies of specifications, standards, handbooks, drawings, and publications required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. The issues of the documents which are indicated as DoD adopted shall be the issue listed in the current DoDISS and the supplement thereto, if applicable.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D3951 Standard Practice for Commercial Packaging

(Application for copies of ASTM publications should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

OTHER

Air Transport Association Specification 300 - Packaging

(Application for copies should be addressed to the Air Transport Association, 1709 New York Avenue North West, Washington, DC 20006.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence.

3. REQUIREMENTS

3.1 First article. The touch-up corrosion control kits furnished under this specification shall be a product that has been inspected and has passed the first article inspection specified herein. When specified the contractor shall furnish samples for first article inspection (see 4.3 and 6.2).

3.2 Materials, construction and design. The touch-up corrosion control kit shall conform to the materials, construction and design requirements specified herein.

3.2.1 Materials. Materials used shall conform to the applicable specifications and as specified herein. Materials which are not covered by applicable specifications or which are not specifically described herein, shall be of the best quality, of the lightest practicable weight, and suitable for the purpose intended. Materials shall be free of defects and imperfections that will affect the serviceability of the touch-up corrosion control kits. Approval of non-specification material shall be obtained from the contracting officer.

3.2.2 Container. The container shall meet all applicable manufacturing, quality control standards, and requirements of Air Transport Association Specification 300, Category I, as well as the following additions and exceptions.

3.2.2.1 Container shell. The container shell shall be molded of linear polyethylene and shall be in accordance with L-P-390.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

3.2.2.2 Size and weight. The container size and weight shall be the minimum necessary to meet the structural requirement of this specification, be portable and retain the components of the kit in their assigned position throughout the testing. The maximum inside dimensions shall be 20 inches in length, 15 inches width, and 12 inches in height.

3.2.2.3 Color. The color of the shell shall be orange yellow conforming to color 13538 of FED-STD-595.

3.2.2.4 Finish. All aluminum parts shall be furnished in accordance with MIL-A 8625, Type II, Class 1.

3.2.2.5 Closure. A water-tight seal shall be accomplished by using an integrally molded plastic or an extruded aluminum tongue-in-groove, gasketed closure. The gasket must be one continuous length, round or extruded. When an aluminum extrusion is used for the closure, the aluminum shall conform to QQ-A-250/11, and both male and female extrusions shall be formed to the shape of the container parting line, welded to form two continuous pieces, and then treated. The extrusions must be joined to the container shell by a stake and roll method or mechanical crimping. Staking-crimping must be on 1/2 inch centers on all straight surfaces; staking of radii may be omitted at the contractor's discretion.

3.2.2.6 Cover. The container cover shall be attached to the container body by a hinge conforming to MS20257. It shall be designed so that thrusts on the corners, as encountered in service and testing, will not be transmitted to the catches.

3.2.2.6.1 Cover fastening. The cover shall be secured to the body by means of quarter-turn type Simmons part number (82240)-B1900-1144 fasteners or equivalent. Fasteners must have provisions for lead wire seals. A steel hasp, zinc plated or equivalent, conforming to MS27971-4, shall be included for locking purposes.

3.2.2.6.2 Handle. A handle, conforming to MS18012, shall be provided on the top center of the container. The handle shall be installed parallel to the plane of the cover and in use shall pivot to a position perpendicular to the cover of the container. In the extended position an opening 4-1/2 inches by 2-1/2 inches shall be provided for gripping the handle.

3.2.2.6.3 Protection of external hardware. Catches and handles as well as the main body of the container and closure shall be protected with bosses or corrugations, as required.

3.2.2.6.4 Reinforcement. Points of stress in the container, such as corners, shall be reinforced to prevent cracking or undue deformation during usage, as required.

3.2.2.7 Component restrainers. Restraining devices and pocketed cushioning medium shall be incorporated to retain the kit components in position during drop tests and usage.

3.2.2.8 Resistance to static load. The container shall show no permanent deformation, cracking, or other detrimental effects under load (see 4.5.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

3.2.2.9 Resistance to rough handling. The container shall show no cracking or deformation when tested as specified in 4.5.2. The container shall remain in the assigned spaces and shall not be damaged.

3.2.2.10 Resistance of handle. The handle shall not malfunction and the container and handle shall not be damaged or deformed when tested as specified in 4.5.3.

3.2.2.11 Resistance to rain. The container shall show no leakage when tested as specified in 4.5.4.

3.2.2.12 Identification plate. Each kit shall have a 2 by 4 inch decal or nameplate attached to the outside and centered on one end of the container. The decal or nameplate shall contain the following:

Stock number
Specification number
Corrosion Control Touch-Up Kit for Weapons Systems
(Contractor's name)
(Contract number)

3.2.3 Container contents. The materials and equipment listed in Table I shall be suitably stowed within the container. Stowage shall be effected in such a manner as to utilize the maximum cushioning obtainable for the packed items and the arrangement should provide maximum accessibility of equipment. The contents arrangement shall be standardized and the location of each item numbered and indicated in Table I. A list shall be made with replacement stock numbers included and attached in a readily visible location within the container (see 6.5). Directions for use shall also be enclosed with each kit (see Figure 1 and 5.4).

3.2.3.1 Description of contents. Detailed descriptions of the contents of the kit are as listed below.

TABLE I. Contents of kit.

Item No.	Total number to be included in kit	Name and size (where applicable)
1	1 each	Safety Goggles
2	1 roll	Gloves, Polyethylene, Disposable, Handguard, Wrist Length (medium size)
3	1 each	Marking Pencil
4	2 tubes	Maskant Material
5	1 roll	Masking Tape 2"
6	1 each	Pipe Hanger

Source: https://assist.dla.mil -- Downloaded: 202640-26T04:35Z
Check the source to verify that this is the current version before use.

TABLE I. Contents of kit - (Continued)

Item No.	Total number to be included in kit	Name and size (where applicable)
7	1 each	Bottle, Polyethylene with Delivery Tube (short neck) (1/2 pint capacity)
8	3 each	Brush, Acid Swabbing
9	1 pint	Paint Remover (1 pint - flat can)
10	1 each	Micarta Scraper 2-1/2" x 6" x 1/16"
11	1 box	Disposable Wipers (small)
12	1 box	Bag, Polyethylene, Non-perforated
13	1 each	Toothbrush
14	1 each	1/2 pint can with black label
15	3 pads	Abrasive Pad (very fine)
16	8 sheets	Abrasive Cloth, Aluminum Oxide Wet or Dry, No. 320
17	1 box	Pipe Cleaner (36 in a box)
18	2 each	Brush, Varnish, Flat
19	1 pint	Surface Treatment Compound, Premixed in Polyethylene Container (1 pint)
20	1 each	Polyethylene Beaker - 600 cc
21	20 packages	Primer, Epoxy Polyamide (Packaged in two part plastic bags containing a total of 20 cc in each package and supplied in cardboard container) (see 6.4)
22	1 each	Spatula (hard rubber of Micarta) 1" x 6" x 3/16"
23	1 kit	Polyurethane Coating, White in 2 half-pint containers per kit
24	1 kit	Polyurethane Coating, Light Gull Gray in 2 half-pint containers per kit

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

TABLE I. Contents of kit - (Continued)

Item No.	Total number to be included in kit	Name and size (where applicable)
25	1 each	Preservative Compound in 16 oz aerosol container
26	1 each	Compound, Corrosion Preventive, Water Displacing, Ultra Thin Film (16 oz aerosol container)
27	2 each	Sealant in a two part kit
28	1 each	Mirror, Inspection 1-1/4"D x 8" L
29	12 each	Disposable Brushes
30	1 each	Cleaning Compound, Aircraft Surface in aerosol container
31	1 each	Corrosion Preventive Compound, Water Displacing, Ultra Thin
32	1 each	Lubricating Oil, General Purpose, Preservative (4 oz.) NSN-9150-00-273-2389
33	1 each	Cleaning Compound, Solvent, Trichlorotrifluoroethane (16 oz. aerosol can)

3.2.3.1.1 Safety goggles. Goggles shall conform to GG-G-531.

3.2.3.1.2 Gloves. Gloves shall be of polyethylene, handguard, wrist length, disposable, medium size.

3.2.3.1.3 Marking pencil. The marking pencil shall be of the "china marking type," wax with organic dyes, free of graphite and metallic salts.

3.2.3.1.4 Maskant material. Maskant material shall be viscous, light blue in color, capable of being formed into dams to retain the paint remover. It shall be packaged in a compressible tube which shall contain at least 5 ounces, by weight, of material. The material shall be safe on all aircraft metals, shall not affect, adversely, painted surfaces, acrylic plastic, electrical insulation or structural adhesives. It shall be easily removable with petroleum solvent conforming to MIL-C-43616 or similar type cleaners.

3.2.3.1.5 Masking tape. Two inch wide masking tape shall conform to the requirements of MIL-T-21595.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

3.2.3.1.6 Pipe hanger. The pipe hanger or spring clip, suitable for attachment to the screw cap of the paint remover can (see 3.2.3.1.9) shall be so designed that it will hold the acid brush, Item 8, Table I, in a horizontal position.

3.2.3.1.7 Bottle. The bottle shall be a polyethylene "wash bottle" type, 1/2 pint capacity, equipped with a short-necked delivery tube. The whole assembly shall be short enough to fit upright in the kit.

3.2.3.1.8 Brush, acid swabbing. The acid brush shall conform to the requirements of H-B-643, Type II, Class 1, size 1, 3/8".

3.2.3.1.9 Paint remover. The paint remover shall conform to the requirements of MIL-R-81294. It shall be packaged in 1 pint, oblong cans in accordance with PPP-P-1892.

3.2.3.1.10 Scraper. The scraper shall be fabricated of plastic conforming to MIL-P-17171, 2-1/2 x 6 x 1/16 inches.

3.2.3.1.11 Wipers. Wipers shall be the disposable type, lint free, Type I, size S of UU-T-595.

3.2.3.1.12 Plastic bag. Bags shall be polyethylene film, 1 mil thick, non-perforated, conforming to PPP-B-28. Inside dimensions shall be 8-1/2 x 6-1/4 inches.

3.2.3.1.13 Toothbrush. The toothbrush shall conform to H-T-560.

3.2.3.1.14 Empty container. The empty container, intended for mixing purposes, shall be a 1/2 pint friction top can conforming to PPP-C-96, Type V, Class 2.

3.2.3.1.15 Abrasive pads. The abrasive pads shall be nonmetallic, nonwoven, in accordance with MIL-A-9962.

3.2.3.1.16 Abrasive cloth. The abrasive cloth shall conform to P-C-451, Type I, Class 1, No. 320.

3.2.3.1.17 Pipe cleaner. Pipe cleaners shall be of the type used in cleaning tobacco residues from smokers' pipes.

3.2.3.1.18 Varnish brush. The varnish brush shall be metal bound, flat, 1 inch wide, nylon bristle conforming to H-B-695.

3.2.3.1.19 Surface treatment compound. The surface treatment compound shall conform to Type I, Grade B, Class 1 and 2, of MIL-C-5541. It shall be premixed, ready for use and packaged in 1 pint screw cap polyethylene bottles conforming to L-B-560. The material as packaged shall meet all requirements of the specification after storage for one year at room temperature.

3.2.3.1.20 Beaker. The beaker shall be 600 cc capacity, low profile. The material of the beaker shall be polyethylene.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

3.2.3.1.21 Primer coating. The primer shall conform to MIL-P-23377. The primer shall be packaged in 2 part containers so that one part, containing 10 cc of Component II, shall be encapsulated by the other part containing 10 cc of Component I. Twenty packages of coating material shall be packed in a cardboard container 3 x 5 x 6 inches. The material shall be acceptable for use after storage for one year.

3.2.3.1.22 Scraper. The scraper shall be made of hard rubber or plastic conforming to ZZ-S-70.

3.2.3.1.23 Polyurethane coating, white. Polyurethane coating conforming to MIL-C-83286, Color No. 37875 of FED-STD-595, shall be packaged in 2 half-pint kit containers. Film properties shall conform to MIL-C-83286. Marking shall contain identification and mixing instructions.

3.2.3.1.24 Polyurethane coating, light gull gray. Polyurethane coating conforming to MIL-C-83286, Color No. 36440 of FED-STD-595, shall be packaged in 2 half-pint kit containers. Film properties shall conform to MIL-C-83286. Marking shall contain identification and mixing instructions.

3.2.3.1.25 Preservative compound. The compound shall be packaged in 16 ounce aerosol containers, and it shall conform to the requirements of MIL-C-16173, Grade IV when applied. Propellant shall be dichlorodi-fluoromethane.

3.2.3.1.26 Corrosion preventive compound. The compound shall be packaged in 16 ounce aerosol containers, and it shall conform to the requirements of MIL-C-85054, Type I, Class A when applied.

3.2.3.1.27 Sealant. The sealant shall conform to the requirements of MIL-S-8802, Class B-2, dichromate cure. It shall be packaged in 1/2 pint, 2 part kit, having a total content of not less than 3-1/2 ounces of material.

3.2.3.1.28 Mirror. The mirror shall be 1-11/16 x 2-9/16 x 16-1/2 inches, conforming to GGG-M-350.

3.2.3.1.29 Disposable brushes. Brushes shall conform to H-B-695, 1/2 inch.

3.2.3.1.30 Cleaning compound. The cleaning compound shall be packaged in 14 to 16 ounce aerosol containers, and it shall conform to the requirements of MIL-C-43616.

3.2.3.1.31 Corrosion preventive compound. The compound shall be packaged in 16 ounce aerosol containers, and it shall conform to the requirements of MIL-C-81309, Type II. Propellant shall be dichlorodi-fluoromethane.

3.2.3.1.32 Lubricating oil. The lubricating oil shall conform to VV-L-800 and shall be in 4 ounce application type containers.

3.2.3.1.33 Cleaning compound. The compound shall be packaged in 16 once aerosol containers and it shall conform to the requirements of MIL-C-81302, Type IIA.

Source: https://assist.dla.mil -- Downloaded: 202640-26T04:35Z
Check the source to verify that this is the current version before use.

3.3 Workmanship. Workmanship shall be in accordance with the best commercial practice. The kit shall be uniform in quality and shall be free from irregularities or defects which could adversely affect performance, reliability or durability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classificaton of inspections. The inspections specified herein are classified as follows:

a. First article inspection (4.3).

b. Quality conformance inspection (4.4).

4.3 First article inspection. First article inspection shall include the visual examination (4.4.2) and all tests (4.5) of this specification. Unless otherwise specified, no corrosion kit shall be submitted for acceptance under any contract or order until the first article samples have been subjected to first article inspection and pronounced satisfactory by the acquiring activity. However, approval of the first article samples shall not relieve the supplier of his obligation to meet the quality conformance inspection (see 6.2 and 6.3).

4.3.1 First article test samples. The first article samples shall consist of a touch-up kit assembly which has been produced by the contractor using the same production process, procedures and equipment as will be used in fulfilling the contract. Samples when required for Government testing shall be forwarded to the Commanding Officer, Naval Air Development Center, Aircraft and Crew Systems Technology Directorate, Attention: Code 60612, Warminster, PA 18974. Samples shall be identified by securely attached durable tags marked with the following information:

Kit - Touch-Up for Corrosion Control of Weapon Systems
First article samples
Name of manufacturer (plant in which manufactured)
Manufacturer's designation
Date of manufacture
Submitted by (name) (date) for contract _____

The manufacturer shall submit a copy of test results with the sample showing conformance with the first article inspection requirements of this specification.

4.3.2 Rejection. If the sample fails to comply with any of the applicable requirements, the first article sample shall be rejected. The

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

Government reserves the right to terminate its inspection upon any failure of the sample to comply with any of the performance requirements.

4.3.3 First article samples and inspection for a subsequent contract. If a contractor has previously furnished the touch-up kit in accordance with the requirements of this specification and his product has been found satisfactory, the requirement for a first article sample and its submittal for any subsequent contract or order may be waived at the discretion of the acquiring activity (see 6.2.1.1). However, waiver shall not relieve the supplier of his obligations to meet the quality conformance inspection requirements.

4.4 Quality conformance inspection. Sample kits, including contents items, shall be selected for quality conformance inspection in accordance with MIL-STD-105, Inspection Level II, Acceptable Quality Level 2.5 percent defective. Unit of sampling shall be one complete kit. Quality conformance inspection shall consist of the visual examination only (see 4.4.2).

4.4.1 Lot. A lot shall consist of all kits manufactured and assembled under the same conditions and submitted for acceptance at the same time, except that the lot shall not exceed 100 complete kits.

4.4.2 Visual examination. The sample touch-up kits, selected in accordance with 4.4, shall be visually examined to determine compliance with this specification with particular emphasis on the following points:

a. Kit materials and construction

b. Container design

c. Container color

d. Container closure design and gasket seating

e. Container handles operation, size, and clearance

f. Container cover characteristics

g. Completeness of contents items

h. Fit of contents items

i Workmanship

4.5 Test methods.

4.5.1 Resistance to static load. A weight equal to the weight of seven (7) containers complete with material and equipment shall be placed on the test container in such a manner as to simulate the effects of stacking. The weight shall remain in this position for 24 hours, at an ambient temperature of 120 +5°F. At the end of this time no permanent deformation, cracking or other detrimental effects shall be evident (see 3.2.2.8).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

4.5.2 Resistance to rough handling. The container shall be tested in accordance with rough handling tests for small containers as specified in MIL-STD-794 except that the flat-wise test shall be conducted on the bottom only and the tip over and vibration tests shall be eliminated (see 3.2.2.9). Drop heights shall be those listed for level A.

4.5.3 Resistance of handles. The container shall be suspended by a rope, 1 inch minimum diameter and 10 feet long, to an overhead by fastening the rope to the handle. The container shall be lifted 3 feet from the normal suspended level and allowed to drop with no restraint. This test shall not cause the handle to malfunction or cause undue deformation of the handle or container (see 3.2.2.10).

4.5.4 Resistance to rain. The closed container shall be placed upright on a level area 36 inches below adjustable spray nozzles so that the water droplets will fall vertically in a uniform distribution onto the top of the container and on the floor or pavement around the container for 2 hours. The water shall fall at a rate such that 4 inches ±1 inch of water per hour will accumulate in open top cylinder cans positioned adjacent to the containers completely within the spray area. The test shall be repeated with the container upside down for two hours. At the end of the test period, the outside of the container shall be dried carefully around the parting line. Open and inspect the inside, particularly joints, connectors, and seams for leakage, or adverse effect of spraying (see 3.2.2.11).

5. PACKAGING

5.1 Preservation. Preservation shall be level A and shall be effected by closure of the rectangular container. All kit contents items shall be preserved in accordance with their respective specifications, where appropriate (see 6.4).

5.2 Packing. Packing shall be level B, C or industrial, as specified (see 6.2).

5.2.1 Level B. The rectangular container shall be overboxed in a weather-resistant fiberboard box conforming to PPP-B-636.

5.2.2 Level C or industrial. Packing shall be accomplished in accordance with ASTM D 3951-82.

5.3 Marking. In addition to any special or other identification marking required by the contract, each rectangular container and shipping container shall be marked in accordance with MIL-STD-129. In addition, containers shall bear a printed label showing the information required by the applicable specification for the contents of the kit.

5.4 Instructions for use of kit. One copy of the instructions for use, Figure 1, shall be included in the contents of each kit. The instructions shall be printed on one side of a card, approximately 13 x 8 inches, and a sketch of the item position with replacement stock numbers shall be printed on the reverse side of the card.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The touch-up kit covered by this specification contains all the material and equipment necessary in treating small areas of corrosion on weapons systems. It is intended to simplify treatment of these areas by providing on-the-job accessibility of supplies and equipment in one small, portable package.

6.2 Ordering data. Acquiring documents should specify the following:

a. Title, number and date of this specification.

b. Quantity.

c. Level of packing (5.2).

d. Special marking required (5.3).

e. If first article is to be sent to a Government laboratory (3.1).

6.3 First article. When a contractor is in continuous production of touch-up kits from contract to contract, consideration should be given to waive the first article inspections. If inspection is required, indicate:

a. If first article inspections are conducted at the contractor's plant or a Government approved laboratory, an inspection report shall be forwarded to the procuring activity for verification.

b. The approval of first article samples or the waiving of the first article inspection shall not relieve the contractor of his obligation to fulfill all other requirements of the specification and contract.

6.4 Epoxy primer. The following is a suggested and acceptable method of packaging the epoxy primer, Item 21: Coat aluminum foil, QQ-A-1876, with 0.002 inch film of polyethylene on both faces. Make up into flat bags 2-1/2 x 2-1/4 inches. Fill with 10 cc of Component II of epoxy primer and heat seal. The packaging is inserted in flat bags 3 x 5 inches made from film, MIL-B-22191, Type I, containing 10 cc of Component I of epoxy primer. The larger bag is sealed and ready to use.

6.5 Replacement items. The following is a list of replacement items for replenishment of the corrosion control kit.

	Item	Source or NSN
1	Safety Goggles	4240-00-032-3776 4240-00-253-5380
2	Gloves	8415-00-728-0448
3	Marking pencil	7520-00-223-6672

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

	Item	Source or NSN
4	Maskant material	Cee Bee Chemcial Company 9503 E. Ceebee Drive Downey, CA
5	Masking tape	7510-00-680-2395
6	Pipe hanger	5340-00-184-1713
7	Bottle	Any chemical supply house
8	Brush, acid swabbing	7920-00-514-2417
9	Paint remover	8010-00-142-9273
10	Scraper	Any chemical supply house
11	Wipers	7920-00-721-8884
12	Plastic bag	8105-00-773-7581
13	Toothbrush	8530-00-258-1509 or 8530-00-290-2920
14	Empty container	8110-00-178-8280
15	Abrasive pad	5350-00-967-5089
16	Abrasive cloth	5350-00-246-0330
17	Pipe cleaner	Any place pipe tobacco is sold
18	Varnish brush	8020-00-263-3866
19	Surface treatment compound	8030-00-142-9272
20	Beaker	Any chemical supply house
21	Primer coating	8010-01-050-4082
22	Scraper	Any chemical supply house or 7330-00-849-5194
23	Polyurethane Coating (White)	8010-00-181-8286
24	Polyurethane Coating (Gray)	8010-00-935-7085
25	Preservative compound	8030-00-142-9281
26	Corrosion preventive compound	8030-01-041-1596
27	Sealant	8030-00-753-4598

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

	Item	Source or NSN
28	Mirror	5120-00-456-0856
29	Disposable brushes	8020-00-597-4761
30	Cleaning compound, aircraft surface	6850-00-005-5305
31	Corrosion Preventive Compound	-
32	Lubricating Oil	9150-00-273-2389
33	Cleaning compound	6850-00-142-9247

Preparing activity:
Navy - AS
(Project No. 8010-N240)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

DIRECTIONS (NUMBERS IN PARENTHESES REFER TO KIT ITEM NUMBERS)

CAUTION

CLEAN BRUSHES (8) AND (18), BEAKER (20), AND SCRAPER (10) AFTER EACH USE TO AVOID CONTAMINATION OF MATERIALS.

1. Inspect aircraft for corrosion or paint failure - encircle with marking pencil (3).

2. Remove paint in defective area by either:

   a. Abrasion - Rub with abrasive pad or cloth (15 or 16).

   b. Paint remover - Wear gloves and goggles (1 and 2). Mask first with tape (5) or maskant (4). Dab on remover (9) with brush (8) and after about 30 minutes, remove loosened paint, remover and maskant (if used) with scraper (10). Peel off tape (if used). Place residues in bag (12). Clean with cloth (11) and rinse with water using bottle (7). Repeat if necessary.

3. Corrosion removal - Remove loose corrosion by rubbing with abrasive pad (15) moistened with cleaner (30). (Temporarily treat extensive corrosion with preservative compound (25) and consult cleaning and corrosion control of aircraft manual for further directions.) "Feather in" paint edges.

4. Cleaning - Spray entire area with water emulsion cleaner (30) and then flush with water using bottle (7). Repeat, if necessary.

5. Application of chemical film - Wear goggles and gloves (1 and 2). Mask off areas with tape (5). Pour small amount of chemical film (19) into beaker (20). Apply with nylon brush (18). When uniform, light brown color is obtained, rinse with water. Allow to dry. DO NOT TOUCH. Peel off tape.

6. Application of sealant (on non-removable fastener heads) - Mix two parts of sealant (27) together and apply between two parallel strips of masking tape (5). Smooth with scraper (10) and remove tape.

7. Painting - One hour before use, mix two parts of primer together (21) and apply from plastic bag with brush (29). After on hour minimum, mix sufficient amount of two parts of polyurethane and apply thin coats of the topcoat (30 minutes between coats) in appropriate color (23 or 24).

8. Preservative compounds - MIL-C-85054 (26) displaces water and may be used for temporary protection. MIL-C-16173, IV, (25) may be used alone or over (26) for a more durable film. (4) can be used as an alternate for (25).

NOTES: 1. Use pipe cleaners (17) to clean out drain holes.
2. For more detailed instructions refer to Manual NAVAIR 01-1A-509, Corrosion Control for Aircraft.

FIGURE 1

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T04:35Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-K-81576A(AS)	KIT - TOUCH-UP, FOR CORROSION CONTROL OF WEAPONS SYSTEMS

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)*:
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:35Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY
Commanding Officer
Naval Air Engineering Center
Engineering Specifications and Standards Department
(ESSD), Code 93
Lakehurst, NJ 08733

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

BUSINESS REPLY MAIL.
FIRST CLASS PERMIT NO 12503 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Commanding Officer
Naval Air Engineering Center
Engineering Specifications and Standards Dept.
(ESSD), Code 93
Lakehurst, NJ 08733

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:35Z
Check the source to verify that this is the current version before use.