P-P-101E
AMENDMENT - 1
June 14, 1978

FEDERAL SPECIFICATION

PAPER, ABRASIVE, SILICON CARBIDE, WATERPROOF

This amendment, which forms part of Federal Specification P-P-101E, dated October 3, 1973, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal Agencies.

PAGE 2

Paragraph 2.2: Delete "Department of Commerce Product Standard", "PS8 - Grading of Abrasive Grain on Coated Abrasive Products" and parenthetical ordering instructions.

Paragraph 2.2: Add the following:

"American National Standards Institute (ANSI) Standard:

ANSI B74.18 - Specification for Grading of Certain Abrasive Grain on Coated Abrasive Products.

(Application for copies should be addressed to the American National Standards Institute, 1430 Broadway, New York, N.Y. 10018.)"

Paragraph 3.1: After the word "Material" add "(see 6.4)".

Paragraph 3.1.1.1: Add at the end of the paragraph "(see 6.3)".

Paragraph 3.1.1.2: On the second line delete "PS8" and add "ANSI B74.18" in its place.

Paragraph 3.1.2: Change the next to last sentence to read as follows: "The backing weight shall meet the requirements of table I immediately after being conditioned at 21° ± 1°C (70° ± 2°F) and 50 ± 2 percent relative humidity for at least 24 hours."

PAGE 3

Table I - Under Minimum Average Breaking Strength in the machine direction for "A" weight paper change 20 pounds to read 18 pounds, and for "C" weight paper change 40 pounds to read 35 pounds.

FSC 5350

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:16Z
Check the source to verify that this is the current version before use.

PAGE 3 (con.)

Table I, footnote 1/: Change the footnote to read as follows: The basic weight of the paper (includes paper and saturant) is calculated in pounds per ream of 480 sheets 24 x 36 inches at 21° ± 1°C (70° ± 2°F) and 50 ± 2 percent relative humidity.

Paragraph 3.1.4: At end of paragraph delete "(see 6.4)".

Paragraph 3.2: On the third line beginning with the word "when", change the last part of the sentience to read as follows: "When measured at and after conditioning at 21° ± 1°C (70° ± 2°F) and 50 ± 2 percent relative humidity for at least 24 hours.

PAGE 5

Paragraph 4.4.1.1: On the third line delete "Product Standard PS8" and add "ANSI B74.18" in its place.

Paragraph 4.4.1.2: On the third line delete "PS8" and add "ANSI B74.18" in its place.

Paragraph 4.4.2: Change the first part of the first sentence to read as follows: "The tensile breaking strength of the coated abrasive paper immediately after conditioning for at least 24 hours at 21° ± 1°C (70° ± 2°F) and 50 ± 2 percent relative humidity."

PAGE 6

Paragraph 6.4: Delete in its entirety and replace with the following:

"6.4 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the specification."

Custodian:

Army - MR
Air Force - 99

User Activities:

Army - MI, ME
Navy - YD, MC, OS, AS

Preparing Activity:

Air Force - 99

Project No - 5350-0059

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:16Z
Check the source to verify that this is the current version before use.