P-W-120a
May 3, 1963

SUPERSEDING
Int. Fed. Spec. P-W-00120(Army-QMC)
September 13, 1962

FEDERAL SPECIFICATION

# WAX, AUTOMOBILE, PASTE

*This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.*

## 1. SCOPE AND CLASSIFICATION

**1.1 Scope.** This specification covers a wax in paste form suitable for polishing and protecting previously cleaned lacquer, baked enamel, and synthetic enamel finishes of automobiles (see 6.1).

**1.2 Classification.**

1.2.1 *Types.* The automobile paste wax shall be of the following types, as specified (see 6.2).

Type I.—Slow drying wax
Type II.—Fast drying wax

## 2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

**2.1 Specifications and standards.** The following specifications and standards, of the issues in effect on date of invitations for bids, form a part of this specification to the extent specified herein:

*Federal Specifications*:

P-S-320—Scouring Powder, Glass Cleaning.
P-D-680—Dry Cleaning Solvent
TT-L-31—Lacquer, Cellulose Nitrate, Gloss.
PPP-B-636—Box, Fiberboard.
PPP-C-96—Cans, Metal, 28 Gage and Lighter.

*Federal Standards*:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.
Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).
Fed. Test Method Std. No. 141—Paint, Varnish, Lacquer, and Related Materials: Methods of Inspection, Sampling, and Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, and Auburn, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

*Military Specification*:

MIL-P-11414—Primer, Lacquer, Rust-Inhibiting.

*Military Standards*:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:16Z
Check the source to verify that this is the current version before use.

procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 **Other publications.** The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitations for bids, shall apply.

*American Society For Testing And Materials Standards*:

D217-60T—Method of Test for Cone Penetration of Lubricating Grease (Tentative).

D609-61—Methods for Preparation of Steel Panels for Testing Paint, Varnish, Lacquer and Related Products.

(Copies of ASTM Standards may be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia 3, Pennsylvania.)

## 3. REQUIREMENTS

3.1 **Material.** The wax polishes shall consist of carnauba wax and other natural or synthetic waxes, and aliphatic solvents. Type I, in addition shall contain silicone oils.

3.2 **Chemical and physical requirements.** The paste wax shall conform to the requirements in table I when tested as specified in table II.

3.3 **Performance.**

3.3.1 *Gloss increase and uniformity.* The wax shall increase the gloss of prepared lacquered panels not less than 15 gloss units when tested as specified in table II. The polished panels shall have a uniform gloss and shall be free from streaks.

3.3.2 *Gloss retention after weathering.* Lacquered panels polished with the test wax shall have an average gloss retention efficiency of not less than 50 percent when tested as specified in table II.

3.3.3 *Smear resistance.* The wax shall not smear when tested as specified in table II.

3.3.4 *Water spotting.* The test wax shall not spot when tested as specified in table II.

3.4 **Stability.** The wax shall be stable and shall show no evidence of separation when tested as specified in table II.

3.5 **Workmanship.** The wax shall be a uniform, homogeneous mixture in paste form.

3.6 **Quality.** The quality of the paste wax shall conform to the levels established herein. The occurrence of defects shall not exceed the number permitted under the acceptable quality levels (AQLs) specified in section 4 for any examinations and tests of materials, components and end item, as applicable.

## 4. SAMPLING, INSPECTION, AND TEST PROCEDURES

TABLE I. *Requirements*

| | Type I | | Type II | |
|---|---|---|---|---|
| | Minimum | Maximum | Minimum | Maximum |
| Matter nonvolatile at 105°C., percent | 25.0 | 31.0 | 21.0 | 31.0 |
| Silicone oil, percent | 5.0 | 10.0 | no requirement | |
| Solvent insoluble matter, percent | — | 0.2[1] | — | 0.2 |
| Consistency, cone penetration | — | 70 | — | 70 |
| Distilled solvent: Flash point, closed cup °F. | 82 | — | 82 | — |
| Aniline point °F. | 115 | — | 115 | — |

[1] The insoluble matter shall be nonabrasive to the touch.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:16Z
Check the source to verify that this is the current version before use.

**4.1 Responsibility for inspection.** Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

**4.2 Sampling for inspection and tests.** Sampling for inspection and tests shall be in accordance with the provisions of MIL-STD-105, except where otherwise indicated. For purposes of sampling for inspection, a lot shall consist of all material of the same type, form, and construction from the same manufactured batch.

**4.2.1** *Inspection of components and materials.* In accordance with 4.1 the supplier shall be responsible for insuring that the quality assurance provisions for components or materials shall be in accordance with this specification and with referenced subsidiary specifications to the extent applicable. In the event of conflict, this specification shall govern.

**4.3 Inspection of the end item.**

**4.3.1** *Examination of the end item.* The end item shall be examined in accordance with the classification of defects in the applicable subparagraphs at the inspection levels and acceptable quality levels (AQLs) set forth in 4.3.1.5. Random samples shall be drawn from each lot of end items of the same type and size offered for acceptance for visual, contents and preparation for delivery defects. The lot size for purposes of determining the sample size, in accordance with MIL-STD-105, shall be expressed in units of filled primary containers of the same capacity, consisting of paste wax manufactured in one batch of the specified type, for the examination in 4.3.1.1, 4.3.1.2 and 4.3.1.3, and in units of shipping containers for examination under 4.3.1.4.

**4.3.1.1** *Examination of the primary container.* The sample unit for this examination shall be one filled primary container.

| Examine | Defect |
|---|---|
| Construction ... | Not type and class specified (see 5.1). |
| Closure ..... | Not type specified: imperfect. |
| Exterior coating | Not as specified. |
| Workmanship .. | Dented, abraded, dirty, split, punctured; any other defect affecting serviceability; any seepage of contents. |
| Markings ..... | Missing, incomplete, incorrect, not as specified. |

**4.3.1.2** *Examination of contents of the primary container.* The sample unit for this examination shall be the contents of one filled primary container.

| Examine | Defect |
|---|---|
| Form and workmanship | Not paste, not uniform, not homogeneous, contains lumps, liquid separates out, presence of foreign material. |

**4.3.1.3** *Examination of the end item for net contents.* The sample unit for this examination shall be one filled primary container. The average net weight of contents shall not be less than specified or indicated for all sample units examined.

**4.3.1.4** *Examination of the end item for defects in preparation for delivery.* An examination shall be made to detemine that markings, materials, workmanship and contents comply with the requirements of section 5 of this specification. The sample unit shall be one shipping container, fully packed, selected just prior to the closing operation. Closed shipping containers, fully prepared for delivery, shall be examined for closure defects.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:16Z
Check the source to verify that this is the current version before use.

| Examine | Defect |
|---|---|
| Markings | Incorrect, incomplete, illegible, omitted; of improper size, sequence, or method of application; not in accordance with contract requirements. |
| Material | Any nonconforming component; component missing, damaged, or otherwise defective. |
| Workmanship | Inadequate application of components such as: Incomplete closure of case liners, container flaps; loose or inadequate sealing, strapping, or stapling. |
| | Bulged or distorted containers. |
| Contents | Number of intermediate packages per shipping container is more or less than required. |
| | Number of primary containers per intermediate package is less than specified. |

4.3.1.5 *Inspection levels and acceptable quality levels (AQLs) for examinations.* The inspection levels and the acceptable quality levels (AQLs) expressed in defects per 100 units shall be as follows:

| Examination paragraph | Inspection level | AQL |
|---|---|---|
| 4.3.1.1 | I | 2.5 |
| 4.3.1.2 | I | 2.5 |
| 4.3.1.3 | L-4 | — |
| 4.3.1.4 | L-4 | 4.0 |

4.3.2 *Testing of the end item.* The end item shall be tested for the characteristics specified in table I in accordance with test methods specified in table II. The lot size for test purposes shall be the number of containers of the same type filled with paste wax of the same type from a single manufactured batch. The sample unit shall be 1 pound of wax. The sample size shall be five. Each sample unit shall be taken from a different container. A single determination shall be made on each sample unit for all characteristics. The lot shall be unacceptable if there is any evidence of failure to meet any characteristic applicable to the sample unit.

**4.4 Test procedures.**

4.4.1 *Nonvolatile matter.* Accurately weigh 4 to 5 grams of a uniform sample of wax in a weighed flat-bottom dish about 8 cm. in diameter, provided with a tightly fitted cover. Remove the cover and place sample over a steam bath until the bulk of volatile matter has evaporated, and then place in an oven at 105° ± 2.5°C. (221° ± 4.5°F.) for 4 hours. Cool in a desiccator, replace cover and weigh residue. Repeat drying until weight is constant. Calculate percent nonvolatile matter. Save residue of type I wax for silicone oil content determination.

4.4.1.1 *Calculation*:

$$\text{Percent nonvolatile matter} = \frac{\text{weight of residue} \times 100}{\text{weight of paste wax}}$$

4.4.2 *Silicone oil content (dimethyl-siloxane polymer).* Accurately weigh the total nonvolatile residue obtained in 4.4.1., into a tared platinum or vycor crucible. To reduce subsequent frothing of sample, add 4 or 5 drops of chlorobenzene and then agitate or warm contents to affect solution. Add 2 milliliters of fuming sulfuric acid (15 percent) to the solution at room temperature. Add 0.5 milliliter of fuming nitric acid immediately following the addition of the sulfuric acid. Heat crucible and contents over a low flame for several hours to accomplish digestion. When the mass has solidified and danger of frothing is past, heat the crucible over a Meker burner to complete expulsion of sulfur trioxide fumes. Place residue in a muffle furnace for 1 hour at 800°C. (1472°F.). Cool in a desiccator and weigh residue.

4.4.2.1 *Calculation.* Calculate percent silicone oil in original sample.

$$\text{Percent silicon dioxide} = \frac{B \times 100}{A/C}$$

where: A = nonvolatile residue, grams.
B = residual silicon dioxide, grams
C = percent nonvolatile matter (as determined in 4.4.1) divided by 100

$$\text{Percent dimethyl siloxane polymer (silicone oils)} = \text{Percent silicon dioxide} \times \frac{74.}{60}$$



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:16Z
Check the source to verify that this is the current version before use.

TABLE II. *Instructions for testing of the end item*

| Characteristic | Specification reference | | Requirements applicable to | | Number determinations per unit sample | Results reported as | |
|---|---|---|---|---|---|---|---|
| | Requirement | Test method paragraph | Individ. unit | Lot aver. | | Pass or fail[2] | Numerically to nearest |
| Nonvolatile matter, percent | Table I | 4.4.1 | X | | 1 | X | 0.1 |
| Silicone content (Type I only), percent | Table I | 4.4.2 | X | | 1 | X | 0.1 |
| Solvent insoluble matter[1], percent | Table I | 4.4.3 | X | | 1 | X | 0.01 |
| Consistency | Table I | 4.4.4 | X | | 1 | X | 1 unit |
| Distilled solvent, Flash point, °F. | Table I | 4.4.5.2 | X | | 1 | X | 1°F. |
| Aniline point, °F. | Table I | 4.4.5.3 | X | | 1 | X | 1°F. |
| Stability | 3.4 | 4.4.6 | X | | 1 | X | |
| Gloss increase | 3.3.1 | 4.4.7.3.4 | X | | 1 (average of 10 panels) | X | 1 unit |
| Gloss retention, percent | 3.3.2 | 4.4.7.3.5 | X | | 1 (average of 5 panels) | X | 0.1 |
| Smear resistance | 3.3.3 | 4.4.7.4 | X | | 1 (2 panels) | X | |
| Water spotting | 3.3.4 | 4.4.7.5 | X | | 1 (2 panels) | X | |

[1] The insoluble matter shall be nonabrasive to the touch.
[2] If failure is indicated, report description or numerical point of failure, as applicable.





Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:16Z
Check the source to verify that this is the current version before use.

4.4.3 *Solvent insoluble matter.* Accurately weigh 2 grams of a uniform sample of wax and dissolve in 100 milliliters of Stoddard solvent (P-D-680). Warm mixture to promote solution. If sample is not completely soluble, filter the solution through a tared Gooch crucible or filter paper. Wash Gooch crucible or filter paper with Stoddard solvent and dry Gooch crucible or filter paper in an oven at 105° ± 2.5°C. (221° ± 4.5°F.) for 4 hours. Repeat drying till weight is constant. Calculate the percent of solvent insoluble matter.

4.4.3.1 *Calculation.*

$$\text{Percent solvent insoluble matter} = \frac{\text{weight of residue} \times 100}{\text{weight of paste wax}}$$

4.4.4 *Consistency.* Determine cone penetration of wax in block form in accordance with procedure specified in ASTM Designation D217-60T.

4.4.5 *Properties of solvent distilled from paste wax.*

4.4.5.1 *Distillation of solvent.* Approximately one hundred grams of wax shall be placed in a distilling flask and the solvent distilled, preferably under reduced pressure, and collected for testing.

4.4.5.2 *Flash point (Tag closed tester).* The flash point of distilled solvent shall be determined in accordance with method 4292 of Fed. Test Method Std. No. 141.

4.4.5.3 *Aniline point.* The aniline point of distilled solvent shall be determined in accordance with method 4382 of Fed. Test Method Std. No. 141.

4.4.6 *Stability.* A sample of the wax inclosed in its original container shall be placed unopened for 72 hours in an oven maintained at 42° -43°C. (108° -110°F.) The container shall then be cooled to room temperature and the contents examined for separation of liquid.

4.4.7 *Performance.*

4.4.7.1 *Test materials.*

4.4.7.1.1 *Test panels.* The test panels (see 6.3) of rust free, cold rolled steel shall measure 0.032 by 3 by 6 inches and shall be ground flat and even on one side and shall have received a zinc phosphate treatment in accordance with method 2011 of Fed. Test Method Std. No. 141.

4.4.7.1.2 *Lacquer primer.* A lacquer primer with rust inhibiting properties conforming to MIL-P-11414 is suitable.

4.4.7.1.3 *Lacquer.* An automotive-type black lacquer, gloss type is suitable.

4.4.7.1.4 *Lamb's wool pad.* The lamb's wool pad used in the tests shall be made from clean one hundred percent virgin unbleached lambs wool. Size shall be approximately 5-1/2 by 3 inches.

4.4.7.2 *Equipment for tests.*

4.4.7.2.1 *Doctor blade.* A doctor blade (see 6.3) capable of laying down a uniform 3-inch width wet film having a thickness of 0.001 inch.

4.4.7.2.2 *Glossmeter.* A glossmeter (see 6.3) capable of measuring the 60-degree specular gloss of a lacquered panel with an accuracy of ± 2 gloss units.

4.4.7.2.3 *Polishing apparatus.* The polishing apparatus (see 6.3) shall consist essentially of an electric motor mounted on a flat metal plate, and a mechanism through which the motor imparts a reciprocating motion to a lambs wool polishing head lengthwise across a test panel positioned on a platform situated above the mechanism (see 6.3). The power is transmitted from the motor to a driving arm by means of a belt, pulley, and gear reduction box. A flexible wire, guided by a pulley at each end of the platform runs from the driving arm to each end of the metal box assembly. Tension on the wire is just sufficient to take up any slack. The metal box assembly, including the lambs wool pol-



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:16Z
Check the source to verify that this is the current version before use.

ishing head, is 3-3/4 inches long, 3 inches wide and 1 inch deep. The metal box assembly is reciprocated through a distance of 13 inches in a straight path over the length of the test panel at approximately 37 oscillations (74 strokes) per minute.

4.4.7.2.3.1 *Polishing head.* The polishing head shall consist of a wooden block and a lambs wool pad specified in 4.4.7.1.4. The wooden block shall be rectangular, appoximately 3-3/8 inches long, 2-7/8 inches wide, and 1 inch deep, to which is cemented a sheet of soft rubber 3-1/2 inches wide, 2-7/8 inches long and at least 1/4 inch thick. The lambs wool pad shall be secured to the rubber face of the wooden block, over-lapping each end approximately 1 inch. The polishing head is then inserted into the metal box assembly. Small spacers between the polishing head and metal box assembly may be necessary to accomplish a snug fit and hold the lambs wool surface wrinkle-free during the polishing operation. The total weight of the metal box assembly including the polishing head shall be 1.0 ± 0.05 pounds.

4.4.7.2.4 *Weathering apparatus.* A weathering apparatus (see 6.3) as specified in method 6152 of Fed. Test Method Std. No. 141 for exposing polished panels to cycles of carbon arc light and water spray shall be used.

4.4.7.3 *Performance.*

4.4.7.3.1 *Preparation of test panels.*

4.4.7.3.1.1 *Surface preparation.* A minimum of twelve test panels shall be vapor degreased or solvent-cleaned to remove all oil, grease and fingerprints.

4.4.7.3.1.2 *Application of lacquer.* The test panels (4.4.7.1.1) shall be spray coated on both sides with a lacquer primer conforming to MIL-P-11414, applying a minmum of two medium wet coats. Air dry the panels for a minimum of two hours after each primer application, then apply to the ground side of each panel at least 2 medium wet coats of automotive-type black lacquer conforming to TT-L-31. The panels shall air dry a minimum of 4 hours between coats of lacquer. Allow the finished panels to air dry for a minimum of 7 days prior to use.

4.4.7.3.2 *Gloss of lacquered panels.* The lacquered panels (4.4.7.3.1.2) shall be lightly and uniformly rubbed by hand with a mild abrasive such as scouring powder of P-S-320, to obtain a 60-degree specular gloss in the range of 40-50 gloss units. The abrasive material shall be thoroughly removed by washing the panel in water, rinsing in distilled water and wiping dry with a soft tissue. Gloss determinations shall be accurately made and recorded in accordance with method 6101 of Fed. Test Method Std. No. 141 using a Gardner 60-degree Glossmeter or the equivalent (see 6.3). All gloss readings shall be taken along the lengthwise axis of each panel. A minimum of three readings shall be taken on each panel to determine the average gloss value for the panel. All readings shall be within 5 percent of the average gloss for the panel.

4.4.7.3.3 *Gloss of waxed panels.*

4.4.7.3.3.1 *Application of wax.* Apply a small amount of paste wax to the rubbed side of the lacquered panel with a soft cheesecloth saturated with the wax at room temperature 21° - 34°C. (70° - 76°F.) Continue rubbing with moderate finger pressure for a few seconds spreading a slight excess of paste wax over the panel. Immediately draw a doctor blade lengthwise over the panel in order to apply a 1 mil (0.001 inch) thickness of wax. After this drawdown, the time should be recorded as the start of drying period.

4.4.7.3.3.2 *Polishing of panels.* Place the test waxed panel in the polishing apparatus in a position so that the length of the panel is parallel to the motion of the polishing head which shall pass over the entire panel surface. Place metal or other suitable pan-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:16Z
Check the source to verify that this is the current version before use.

els of equal thickness on both ends of the test panel to hold it in place and to provide a level surface for the polishing head to travel. The waxed panel shall be allowed to dry at room temperature 21° - 24°C. (70° - 76°F.) as follows:

Type I Wax.—Type I wax shall be allowed to dry for 20 ± 0.5 minutes and then polished for 200 strokes (100 complete oscillations) of the polishing head.

Type II Wax.—Type II wax shall be allowed to dry for 5 ± 0.5 minutes and then polished for 200 strokes (100 complete oscillations) of the polishing head. The polished panels shall be observed visually for gross uniformity and streaking. The waxing and polishing procedures shall be repeated for each of the 12 test panels.

4.4.7.3.4 *Gloss of polished panels.* The gloss of the twelve polished test panels shall be determined in accordance with the procedure specified in 4.4.7.3.2. The increase in gloss shall be the difference between the gloss of the polished panel and the unpolished rubbed panel (4.4.7.3.2). Determine the gloss increase of each panel and average the results obtained on a minimum of 10 panels to obtain the average gloss increase.

4.4.7.3.5 *Gloss retention after weathering.* Six polished panels shall be placed in an accelerated weathering apparatus (see 6.3) and subjected to a cycle of 102 minutes of carbon arc light and 18 minutes of water spray for a total of 48 hours. Remove the panels from the apparatus at the end of the time period and wipe lightly with a damp cheesecloth. Allow to dry and measure the gloss within 24 hours as specified in 4.4.7.3.2. Calculate the gloss retention efficiency as follows:

$$\text{Gloss retention efficiency, percent} = \left\{ \frac{1.00 - (G_p - G_w)}{(G_p - G_o)} \right\} \times 100$$

where: $G_o$ = Gloss of prepared lacquered panel (4.4.7.3.2)

$G_p$ = Gloss of waxed unweathered panel (4.4.7.3.4)

$G_w$ = Gloss of waxed panel after weathering (4.4.7.3.5)

Determine the gloss retention efficiency of each of the 6 panels and average the results obtained on a minimum of 5 panels to obtain the average gloss retention efficiency.

4.4.7.4 *Smear resistance.* Two of the waxed panels, immediately following the polishing operation specified in 4.4.7.3.3 shall be stroked firmly once using a clean dry pad of cheesecloth. Visible streaks produced in this manner indicates smearing of the wax.

4.4.7.5 *Water spotting.* Two or three large drops of distilled water shall be placed on two of the polished panels prepared in accordance with 4.4.7.3.3 and allowed to stand in a horizontal position for a 6-hour period at room temperature. The droplets shall be large enough (approximately one-half milliliter) so that the droplets do not evaporate to dryness for this 6-hour period. Following the 6 hour standing period, the water droplets shall be lightly wiped from the panels using a soft tissue and the panels observed for spotting.

## 5. PREPARATION FOR DELIVERY

(Fed. Std. No. 102 shall be referred to for definitions and application of the various levels of packaging and packing for civil agency procurements.)

5.1 **Packaging.** Packaging shall be level A, B, or C, as specified (see 6.2).

5.1.1 *Level A.*

5.1.1.1 *Unit packaging.* Seven ounces or one pound (see 6.2) of one type of wax only shall be furnished in round cans conforming to type V, class 1 or 2, exterior coating plan B of PPP-C-96.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:16Z
Check the source to verify that this is the current version before use.

5.1.1.2 *Intermediate packaging.* Twelve cans of wax, of one type and size only shall be packaged in a snug-fitting fiberboard box conforming to type I or II, class 1, style RSC of PPP-B-636, except that the minimum bursting strength shall be 175 p. s. i. All flaps of the fiberboard box shall be securely sealed with an adhesive commercially used for the specific product being packed by application throughout the entire area of contact between the flaps, or by a combination of metal stitching the bottom flaps and sealing the top flaps with adhesive.

5.1.2 *Level B.*

5.1.2.1 *Unit packaging.* Seven ounces or one pound (see 6.2) of one type of wax shall be furnished in round cans as specified in 5.1.1.1 except the exterior coating shall be plan A.

5.1.2.2 *Intermediate packaging.* Twelve cans of wax of one type and size shall be packaged in a snug-fitting fiberboard box as specified in 5.1.1.2.

5.1.3 *Level C.* The wax shall be packaged in accordance with the industry's practice.

5.2 **Packing.** Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 *Level A.* Seventy-two 7-ounce cans, or forty-eight 1-pound cans, of one type of wax only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to class 2, V3c or V3s, style RSC of PPP-B-636. Each shipping container shall be closed waterproofed with tape and reinforced with flat steel strapping or tape banding in accordance with the appendix of the applicable container specification.

5.2.2 *Level B.* Seventy-two 7-ounce cans, or forty-eight 1-pound cans, of one type of wax only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to type I or II, class 1, style RSC of PPP-B-636, except that the minimum bursting strength of the fiberboard shall be 200 p. s. i. All flaps of the fiberboard shipping container shall be securely sealed with an adhesive commercially used for the specific product being packed by application throughout the entire area of contact between the flaps, or by a combination of metal stitching the bottom flaps and sealing the top flaps with adhesive.

5.2.3 *Standard pack (civil agencies).* The Standard Pack for this commodity shall be as specified in 5.1.2.1 and 5.1.2.2.

5.2.4 *Level C.* The wax, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with rules or regulations of carriers applicable to the mode of transportation.

5.3 **Marking.**

5.3.1 *Civilian agencies.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 *Military requirements.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

## 6. NOTES

6.1 **Intended use.** Automotive paste wax is intended to be used primarily in polishing and protecting automobile surfaces. Type I wax may be applied to a large surface prior to buffing or polishing. Type II wax shall be applied to a small area and buffed or polished within a few minutes thereafter.

6.2 **Ordering data.** Purchasers should exercise any desired options offered herein



Source: https://assist.dla.mil -- Downloaded: 20261O-26T11:16Z
Check the source to verify that this is the currentversion before use.

and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.

(*b*) Type required (see 1.2).

(*c*) Applicable levels of packaging and packing (see 5.1 and 5.2).

(*d*) Quantity of wax required (see 5.1.1.1).

**6.3 Materials and equipment.** The following testing materials and equipment are satisfactory for the purpose intended:

Test panels.—Q-Panels, 3 by 6-inch zinc phosphate treated steel test panels. One side of panel ground in accordance with ASTM D-609-61. The Q-Panel Company, 15610 Industrial Parkway, Cleveland 35, Ohio.

Doctor blade.—Boston Bradley Adjustable Blade, Gardner Laboratories, Inc. Bethesda 14, Maryland.

Glossmeter.—Glossmeter, 60-degree, Portable, Gardner Laboratories, Inc., Bethesda 14, Maryland.

Polishing apparatus.—Washability Machine, Gardner Laboratories, Inc., Bethesda 14, Maryland.

Weathering apparatus.—Weather-O-meter, Atlas Electric Devices Company, Chicago 13, Illinois.

Penetration apparatus.—Penetrometer, Precision Scientific, Chicago, Illinois

**6.4 Civil procurements.** The Standard Pack requirements in paragraphs 5.1.2.1 and 5.1.2.2 are intended for use in procurements of stores stock replenishment. Procuring officers should use the Standard Pack requirements when it is known that the material will be shipped from a supplier to a domestic warehouse, supply depot, or intermediate storage point for temporary storage, subsequent issue, and/or shipment to eventual user.

**6.5 Military procurements.** For military procurements, level B packaging should be used when it is known that the material will be shipped from supplier to a domestic warehouse, supply depot, or intermediate storage point for temporary storage not to exceed 1 year, subsequent issue, or shipment to user.

**6.6 Transportation description.** Transportation descriptions and minimum weights applicable to this commodity are:

*Rail*:

Vehicle polish or wax.
Carload minimum weight 36,000 pounds.

*Motor*:

Vehicle polish or wax.
Truckload minimum weight 36,000 pounds, subject to Rule 115, National Motor Freight Classification.

**Notice.** When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

**MILITARY CUSTODIANS:**

**Army—GL**
**Navy—Sh**
**Air Force—MOA**

**OTHER INTERESTS:**

**Army—M O**
**Navy—MC**



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:16Z
Check the source to verify that this is the current version before use.