INTERIM FEDERAL SPECIFICATION

CARPETS AND RUGS, EXTRA HEAVY PILE WEIGHT, WOVEN, TUFTED AND CUSTOM TUFTED SPECIAL PURPOSE

This Interim Federal Specification was developed by the Federal Supply Service, General Services Administration, Washington, D C 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

1 SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the requirements for woven, tufted and custom tufted carpets and rugs with extra heavy pile weight for high level executive use and special traffic situations (6.1)

1.2 Classification. The carpets and rugs covered by this specification shall be of the following types and classes, as specified

Type I - Woven

Class 1 - Alternate round and cut pile - woven thru back (60 oz./sq. yd. pile).
Class 2 - Single level cut or loop pile - woven thru back (63 oz./sq. yd. pile).
Class 3 - Single level loop pile, twist (65 oz./sq. yd. pile).
Class 4 - Single level cut pile, hard twist (76 oz./sq. yd. pile)
Class 5 - Single level cut pile - woven thru back (78 oz./sq. yd. pile).

Type II - Tufted

Class 1 - Cut (or sheared) and uncut pile (76 oz./sq. yd. pile)

Type III - Custom Tufted

Class 1 - Uncut pile with surface shear (76 oz./sq. yd pile)
Class 2 - Uncut pile with surface shear (96 oz./sq. yd. pile).

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of the specification to the extent specified herein

Federal Specifications

UU-P-268 - Paper, Kraft, Untreated, Wrapping
PPP-B-35 - Bags, Textile, Shipping, Burlap, Cotton and Waterproof Laminated.
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-B-640 - Boxes, Fiberboard, Corrugated, Triple Wall.
PPP-T-45 - Tape, Gummed, Paper, Reinforced and Plain, for Sealing and Securing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

Federal Standards:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civilian Agencies)
Fed. Std. No. 191 - Textile Test Methods.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U S Government Printing Office, Washington, D. C 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, MO., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specifications

MIL-C-43665 - Cloth, Wool, Mothproofing Treatment Of

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D C. 20580)

American Society for Testing and Materials (ASTM) Standards

D-297 - Chemical Analysis of Rubber Products
D-418 - Woven and Tufted Pile Floor Covering
D-1335 - Tuft Bind of Pile Floor Coverings.
D-2654-67T - Amount of Moisture in Textile Materials.

American Association of Textile Chemists and Colorists

AATCC-8 - Colorfastness to Crocking.
AATCC-134 - Electrostatic Propensity of Carpets

(Application for copies should be addressed to the American Association of Textile Chemists and Colorists, P O Box 12215, Research Triangle Park, NC 27709)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

National Motor Freight Traffic Association, Incorporated, Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Association, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, D C 20036.)

Uniform Classification Committee, Agent

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Preproduction sample. When specified (6.2), a preproduction sample of the carpet or rug, measuring 12 inches by 12 inches, shall be submitted to the contracting officer for approval.

3.2 Standard sample When a standard sample is available, the finished carpet or rug shall match the standard sample for color and appearance and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (6.3)

3.3 Material.

3.3.1 Pile yarn. Unless otherwise specified (6.2), the pile yarn shall be as specified in Tables I thru VIII. The pile yarn specified in Tables I thru VIII, or as otherwise specified, shall conform to the requirements specified in 3.3.1.1 thru 3.3.1.7, as applicable. When blends are specified and percent composition not specified, not less than 20 percent of any of the fibers listed below, as applicable, shall be used when blended and such blends cannot consist of more than two fibers The yarn ply shall be as specified in the physical requirements tables or as specified in the contract or order. When the ply is not specified, the yarn shall be at least 2-ply Fiber denier and staple length specified in this document are subject to normal fiber manufacturing variances. When a static resistance system is specified (6.2), the yarn may contain other fibers, e.g metallic, or materials to furnish static resistance and to this extent the foregoing percents specified may be adjusted

3.3.1.1 Wool Wool shall be thoroughly scoured carpet type fiber which has never been reclaimed from any woven, tufted, knitted, or felted products The wool yarn shall contain a minimum of 95 percent wool based on the original dry weight of the specimen when tested as specified in 4.3.1

3.3.1.2 Staple nylon. Staple nylon shall be carpet type fiber with a minimum fiber size of 15 denier and of uniform fiber length which has never been reclaimed from any woven tufted, knitted, or felted products For level loop carpet, the staple length shall be a minimum of 6 inches and the finished yarn shall contain a minimum of 3.5 turns per inch in the singles, and a minimum of 3.0 turns per inch in the ply The finished yarn shall contain not more than 2.0 percent chloroform soluble material when tested as specified in 4.3.1 When specified (6.2 and 6.5), the nylon yarn shall be of the soil hiding type.

3.3.1.3 Filament nylon. Filament nylon shall be continuous filament high bulk or textured carpet type yarn. Individual filament size shall be a minimum of 15 denier. Filament nylon shall be used only in those fabrics where specified in the tables of physical requirements The finished yarn shall contain not more than 2.0 percent chloroform soluble material when tested as specified in 4.3.1. When specified (6.2 and 6.5), the nylon yarn shall be of the soil hiding type.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

3.3.1.4 Staple acrylic. Staple acrylic shall be carpet type fiber with a minimum fiber size of 15 denier and of uniform fiber length which has never been reclaimed from any woven, knitted, tufted, or felted products. The minimum staple length shall be 6 inches. The finished yarn shall contain not more than 2.0 percent chloroform soluble material when tested as specified in 4.3.1.

3.3.1.5 Staple modacrylic. Staple modacrylic shall be carpet type fiber with a minimum fiber size of 15 denier and of uniform fiber length which has never been reclaimed from any woven, tufted, knitted, or felted products. The finished yarn shall contain not more than 2.0 percent ether soluble material when tested as specified in 4.3.1.

3.3.1.6 Polyester. Polyester shall be carpet type fiber with a minimum fiber size of 12 denier and of uniform fiber length which has never been reclaimed from any woven, tufted, knitted, or felted products. For level loop carpet, the staple length shall be a minimum of 6 inches and the finished yarn shall contain a minimum of 3.5 turns per inch in the singles, and a minimum of 3.0 turns per inch in the ply. The finished yarn shall contain not more than 2.0 percent chloroform soluble material when tested as specified in 4.3.1.

3.3.1.7 Filament polypropylene olefin. Filament polypropylene olefin shall be continuous filament high bulk or textured carpet type yarn. Individual filament size shall be a minimum of 15 denier. The finished yarn shall contain not more than 2.0 percent cold isopropanol soluble material when tested as specified in 4.3.1.

3.3.1.8 Staple polypropylene olefin. Staple polypropylene olefin shall be of the carpet type, with a minimum fiber size of 15 denier and a minimum staple length of 6 inches, which has never been reclaimed from any woven, tufted, knitted, or felted products. The finished yarn shall contain not more than 2.0 percent cold isopropanol soluble material when tested as specified in 4.3.1. For level loop carpet, the finished yarn shall contain a minimum of 3.5 turns per inch in the singles and a minimum of 3.0 turns per inch in the ply.

3.3.2 Attached rubber cushioning. When specified (6.2), rubber cushioning shall be attached to the carpet or rug as a secondary backing. The compound used in making the cushioning shall be made from natural or synthetic latex or a mixture of natural and synthetic latices. The cushioning shall be free of objectionable odor and shall have a skin on the floor side when affixed to the carpet or rug. The rubber cushioning shall be class 1 or class 2 as follows, unless otherwise specified (6.2)

Class 1 (Foam)

a. Cushioning shall average not less than 1/8 inch.
b. The weight per square yard shall be not less than 2.37 pounds.
c. The density shall be not less than 17 pounds/cu. ft.
d. The compression resistance shall be not less than 5 pounds per square inch.
e. The compression set shall be not more than 15 percent.
f. Delamination strength - more than 2 pounds per inch of width must be required to pull the cushion from the carpet.
g. Accelerated aging.

1. Heat aging - after exposure for 24 hours at 275°F the cushion, after flexing, should remain flexible and serviceable.
2. Fade Ometer - after 20 hours exposure to the Fade-Ometer, the cushion shall show only slight discoloration or crazing.

h. The maximum ash content of the cushion shall be 50 percent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

Class II· (Foam or sponge)

a Cushioning shall average not less than 3/16 inch.
b The weight per square yard shall be not less than 3.50 pounds nor more than 4 25 pounds.
c. The compressibility shall be not less than 5 pounds nor more than 9 pounds
d The compression set shall be not more than 15 percent
e Delamination strength - more than 2 0 pounds per inch of width must be required to pull the cushion from the carpet
f When subjected to an accelerated aging test, the cushion shall not deteriorate

3.3.3 Back coating. The back coating compound shall be a synthetic resin or synthetic latex compound.

3.4 Color and matching. The color shall be as specified (6.2) and shall match the standard sample, when available, under natural (north sky) daylight or artificial daylight having a color temperature of 7500° Kelvin (K.) and shall be a good approximation to the standard sample under incandescent lamplight at 2800° K when tested as specified in 4 5.14.

3.4 1 Colorfastness. The carpet or rugs shall show fastness to light and wet and dry crocking equal to or better than the standard sample When no standard sample is established, the carpet or rugs shall show good fastness to wet and dry crocking and light They shall show a rating of good for light colors after 20 standard fading hours and for dark colors after 40 standard fading hours The supplier is to submit with his bid and samples a certified list of the colors, identification of these colors by the bidder's color number, and the category of "light" or "dark" into which each color is classified by the supplier This list is to be submitted for each pattern and coloration. Testing shall be as specified in 4 4

3.5 Physical requirements. The finished carpets or rugs shall conform to the physical requirements specified in Tables I thru VIII. The total weight given is exclusive of back coating Tolerances of minus 6.0 percent will be allowed for pile and total weight only All other requirements shown in Tables I thru VIII are minimum, unless otherwise specified.

TABLE I Type I, Class 1 - Physical requirements

Description - Carpet, velvet (woven), alternate round and cut-woven thru back.

Weight, oz./sq yd	
Pile	- 60
Total	- 82
Tufts/sq inch	- 60
Pile height (inches)	
Minimum	- 0.230
Maximum	- 0.270
Material	
Pile yarn	- Wool, 4 ply, or as otherwise specified
Chain	- Cotton and/or rayon.
Filling	- Cotton and/or rayon, or jute
Stuffer	- Cotton, jute, or kraftcord
Back coating (ozs. sq. yd.)	- 8.5
Tuft bind (ozs.), minimum	- 50
Ply twist (turns per inch)	
Minimum	- 2.0
Maximum	- 3.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

TABLE II. Type I, Class 2 - Physical requirements

Description - Carpet, velvet, woven thru back, cut or loop (unless otherwise specified, (6.2), single level pile.	
Weight, oz /sq. yd	
Pile	- 65
Total	- 90
Tufts/sq. inch	- 58
Shots	- 2
Pile height (inches)	
Minimum	- 0 400
Maximum	- 0.475
Material	
Pile yarn	- Wool or acrylic/modacrylic, or as otherwise specified.
Chain	- Cotton, rayon or synthetic.
Filling	- Cotton, rayon, jute or synthetic
Stuffer (when used)	- Cotton, rayon, jute, kraftcord or synthetic.
Back coating (ozs sq. yd.)	- 12
Tuft bind (ozs), minimum	- 80
Ply twist (turns per inch)	
Minimum	- 1 5
Maximum	- 4.5

TABLE III Type I, Class 3 - Physical requirements

Description - Carpet, woven, single level loop, twist	
Weight, oz./sq yd.	
Pile	- 65
Total	- 110
Tufts/sq inch	- 140
Shots/wire	- 1
Pile height (inches)	
Minimum	- 0.480
Maximum	- 0.550
Material	
Pile yarn	- Wool, or as otherwise specified
Chair	- Cotton and/or rayor
Filling	- Cotton and/or rayor or jute
Back coating (ozs sq yd)	- 20
Tuft bind (ozs.), minimum	- 70
Ply twist (turns per inch)	
Minimum	- 7.0
Maximum	- 9.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

TABLE IV. Type I, Class 4 - Physical requirements

Description	Carpet, modified velvet (woven), cut pile, wool pile, hard twist, with secondary backing.
Weight, oz /sq yd	
Pile	76
Total	118
Construction 1/	
Pitch	162
Rows (wires) per inch	9.5
Pile height, inch	
Minimum	0 420
Maximum	0.570
Material	
Pile yarn	Wool, hard twist, or as otherwise specified
Chain	Cotton.
Filling	Jute or cotton.
Stuffer	Jute or cotton.
Secondary backing	Jute fabric.
Back coating (ozs. sq. yd.)	12
Tuft bind (oz.), minimum	80
Ply twist (turns per inch)	
Minimum	1.5
Maximum	4.5

1/ Any number of rows (wires) per inch in excess of that specified is acceptable. Nine rows (wires) per inch are acceptable with 180 or 189 pitch construction

TABLE V Type I, Class 5 - Physical requirements

Description	Carpet, velvet, woven thru back, cut or loop (unless otherwise specified, 6.2), single level pile
Weight, oz./sq yd.	
Pile	78
Total	104
Construction	
Pitch	Back 216
	Face 324
Rows (wires) per inch	7.5
Pile height (inches)	
Minimum	0.220
Maximum	0.240
Material	
Pile yarn	Acrylic, 4 ply or as otherwise specified.
Chain	Synthetic.
Filling	Resin impregnated jute.
Stuffer	Synthetic.
Back coating (ozs. sq. yd.)	14
Tuft bind (ozs.), minimum	100
Ply twist (turns per inch)	
Minimum	1.5
Maximum	4.5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

TABLE VI. Type II, Class 1 - Physical requirements

Description	Carpet, tufted, cut (or sheared) and uncut pile.
Weight, oz./sq. yd.	
Pile	76
Total	115
Construction 1/	3/16 inch gauge, 6.5 stitches per inch
Yarn ends/needle, minimum 2/	2
Pile height (inches)	
Minimum	0.375
Maximum	0.530
Material	
Pile yarn 2/	Wool, 3 ply, twisted; or as otherwise specified.
Backing material	Heavy duty fabric made of vegetable fiber yarns.
Secondary back	Light or heavy duty fabric made of vegetable fiber yarns.
Back coating (ozs sq. yd.)	12
Tuft bind (ozs.), minimum	80

1/ An alternate construction (i.e a gauge and stitches per inch other than specified) is acceptable when approved by the contracting officer, except that carpet with such construction shall contain not less than 60 tufts per square inch and all other requirements of the specification shall be complied with. Tufts per square inch shall be determined by multiplying the number of ends per inch by the number of stitches per inch

2/ A 2-ply pile yarn is acceptable only when 4 or more yarn ends per needle are used

TABLE VII Type III, Class 1 - Physical requirements

Description	Carpet, custom tufted, uncut pile with approximate 5 percent surface shear, stitched or punched horizontally and vertically, criss-cross type of surface pattern
Weight, oz /sq. yd.	
Pile	76
Total	115
Yarn ends/needle, minimum 1/	3
Stitches or tufts per inch	
Horizontal	5 to 6
Vertical	4.8 to 5.3
Pile height (inches)	
Minimum	0.375
Maximum	0.530
Material	
Pile yarn	Wool 1/, twisted, or as otherwise specified.
Backing material	Heavy duty fabric made of vegetable fiber yarns.
Secondary back	Light or heavy duty fabric made of vegetable fiber yarns
Back coating (ozs. sq. yd.)	12
Tuft bind (ozs.), minimum	50

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

1/ Yarn size shall be 3/36. Yarn size of 2/60 is acceptable when 4 or more yarn ends per needle are used. The 3/36 yarn size covers a 3 ply yarn, with 36 yards of the 3 ply yarn weighing one ounce and the 2/60 yarn covers a 2 ply yarn, with 60 yards of the 2 ply yarn weighing one ounce.

TABLE VIII. Type III, Class 2 - Physical requirements

Description -	Carpet, custom tufted, uncut pile with approximate 5 percent surface shear, punched horizontally and vertically, criss-cross surface construction
Weight, oz./sq. yd.	
Pile	- 96
Total	- 120
Construction, lines per foot 1/	
Horizontal	- 28
Vertical	- 28
Yarns ends/needle	- 3
Stitches or tufts per inch.	
Horizontal	- 5 to 6
Vertical	- 4.8 to 5
Pile height (inches)	
Minimum	- 0.340
Maximum	- 0.420
Material	
Pile yarn	- Wool, 3/36 yarn 2/, twisted, or as otherwise specified
Backing material	- Heavy duty fabric made of vegetable fiber yarns
Secondary back	- Light or heavy duty fabric made of vegetable fiber yarns.
Back coating (ozs sq. yd.)	- 12
Tuft bind (ozs.), minimum	- 50

1/ Lines per foot may be adjusted slightly to meet final range requirements of stitches or tufts per inch.
2/ The yarn size covers a 3 ply yarn, with 36 yards of the 3 ply yarn weighing one ounce.

3.6 Shrinkage. The shrinkage shall not exceed 5.0 percent in either the length or the width when tested as specified in 4.4

3.7 Moth repellency. Moth repellency shall be in accordance with the provisions of MIL-C-43665

3.8 Construction.

3.8.1 Applicable to all types and classes.

3.8.1.1 Type I, classes 1 thru 5 Type I, classes 1 thru 5, carpets and rugs shall be coated on the back or floor side. The minimum amount of coating compound shall be as specified in Tables I thru V. Type I, class 4, carpets or rugs shall also have a secondary backing as specified in Table IV.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

3.8.1.2 Type II, class 1, and type III, class 1 and 2. Type II, class 1, and type III, classes 1 and 2, carpets or rugs shall have a backing material as specified in Table V thru VII, as applicable, into which the tufts are needled to form the carpet or rug. The carpets and rugs shall also have a secondary back as specified in Tables VI thru VIII, as applicable, applied to the back or floor side of the carpet or rug using the backing compound specified in 3 3.3. The adherence shall be such that the strip requirement shall be a minimum of 2.0 pounds per inch of width when tested as specified in 4.4.

3.8.2 Edges and binding. Unless otherwise specified (6.2), all cut edges shall be tape bound, except for carpeting supplied specifically for wall-to-wall installation and carpets and rugs with attached rubber cushioning. Carpets and rugs may be serged at the contracting officer's option

3.8.3 Seaming. Standard seamless broadloom widths shall be used unless the size required necessitates seaming. Seams shall be kept to the minimum practicable. Seams, where required, are to be sewn or taped (or both) as specified (6.2). Seams on carpets and rugs without attached rubber cushioning shall have a breaking strength of not less than 100 pounds when tested as specified in 4.4. Tape used in making seams shall be a minimum of 2-1/2 inches wide. Seams on rugs with attached rubber cushioning, not installed wall-to-wall, shall be made with carpet type, single face, pressure sensitive adhesive tape with a minimum width of three inches. The tape used should be that recommended by the carpet manufacturer, or equal In addition, adhesive shall be applied to both edges of the carpet at the joint These edges shall be brought together to insure direct contact of the adjoining edges after application of the adhesive. The finished seams shall be secure and able to withstand conventional commercial rug cleaning processes.

3 9 Size and pattern. The length, width, and pattern of the carpets and rugs shall be as specified (see 6.2)

3.9.1 Dimensional tolerance. The dimensional tolerances shall be as follows

Cut rugs	- width or length - not more than 1 percent less than specified
Rolls	- width - not more than 1 percent less than specified. - length - not less than specified nor more than 10 percent longer than specified
Individual roll	- not more than 1 yard less than indicated on piece ticket.
Total yardage in sample	- total gross length of all pieces in sample not less than the total gross length marked on piece tickets

3 10 Flame resistance. Unless otherwise specified (6.2), charred portion shall not extend to within 1 inch of the edge of the hole in the flattening frame at any point. The test shall be conducted on both the face and back surface of the carpet or rug When a carpet or rug has an attached rubber cushion, the rubber cushion shall be tested as the back surface of the carpet or rug

3.11 Fiber identification Each carpet and rug shall be labeled, ticketed, or invoiced for fiber content in accordance with the Textile Fiber Products Identification Act.

3 12 Static control When specified (6 2), a static control system shall be incorporated in the carpeting which permanently controls static buildup to less than 2500 volts when tested at 20 percent relative humidity and 70°F

3.13 Workmanship Carpets and rugs shall conform to the quality and grade of product established by this specification The occurence of defects shall not exceed the applicable acceptable quality levels (AQL's).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Preproduction sample inspection. When a preproduction sample is required, inspection shall be made of the completed end item for conformance with all provisions of this specification.

4.3 Inspection for acceptance. Inspection shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated.

4.3.1 Inspection of components and materials. In accordance with 4.1 above, the supplier is responsible for insuring that components and materials meet the requirements of this specification. Testing shall be performed on the components listed in Table IX, as applicable. Except as otherwise specified, test methods referenced are specified in Federal Test Method Standard No. 191. The sample unit shall be of sufficient size to conduct the required tests. The sample size shall be as specified in Table X. The lot shall be unacceptable if one or more sample units fail to meet any specified requirement.

4.3.2 Examination of the end item. Defects found during the visual examination shall be classified in accordance with 4.3.2.1, 4.3.2.2, and 4.3.2.3

4.3.2.1 Visual examination. The defects listed in Table XI shall be counted regardless of their proximity to one another, except where two or more defects represent a single local condition of the carpet, in which case only the more serious defect shall be counted. Continuous defects shall be counted as one defect for each yard or fraction thereof in which they occur. The sample unit shall be 1 linear yard. The acceptable quality levels (AQL's) shall be 2.5 major and 6.5 total defects (major and minor combined) per hundred units (linear yards). The sample size shall be based on inspection level II of MIL-STD-105. The lot size shall be expressed in units of 1 linear yard. When examination is made of full rolls, not more than one third of the total sample yardage shall be examined in any one roll. When the lot consists of less than 5 rolls, an approximate equal number of yards shall be examined on each roll to yield the sample yardage. When examination is made on carpets cut to size, the number of units selected shall be sufficient to yield the sample yardage. Visual examination shall be made at a distance of approximately six feet.

4.3.2.2 Overall examination. Each defect listed shall be counted not more than once in each unit examined. The sample unit for this examination shall be one roll or cut piece. The number of rolls or cut pieces examined for visual examination shall be the sample size. The lot shall be unacceptable if one or more of the following defects are found:

Overall uncleanness.
Color or pattern other than specified.
Objectionable odor.
Type not as specified.
Edges not finished as required.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

TABLE IX. Component testing

Component and lot size expressed in terms of	Characteristic	Requirement paragraph	Test method	Sample unit
Pile yarn (lbs.)	Material identification	3.3.1	1/	
	Ply	3.3.1	Visual	
	Denier	3.3.1.2, 3.3.1.3, 3.3.1.4, 3.3.1.5, 3.3.1.6, 3.3.1.7, and 3.3.1.8	4021	
	Turns per inch	Tables I thru V	4054	1/2 lb
	Wool content	3.3.1.1	2101	
	Chloroform soluble material	3.3.1.2, 3.3.1.3, 3.3.1.4, and 3.3.1.6	2611	
	Ether soluble material	3.3.1.5	Standard Commercial 2/	
	Isopropanol soluble material	3.3.1.7	Standard Commercial 2/	
Chain, filling and stuffer yarns (lbs. ea.)	Material identification	Tables I thru V	1/	1/2 lb
Backing material and reinforcement (yds.)	Material identification	Tables VI thru VIII	1/	1/2 yd
Back coating compound (pt.)	Material identification	3.3.3	1/	1/2 pt
Rubber cushioning				
Class 1	Material identification	3.3.2	1/	1/2 lb.
Class 2	Material identification	3.3.2	1/	
	Thickness	3.3.2	4.5.6	1 lin yd.
	Weight	3.3.2	4.5.8	
	Density (class 1)	3.3.2	4.5.7	
	Compressibility	3.3.2	4.5.9	
	Compression set	3.3.2	4.5.10	

1/ Acceptance of these characteristics shall be based on a supplier's certification of compliance

2/ The contractor shall submit a certificate of compliance for this characteristic The certificate shall be accompanied by actual test or other verifiable quality data Test may be conducted on finished carpet specimens.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

TABLE X. Sample size

Lot size (units)	Sample size
800 or less	2
801 to 22,000	3
22,001 and over	5

TABLE XI Classification of defects

Defects	Classification Major	Minor
Spot or stain		X
Not evenly constructed, affecting appearance		X
Marks across carpet.	X	
Discolored areas affecting appearance.		X
Any noticeable unevenness on top surface affecting appearance.		X
Any obviously objectionable streak lengthwise of roll or piece.	X	
Tufts missing in pile.	X	
Cut, hole or tear	X	
Seams (where required) not properly sewed, or taped	X	
Cushioning (when required) imperfectly applied, poor adherence.	X	
Imbedded foreign matter.		X

4.3.2.3 Dimensions examination. Each defect listed below shall be counted not more than once in each unit examined The sample unit for this shall be one roll or rug. The number of rolls or rugs examined for visual examination (4.3.2.1) shall be the sample size for this examination. The lot shall be unacceptable if one or more of the following defects are found

Cut rugs - Width or length more than 1 percent less than specified.

Rolls - Width - more than 1 percent less than specified
Length - less than specified, or more than 1 yard less than indicated on piece ticket Total yardage in sample - total gross length of all pieces in sample less than the total gross lengths marked on piece tickets.

4.4 Testing of the end item. Tests shall be performed for the characteristics specified in Table XII Except as otherwise specified, test methods referenced are specified in Fed Test Method Std. No 191 Unless otherwise specified, the physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes in the applicable test method The sample unit shall be 1 square yard for the rolls or one carpet cut to size, as applicable The lot size for purposes of end item testing shall be expressed in units of square yards for rolls and pieces of carpet as applicable. The sample size shall be as listed in Table X. The lot shall be unacceptable if one or more units fail to meet any requirement specified.

4.5 Tests.

4.5.1 Tufts per square inch. Tufts per square inch shall be determined by multiplying the pitch per inch of pile yarn ends by the rows of pile per inch, or by equivalent thereof. Pitch and rows per inch shall be determined in accordance with ASTM D-418. Pitch is defined as the number of pile yarn ends per inch of width in the carpet. Rows is defined as the number of rows of tufts per inch of length (also referred to as stitches per inch for tufted).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

TABLE XII. End item testing

Characteristic	Requirement references	Test method
Construction (including tufts per square inch)	Tables I thru VIII	Standard Commercial (see 4.5.1 for tufts per square inch)
Weight of pile yarn	Tables I thru VIII	4.5.2
Total weight	Tables I thru VIII	5040 or 5041 2/
Pile height	Tables I thru VIII	4.5.3
Weight of back coating 4/	Tables I thru VIII	4.5.4
Tuft bind	Tables I thru VIII	ASTM D-1335
Adherence of backing reinforcement	3.8.1.2	4.5.5
Attached rubber cushioning		
Thickness 4/	3.3.2	4.5.6
Weight (class 1) 4/	3.3.2	4.5.8
Density (class 1)	3.3.2	4.5.7
Compressibility (class 1)	3.3.2	4.5.9
Compression set (class 1)	3.3.2	4.5.10
Adherence (classes 1 & 2)	3.3.2	4.5.11
Accelerated aging (classes 1 & 2)	3.3.2	4.5.12
Ash content	3.3.2	ASTM D-297
Colorfastness		
To light	3.4.1	5660 3/
To wet and dry crocking	3.4.1	AATCC-8
Shrinkage	3.6	4.5.14
Moth repellency (insect resistance)	3.7	5/
Seam strength	3.8.3	5100
Flame resistance	3.10	4.5.15
Static control	3.12	AATCC-134

1/ One determination shall be made on each sample unit and the result reported as "pass or fail".
2/ When method 5041 is used, one specimen with an area of at least 16 square inches shall be used.
3/ In the event of a dispute resulting from the test with method 5660, or as a result of suspected anomalous behavior of certain dye types or formulations, the contracting officer shall authorize the exposure to natural light in accordance with method 5662.
4/ The test results for each of these characteristics shall be reported as the lot average.
5/ See MIL-C-43665.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

4.5.2 Weight of pile yarn. The pile yarn shall be separated from other yarns on a sample containing 16 square inches. To express weight of pile yarn per carpet or rug (36 inches by 36 inches), the weight of the pile shall be calculated as follows. Weight of pile yarn (ounces) in 16 square inch sample X 81.0 = weight of pile yarn in ounces per square yard of carpet or rug

4.5.3 Pile height and tuft length and pile height differential. For single level pile fabrics, pile height or tuft length shall be determined in accordance with ASTM D-418 For multilevel or profile wire carpet, use the following method A metal rule graduated in 1/100 inch approximately 3/4 inch wide and 0.040 inch thick shall be inserted between the lengthwise pile rows parallel thereto, and the height of pile in the high pile areas measured five times and the height of the pile in the low pile areas measured five times The areas measured shall be selected so that lines drawn parallel to and perpendicular to the edge of the sample through the points of measurement shall be at least 2 inches apart. The average of the five measurements in the high pile area shall be the high pile height and the average of the five measurements in the low pile area shall be the low pile height The difference between the high pile height and the low pile height shall be the differential pile height.

4.5.4 Weight of back coating. The weight of the carpet or rug after back coating shall be determined in accordance with method 5040 or 5041 of Fed. Test Method Std No. 191. When method 5041 is used, one specimen with an area of at least 16 square inches shall be used. The results of this test shall be reported as the lot average The individual sample unit results obtained for the total weight characteristic (exclusive of back coating) shall be averaged and this result subtracted from the lot average weight after back coating. The difference obtained shall be the lot average weight of the back coating and shall be reported to the nearest ounce.

4.5.5 Adherence of backing reinforcement. The adherence of backing reinforcement shall be determined in accordance with method 5100 of Fed. Test Method Std No. 191, except as noted below Cut finished samples, with backing reinforcement applied, 2 inches wide in width direction by 6 inches long in length direction Strip the backing reinforcement from the test specimen for approximately 1-1/2 inches at one of the 2 inch wide ends Set jaws 1 inch apart, clamp the loose end of the backing reinforcement in the lower jaw and the loose end of the carpet in the upper jaw. Start tester and record the average load required to strip the backing reinforcement Make three tests, average results, and divide by two to secure the pounds strip per inch of width The average shall be reported to the nearest 0.1 pound

4.5.6 Thickness of rubber cushion.

4.5.6.1 Class 1 rubber cushion. Mark the foam cut from each specimen for identification Using a single determination, measure the total thickness of each specimen to the nearest millimeter The thickness gauge shall have a circular presser foot with a diameter of 1.129 ± 001 inch. The presser foot shall be allowed to exert a pressure of 100 grams per square inch. The load shall be applied slowly without impact and the thickness shall be read immediately. The average of six readings shall be reported as the thickness of the foam.

4.5.6.2 Class 2 rubber cushion. The specimen shall be one square yard of the finished item (with cushioning) The thickness between the two plane surfaces of the specimen shall be determined under pressure of 0.100 pounds per square inch (p.s.i.) (± 0.002 p.s.i.) distributed over a circular area 1.129 inches ± 001 inch (7.5 ±) in diameter. Apply pressure slowly to avoid impact and protect the specimen from vibration during the test. Five readings shall be taken on the specimen and the average computed to the nearest 0.001 inch (millimeter). The results from the sample units in the sample size shall be averaged and computed to the nearest 0.001 inch (millimeter) This is the lot average thickness of the finished item A one square yard specimen of the carpet before application of cushioning shall be tested for thickness as specified above. The results from the sample units in the sample size shall be averaged and computed to the nearest 0.001 inch (millimeter). This is the lot average thickness of the carpet before application of the cushioning. The difference between the thickness before application of the cushioning and the thickness of the finished item shall be the average thickness of the rubber cushioning.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

4.5.7 Density of rubber cushion.

4.5.7.1 Class 1 rubber cushion. The density of class 1 rubber cushion is determined by the following procedure.

The average weight in grams of the six specimens measured for weight shall be converted to pounds by multiplying by 0.002205. The average thickness in inches shall be converted to volume in cubic feet by multiplying 4 inches by 4 inches by average thickness in inches by 0.0005787.

Then Density = $\frac{\text{Weight in pounds}}{\text{Volume in cubic feet}}$

4.5.8 Weight of rubber cushion.

4.5.8.1 Class 1 rubber cushion. Die cut a total of six 4 inch by 4 inch square specimens from the carpet, taking two specimens from the center area and two specimens from each side area. The cut shall not be nearer than 6 inches from the outer edges of the carpet. Die cut the specimens, with the foam side against the cutting die. The specimens shall be conditioned for a minimum of 4 hours under standard conditions of 70°F. (± 2°F.) and 65 percent (± 2 percent) relative humidity for testing. Weigh each specimen to the nearest milligram. Using the electric carving knife and supporting guides, separate from foam carpet backing by cutting at the line where the textile components meet the foam component. Cut as closely as possible without damaging the carpet backing components. Put aside the slabs of foam for future use. Remove the remaining foam from the carpet backing by brushing it with a stiff wire bristled brush Weigh each backing specimen to the nearest milligram Calculate the weight of the foam for each specimen as the difference between the total weight of the carpet with foam backing and without foam backing. Report the average of the six specimens as the weight of the foam.

4.5.8.2 Class 2 rubber cushioning. The specimen shall be one square yard of the finished item (with cushioning) The specimen shall be conditioned for a minimum of 4 hours under standard conditions of 70°F. (± 2°F) and 65 percent (± 2 percent) relative humidity for testing. The specimen shall be weighed to the nearest 0.01 pound per sq. yd. The results from the sample units in the sample size shall be averaged and computed to the nearest 0.01 pound per sq. yd. This is the lot average weight of the finished item. A one square yard specimen of the carpet, before application of the cushioning, shall be tested for weight as specified above The results from the sample units in the sample size shall be averaged and computed to the nearest 0.01 pounds per square yard This is the lot average weight of the carpet before application of the cushioning The difference between the weight before application of the cushioning and the weight of the finished item shall be the lot average weight of the cushioning and shall be reported to the nearest 0.01 pound per square yard.

4.5.9 Compression resistance.

4.5.9.1 Class 1 rubber cushion. Using 2 inch by 2 inch foam specimens, form plies of plied specimens approximately 1 inch thick Place the plied specimens in a compression tester (Instron recommended) and, with a circular presser foot one square inch in area (1.129 inch diameter), determine the total thickness of the plied specimen at a load of 100 grams per square inch. Compress the specimen to 75 percent of its original thickness using the 1.00 square inch presser foot and immediately determine the load required to compress the specimen this amount This reading, exclusive of the 100 gram preload, is the compression resistance of the foam Using a second set of specimens, repeat the test to obtain a second set of values Both values shall be averaged and the result reported as the compression resistance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

4.5.9.2 Class 2 rubber cushion. The specimen shall be a one inch (2.5 cm.) square sample cut from full thickness of cushion material before adhering to the carpet. The specimen shall be compressed to 75 percent of its original thickness. Thickness shall be measured with a guage having a circular foot one square inch (6.5 square centimeters) area under a load of 100 grams (g) (0.220 lbs.). The number pounds required to compress the sample shall be the compressibility and shall be reported to the nearest pound.

4.5 10 Compression set.

4.5.10.1 Class 1 rubber cushion. Pile up 2 inch by 2 inch specimens one on another until the pile has a total thickness of approximately 1 inch. Prepare two such piles using a total of approximately 16 of the 2 inch by 2 inch specimens for 1/8 inch foam and approximately 10 of the 2 inch by 2 inch specimens for 3/16 inch foam. Apply a load of 100 grams per square inch and determine the thickness of the plied specimens using a fixture consisting of two parallel plates that are larger than the 2 inch by 2 inch specimens and spacer bars that are equal in thickness to 50 percent of the thickness of the plied specimens. Compress the plied specimens of 50 percent of its original thickness as determined under a 100 gram per square inch load. Place the fixture with the compressed specimens in a circulating air oven at 158° + 2°F for 22 hours + 1/2 hour. Remove the fixture from the oven, unclamp immediately and remove the plied specimen from the fixture. After 30 minutes recovery period, remeasure the thickness of the plied specimens under a load of 100 grams per square inch. Determine the difference from the original thickness Divide the difference by the original thickness by 100. This value is the compression set Do the tests on both sets of specimens and report the average. When plying the specimens, place a skin side against a cut side. If the plies adhere together after the oven treatment, do not separate before measuring.

4.5.10.2 Class 2 rubber cushion. The specimen shall be 2 inches by 2 inches sample cut from the full thickness of the cushion before adhering to the carpet. The specimen shall be compressed 50 percent of its original thickness between two parallel plates. The thickness shall be measured in accordance with 4 5.8.1. The sample compressed shall be placed in a Geer oven at 158°F (+ 2°F.) for 22 hours (+ 1/2 hour) At the end of the specified time, the sample shall be removed from the plates and allowed to rest at room temperature for 30 minutes The thickness measurement shall be taken and subtracted from the original thickness The loss in thickness shall be expressed as a percentage of the original thickness and reported to the nearest percent.

4.5.11. Adherence.

4.5.11.1 Class 1 rubber cushion. From the original sample cut a 2 inch by 6 inch strip lengthwise of the carpet, one from the center, and one from each side area Cover the foam side with self-adhering tape. Separate the foam from the carpet for approximately 1-1/2 inches at one end of the 2 inch wide ends A tensile tester equivalent to that described in Method 5100 of Fed. Test Method Std No. 191 shall be used Set the clamps 1 inch apart, clamp the loose end of the attached foam in the lower clamp and the loose end of the carpet in the upper clamp The clamps must be as wide as the strips that are being gripped Start the tester at a speed of 12 inches per minute and record the five highest readings required to strip the attached foam from the carpet. Test the three specimens, average the results, and divide by two to determine the load in pounds per inch of width.

4.5.11.2 Class 2 rubber cushion. A specimen of the finished carpet with rubber cushioning attached shall be subjected to accelerated aging by exposure in a circulating air oven for 96 hours at a temperature of 90°F (+ 2°F.). After removal of the sample from the oven and allowing it to cool to room temperature, grasp the base carpet with the fingers of one hand and the thickness of the rubber cushioning with the fingers of the other hand and pull firmly in opposite directions. The cushioning should tear before pulling free from the carpet.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

4.5.12 Accelerated aging.

4.5.12.1 Class 1 rubber cushion. Place a 2 inch by 4 inch specimen of the foam, attached to the carpet, in a circulating air oven at 275°F. for 24 hours. Place another 2-1/2 inches by 3 inches specimen attached to the carpet in a Fadeometer in accordance with method 5660 of Fed. Test Method Std. No. 191. Foam samples should withstand these exposures with no more than slight discolorations and/or surface degradation following either test Upon flexing, a slight cracking or crazing is acceptable

4.5.12.2 Class 2 rubber cushion. A piece of the rubber cushioning shall be placed in an oxygen bomb (not more than 1 ounce of rubber per 170 cubic inches of oxygen) at a temperature of 158°F and a pressure of 300 pounds (+ 10 pounds) per square inch for a period of seven days. Upon removal, sample should not be sticky and should not crack when bent back upon itself.

4.5.13 Color matching test. A test specimen at least 8 inches square shall be mounted at an angle of 45° to the horizontal and compared with the standard sample or the approved color sample furnished by the contracting officer, similarly mounted under the light conditions specified in 3.4 When an artificial light source is used it shall be placed so that its rays strike the sample normal to its surface. The viewing distance shall be 18 to 24 inches.

4.5.14 Shrinkage test. A 12 by 12 inch sample of the specified carpet shall be conditioned under standard conditions as defined in Fed Test Method Std No 191 for a period of 24 hours. Specimen shall then be marked and measured at three different locations in the length and width directions, immerse sample in 110°F. water for 15 minutes, mix 2 g of sodium alkylsulfate type of detergent with 50 g of water at 110°F and apply to pile surface of carpet. Scrub sample with a soft bristle brush by stroking back and forth 20 times (10 times in each unilateral direction), and in both length and width directions, rinse well to remove majority of detergent, squeeze and dry at 125°F. until bone dry, again condition under standard conditions for 24 hours.

4.5.14.1 Shrinkage evaluation The specimen shall be measured and the shrinkage computed using the following formula

$$\text{Shrinkage} = \frac{A - B}{A} \times 100$$, where A = Average of initial measurement and B = Average measurements after shampooing The shrinkage in both the length and width directions shall be reported to the nearest 0 1 percent

4 5.15 Flame resistance.

4.5.15.1 Test specimens. Each test specimen shall be a 9 + 1/4 inches square section of the carpet or rug to be tested Eight specimens are required

4.5.15.2 Apparatus.

a Test chamber The test chamber shall consist of an open top hollow cube made of noncombustible material 1/ with inside dimensions 12 by 12 by 12 inches and a minimus of 1/4 inch wall thickness The flat bottom of the box shall be made of the same material as the sides and shall be easily removable The sides shall be fastened together with screws or brackets and taped to prevent air leakage into the box during use

NOTE A minimum of two chambers and two extra bottoms is suggested for efficient operation.

b. Flattening frame. A steel plate, 9 by 9 inches, 1/4 inch thick with a 8 inch diameter hole in its center is required to hold the carpet or rug flat during the course of the test. It is recommended that one be provided for each test chamber.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

c. Standard igniting source. No. 1588 methenamine timed burning tablet or equal tablet. These tablets shall be stored in a desiccator over a desiccant for 24 hours prior to use. (Small quantities or sorbed water may cause the tablets to fracture when first ignited. If a major fracture occurs, any results from that test shall be ignored, and it shall be repeated.)

d. Circulating air oven. A forced circulating drying oven capable of removing the moisture from the specimens when maintained at 105°C. (221°F.) for 2 hours. 2/

e Desiccating cabinet. An airtight and mosturetight cabinet capable of holding the floor covering specimens horizontally without contacting each other during the cooling period following drying, and containing silica gel dessicant

f. Gloves. Nonhygroscopic gloves (such as rubber polyethylene) for handling the sample after drying, and raising the pile on specimens prior to testing.

g. Hood. A hood capable of being closed and having its draft turned off during each test and capable of rapidly removing the products of combustion following each test. The front or sides of the hood should be transparent to permit observation of the tests in progress

h. Mirror. A small mirror mountec above each test chamber at an angle to permit observation of the specimen from outside of the hood.

i. Vacuum cleaner. A cacuum cleaner to remove all loose material from each specimen prior to conditioning. All surfaces of the vacuum cleaner contacting the specimen shall be flat and smooth.

4.5.15.3 Procedure.

a. Cutting, and when specified, washing procedure if fire retardant treated. Cut eight 9 + 1/4 inch square specimens of each carpet or rug to be tested Note, if the carpet or rug has had a fire-retardant treatment, or is made of fibers which have had a fire-retardant treatment, and when specified in the contract or order (6.2), the selected sample or oversized specimens thereof shall be washed, prior to cutting of test specimens, 10 times under the washing and drying procedure prescribed in Method 124-1967 of the American Association of Textile Chemists and Colorists (washing procedure 6.2 (III) with a water temperature of 60° + 2.8°C (140°F. + 5°F), drying procedure 6.3.2 (B), maximum load 3 64kg. (8 pounds), unless otherwise specified

b Conditioning. Clean each specimen with the vacuum cleaner until it is free of all loose ends left during the manufacturing process and from any material that may have been worked into the pile during handling 3/ Care must be exercised to avoid "fuzzing' of the pile yarn.

Place the specimens in the drying oven in a manner that will permit free circulation of the air at 105°C. (221°F.) around them for 2 hours 4/ Remove the specimens from the oven with gloved hands and place them horizontally in the desiccator with traffic surface up and free from contact with each other until cooled to room temperature, but in no instance less than 1 hour.

c. Testing. Place the test chamber in the draft-protected environment (hood with draft off) with its bottom in place Wearing gloves remove a test specimen from the desiccator and brush its surface with a gloved hand in such a manner as to raise its pile. Place the specimen on the center of the floor of the test chamber, traffic surface up, exercising care that the specimen is horizontal and flat Place the flattening frame on the specimen and position a methenamine tablet on one of its flat sides in the center of the 8 inch hole

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

Ignite the tablet by touching a lighted match or an equivalent igniting source carefully to its top. If more than 2 minutes elapse between the removal of the specimen from the desiccator and the ignition of the tablet, the conditioning must be repeated.

Continue each test until one of the following conditions occurs

(1) The last vestige of flame or glow disappears. (This is frequently accompanied by a final puff of smoke)

(2) The flaming or smoldering has approached within 1 inch of the edge of the hole in the flattening frame at any point

When all combustion has ceased, ventilate the hood and measure the shortest distance between the edge of the hole in the flattening frame and the charred area. Record the distance measured for each specimen.

Remove the specimen from the chamber and remove any burn residue from the floor of the chamber Before proceding to the next test, the floor must be cooled to normal room temperature or replaced with one that is at normal room temperature.

After completion of the testing on the specimens with the traffic surface up, the same testing shall be performed on the specimens except that the back surface shall be up and tested with the methenamine tablet.

(d) Report The number of specimens of the eight tested in which the charred area does not extend to within 1 inch of the edge of the hole in the flattening frame shall be reported

e. Interpretation of results. If the charred area does not extend to within 1 inch of the edge of the hole in the flattening frame at any point for at least seven of the eight specimens, the carpet or rug meets the acceptance criterion. That is, at least seven of the eight specimens must meet the acceptance criterion when tested with the traffic surface up and at least seven of the eight specimens must meet the acceptance criterion when tested with the back surface up.

Footnotes

1/ 6.35 mm. (1/4 inch) cement asbestos board is a suitable material
2/ Option 1 of ASTM D 2654-67T, Methods of Test for "Amount of Moisture in Textile Materials" describes a satisfactory oven.
3/ The vacuum cleaning described is not intended to simulate the effects of repeated vacuum cleaning in service
4/ If the specimens are moist, permit them to air-dry at laboratory conditions prior to placement in the oven

4 6 Inspection for preparation for delivery. An inspection shall be made to determine whether the packaging, packing and marking comply with the requirements in section 5 of this specification. Defects shall be scored in accordance with table VIII For examination of interior packaging the sample unit shall be one shipping container fully prepared for delivery, selected at random just prior to the closing operations Sampling shall be in accordance with MIL-STD-105. Defects of closure listed shall be examined on shipping containters fully prepared for delivery The lot size shall be the number of shipping containers in the end item inspection lot The inspection level shall be S-2 with an AQL of 4.0 defects per hundred units

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

TABLE XIII. Classification of preparation for delivery defects

Examine	Defects
Markings	Omitted, incorrect; illegible, improper size, location, sequence, or method of application.
Material	Any component missing or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, loose strapping, inadequate stapling or distortion of container.
Contents	Quantity per container is more or less than required. Net weight exceeds requirements of the applicable box specification.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, or C, as specified (6.2).

5.1.1 Level A. Carpet or rugs, singly or in multiples, shall be tightly rolled Carpet or rugs six feet or more in width shall be rolled open-width on a convolute or spirally wound chipboard tube, or on a pole The tube shall have a minimum wall thickness of .250 inches with a minimum inside diameter of 2 inches For rolls weighing 200 pounds or more, regardless of width, the tube shall have a minimum wall thickness of .375 inches with a minimum inside diameter of 3 inches The ends of the tube or pole shall be flush with or extend not more than one inch beyond each end of the maximum width of the rolled carpet or rug. Carpet or rugs shall be secured to prevent unwinding with cotton tape or twine placed approximately one-sixth of the width from each end Rolls wider than 36 inches shall have additional fastening placed at the center of the roll. Rolled and tied carpet or rugs shall be completely wrapped with 60 pound minimum basis weight kraft paper conforming to UU-P-268, grade B All seams and folds of the paper wrap shall be securely sealed with 2-1/2 inch minimum width tape conforming to PPP-T-45, type III, class 2, grade B.

5.1.2 Level C. Carpet or rugs, singly or in multiples, shall be packaged to insure protection during shipment and safe delivery to destination.

5.2 Packing. Packing shall be level A, B or C, as specified (6.2).

5.2.1 Level A Rolled carpet or rugs of one size, type, class, pattern and color only, packaged as specified in 5.1 shall be packed in boxes conforming to PPP-B-636, class weather-resistant, style FOL, or to PPP-B-640, class 2, style A, B or C Closure and water-proof sealing of the boxes shall be in accordance with the appendix to the applicable box specification. When specified (6.2) individual rolls of carpets or rugs shall be packed in laminated textile shipping bags conforming to PPP-B-35, type III, class 2, Number P-14; style B with water-proof sewn seams Cloth covered rolls shall have each open and closed with two double looped wire ties. The wire ties shall be not less than 6 inches long and of .072 inch minimum diameter soft steel wire with a 1/2 inch diameter formed eye at each end The first tie shall be applied as close to the end of the roll as practicable The second wire tie shall be applied at a distance approximately one inch from the first tie. The twisted ends shall alternate and face in opposite directions

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

5.2.2 Level B. Rolled carpet or rugs of one size, type, class, pattern and color only, packaged as specified in 5.1 shall be packed in boxes conforming to PPP-B-636, class domestic, style FOL, or to PPP-B-640, class I, style A, B or C. Closure of the boxes shall be in accordance with method II of the appendix to PPP-B-636 or the applicable method of PPP-B-640. When specified (6.2) individual rolls of carpets or rugs shall be packed in laminated textile shipping bags conforming to PPP-B-35, type III, class I, Number P-5, style A or B. Cloth covered rolls shall have each open end closed with two double looped wire ties. The wire ties shall be not less than 6 inches long and of .072 inch minimum diameter soft steel wire with a 1/2 inch diameter formed eye at each end. The first tie shall be applied as close to the end of the roll as practicable. The second wire then shall be applied at a distance approximately one inch from the first tie. The twisted ends shall alternate and face in opposite directions.

5.2.3 Level C. Rolled carpet or rugs of one size, type, class, pattern and color only, packaged as specified in 5.1 shall be packed to comply with the National Motor Freight Classification rules or the Uniform Freight Classification rules, as applicable.

5.3 Marking. In addition to any special marking required by the contract or order, all marking shall be in accordance with 5.3.1 or 5.3.2, as specified (6.2).

5.3.1 Civil agencies. All marking shall be in accordance with Fed. Std. No. 123.

5.3.2 Military agencies. All marking shall be in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The carpets and rugs included in this specification are constructed with extra heavy pile weight. The carpets are intended primarily for high level executive use and special traffic situations.

6.2 Ordering data. Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type and class required (1.2).
(c) When preproduction sample is required (3.1).
(d) Pile yarn if other than as specified in Tables I thru VIII (3.3.1).
(e) Specify when soil hiding nylon yarn required (3.3.1.2 and 3.3.1.3).
(f) When attached rubber cushioning is required (3.3.2).
(g) Color required (3.4).
(h) If either cut or loop only is required for type I, class 2, and type I, class 5, carpets or rugs (tables II and V).
(i) Edge and binding finish, if other than as specified (3.8.2).
(j) Specify whether seams are to be sewn, taped, or both (3.8.3).
(k) Flame resistance requirement, if other than as specified (3.10).
(l) Specify when static control is required (3.12).
(m) Specify when washing procedure is applicable, if fire-retardant treated (4.5.15.3).
(n) Selection of applicable levels of packaging and packing (5.1 and 5.2).

6.3 For access to the standard sample, when available, address the procuring office issuing the invitation for bids.

6.4 Special flame resistance. Federal agencies responsible for hospitals and medical facilities are directed to publication General Standards of Construction and Equipment for Hospital and Medical Facilities, issued by the U.S. Department of Health, Education, and Welfare. This publication contains regulations relating to the implementation of the Hill-Burton program, including special construction and fire-resistive requirements.

6.5 Soil hiding type nylon yarns are Antron, Anso, Enkalure 3000, or equal.

6.6 Special flame resistance (carpeting/cushion assembly). Federal agencies requiring flame resistance testing accomplished on the carpet/cushion assembly as it will be installed shall require testing on the complete assembly.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.