AMENDMENT

TO

INTERIM FEDERAL SPECIFICATION

MAT, FLOOR, AND MATTING, PILE SURFACE,

ENTRANCE WAY TYPE

This amendment was developed by the General Services Administration, Federal Supply Service, Washington, D. C., 20406, based upon currently available technical information. The General Services Administration has authorized this amendment as a part of Interim Federal Specification DDD-M-001349(GSA-FSS) dated July 12, 1967.

PAGE 2

Paragraph 3.4.1.1 - line 1 - delete "15" and substitute "10".

Paragraph 3.4.2.1 - delete last sentence and substitute:

"The reinforcement or second backing shall be woven polypropylene fabric, not less than 4.50 ozs. sq. yd. or fabric made of jute or plasticized kraftcord yarns, not less than 5.0 ozs. sq. yd. At the option of the contracting officer, a reinforcement or second backing made of only woven polypropylene fabric, not less than 4.50 ozs. sq. yd. may be specified (6.2)."

PAGE 3

Paragraph 3.4.2.2 - delete in its entirety and substitute:

3.4.2.2 Type II, classes 1 and 2. The base cloth for type II, classes 1 and 2, mats or matting shall be woven cotton or jute fabric, 6 ozs. sq. yd. minimum; or nylon fabric of not less than 850 denier with superimposed vinyl sheeting not less than 0.006 gauge; or vinyl coated or impregnated fibrous glass cloth or mesh material, not less than 17.5 by 15.5 mesh size, with woven or mock selvage when used having at least six ends on each edge; or woven nylon cloth, 4.5 ozs. sq. yd. minimum; or nonwoven fabric consisting of 100 percent polypropylene or polyester fibers (may consist of less than 100 percent of these fibers but shall be not less than 75 percent of polypropylene or polyester fibers with a balance of cellulosic fibers), not less than 3.5 ozs. sq. yd.; unless otherwise specified (6.2). The solid backing for type II, class 1, mats or matting shall be vinyl as specified in 3.4.2.2.1 and for type II, class 2, mats or matting shall be rubber as specified in 3.4.2.2.2.

TABLE I - delete the flame resistance characteristic and requirement in its entirety and substitute:

"Flame resistance. Charred portion shall not extend to within 1 inch of the edge of the hole in the flattening frame at any point."

Paragraph 3.5.1.1 - delete second sentence in its entirety. Also, add to paragraph:

"At the option of the contractor, the tape may be 3/4 inch vinyl plastic nonwoven tape, approximately 0.0200 inch thickness, solution dyed, sewn with a zigzag stitch. The color of the tape shall be black or a color compatible with the color of the pile."

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

PAGE 4

TABLE II - under "Class 2",.insert footnote reference "6/" after "33.0" for "Tufts per square inch, minimum".

TABLE II - delete the flame resistance characteristic and requirements in their entirety and substitute for both Classes 1 and 2:

"Flame resistance. Charred portion shall not extend to within 1 inch of the edge of the hole in the flattening frame at any point."

TABLE II - add new footnote 6/ below table as follows:

"6/ For class 2 mats, or matting,made with nylon pile yarn, the tufts per square inch may be less than 33.0 but not less than 25.0 if average fiber size is 15 denier or coarser and the pile height does not exceed 0.65 inch."

PAGE 9

TABLES VII and VIII - Relocate entire line reading "Resistance to curl - 3.5.2 and 3.6.2 - 4.5.12" from table VII to table VIII.

PAGES 10 AND 11

Paragraph 4.5.8 - delete in its entirety and substitute:

4.5.8 Flame resistance.

4.5.8.1 Test specimens. Each test specimen shall be a 9 ± 1/4 inches square section of the carpet or rug to be tested. Eight specimens are required.

4.5.8.2 Apparatus.

a. Test chamber. The test chamber shall consist of an open top hollow cube made of noncombustible material 1/ with inside dimensions 12 by 12 by 12 inches and a minimum of 1/4 inch wall thickness. The flat bottom of the box shall be made of the same material as the sides and shall be easily removable. The sides shall be fastened together with screws or brackets and taped to prevent air leakage into the box during use.

NOTE: A minimum of two chambers and two extra bottoms is suggested for efficient operation.

b. Flattening frame. A steel plate, 9 by 9 inches, 1/4 inch thick with a 8 inch diameter hole in its center is required to hold the carpet or rug flat during the course of the test. It is recommended that one be provided for each test chamber.

c. Standard igniting source. No. 1588 methenamine timed burning tablet or an equal tablet. These tablets shall be stored in a desiccator over a desiccant for 24 hours prior to use. (Small quantities of sorbed water may cause the tablets to fracture when first ignited. If a major fracture occurs, any results from that test shall be ignored, and it shall be repeated.)

d. Circulating air oven. A forced circulation drying oven capable of removing the moisture from the specimens when maintained at 105°C. (221°F.) for 2 hours. 2/

e. Desiccating cabinet. An airtight and moisturetight cabinet capable of holding the floor covering specimens horizontally without contacting each other during the cooling period following drying, and containing silica gel desiccant.

f. Gloves. Nonhygroscopic gloves (such as rubber polyethylene) for handling the sample after drying, and raising the pile on specimens prior to testing.

g. Hood. A hood capable of being closed and having its draft turned off during each test and capable of rapidly removing the products of combustion following each test. The front or sides of the hood should be transparent to permit observation of the tests in progress

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

h. Mirror. A small mirror mounted above each test chamber at an angle to permit observation of the specimen from outside of the hood.

i. Vacuum cleaner. A vacuum cleaner to remove all loose material from each specimen prior to conditioning. All surfaces of the vacuum cleaner contacting the specimen shall be flat and smooth.

4.5.8.3 Procedure.

a. Cutting, and when specified, washing procedure if fire retardant treated. Cut eight 9 ± 1/4 inches square specimens of each carpet or rug to be tested. Note, if the carpet or rug has had a fire-retardant treatment, or is made of fibers which have had a fire-retardant treatment, and when specified in the contract or order (6.2), the selected sample or oversized specimens thereof shall be washed, prior to cutting of test specimens, 10 times under the washing and drying procedure prescribed in Method 124-1967 of the American Association of Textile Chemists and Colorists (washing procedure 6.2 (III) with a water temperature of 60° ± 2.8°C. (140° ± 5°F.), drying procedure 6.3.2 (B), maximum load 3.64 kg. (8 pounds), unless otherwise specified.

b. Conditioning. Clean each specimen with the vacuum cleaner until it is free of all loose ends left during the manufacturing process and from any material that may have been worked into the pile during handling.3/ Care must be exercised to avoid "fuzzing" of the pile yarn.

Place the specimens in the drying oven in a manner that will permit free circulation of the air at 105°C. (221°F.) around them for 2 hours.4/ Remove the specimens from the oven with gloved hands and place them horizontally in the desiccator with traffic surface up and free from contact with each other until cooled to room temperature, but in no instance less than 1 hour.

c. Testing. Place the test chamber in the draft-protected environment (hood with draft off) with its bottom in place. Wearing gloves, remove a test specimen from the desiccator and bruch its surface with a gloved hand in such a manner as to raise its pile. Place the specimen on the center of the floor of the test chamber, traffic surface up, exercising care that the specimen is horizontal and flat. Place the flattening frame on the specimen and position a methenamine tablet on one of its flat sides in the center of the 8 inch hole.

Ignite the tablet by touching a lighted match or an equivalent igniting source carefully to its top. If more than 2 minutes elapse between the removal of the specimen from the desiccator and the ignition of the tablet, the conditioning must be repeated.

Continue each test until one of the following conditions occurs:

(1) The last vestige of flame or glow disappears. (This is frequently accompanied by a final puff of smoke.)

(2) The flaming or smoldering has approached within 1 inch of the edge of the hole in the flattening frame at any point.

When all combustion has ceased, ventilate the hood and measure the shortest distance between the edge of the hole in the flattening frame and the charred area. Record the distance measured for each specimen.

Remove the specimen from the chamber and remove any burn residue from the floor of the chamber. Before proceeding to the next test, the floor must be cooled to normal room temperature or replaced with one that is at normal room temperature.

d. Report. The number of specimens of the eight tested in which the charred area does not extend to within 1 inch of the edge of the hole in the flattening frame shall be reported.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.

e. Interpretation of results. If the charred area does not extend to within 1 inch of the edge of the hole in the flattening frame at any point for at least seven of the eight specimens, the carpet or rug meets the acceptance criterion.

Footnotes:

1/ 6.35 mm. (1/4 inch) cement asbestos board is a suitable material.
2/ Option 1 of ASTM D 2654-67T, Methods of Test for "Amount of Moisture in Textile Materials" describes a satisfactory oven.
3/ The vacuum cleaning described is not intended to simulate the effects of repeated vacuum cleaning in service.
4/ If the specimens are moist, permit them to air-dry at laboratory conditions prior to placement in the oven.'

PAGE 12

Paragraph 6.2, add subparagraphs as follows:

(o) When polypropylene reinforcement or second backing only is required (3.4.2.1).
(p) Base cloth requirement, if other than as specified (3.4.2.2).
(q) Specify when washing procedure is applicable, if fire-retardant treated (4.5.8.3).

GSA DC 71-9507

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:36Z
Check the source to verify that this is the current version before use.