QQ-C-530C
November 22, 1971
SUPERSEDING
Fed. Spec. QQ-C-530b
April 12, 1967

FEDERAL SPECIFICATION

COPPER-BERYLLIUM ALLOY BAR, ROD, AND WIRE (COPPER ALLOY NUMBERS 172 AND 173)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers two alloys of copper-beryllium bar, rod, and wire (see 1.2.1).

1.2 Classification.

1.2.1 Alloys. Bar, rod, and wire furnished under this specification shall be of one of the following alloys:

Copper alloy numbers 172 or 173 - Incl. 1.80 to 2.00 percent beryllium.

1.2.2 Tempers. Copper alloy numbers 172 and 173 bar, rod, and wire shall be furnished in the tempers listed below, as specified. "T" following the temper designation denotes material after precipitation hardening treatment:

Bar and rod:

A - Hot-worked (or cold-worked) and solution heat treated.
H - Hot-worked (or cold-worked), solution heat treated, and worked hard.

Wire:

A - Cold-drawn and solution heat treated.
1/4 H - Cold-drawn, solution heat treated, and drawn quarter hard.
1/2 H - Cold-drawn, solution heat treated, and drawn half hard.
3/4 H - Cold-drawn, solution heat treated, and drawn three-quarters hard.
H - Cold-drawn, solution heat treated, and drawn fully hard.
XHT - Pretempered (mill hardened) (see 6.5).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Standards:

Fed. Std. No. 123	- Marking for Domestic Shipment (Civilian Agencies)
Fed. Std. No. 146	- Tolerances for Copper and Copper Base Alloy Mill Products
Fed. Test Method Std. No. 151	- Metals: Test Methods.
Fed. Std. No. 185	- Identification Marking of Copper and Copper Base Alloy Mill Products.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.)

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-C-3933 - Copper and Copper Base Alloy Mill Products; Packaging of

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM) Standards:

E 8 - Tension Testing of Metallic Materials.
E 18 - Test for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials.
E 112 - Estimating the Average Grain Size of Metals.
E 290 - Semi-Guided Bend Test for Ductility of Metallic Materials.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Chemical composition. The material shall conform to the chemical requirements specified in table I.

TABLE I. Chemical composition

Copper Alloy No.	Beryllium percent	Cobalt, nickel, or both, percent, min.	Nickel plus cobalt plus iron, percent, max.	Lead, percent	Copper plus beryllium plus named elements, percent, min.
172	1.80 to 2.00	0.20	0.6	--	99.5
173	1.80 to 2.00	0.20	0.6	0.20 to 0.6	99.5

3.1.1 Analysis shall be made regularly only for the elements specifically mentioned in table I. If however, the presence of other elements is suspected or indicated in the course of routine analysis, further analysis shall be made to determine that the total of other elements is not in excess of the limits specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06Z
Check the source to verify that this is the current version before use.

3.2 Mechanical properties.

3.2.1 As-supplied. As-supplied material shall conform to the mechanical properties shown in table II for the respective tempers.

TABLE II. Mechanical properties, as-supplied

Form	Temper	Diameter or thickness, inch	Tensile strength, k.s.i.	Elongation in 2 in., min., percent	Rockwell B hardness 1/
Bar and rod	A	0.020 to 0.311, incl.	60 to 85	--	--
		Over 0.311	60 to 85	20	45 to 85
	H	0.020 to 0.249, incl.	95 to 130	--	--
		Over 0.249 to 0.375, incl.	95 to 130	--	92 to 103
		Over 0.375 to 1.000, incl.	90 to 120	--	91 to 102
		Over 1.000	85 to 115	8	88 to 101
Wire	A	--	58 to 78	--	--
	1/4 H	--	90 to 115	--	--
	1/2 H	--	110 to 135	--	--
	3/4 H	--	130 to 155	--	--
	H 2/	--	140 to 165	--	--

1/ Hardness requirements apply only under the conditions stated in 3.2.4.
2/ H temper available in wire up to 0.080 inch, incl. in diameter.

3.2.2 After precipitation hardening. Samples of as-supplied material shall be heat-treated in accordance with table III and shall conform to the tensile property requirements of table IV applicable to the corresponding precipitation-hardened temper

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06Z
Check the source to verify that this is the current version before use.

TABLE III. Precipitation-hardening treatment

Form	Temper	Diameter or thickness, inch	Number of hours at 600°-625°F 1/ 2/
Bar and rod	A	All sizes	3
	H	Up to 3/4, incl.	2
		Over 3/4	3
Wire	A	All sizes	3
	1/4 H	All sizes	2
	1/2 H	All sizes	1-1/2
	3/4 H	All sizes	1
	H	All sizes	1

1/ All parts of the charge shall be up to the specified temperature before beginning the time record. No distinction shall be made for time at heat between liquid bath or air-furnace type of heat treatment.

2/ Applicable to testing of material under this specification. See 6.4 for heat treatment of finished parts.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06Z
Check the source to verify that this is the current version before use.

TABLE IV. Mechanical properties after precipitation hardening

Form	Temper	Diameter or thickness, inch	Tensile strength k.s.i.[1/]	Yield strength, 0.2 percent offset, minimum, k.s.i.	Elongation in 2 in., min., percent	Rockwell C hardness [2/3/]
Bar and rod	AT	0.020 to 0.249, incl.	165 to 190	130	3	--
		Over 0.249	165 to 190	130	3	36 to 40
	HT	0.020 to 0.249, incl.	185 to 215	160	1	--
		Over 0.249 to 0.375, incl.	185 to 215	160	1	39 to 45
		Over 0.375 to 1.000, incl.	180 to 210	155	1	38 to 44
		Over 1.000 to 2.000, incl.	175 to 205	150	2	37 to 43
		Over 2.000	175 to 205	130	2	37 to 43
Wire	HT	--	165 to 190	--	--	--
	1/4 HT	--	175 to 205	--	--	--
	1/2 HT	--	185 to 215	--	--	--
	3/4 HT	--	190 to 230	--	--	--
	HT	--	195 to 230	--	--	--

1/ Upper limits of tensile strength apply only to material thicker than 0.020 inch.
2/ Hardness requirements apply only under the conditions stated in 3.2.4.
3/ Applicable to material 0.030 inch thick and over.

3.2.3 Pretempered (mill hardened). Pretempered (mill hardened) wire shall conform to the mechanical properties shown in table V.

3.2.4 Substitution of hardness tests for tensile property tests. When specified only (see 6.2), the tension tests for bar and rod shall be waived provided the material meets the hardness requirements shown in table II for the as-supplied mill treated temper, and in table IV for the mill treated, precipitation-hardened temper, as applicable. Failure of material to conform to the Rockwell hardness requirements either before or after precipitation hardening shall require tension tests to be the basis for acceptance.

3.2.5 Bend test, wire only. Wire in the A, 1/4 H, 1/2 H, 3/4 H, and H tempers shall withstand, without cracking, being wound at room temperature five times around a radius equal to the diameter or thickness of the wire.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06Z
Check the source to verify that this is the current version before use.

TABLE VV. Mechanical properties of wire; pretempered (mill hardened) (EHT) 1/

Diameter, inch	Tensile strength, ksi
Over 0.055 to 0.0735, excl.	1640 to 1665
0.0735 to 0.1000, excl.	1220 to 1640
0.1000 to 0.1144, incl.	1155 to 1330

1/ See 6.5.5

3.3.3 Metallographic examinations.

3.3.3.1 Grain size. When specified (see 6.2.2), the average grain size of solution heat treated AA or AAT tempered rod, bar and wire over 0.1000 inch in thickness, as determined in a plane perpendicular to the surface and parallel to the direction of rolling, shall not exceed the limits stated in table VI.

TABLE VII. Grain size requirements

Thickness, inch	Maximum average grain size	
	Millimeter	Inch
From 0.010 to 0.039, incl.	0.035	0.00164
From .039 to .090, incl.	.055	.00188
From .091 to .188, incl.	.060	.00233

3.3.3.2 Grain count. When specified (see 6.2.2), the grain count of rod, bar and wire, in any temper from 0.0044 to 0.0100 inch, inclusive, in thickness, determined in a plane perpendicular to the surface and parallel to the direction of rolling, shall be not less than the limits stated in table VIII.

TABLE VIII. Grain count requirements

Thickness, inch	Minimum number of grains
From 0.004 to 0.006, incl.	6
From .007 to .008, incl.	7
From .009 to .010, incl.	8

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06
Check the source to verify that this is the current version before

3.4 Dimensional tolerances.

3.4.1 Cold rolled or drawn bar and rod. The following references of Fed. Std. No. 146 shall apply for cold rolled or drawn bar and rod:

Form	Dimension	Reference
Bar	Thickness	2b (1)
	Width	2b (2)
	Length	2b (3), 2b (4)
	Straightness	2b (5)
	Standard edge contour	2b (6)
Rod	Diameter	11b (1)
	Length	11b (2), 11b (3)
	Straightness	11b (4)

3.4.2 Hot-worked bar and rod.

3.4.2.1 Thickness, bar. Hot worked bar shall conform to the thickness tolerances shown in table VIII.

TABLE VIII. Thickness tolerances for hot worked bar (plus or minus)

Thickness, inches	Tolerance, inch
0.420 to 0.750, incl.	0.015
Over 0.750 to 1.250 incl.	.020
Over 1.250 to 1.500, incl.	.030
Over 1.500 to 2.000, incl.	1/16
Over 2.000 to 4.500, incl.	1/8

3.4.2.2 Diameter, rod. The diameter tolerances for hot-worked rod shall be in accordance with reference 13b (1) of Fed. Std. No. 146.

3.4.3 Cold-worked or annealed bar with sawed edges.

3.4.3.1 Thickness. Cold-worked or annealed bar with sawed edges shall conform to the thickness tolerances shown in table IX.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06Z
Check the source to verify that this is the current version before us

TABLE IX. Thickness tolerances for cold-worked or annealed bar with sawed edges (plus or minus)

Finish	Thickness, inch	Tolerance, inch	
		Up to 8 in. wide	Over 8 to 14 in. wide
Cold-worked or annealed	0.188 to 0.205, incl.	0.0045	0.008
	Over 0.205 to 0.300, incl.	.005	.009
	Over .300 to .437, incl.	.006	.010
Annealed	Over 0.437 to 0.750, incl.	0.008	0.012
	Over .750 to 1.000, incl.	.010	.014

3.4.3.2 Width, length, and straightness. The width, length, and straightness tolerances of cold-worked or annealed bar with sawed edges shall be the same as those specified in 3.4.1 for cold-rolled or drawn bar.

3.4.4 Wire. The diameter tolerances for wire shall be in accordance with reference 24b (1) of Fed. Std. No. 146.

3.5 Identification marking. When specified (see 6.2), item identification marking shall be in accordance with Fed. Std. No. 185 (see 6.2 and 6.3).

3.6 Workmanship. Material shall be uniform in quality and temper; shall be clean, sound, and smooth; and shall be free from injurious defects including foreign material, pipes, slivers, laps, cracks, twists, seams, scale, damaged ends, corners, or edges, which due to their nature, degree, or extent, detrimentally affect the suitability of the material for the purpose intended.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Lot. Unless otherwise specified (see 6.2), a lot shall consist of 5,000 pounds or fraction thereof, of material of the same composition, form, temper, and size, subjected to inspection at one time.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06Z
Check the source to verify that this is the current version before use.

4.3 Sampling.

4.3.1 For chemical analysis. A random sample shall be selected from four different pieces in each lot. From each sample, not less than 2 ounces of copper alloy material shall be obtained either as cleaned millings, drillings, or clippings or as machined platelets, rods, or pins to form a composite sample.

4.3.2 For mechanical properties.

4.3.2.1 Tension test. Unless tension tests are waived (see 3.2.4), tension-test specimens shall be prepared from pieces selected from each lot. For determination of the tensile properties of pretempered wire, two samples shall be selected from each lot. For determination of the as-supplied tensile properties of bar, rod, and wire, four samples shall be selected from each lot, two of which shall be selected without further treatment, and two of which shall be tested for determination of tensile properties after precipitation hardening to the AT, 1/4 HT, 1/2 HT, 3/4 HT, and HT tempers, as applicable. Each sample shall be selected from a different piece unless the number of pieces in the lot is less than the required number for specimens. In this case, at least one specimen shall be selected for determination of tensile properties after precipitation hardening as specified herein, in addition to one for as-supplied properties.

4.3.2.2 Hardness test. When hardness tests are authorized (see 3.2.4), four samples shall be selected from each lot, two of which shall be tested after precipitation hardening in accordance with 3.2.2. The number of hardness readings shall be not less than three on each of the samples when tested in accordance with 4.5.2.4. For material in coils, the sample footage shall consist of equal lengths of strip taken from the outer ends of the coils in the lot. Not less than 2 coils shall be tested in each lot.

4.3.2.3 Bend test for wire. Five specimens shall be selected from each lot.

4.3.3 For metallographic examination. Two samples shall be selected from each lot.

4.3.4 For visual and dimensional examination.

4.3.4.1 Pieces weighing over 150 pounds. Each piece shall be examined.

4.3.4.2 Pieces weighing 150 pounds or less. From each lot of material with pieces weighing 150 pounds or less, a representative sample shall be selected in accordance with MIL-STD-105, inspection level II, with an acceptable quality level (AQL) of 1.5 percent. The samples selected for dimensional examination may be the same as those selected for visual examination but shall be evaluated separately.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06Z
Check the source to verify that this is the current version before use.

4.3.4.3 When material is furnished on spools, reels, or bucks, the sample for examination shall be taken from within 10 feet of the outer end. If the sample is rejected due to handling marks, an additional sample within the next 20 feet shall be selected for examination.

4.4 Examination.

4.4.1 Visual and dimensional. Pieces selected in accordance with 4.3.4 shall be visually examined to determine compliance with the requirements for identification marking (see 3.5), and workmanship (see 3.6), and shall be measured for compliance with the dimensional requirements (see 3.4).

4.4.2 Straightness. Straightness shall be determined by placing the piece on a level surface so that the arc or departure from straightness is horizontal. The maximum depth of the arc shall be measured to the nearest 1/32 inch by means of a straightedge and a steel scale.

4.4.3 Preparation for shipment. Examination of the packing and marking for shipment shall be made for conformance to the requirements of section 5.

4.5 Tests.

4.5.1 Tension test specimens.

4.5.1.1 Bar and rod. Whenever practicable, bar and rod shall be tested in full section. Specimens for tensile testing shall be prepared in accordance with ASTM E 8.

4.5.1.2 Wire. Tension test specimens for wire shall be full cross section and not less than 15 inches in length. Specimens shall be free from bends or kinks. The distance between the jaws of the testing machine with the specimen in place ready for testing shall be not less than 10 inches.

4.5.2 Test procedures.

4.5.2.1 Chemical analysis. The samples selected in accordance with 4.3.1, shall be analyzed in accordance with method 111 or method 112 of Fed. Test Method Std. No. 151, to determine conformance to 3.1. A single analysis of a composite sample may be made when emission methods are not used. In case of dispute, the analysis by the wet method (method 111) shall be the basis for acceptance.

4.5.2.2 Tension tests. Specimens from samples selected in accordance with 4.3.2.1 shall be tested in accordance with ASTM E 8.

4.5.2.3 Yield strength. The yield strength shall be determined by the offset method (0.2 percent) in accordance with ASTM E 8.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06
Check the source to verify that this is the current version before

4.5.2.4 Hardness tests. The hardness of specimens selected in accordance with 4.3.2.2 shall be determined in accordance with ASTM E 18. Readings shall be taken on an outside surface (not cross section).

4.5.2.5 Bend tests. Specimens selected in accordance with 4.3.2.3 shall be tested in accordance with ASTM E 290.

4.5.2.6 Metallographic tests. Specimens selected in accordance with 4.3.3 shall be prepared, etched, and tested in accordance with the metallographic procedures contained in ASTM E 112 (see 6.13).

4.6 Rejection.

4.6.1 Examination defects. Any sample unit having one or more defects shall be rejected. If the number of nonconforming sample units in the sample exceeds the acceptance number specified in 4.3.4.2 for that sample size, the entire lot shall be rejected subject to the provisions of the section on "Acceptance and Rejection" of MIL-STD-105.

4.6.2 Test failures. A lot shall be rejected for failure to meet any of the test requirements when tested in accordance with 4.5, subject to the provisions of the section on "Rejection and Retests" of Fed. Test Method Std. No. 151.

5. PREPARATION FOR DELIVERY

5.1 Packing (see 6.2).

5.1.1 Levels A and B. The material shall be packed in accordance with MIL-C-3993.

5.1.2 Level C. The products shall be separated by size, composition, and temper and packed in accordance with the manufacturer's standard practice into containers of a type and size commonly used for the purpose, in such a manner as to insure acceptance by carrier for transportation at the lowest rate applicable and to afford maximum protection from normal hazards of transportation.

5.2 Marking (see 6.2 and 6.3).

5.2.1 Civil agencies. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.2.2 Military agencies. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The material covered by this specification is intended for use in the manufacture of items such as springs, bearings, valve sleeves and seats, gears, etc., where high strength, good corrosion resistance, and high electrical conductivity are required. Bars and rods are also intended for use in some nonsparking tools.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

a. Title, number, and date of this specification.
b. Alloy, form, size, and temper required (see 1.2).
c. When hardness tests may be substituted for tensile tests (see 3.2.4).
d. When grain size and grain count requirements are required (see 3.3.1 and 3.3.2).
e. Lengths, whether specific or stock lengths with or without ends (see 3.4).
f. When item identification marking in accordance with Fed. Std. No. 185 is required (see 3.5).
g. When a lot size of other than 5,000 pounds is required (see 4.2).
h. Whether material is to be packed by level A, B, or C (see 5.1).
i. Maximum gross weight of container (see 5.1).
j. Special marking, if required (see 5.2).

6.3 The requirements for item identification marking (see 3.5), for packing (see 5.1), and marking (see 5.2), for shipment specified herein apply to direct shipment for Government activities and apply also, when specified to contracts or orders between the manufacturer and the Government prime contractor.

6.4 Copper-beryllium alloy material may be cold-formed and readily machined before precipitation hardening. After forming and machining to the desired dimensions, it may be precipitation hardened to develop high tensile properties. The precipitation-hardening treatment procedures stated in table III are mandatory for use in determining the ability of material procured under this specification to develop suitable properties after such treatment but do not necessarily apply to the treatment of finished parts. In the heat treatment of parts however, individual procedures differing from table III producing different properties from table IV may be employed.

6.5 Pretempered (mill hardened) wire (temper XHT) is furnished in a precipitation hardened condition by the material supplier to meet the properties shown in table V. It is ductile enough to be cold formed into some spring and wire form configurations.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06Z
Check the source to verify that this is the current version before use.

6.6 Material after precipitation hardening is considered to have more stable and uniform properties than cold-worked material (even though the latter may show adequate tensile strength) and the use of cold-worked material without precipitation hardening is, therefore not recommended.

6.7 The chemical composition and mechanical properties of alloy number 172 are similar to ASTM B 196 for bar and rod, to ASTM B 197 for wire, and to ASTM B 194 for rolled bar.

6.8 Definition of forms.

6.8.1 Bar. A bar is a solid rectangular section, or one with two plane parallel surfaces and round or other simple regularly shaped finished edges, up to and including 12 inches in width and over 0.188 inch in thickness furnished in straight lengths or in rolls and with finished edges, either rolled, drawn or extruded.

6.8.2 Rod. A rod is a round, regular hexagonal or regular octagonal solid section furnished in streight lengths. Note: A regular hexagonal or a regular octagonal rod is a solid section having equal sides and equal angles.

6.8.3 Wire. Wire is a solid section, other than strip, furnished in coils or on spools, reels, or bucks.

6.9 Copper alloy number 172 in the form of strip is covered by QQ-C-533.

6.10 Copper alloy number 172 is available as flat wire. When this form is required, the mechanical properties of QQ-C-533 and dimensional tolerances of this specification are usually applicable. However, square wire (a form of flat wire), may be supplied entirely to this specification.

6.11 With reference to tensile and yield strength values, the term "k.s.i." replaces the former term "p.s.i.". It means "thousand pounds per square inch".

6.12 Metric equivalents. To obtain tensile and yield strength values in kilograms per square millimeter ($kg.f/mm.^2$), multiply the values in tables II, IV, and V by 0.703.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:06
Check the source to verify that this is the current version before

6.13 For greater information than can be obtained from ASTM E 112, ASTM E 3, Methods of Preparation of Metallographic Specimens, may be used for specimen preparation and etching. When photomicrographs are used for estimating grain size and count, ASTM E 2, Methods of Preparation of Micrographs of Metals and Alloys (Including Recommended Practice for Photography as Applied to Metallography), may be used.

MILITARY CUSTODIANS:

Army - MR
Navy - AS
Air Force - 11

Review activities:

Army - MR, MU, MI, EL
Navy - AS, SH, OS
DSA - IS

User activities:

Army - AV, WC
Navy - YD

Preparing activity:

Army - MR

CIVIL AGENCIES INTEREST:

DC
COM
AGR
GSA
HEW
AEC

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12
Check the source to verify that this is the current version befo