RR-C-114E
March 11, 1973
SUPERSEDING
Fed. Spec. RR-C-114D
November 3, 1969

FEDERAL SPECIFICATION

CANS, FLAMMABLE WASTE

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers metal foot and hand operated flammable waste cans.

1.2 Classification.

1.2.1 Types and capacities. Flammable waste cans shall be of the following types and capacities, as specified (see 6.2).

Type I - Foot operated.

6-gallon capacity
10-gallon capacity

Type II - Hand operated.

21-gallon capacity

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

QQ-T-191 - Terne Sheets (Long and Short Ternes)
PPP-P-130 - Pails, Cans, and Waste Receptacles, Packing Of.

FSC 7240

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:08Z
Check the source to verify that this is the current version before use.

Federal Standard:

Fed. Std. No 595 - Colors.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply:

Underwriters' Laboratories, Inc. (UL)

Standard No. 32 - Waste Cans

Gas and Oil Equipment List.

(Copies of UL publications are available from the Underwriters' Laboratories, Inc., 207 East Ohio Street, Chicago, Illinois 60611; 1285 Walt Whitman Road, Melville, L.I., New York 11746; or 1655 Scott Boulevard, Santa Clara, California 95050.)

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:08Z
Check the source to verify that this is the current version before use.

American Society for Testing and Materials (ASTM) Standard

A90-Method of Test for Weight of Coating on Zinc-Coated (Galvanized) Iron or Steel Articles.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa. 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups, and using Federal agencies.)

3. REQUIREMENTS

3.1 Standard product. The flammable waste cans shall be standard commercial items, except for any changes necessary to conform to the requirements specified herein.

3.2 Safety standard. Flammable waste cans shall conform to Underwriters' Laboratories, Inc. Standard No. 32 for Waste Cans. Prior to approval of the first shipment, the supplier shall submit satisfactory evidence to the contracting officer or his authorized representative that the flammable waste cans he proposes to furnish under this specification meet the requirements of UL Standard No. 32. Acceptable evidence of meeting the requirements of this standard shall be the UL label, a listing in the UL "Gas and oil Equipment List" or a certified test report from a recognized independent testing laboratory, acceptable to the Government, indicating that the cans offered have been tested and conform to the requirements of UL Standard No. 32.

3.3 Materials and components. Materials and components shall be as specified herein. Materials not definitely specified shall be of the quality normally used by the manufacturer in his commercial product, provided that the completed item complies with all provisions of this specification.

3.4 Design and construction. The flammable waste can shall be fabricated from terne plate, conforming to type I or II, class 1, grade A with a coating weight of 0.35 ounce of QQ-T-191, corrosion-resisting steel, zinc coated carbon steel, or uncoated sheet steel, galvanized after forming. Type I cans shall be foot operated. The type II can shall be hand operated. The cans shall conform to the design and construction requirements of UL-32, except as otherwise specified herein. The can shall have dimensions shown in table I and shall not leak when tested as specified in 4.4.1.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:08Z
Check the source to verify that this is the currentversion before use.

TABLE I. Dimensions of cans

Capacity gallons	Volume cubic inches (minimum)	Inside height inches (maximum)	Sheet metal thickness (bare) US standard gage - inches (minimum) Body, bottom 2-piece cover fixed section and single cover	2-piece cover hinged section
6	1,386	13-3/8	26-0.0179	24-0.0239
10	2,310	15-1/4	25-0.0218	23-0.028;
21	4,851	19-3/4	24-0.0239	22-0.0299

3.5 Finish.

3.5.1 Zinc coating. Prior to plating cans fabricated from uncoated steel, grit, loose scale, and rust shall be removed, and the cans without bails, hot dipped coated. When tested as specified in 4.4.2, the weight of zinc coating on cans fabricated of either precoated steel sheet or uncoated steel, shall be not less than 1.25 ounces per square foot. Alternatively, when tested in 4.4.3 the thickness of the zinc coating, on one side, shall be not less than 0.002 inch.

3.5.2 Painting. Exterior and interior surfaces of the cans shall be prepared for painting. Cans shall be painted with a solvent-resistant enamel matching color No. 13538 of FED-STD-595 unless otherwise specified (see 6.2).

3.6 Workmanship. The cans shall indicate workmanship as follows:

(a) The sides of the cans shall be perpendicular to the base, movable components shall move without binding, and the can shall be free from slivers, sharp edges, fractures, loose components, incompletely formed and uneven joints or seams.

(b) Galvanizing shall be adherent and free from lumps of embedded foreign material, cracks, dross, or flux.

(c) Soldering, welding, and brazing shall be adherent, free from pits, acid, or flux deposits.

(d) Spot welds shall be adherent and free from craters.

(e) Rivets shall be tight, peened with no feathered edges, and free from fractures.

3.7 Marking. All cans shall be permanently marked, to show capacity, or trade number representing capacity, manufacturer's name or readily identifying trademark, and the instruction in 1/4 inch block letters, "EMPTY EVERY NIGHT" located on the side of the can.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:08Z
Check the source to verify that this is the currentversion before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications and standards to the extent specified, or if none, in accordance with this specification.

4.2.2 In-process inspection.

4.2.2.1 Examination. Examination shall be made during the manufacturing process to determine that cleaning and removing of loose scale and rust prior to hot dipped zinc coating is accomplished and enameling is accomplished over the metal plating in accordance with 3.6, as applicable. Whenever nonconformance is noted, correction shall be made to affected items and lot in process.

4.2.2.2 Hot dipped zinc coating weight testing. Hot dipped zinc coating weight shall be tested on three specimens, 2-1/4 inch square, minimum, of each batch or lot as representing the batch or lot of can body and cover being hot-dipped. The specimen shall be of the same material for the body and cover, prepared as specified in 3.6, and hot-dipped under the same process conditions. Failure to pass the test, as specified in 4.4.2, shall be cause for rejection of the process. Alternatively, the hot dipped zinc coating of the can and cover prior to enameling shall be tested for thickness in accordance with 4.4.3. Failure to pass the test shall be considered a defect. The inspection level shall be S-1 with an acceptable quality level (AQL) of 2.5, expressed in terms of defects per hundred units.

4.2.3 End item inspection. The lot shall consist of all complete cans of one type and capacity, offered for inspection at one time. The sample unit shall be one completely fabricated can.

4.2.3.1 Visual examination. The end item shall be examined for defects in accordance with table II. The inspection level shall be level II with AQL of 2.5 for major defects, and 6.5 for total defects expressed in terms of defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

TABLE II. Classification of defects

Examine	Defect	Classification Major	Minor
Design and construction (general)	Not type specified.	X	
	Corners of flat sided can not rounded with radius.	X	
	Cover does not close due to projections, ridges, or other obstructions.	X	
	Cover does not close by gravity.	X	
	Metallic coating impaired or removed during fabrication not replaced by solder or aluminum paint.		
	Can configuration allows appreciable body area to be in close proximity to wall.	X	
	Handles do not allow can to be carried in upright position.	X	
	Can not of configuration specified.	X	
	Strip steel for legs and reinforcement not painted or plated.	X	
	Bent component.	X	
Seams and joints	Not welded, sealed, or seamed, as specified.	X	
	Not of types specified.	X	
Body reinforcement	Upper edge of body not reinforced by hemming, rolling, wiring or other stiffening method.	X	
	Bottom edge of sheet metal support not reinforced as specified for upper body edge.	X	
	Steel strip reinforcement not riveted, welded, or brazed.	X	
Cover	Hinged section, when applicable, not flanged.	X	
	Handle on cover missing.	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

TABLE II. Classification of defects (cont.)

Examine	Defect	Classification Major	Minor
Cover reinforcements	Cover reinforcements for single and two-piece cover not as specified.	X	
	Reinforcements for two-piece cover stop not as specified.	X	
	Two-piece cover fixed section hinged edge reinforcements missing.	X	
	Method of reinforcing strips, attachment not as specified (when applicable).	X	
Cover hinge	Cover not hinged to body of can as specified.	X	
	Hinge pins not headed over or secured from working out of position.	X	
	Hinge not attached as specified.	X	
Cover stop	Cover stop allows cover opening to exceed 60 degrees.		X
	Not adequate to prevent deformation of stop or cover when stopping cover.	X	
Foot-operated cover-lifting mechanism	Cover-lifting mechanism causes instability.	X	
	Interferes with closing of lid when can side or back located against wall.	X	
	Disengaged.		X
Can supports	Can not supported on 3 legs or on cylindrical support, as applicable.	X	
	Cylindrical support not an extension of the body, as applicable.	X	
	Not reinforced at bottom.	X	
	Not provided with 8 ventilating holes.	X	
	Support leg castings not malleable iron, as applicable.	X	
	Not provided with flat floor rests in same plane.	X	
	Fastened with less than two rivets (when fasteners are not provided).	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

TABLE II. Classification of defects (cont.)

Examine	Defect	Classification Major	Minor
Handles	Bail handle used on can 16 inch diameter or larger.	X	
	Bail handle interferes with cover opening.		X
	Not welded or held with two or more rivets.	X	
	Can of 16 inch diameter or larger not provided with two carrying handles.	X	
	Brackets not secured by brazing four or more rivets.	X	
	Ears or loops not welded or attached by three or more rivets for ears or four or more rivets for loops.	X	
Finish	Enamel not color specified.	X	
	Enameled surface blistered, not adherent or free from embedded foreign material, areas of no film, runs, sags or tackiness.		X
Workmanship	Can sides not perpendicular to base.	X	
	Moveable component binds.		X
	Sliver or sharp edge.		X
	Fracture.	X	
	Joint or seam incompletely formed or uneven.	X	
	Soldering, welding and brazing not adherent, free from pits, acid or flux.		X
	Spot welds not adherent, free from craters due to metal burnout or spattering.		X
	Rivets not tight, peened with feathered edges and not free from fractures.		X
Marking	Missing, illegible, incomplete, or not as specified.		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

4.2.3.2 Examination for defects in dimensions. Examination shall be made of cans for defects in dimensions. Any dimensions not within the specified requirements shall constitute a defect. The inspection level shall be S-2 with an AQL of 4.0, expressed in terms of defects per hundred units.

4.2.4 Examination of preparation for delivery. An examination shall be made to determine that the packing and marking comply with the applicable requirements of PPP-P-130.

4.3 Testing of the end item. Each completely finished can shall be tested as specified in 4.4.1. Any failure to pass the test shall be cause for rejection of the item.

4.4 Tests.

4.4.1 Leak. The can shall be tested for leaks in accordance with UL-32, to determine compliance with the requirements of 3.4. Evidence of any leaks shall constitute failure to pass this test.

4.4.2 Zinc coating weight. When applicable, the weight of zinc coating on hot-dipped galvanized cans shall be found to the nearest 0.01 ounce, in accordance with ASTM 90, to determine compliance with the hot dipped zinc coating weight requirements of 3.5. Any noncompliance shall constitute failure to pass this test.

4.4.3 Zinc coating thickness. When applicable, the thickness of the zinc coating shall be checked to the nearest 0.001 with a magnetic type gage in accordance with industry's standard commercial practice. Readings shall be taken alternately on the inside surface of one can or cover and on the outside surface of the next can or cover, until all the samples have been tested to determine compliance with hot dipped zinc coating thickness requirements of 3.5. Any nonconformance shall constitute failure to pass this test.

5. PREPARATION FOR DELIVERY

5.1 Packing and marking. The packing and marking of the cans shall conform to the applicable requirements of PPP-P-130. Packing shall be level A, B, or C, as specified (see 6.2).

6. NOTES

6.1 Intended use. The flammable waste cans covered by this specification are to provide safe temporary storage of oily waste rags and other similar combustible waste materials within buildings.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Purchasers should select the preferred options permitted herin and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type and capacity required (see 1.2.1).
(c) When color is other than specified (see 3.5.2).
(d) Level of packing required (see 5.1).

MILITARY CUSTODIANS:

Army - GL
Navy - YD
Air Force - 84

Review activity:

Army - MD

User activities:

Army - SM
Navy - CG

Preparing activity:

Army - GL

CIVIL AGENCY COORDINATING ACTIVITY:

GSA-FSS

Project No. 7240-0139

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.