RR-P-89F
August 12, 1970
SUPERSEDING
Int. Fed. Spec. RR-P-0089E(GL)
February 6, 1970 and
Fed. Spec. RR-P-89D
March 13, 1969

FEDERAL SPECIFICATION

PANS, FRYING

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers corrosion-resisting steel frying pans.

1.2 Classification. The frying pans shall be of the following sizes, as specified (see 6.2).

Size 1 - 6-inch diameter.
Size 2 - 12-inch diameter.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

UU-P-268	-	Paper, Kraft, Untreated, Wrapping.
PPP-B-636	-	Box, Fiberboard.
PPP-F-320	-	Fiberboard; Corrugated and Solid, Sheet Stock (Container Grade) and Cut Shapes.
PPP-T-45	-	Tape, Gummed, Paper, Reinforced and Plain, for Sealing and Securing.

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Forth Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	-	Marking for Shipment and Storage.
MIL-STD-130	-	Identification Marking of U. S. Military Property.
MIL-STD-147	-	Palletized and Containerized Unit Loads, 40" x 48" Pallets, Skids, Runners, or Pallet-Type Base.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Sanitation Foundation (NSF) Publications:

Standard No. 2 - Food Service Equipment.

Listing of Food Service Equipment.

(Application for copies should be addressed to the National Sanitation Foundation, P. O. Box 1468, Ann Arbor, Michigan 48106.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

American Society for Testing and Materials (ASTM) Standard:

A167 - Corrosion-Resisting Chromium-Nickel Steel Plate, Sheet and Strip.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa. 19103.)

National Classification Board:

National Motor Freight Classification.

(Application for copies should be addressed to America Trucking Associations, Attn: Traffic Order Section, 1616 P Street, N. W., Washington, D.C. 20036.)

Uniform Classification Committee:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, 202 Union Station, Chicago, Illinois 60606.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 First article. This specification contains provisions for first article test and approval (see 4.2, 6.2, and 6.4).

3.2 Standard product. The frying pans shall be the current standard product of the manufacturer except for any changes necessary to comply with the specification requirements.

3.3 Standard compliance. The frying pans shall conform to the applicable requirements of NSF Standard No. 2.

3.3.1 NSF certification. The supplier shall submit satisfactory evidence to the contracting officer or his authorized reresentative that the frying pans he proposes to furnish under this specification meet the applicable requirements of NSF Standard No. 2 as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

(1) A listing in the current edition of the NSF "Listing of Food Service Equipment" or display of the NSF seal on the finished frying pan shall be submitted prior to approval of the preproduction sample, if one is submitted, or prior to approval of the first shipment, or

(2) A certification for the frying pans issued by NSF under their special one-time contract evaluation/certification service shall be submitted prior to approval of the preproduction sample, if one is submitted, or prior to approval of the first shipment, or

(3) A certified test report from a recognized independent testing laboratory acceptable to the medical authority functioning in advisory capacity to the preparing agency of the specification indicating that the frying pans have been tested and conform to NSF Standard No. 2 shall be submitted prior to approval of the preproduction sample, if one is submitted, or prior to commencing production.

3.4 Materials. Materials not definitely specified shall be of the quality normally used by the manufacturer for frying pans provided the completed items comply with all provisions of this specification. Commercial tolerances are applicable to all metal thicknesses and diameters.

3.4.1 Steel, sheet and strip, corrosion-resisting. The corrosion-resisting steel sheet and strip shall conform to type 302 or 304 of ASTM Specification A167.

3.5 Construction. The frying pans shall be constructed as specified herein and shall conform to the dimensions shown in table I.

TABLE I. Dimensions

Size	Inside diameter at top of body	Outside diameter at bottom of body	Vertical inside depth	Length of handle
	Inches	Inches	Inches	Inches
1	6 to 6-3/4	4-1/8 to 4-3/4	1-1/8 to 1-1/2	5-1/2 to 7-1/2
2	12 to 12-3/4	8-3/4 to 9-7/8	2 to 2-3/8	10-1/4 to 12-1/4

3.5.1 Body. The body shall be formed seamless from a single piece of material specified in 3.4.1. The body shall have a minimum bottom thickness of 0.078-inch for the 6-inch and 12-inch frying pans, after forming.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

3.5.2 Handle. The handle shall be made from a single piece of material specified in 3.4.1. The handle shall have minimum thicknesses of 0.109 inch for the 6-inch frying pan and 0.125 inch for the 12-inch frying pan, after forming. The handle shall be made slightly concave in cross section and shall be attached to the body by at least three spot welds or continuous welding. When spot welding is used the crevice between the handle end and the body shall be sealed by welding or brazing. A hole shall be provided at the end of the handle for hanging the frying pan. The handle when tested as specified in 4.4.1 shall not become distorted or damaged or become separated from the frying pan body.

3.6 Identification marking. The frying pans shall bear the manufacturer's name, trade name, or trademark of such known characters as to be easily identifiable with the manufacturer. Marking shall be applied in accordance with MIL-STD-130.

3.7 Finish. All rust, dirt, grease, graphite, sharp edges, burrs, or slivers shall be removed.

3.8 Workmanship. The finished frying pans shall be clean and free from any cracks, fractures, or malforming. Welding shall be accomplished in a manner that will prevent the occurrence of pits or flashes. All scale or flux deposits shall be removed from finished welds.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 First article inspection. When a preproduction sample is required, it shall be examined for the defects in table II and dimensions specified, and tested in accordance with 4.4.1. Failure to pass the test shall be cause for rejection of the preproduction sample. The presence of any defects listed in table II or any dimension not within specified requirements shall be cause for rejection of the preproduction sample.

4.3 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

4.3.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.3.2 End item inspection. The inspection lot shall be all frying pans of one size offered for inspection at one time. The sample unit shall be one completely fabricated frying pan.

4.3.2.1 Visual examination. Examination of the pans shall be made in accordance with the classification of defects set forth in table II. The inspection level shall be II with an acceptable quality level (AQL) of 2.5, expressed in terms of defects per hundred units.

TABLE II. Classification of defects

Examine	Defect
Finish	Sharp edge, burr, or sliver. Grease, rust, dirt, graphite, or other foreign matter embedded in finish.
Design	Any component missing.
Construction and workmanship (general)	Any component cracked, fractured, or malformed. Welding pits or flashes. Scale or flux deposits not removed.
Handle	Handle not attached by spot welding in at least three places or not attached by continuous welding. Hole missing or is not located at end of handle. Crevices not sealed by welding or brazing when handle is spot welded to body.
Body	Not one piece construction.
Marking for identification	Missing, not legible, incomplete.

4.3.2.2 Dimensional examination. Pans shall be examined to determine compliance with dimensions specified herein. Any dimension that is not within specified requirements shall be classified a defect. The inspection level shall be S-1 with an AQL of 4.0, expressed in terms of defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

4.3.2.3 Testing of the end item. The finished pans shall be tested as specified in 4.4.1. The inspection level shall be S-2 with an AQL of 2.5, expressed in terms of defects per hundred units.

4.3.3 Examination of preparation for delivery. An examination shall be made to determine that preservation of packaging, packing, and marking as required by section 5 of this specification are complied with. Defects shall be as indicated in table III. The sample unit shall be one shipping container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 with an AQL of 4.0, expressed in terms of defects per hundred units.

TABLE III. Examination of preparation for delivery

Examine	Defect
Materials	Component missing, damaged, or otherwise defective.
Marking	Missing; incorrect; not legible, of improper size, location, sequence, or method of application.
Contents	Number per container is more or less than required.

4.3.3.1 Examination of shipping container. When shipping containers are required to be in accordance with PPP-B-636, examination for defects in closure, waterproofing, and strapping shall be in accordance with PPP-B-636.

4.3.4 Examination of palletization. An examination shall be made to determine that palletization is in compliance with section 5 of this specification. Defects shall be as indicated in table IV. The sample unit for this examination shall be one palletized unit load ready for shipment. The lot shall be the number of palletized unit loads submitted for inspection at one time. The inspection level shall be S-1 with an AQL of 6.5 expressed in terms of defects per hundred units.

TABLE IV. Examination of palletization

Examine	Defect
Finished dimension	Length, width, or height exceeds specified maximum requirement.
Palletization	Not as specified. Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded with required straps specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

TABLE IV. Examination of palletization (con.)

Examine	Defect
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.

4.3.5 Code and standard compliance.- Proof of compliance with the requirements of NSF (see 3.3 and 3.3.1) shall be submitted to the Government representative.

4.4 Test.

4.4.1 Handle test. Weights totaling the weight of the maximum water capacity of the frying pan plus 25 percent shall be placed in the frying pan. The pan shall be supported at the end of the handle farthest from the pan body for 5 minutes and observation shall be made to determine conformance to the handle bending, breaking and distortion requirements of 3.5.2. Inability to meet handle strength requirements shall constitute failure of the test.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A. Each frying pan shall be completely form-wrapped with minimum 40 pound basis weight kraft paper conforming to UU-P-268. The wrapping shall be secured in place with gummed paper tape conforming to type III, class 1 of PPP-T-45.

5.1.2 Level C. The frying pans shall be packaged to afford adequate protection against damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets this requirement.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. Thirty size 1 frying pans or twenty-four size 2 frying pans, packaged as specified in 5.1, shall be nested and packed in the most compact manner in a snug-fitting fiberboard shipping container conforming to style RSC-L, V2s of PPP-B-636. The inside of each shipping container shall be fitted with a taped liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-F-320. Each shipping container shall be closed, waterproofed by means of tape, and reinforced with flat strapping or tape banding in accordance with the appendix of PPP-B-636.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

5.2.2 Level B. Thirty size 1 frying pans or twenty-four size 2 frying pans, packaged as specified in 5.1, shall be nested and packed in the most compact manner in a snug-fitting fiberboard shipping container conforming to style RSC-L, type CF, variety SW, or type SF, class domestic of PPP-B-636. The inside of each shipping container shall be fitted with a taped liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II of the appendix of PPP-B-636.

5.2.2.1 When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s, fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix thereto.

5.2.3 Level C. Frying pans, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with Uniform Freight Classification Rules or National Motor Freight Classification Rules as applicable.

5.3 Palletization (Military requirements). Unless otherwise specified (see 6.2), frying pans packed as specified shall be palletized in accordance with Load Type I of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L. Pallet patterns shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course. If the container is of a size which does not conform to any of the pallet patterns specified in MIL-STD-147, the pallet pattern used shall first be approved by the contracting officer.

5.4 Marking.

5.4.1 Civil agencies. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with Fed. Std. No. 123.

5.4.2 Military agencies. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The frying pans covered by this specification are intended for frying small quantities of food.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

(a) Title, number, and date of this specification.
(b) Size of frying pan required (see 1.2).
(c) First article, (see 3.1, 4.2 and 6.4).
(d) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(e) When weather-resistant grade fiberboard shipping containers are required for Level B packing (see 5.2.2.1).
(f) When palletization is not required (see 5.3).

6.3 Level B, civil agency packaging. When level B packaging is specified for civil agency procurement, the requirements of 5.1.1 level A packaging shall apply.

6.4 First article. The items covered by this specification require first article test and approval under the appropriate provisions of paragraph 7-104.55 of the Armed Services Procurement Regulations. The first article should be a preproduction sample. The first article should consist of one unit. The contracting officer should include specific instructions in all procurement instruments, regarding arrangement for examination, test and approval of the first article.

MILITARY CUSTODIANS:

Army - GL
Navy - SA
Air Force - 84

Review activities:

Army - MD
Navy - MS

User activity:

Navy - MC

Preparing activity:

Army - GL

CIVIL AGENCY INTEREST:

GSA-FSS
VA
JUS
HEW

Project No. 7330-0383

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

RR-P-89F Pans, Frying

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01760

OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRES-ZQS
Natick, Massachusetts 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.