A-A-1036B
January 12, 1987
SUPERCEDING
A-A-1036A
April 17, 1980

COMMERCIAL ITEM DESCRIPTION

WIRE FABRIC (Insect Screening)

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification RR-W-365, types III, IV, VI, and VII.

This commercial item description covers wire fabric suitable for denying insects access to buildings through windows, doors, and other entrances.

Salient characteristics.

The wire fabric shall be one of the following types:

Type I - Commercial Bronze
Type II - Carbon Steel
Type III - Aluminum Alloy
Type IV - Corrosion Resistant Steel

Length. The wire fabric shall be furnished in a roll with a minimum length of 100 feet.

Continuity. The roll shall contain not more than two pieces, one of which shall be not less than 90% of the required length.

Width. The roll shall be furnished in the following widths as specified: 24, 26, 28, 30, 32, 34, 36, 42, or 48 inches.

Filament size. Unless otherwise specified, the wire diameter shall be 0.011 inch.

Mesh size. The number of openings per linear inch shall be 18 in the warp direction and 14 or 16 as specified in the fill direction.

Crimp type. The mesh shall be crimped at the intersections to lock the wires in place.

Edge type. Both edges of the roll shall be selvaged to prevent ravelling.

FSC 5335

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:11Z
Check the source to verify that this is the current version before use.

Type I. The wire fabric shall be commercial bronze containing 90 percent copper and 10 percent zinc.

Type II. The wire fabric shall be carbon steel of good commercial quality.

Type III. The wire fabric shall be aluminum cladded 5056 aluminum alloy in accordance with ASTM B211.

Type IV. The wire fabric shall be SAE 30316 corrosion resistant steel conforming with AMS 5524.

Workmanship. The wire fabric shall be free from imperfections which may impair serviceability or affect its appearance.

Finishes:

Zinc coating. The type II carbon steel wire fabric shall be electroplated in accordance with ASTM B633 after fabrication. The coating shall be not less than 5% of the bare steel weight.

Paint. Unless otherwise specified, the aluminum alloy shall be coated with aluminum pigment paint.

Passivation. Type IV corrosion resistant steel wire fabric shall be passivated in accordance with QQ-P-35B after fabrication.

Powder coating. When specified, the wire fabric shall be coated with epoxy, polyester or polyethylene.

Tolerances:

Mesh count. The number of meshes per linear inch shall be determined over a square area 2 inches in length. The mesh count shall not vary from that which is specified by more than 1/4 mesh in the warp direction and 1/2 mesh in the fill direction.

Filament size. The wire diameter shall be determined by micrometer measurement. Ten wires each in the warp and fill directions shall be measured. The diameters shall not vary from that which is specified by more than 0.0005 inch.

Width. The width of the material shall not vary more than 1/8 inch from that specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:11Z
Check the source to verify that this is the current version before use.

Quality assurance:

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Certification. Unless otherwise specified, wire fabric offered under this Commercial Item Description shall be certified by the contractor to conform with the material requirements (e.g. chemical analysis) and coating requirements specified, based on documented evidence provided by the manufacturer.

Sampling.

Lot. All wire fabric rolls of the same type presented for inspection at one time shall be considered a lot for purposes of inspection.

Sample unit. For purposes of inspection, the sample unit shall be the first 2-foot seqment for the entire width of each roll in the sample.

Sampling for examination. A random sample shall be of wire fabric rolls shall be selected from each lot in accordance with MIL-STD-105, inspection level I, AQL 2.5 percent defective.

Examination. The wire fabric shall be examined for the following defects.

1. Type and dimensions not as specified
2. Continuity not as specified
3. Selvage not as specified
4. Mesh count not as specified
5. Workmanship not as specified

Regulatory requirements. In accordance with section 23.403 of the Federal Acquisition Regulations, the Governments policy is to acquire items composed of the highest percentage of recovered materials practicable, consistent with maintaining a satisfactory level of competition without adversely affecting performance requirements or exposing suppliers' employees to undue hazards from the recovered materials.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:11Z
Check the source to verify that this is the current version before use.

Preservation,packaging,packing,labeling,and marking (Civil Agencies). The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

Packaging (DoD). The packaging shall be in accordance with ASTM Standard D3951.

The issues of SAE, AMS 5524, ASTM B211 & B633, and Federal Specification QQ-P-35 in effect on the date of the solicitation or purchase order shall be used to determine compliance with these requirements.

ASTM standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

SAE standards are available from the Society Of Automotive Engineers, 400 Commonwealth Drive, Warrendale, PA 15096.

Copies of Federal Specifications required by activities for bidding purposes are available from Business Service Centers at the General Services Aministration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, San Francisco, Los Angeles, and Seattle, WA.

Notes:

Purchaser should specify the type, width, mesh size, wire size, finish and quantity of rolls.

MILITARY INTERESTS:

Military Coordinating Activity
Army - ME

Custodians
Army - ME
Navy - YD
Air Force - 99

Review Activities
Army - MD, MI, EA
Navy - OS, MS
DLA - IS

User Activity
Navy - MC

CIVIL AGENCY COORDINATING ACTIVITY:
VA - OSS
USDA - AFS

PREPARING ACTIVITY
GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 202640-26T08:11Z
Check the source to verify that this is the currenversion before use.