INCH-POUND
MIL-DTL-24643/41D
1 October 2009
SUPERSEDING
MIL-DTL-24643/41C
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -20 °C TO +90 °C, TYPE LS1SAU

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction, Non-Watertight

First	-	Copper conductor, coated or uncoated, ASTM B286, Size 20 – 7 strands.
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation. Nominal wall thickness of 0.015 inch. Wall thickness may vary from nominal as necessary in order for completed cable to meet the specified electrical requirements.
Fourth	-	Braided shield of 34 or 36AWG, coated or uncoated copper. Braid angle of 30 to 35 degrees; minimum coverage of 85 percent.
Fifth	-	Shield insulation of two polyester tapes, outer tape sealed. An alternate shield insulation may consist of one polyester tape, plus an extruded jacket of a suitable transparent material, minimum average thickness of the transparent material 0.003 inch. The standard identification code shall be applied by Method 2.
Sixth	-	The specified number of singles (see table I) shall be cabled together in accordance with 3.4.4 of MIL-DTL-24643. Cabling sequence shall be consecutive starting with no. 1 from the center outward. Fillers may be used as necessary to form a firm well-rounded assembly.
Seventh	-	An optional binder.
Eighth	-	Cross-linked polyolefin jacket. Minimum average wall thickness of 0.063 inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:10Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/41	Type and size	Number of conductors	Overall diameter	
			Min. (inch)	Max. (inch)
-01UN	LS1SAU-44	44	0.910	0.990

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic Electricals:

Conductor resistance (ohms/1000 feet at 25 °C, max.)	10.71
Voltage withstand (volts, root mean square, min.)	
Conductor to component shield	2000
Component shield to component shield	500
Insulation resistance (megohms/1000 feet, min.)	
Conductor to component shield	500
Component shield to component shield	100
Conductor continuity	No failure
Shield continuity	No failure
Group A:	
Visual and dimensional	No failure
Capacitance, 1 kilohertz (KHz) (pF/ft., max.)	72
Group B:	
Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 200 °C)	50
Physicals (unaged)	
Insulation (extruded)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160
Tear (lb/in thickness, min.)	35

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:10Z
Check the source to verify that this is the current version before use.

Group C:	
Physicals (aged) air oven	
Insulation (extruded)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Shrinkage	No failure
Shield (conformance to material, construction and coverage)	No failure
Cable sealant removability	No failure
Group D:	
Flame propagation (cable)	No failure
Qualification Inspection:	
Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:	
Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Shield insulation	2
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index (max.)	
Jacket	25

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:10Z
Check the source to verify that this is the current version before use.

Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LS1SAU-44	1000

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2008-045)

Review Activities:
Army – AR, AV, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:10Z
Check the source to verify that this is the current version before use.