INCH-POUND
MIL-DTL-24643/42E
27 November 2023
SUPERSEDING
MIL-DTL-24643/42D
1 October 2009

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -4 DEGREES FAHRENHEIT (-20 DEGREES CELSIUS) TO +194 DEGREES FAHRENHEIT (+90 DEGREES CELSIUS), 600 VOLTS, TYPE LS1SU

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction (Non-Watertight)

First	-	Copper conductor, tin-coated, ASTM B286, 20 AWG with 7 strands and 18 AWG, class B stranding, ASTM B8 (7 by 0.0152 inches). For LS1SU-36, thirty-two size 20 AWG conductors and four size 18 AWG conductors. For LS1SU-60, sixty size 20 AWG conductors.
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation, white or natural. Nominal wall thickness of 0.017 inch. Wall thickness may vary from nominal as necessary in order for completed cable to meet the specified electrical requirements.
Fourth	-	Braided shield of 34 or 36 AWG, coated or uncoated copper. Braid angle of 30 to 35 degrees; minimum coverage of 85 percent.
Fifth	-	Shield insulation of two polyester tapes, outer tape sealed. An alternate shield insulation may consist of one polyester tape, plus an extruded jacket of a suitable transparent material; minimum average thickness of the transparent material 0.003 inch. Standard identification code shall be applied by method 2. For LS1SU-36, the four 18 AWG conductors shall be numbered 1 through 4.
Sixth	-	The specified number of singles (see table I) shall be cabled together in accordance with 3.4.4 of MIL-DTL-24643. Cabling sequence shall be consecutive, starting with pair no. 1, from the center outward. Fillers may be used as necessary to form a firm, well-rounded assembly.
Seventh	-	An optional binder.
Eighth	-	Cross-linked polyolefin jacket. See table I for thickness.

NOTE: Manufacturer's identification tape is required (see 3.4.9 of MIL-DTL-24643).

Distribution Statement A. Approved for public release: distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:11Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/42	Type and size	Number of conductors	Conductor size (AWG)	Cable jacket thickness min. avg. (inch)	Overall diameter (inches)	
					min.	max.
-01UN	LS1SU-36 1/	4 32	18-7 20-7	0.075	0.910	0.985
-02UN	LS1SU-60	60	20-7	0.100	1.210	1.310

NOTE:

1/ See First construction layer for conductor requirements.

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic electricals:

Conductor resistance (ohms/1,000 feet at 77 °F [25 °C], max.)

ASTM B286, size 20 – 7	10.93
ASTM B8, size 18 (class B)	7.05

Voltage withstand (volts, root mean square, min.)

Conductor to component shield	2,200
Component shield to component shield	500

Insulation resistance (megohms/1,000 feet, min.)

Conductor to component shield	500
Component shield to component shield	100

Conductor continuity	No failure
Shield continuity	No failure

Group A:

Visual and dimensional	No failure
Mutual capacitance (nominal at 1 kilohertz [kHz]) (picofarad [pF]/100 feet)	72

Group B:

Thermoset proof test (percent, max.)

Insulation	50
Jacket (when tested at 392 °F [200 °C])	50

Cold bending (cable)	No failure

Physicals (unaged)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:11Z
Check the source to verify that this is the current version before use.

Insulation (extruded insulation only)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1,300
Elongation (percent, min.)	160
Tear (lb/in thickness, min.)	35

Group C:

Physicals (aged) (air oven)	
Insulation (extruded insulation only)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Shrinkage	No failure
Shield (conformance to material, construction, and coverage)	No failure

Group D:

Flame propagation (cable)	No failure

Qualification inspection:

Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:

Aging and compatibility (cable) (257±9 °F [125±5 °C])	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Shield insulation	2

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:11Z
Check the source to verify that this is the current version before use.

Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	0.5
Fillers	5
Insulation	1.5
Durometer (jacket) – type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LS1SU-36 and LS1SU-60	1,000

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:11Z
Check the source to verify that this is the current version before use.

CONCLUDING MATERIAL

Custodians:
Army – MI
Navy – SH

Preparing activity:
Navy – SH
(Project 6145-2013-058)

Review activities:
Army – AR, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:11Z
Check the source to verify that this is the current version before use.