INCH-POUND
MIL-DTL-24643/46F
1 October 2009
SUPERSEDING
MIL-DTL-24643/46E
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -20 °C TO +90 °C, TYPE LS2WAU

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction, Watertight

First	-	Copper conductor, tin-coated, ASTM B286, 22 AWG - 7 strands.
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation. Nominal wall thickness of 0.024 inch: wall thickness may vary from nominal as necessary, in order for the completed cable to meet the specified electrical requirements. Telephone identification code shall be applied by Method 3.
Fourth	-	Two conductors cabled together with a nominal lay of 1½ inches to form a pair.
Fifth	-	The specified number of pairs (see table I) shall be cabled together with a lay in accordance with 3.4.4 of MIL-DTL-24643. Cabling sequence shall be consecutive, starting with no. 1, from the center outward. Fillers may be used as necessary to form a firm well-rounded assembly.
Sixth	-	An optional binder.
Seventh	-	Braided shield of tin-coated copper.
Eighth	-	An optional binder.
Ninth	-	Cross-linked polyolefin jacket. Minimum average wall thickness of 0.060 inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:13Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/46	Type and size	Number of pairs	Overall diameter	
			min. (inch)	max. (inch)
-01UO	LS2WAU-40	40	1.320	1.370

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic Electricals:

Conductor resistance (ohms/1000 feet at 25 °C, max.)	17.71
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	2500
Conductor to overall shield	2500
Insulation resistance (megohms/1000 feet, min.)	
Conductor to conductor	500
Conductor to overall shield	500
Conductor continuity	No failure
Shield continuity	No failure
Jacket flaws	No failure

Group A:

Visual and dimensional	No failure
Capacitance	
Mutual capacitance, at1 kilohertz (KHz) (pF/ft, max.)	30
Watertightness (see MIL-DTL-24643 for limits of water leakage)	No failure

Group B:

Cold bending cable	No failure
Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 200 °C)	50
Drip (95±1°C)	
Physicals (unaged)	
Insulation (extruded)	

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:13Z
Check the source to verify that this is the current version before use.

Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160
Tear (lb/in thickness, min.)	35
Group C:	
Physicals (aged) air oven	
Insulation (extruded)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Cable fill (sealant) removability	No failure
Shrinkage	No failure
Shield (conformance to material, construction and coverage)	No failure
Surface transfer impedance	
Milliohms per meter (max.)	700
EMP response (dB, min.)	60
Group D:	
Flame propagation (cable)	No failure
Qualification Inspection:	
Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:	
Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Shield insulation	2

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:13Z
Check the source to verify that this is the current version before use.

Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LS2WAU-40	1000

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2008-050)

Review Activities:
Army – AR, AV, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:13Z
Check the source to verify that this is the current version before use.