INCH-POUND

MIL-C-24643/49C
14 March 1994
SUPERSEDING
MIL-C-24643/49B
3 October 1986

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, TYPE LSTNW (INCLUDING VARIATION LSTNWA)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DODISS) specified in the solicitation: MIL-C-24643.

This cable can be manufactured in two variations: LSTNW (unarmored), and LSTNWA (armored).

REQUIREMENTS:

Qualification required.

Construction (non-watertight)

First - Copper conductor, uncoated (see table I for size).
Second - Separator (opaque white) may be used at manufacturer's option where required to provide free-stripping insulation.
* Third - Crosslinked polyethylene insulation or ethylene propylene rubber insulation (see table I for thickness) Standard identification code shall be applied by method 1 or method 3. If identification method 1 is used, insulation color shall be black.
* Fourth - Three conductors cabled together with a lay not greater than 24 times the pitch diameter. Fillers shall be used as necessary to form a firm, well rounded assembly.
Fifth - Binder tape applied helically with overlap.

Construction variant for type LSTNW

* Sixth - Cross-linked polyolefin jacket. (see table I for thickness.)

Construction variant for type LSTNWA

* Sixth - Cross-linked polyolefin jacket. (see table I for thickness.)
* Seventh - Braided metal armor.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:14Z
Check the source to verify that this is the current version before use.

* TABLE I. Details.

Military 1/ part no. M24643/49	Size 2/	AWG conductor size	Insulation thickness min avg (inch)	Cable jacket thickness min avg (inch)	Overall diameter (inches)			
					TYPE LSTNW		TYPE LSTNWA	
					min	max	min	max
-01UN	3	16 (class B)	0.030	0.040	0.380	0.411	0.430	0.461
-02UN	4	14 (class B)	.030	.040	.415	.449	.465	.499
-03UN	9	10 (class B)	.030	.050	.578	.625	.628	.675
-04UN	14	9 (class B)	.045	.050	.620	.670	.670	.720
-05UN	23	7 (class B)	.045	.055	.703	.760	.753	.810
-06UN	50	3 (class C)	.045	.060	.869	.969	.919	.019
-07UN	75	1 (class C)	.055	.070	1.048	1.134	1.098	1.184
-08UN	100	0 (class D)	.055	.075	1.171	1.266	1.221	1.316
-09UN	150	000 (class D)	.055	.075	1.401	1.515	1.451	1.565

1/ Unarmored. When armor option is required, see MIL-C-24643 for configuration of part number.
2/ Type LSTNW and LSTNWA.

TABLE II. Electrical details.

Size 1/	AWG conductor size	Conductor resistance (ohms)	Insulation resistance (megohms)	Voltage Withstand (minimum) (volts)	Cold Bending mandrel diameter (max inch)	Accelerated service loading current (amperes)
3	16 (class B)	4.3	6000	4000	3	----
4	14 (class B)	2.68	5000	4000	4	----
9	10 (class B)	1.08	3800	4000	5	----
14	9 (class B)	.859	4400	5500	5	90
23	7 (class B)	.543	3700	5500	7	115
50	3 (class C)	.21	2600	5500	9	165
75	1 (class C)	.134	2600	7000	10	250
100	0 (class D)	.106	2400	7000	12	295
150	000 (class D)	.0674	1800	7000	14	400

1/ Type LSTNW and LSTNWA.

EXAMINATION AND TESTS:

Requirements

Basic electrical:

Conductor Resistance - ohms/1000 feet at 25°C, max ..... (see table II)
Voltage Withstand - volts, root mean square, minimum ..... (see table II)
* Insulation resistance - Conductor to conductor
Megohms/1000 feet minimum ..... (see table II)
Conductor continuity ..... No failure

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:14Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS (continued):	Requirements
Group A:	
Visual and dimensional	No failure
Group B:	
* Cross-linked proof test (percent, maximum)	
Insulation	50
Jacket (When tested at 200°C)	50
Cold bending, cable - (see table I for mandrel diameter)	No damage
Tear - pounds per inch thickness, minimum (ASTM D 470)	35
Physicals (unaged)	
Insulation	
Ethylene propylene rubber	
Tensile strength - lb/in^2, minimum	700
Elongation - percent, minimum	250
Cross-linked polyethylene	
Tensile strength - lb/in^2, minimum	1800
Elongation - percent, minimum	250
Jacket (cable)	
Tensile strength - lb/in^2, minimum	1300
Elongation - percent, minimum	160
Group C:	
Physicals (aged)	
Insulation	
Ethylene propylene	
Air Oven	
Tensile strength - percent of unaged, minimum	75
Elongation - percent of unaged minimum	75
Cross-linked polyethylene	
Air Oven	
Tensile strength - percent of unaged, minimum	80
Elongation - percent of unaged minimum	80
Jacket (cable)	
Air oven	
Tensile strength - percent of unaged, minimum	60
Elongation - percent of unaged minimum	60
Hot oil immersion	
* Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged minimum	50
Shrinkage	No failure
Heat distortion - percent of unaged, maximum	30

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:14Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS (continued):	Requirements
* Permanence of printing (conductor) - method 1 only, cycles, minimum	25
* Permanence of printing (jacket) - (type LSTNW only), cycles, minimum	125
* Armor type LSTNWA only) - conformance to material, construction and coverage	No failure
* Group D:	
Flame propagation (cable)	No failure

QUALIFICATION INSPECTION:

* Qualification inspection shall include basic electrical, all of groups A, B, C and D, plus the following:

	Requirements
Aging and compatibility (cable)(125 ± 5°C)	No failure
Abrasion resistance (jacket) - scrapes, minimum	75
Acid gas equivalent - percent, maximum	
Jacket	2
Fillers	2
Insulation	18
Halogen content - percent, maximum	
Jacket	0.2
Fillers	0.2
Immersion (jacket)	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Smoke index, maximum	
Jacket	25
* Fillers	45
Insulation	45
Toxicity index, maximum	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - (type A) hardness, minimum	80
Weathering (jacket)	No failure

UNIT ORDERING LENGTHS:

Type and Size	Feet (nominal)
LSTNW-3	2500
LSTNW-4, 9, 14	2000
LSTNW-23	1500
LSTNW-50 through 150	1000

Source: https://assist.dla.mil -- Downloaded: 20260-20T00:14Z
Check the source to verify that this is the current version before use.

NOTE: The margins of this specification are marked with asterisks to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - MI
Navy - SH

Review Activities:
Army - AV, CR, ER
Navy - EC
DLA - IS

Preparing Activity:
Navy - SH

Agent:
DLA-IS

(Project No. 6145-2057-49)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:14Z
Check the source to verify that this is the current version before use.