INCH-POUND
MIL-DTL-24643/49E
22 August 2002
SUPERSEDING
MIL-C-24643/49D
22 November 1994

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, 1000 VOLTS, THREE CONDUCTOR, TYPE LSTNW

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of MIL-DTL-24643 listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation.

REQUIREMENTS:

Qualification required.

Construction (non-watertight)

First -	Copper conductor, uncoated (see table I for size).
Second -	Separator (opaque white) may be used at manufacturer's option where required to provide free-stripping insulation.
Third -	Cross-linked polyethylene insulation or ethylene propylene rubber insulation (see table I for thickness). Standard identification code shall be applied by method 1 or method 3. If identification method 1 is used, insulation color shall be black.
Fourth -	Three conductors cabled together with a lay not greater than 24 times the pitch diameter. Fillers shall be used as necessary to form a firm, well rounded assembly.
Fifth -	Binder tape applied helically with overlap.
Sixth -	Cross-linked polyolefin jacket. (see table I for thickness.)

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.
Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:14Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/49	Size	AWG conductor size	Insulation thickness min avg (inch)	Cable jacket thickness min avg (inch)	Overall diameter (inches) TYPE LSTNW min	Overall diameter (inches) TYPE LSTNW max
-01UN	3	16 (class B)	0.030	0.040	0.380	0.411
-02UN	4	14 (class B)	0.030	0.040	0.415	0.449
-03UN	9	10 (class B)	0.030	0.050	0.578	0.625
-04UN	14	9 (class B)	0.045	0.050	0.620	0.670
-05UN	23	7 (class B)	0.045	0.055	0.703	0.760
-06UN	50	3 (class C)	0.045	0.060	0.869	0.969
-07UN	75	1 (class C)	0.055	0.070	1.048	1.134
-08UN	100	0 (class D)	0.055	0.075	1.171	1.266
-09UN	150	000 (class D)	0.055	0.075	1.401	1.515

TABLE II. Electrical details.

Size	AWG conductor size	Conductor resistance (ohms)	Insulation resistance (megohms)	Voltage withstand (minimum) (volts)	Cold bending mandrel diameter (max inch)	Accelerated service loading current (amperes)
3	16 (class B)	4.3	6000	4000	3	----
4	14 (class B)	2.68	5000	4000	4	----
9	10 (class B)	1.08	3800	4000	5	----
14	9 (class B)	0.859	4400	5500	5	90
23	7 (class B)	0.543	3700	5500	7	115
50	3 (class C)	0.21	2600	5500	9	185
75	1 (class C)	0.134	2600	7000	10	250
100	0 (class D)	0.106	2400	7000	12	295
150	000 (class D)	.0674	1800	7000	14	400

EXAMINATION AND TESTS:

Basic electrical: Requirements

Conductor Resistance - ohms/1000 feet at 25°C, max ..... (see table II)
Voltage Withstand - volts, root mean square, minimum ..... (see table II)
Insulation resistance - Conductor to conductor
Megohms -1000 feet minimum ..... (see table II)
Conductor continuity ..... No failure

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:14Z
Check the source to verify that this is the current version before use.

Group A:
- Visual and dimensional ..... No failure

Group B:
- Cross-linked proof test (percent, maximum)
  - Insulation 50
- Jacket (When tested at 200°C) 50
- Cold bending, cable - (see table I for mandrel diameter) ..... No damage
- Tear - pounds per inch thickness, minimum (ASTM D 470) 35

Physicals (unaged)
- Insulation
  - Ethylene propylene rubber
    - Tensile strength - lb/in^2, minimum 700
    - Elongation - percent, minimum 250
  - Cross-linked polyethylene
    - Tensile strength - lb/in^2, minimum 1800
    - Elongation - percent, minimum 250
- Jacket (cable)
  - Tensile strength - lb/in^2, minimum 1300
  - Elongation - percent, minimum 160

Group C:

Physicals (aged)
- Insulation
  - Ethylene propylene
    - Air Oven
      - Tensile strength - percent of unaged, minimum 75
      - Elongation - percent of unaged minimum 75
  - Cross-linked polyethylene
    - Air Oven
      - Tensile strength - percent of unaged, minimum 80
      - Elongation - percent of unaged minimum 80
- Jacket (cable)
  - Air oven
    - Tensile strength - percent of unaged, minimum 60
    - Elongation - percent of unaged minimum 60
  - Hot oil immersion
    - Tensile strength - percent of unaged, minimum 50
    - Elongation - percent of unaged minimum 50
- Shrinkage ..... No failure
- Heat distortion - percent of unaged, maximum 30
- Permanence of printing (conductor) - method 1 only, cycles, minimum 25
- Permanence of printing (jacket) - cycles, minimum 125

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:14Z
Check the source to verify that this is the current version before use.

Group D:

Flame propagation (cable)	No failure

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B, C and D, plus the following:

	Requirements
Aging and compatibility (cable)(125 ± 5°C)	No failure
Abrasion resistance (jacket) - scrapes, minimum	75
Acid gas equivalent - percent, maximum	
Jacket	2
Fillers	2
Insulation	18
Halogen content - percent, maximum	
Jacket	0.2
Fillers	0.2
Immersion (jacket)	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Smoke index, maximum	
Jacket	25
Fillers	45
Insulation	45
Toxicity index, maximum	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - (type A) hardness, minimum	80
Weathering (jacket)	No failure

UNIT ORDERING LENGTHS:

Type and Size	Feet (nominal)
LSTNW-3	2500
LSTNW-4, 9, 14	2000
LSTNW-23	1500
LSTNW-50 through 150	1000

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:14Z
Check the source to verify that this is the current version before use.

Custodians:
Army - MI
Navy - SH

Review Activities:
Army - AV, CR
Navy - CG, EC
DLA – CC

Preparing Activity:
Navy - SH
(Project 6145-2308-047)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:14Z
Check the source to verify that this is the current version before use.