MIL-C-2991
4 September 1951

MILITARY SPECIFICATION

CAP, DUST, LEATHER, TELESCOPE

This specification was approved by the Departments of the Army, the Navy, and the Air Force for use of procurement services of the respective Departments, and supersedes the following specification:

Army 52-3-39
24 September 1947

This specification consists of this cover sheet and Specification 52-3-39, dated 24 September 1947, attached hereto, without modification.

Copies of this specification may be obtained upon application to the Office, Chief of Ordnance, Washington 25, D. C.

When a request for this specification is received by a supplying activity it will be necessary to attach this cover sheet to the pertinent specification before issue.

Source: https://assist.dla.mil -- Downloaded: 2026-10-1
Check the source to verify that this is the current version

U. S. ARMY
SPECIFICATION

No. 52-3-39
24 SEPTEMBER 1947

CAP, DUST, LEATHER, TELESCOPE

A. APPLICABLE DRAWINGS AND SPECIFICATIONS

A–1. Ordnance Department Drawing C7312018, Cap, Dust, Assembly, lists the drawitngs and specifications necessary to complete the manufacture of the dust cap.

A–2. All drawings and specifications listed on the above-mentioned drawing, of the revision date listed thereon, shall form a part of this specification.

B. TYPE

B–1. This specification covers one type of leather dust cap used with telescope M73B1 (Weaver).

C. MATERIAL AND WORKMANSHIP

C–1. See specificaion No. 52–0–1.

D. GENERAL REQUIREMENTS

D–1. See detail requirements.

E. DETAIL REQUIREMENTS

E–1. *Visual defects and dimensions.*

E–1*a*. *Components.*—All components and assemblies shall comply with material and workmanship requirements and conform to dimensions shown on the drawings. Leather surfaces shall be free of cuts, grub-holes, scratches, wrinkles, and other defects which may effect functioning, serviceability, or appearance.

E–1*b*. *Leather.*—All leather shall be cowhide, 3/32-inch, planished, russet, strap, conforming to the requirements of class 1, grade A, Federal specification KK–I–271.

E–1*c*. *Cementing.*—The outer, inner, front, and rear pieces shall be securely sealed together by using cellulose acetate sheet cement.

E–1*d*. *Stitching.*—Hand or machine stitching shall be done with suitable tension to produce a tight seam, except for the closure at the end of the pockets when the stitch loop shall be stitched slack to be drawn together to form a support for the outer and inner pieces. All threads shall be neatly and securely fastened at the ends of the seams. There shall be 6 stitches per inch for the strap and 7 per inch for the tbottom closures of the pocket. Machine stitching shall be done with a machine making a stitch conforming to stitch type 301, Federal specification DDD–S–751.

E–1*e*. *Thread.*—The thread used shall be heavy, white, soft finish cotton having a minimum tensile strength of 8 pounds and meeting the requirements of 10/3, type III, Federal specification V–T–276.

Source: https://assist.dla.mil -- Downloaded
Check the source to verify that this is the cu

E–2. *Mold resistance.*—Dust caps shall be treated to resist cracking, mildew, and water, and to preserve the original qualities of the leather with a preservative leather dressing compound meeting the requirements of U. S. Army specification No. 92–16.

F. METHODS OF INSPECTION AND TESTS

F–1. *Inspection and tests.*

F–1*a*. *Place of inspection.*—Unless otherwise specified, inspection and tests shall be made at the place of manufacture in accordance with the applicable provisions of specification No. 52–0–1. In addition to the inspection and tests prescribed herein, the inspector may subject all or part of any lot of the commodity to such inspection and tests as he deems necessary to determine compliance with the requirements.

F–1*b*. *Inspection lots.*—An inspection lot shall consist of 500 dust caps or one day's production, whichever is the greater.

F–1*c*. *Visual inspection.*—Each dust cap of the lot shall be visually inspected for completeness of manufacture, assembly, finish, and workmanship; and shall be plug gaged for fit. Leather, cementing, and stitching shall be carefully examined to insure compliance with requirements.

F–2. *Mold resistance test.*—Each dust cap shall be carefully inspected to insure that the preservative meets the requirement and has been applied as specified by U. S. Army specification No. 92–61.

G. PACKAGING, PACKING, AND MARKING FOR SHIPMENT

G–1. *Packaging and packing.*—Unless otherwise specified, the subject commodity shall be delivered in standard commercial containers, so constructed as to insure acceptance by common or other carriers, for safe transportation, at the lowest rate, to the point of delivery.

G–2. *Marking.*—Unless otherwise specified, shipping containers shall be marked in accordance with U. S. Army specification No. 100–2.

H. NOTES

H–1. This specification replaces Springfield Armory Tentative Specification SXS–183.

H–2. The use of this specification, whenever applicable, is mandatory on all procuring agencies of the Army.

Notice.—This specification, together with specifications and drawings pertaining to it and bearing a "Notice" of similar restrictions, is intended for use only in connection with procurement by the United States Government; and shall not be reproduced either wholly or in part except when authorized in connection with Government procurement, nor be used for any other purpose except when specifically authorized by the Chief of Ordnance.

Note.—Copies of this specification may be obtained from the Chief of Ordnance, Department of the Army, Washington 25, D. C.

Source: https://assist.dla.mil -- Downloaded
Check the source to verify that this is the cu

[No. 52–8–39]