## MILITARY SPECIFICATION

# STRAP, WRIST WATCH, NYLON

*This amendment forms a part of Military Specification MIL-S-3035, 8 September 1949, and has been approved by the Departments of the Army, the Navy, and the Air Force*

Page 1, section 2: Delete and substitute:

**"2. APPLICABLE SPECIFICATIONS, STANDARDS, DRAWINGS, AND PUBLICATIONS"**

**"2.1** The following specifications, standards, and drawings, of the issue in effect on date of invitation for bids, form a part of this specification:

### SPECIFICATIONS

MILITARY

JAN-P-108—Packaging and Packing for Overseas Shipment—Boxes, Fiberboard (V-board and W-board), Exterior and Interior.

MIL-P-116—Preservation, Methods of.

NAVY DEPARTMENT

General Specifications for Inspection of Material.*

### STANDARDS

MILITARY

MIL-STD-129—Marking of Shipments.

### DRAWINGS

ORDNANCE CORPS

B7646909—Strap, Wrist Watch.

(Copies of specifications, standards, and drawings required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer).

Page 2, Adding the following paragraphs:

**"3.1.2** *Low temperature resistance.*—When exposed to a temperature of minus 10 to minus 12° F., as specified in 4.3.2.1, the straps shall not break or split."

**"3.1.3** *High temperature-high humidity resistance.*—When exposed to temperature and humidity conditions of 160° ±3° F. and 95 or more percent relative humidity, as specified in 4.3.2.2, the straps shall not warp in a plane parallel to the face of the strap. The longitudinal or lateral shrinkage of the exposed straps shall not exceed 2 percent of the corresponding dimensions of the unexposed straps."

Page 2, paragraph 4.3.2., line 1: Delete "500" and substitute "15,000".

Page 2, paragraph 4.3.2, line 2: Delete "five" and substitute "30".

Page 2, paragraph 4.3.2.1: Delete and substitute:

**"4.3.2.1** *Low temperature test.*—Five straps shall be conditioned for 3 hours in a chamber maintained at minus 10 to minus 12° F. Following the exposure period, and without removing the straps from the chamber, each strap shall be bent rapidly through an angle of 240° around a ¼-inch diameter metal mandrel, and examined for breaks or splits".

Page 2, paragraphs 4.3.2.2 through 4.3.2.3.2: Delete and substitute:

**"4.3.2.2** *High temperature-high humidity test.*

**"4.3.2.2.1** *Test chamber.*—The test chamber shall be capable of maintaining temperature and humidity conditions of 160° ±3° F. and 95 or more percent relative humidity.

**"4.3.2.2.2** *Procedure.*—Place 5 straps flat on a perforated shelf maintained in a horizontal position in the test chamber, and expose them for 5 to 7 hours to the specified temperature and humidity conditions (see 4.3.2.2.1). Following the exposure period remove the straps and place them in a horizontal position in an air oven maintained at 160° ±3° F., for 16 to 20 hours. The test chamber-air oven cycle shall be repeated 3 times. At the end of 3 such cycles the straps shall be examined for distortion and

*Applicable only to Navy purchases.



Source: https://assist.dla.mil -- Downloaded: 2026-10-16T16:03Z
Check the source to verify that this is the current version before use.

warpage, and for lateral or longitudinal shrinkage."

Page 3, paragraphs 5.1, line 3: Delete "JAN–P–116" and substitute "MIL–P–116".

Page 3, paragraph 5.3.2: Delete and substitute:

"5.3.2 *Exterior shipping containers.*—In addition to any special marking required by the contract or order, the exterior shipping containers shall be marked in accordance with Standard MIL–STD–129."

**Custodians:**
**Army—Ordnance Corps**
**Navy—Bureau of Ships**
**Air Force**

**Other interest:**
**Army—TM**
**Navy—*MC*S.**

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T16:03Z
Check the source to verify that this is the current version before use.