MIL-S-3035
8 September 1949
SUPERSEDING
Frankford Arsenal Tentative FXS-1076
15 June 1948

MILITARY SPECIFICATION

STRAP, WRIST WATCH, NYLON

This specification was approved by the Departments of the Army, the Navy, and the Air Force for use of procurement services of the respective Departments.

1. SCOPE

1.1 This specification covers one type of nylon strap for use with wrist watches.

2. APPLICABLE SPECIFICATIONS, OTHER PUBLICATIONS, AND DRAWINGS

2.1 Specifications.—The following specifications, of the issue in effect on date of invitation for bids, form a part of this specification:

MILITARY SPECIFICATIONS

JAN-P-108—Packaging and Packing for Overseas Shipment—Boxes, Fiberboard (V-Board and W-Board), Exterior and Interior.

JAN-P-116—Packaging and Packing for Overseas Shipment — Preservation; Methods of.

U. S. ARMY SPECIFICATIONS

94-40645—Marking, Exterior, Domestic and Export Shipment by Contractors.[1]

100-2—Standard Specification for Marking Shipments by Contractors.[2]

NAVY DEPARTMENT SPECIFICATION

General Specifications for Inspection of Material.[3]

(*Army.*—Copies of specifications should be obtained from the procuring agency or as directed by that agency. Both the title and identifying number or symbol should be stipulated when requesting copies.)

(*Navy.*—Copies of Military and Navy Department specifications may be obtained upon application to the Bureau of Supplies and Accounts, Navy Department, Washington 25, D. C., except that activities of the Armed Forces should make application to the Supply Officer in Command, Naval Supply Center, Norfolk 11, Va. Both the title and identifying number or symbol should be stipulated when requesting copies.)

(*Air Force.*—Copies of Military and the applicable U. S. Army specifications may be obtained upon application to the Commanding General, Air Matériel Command, Wright-Patterson Air Force Base, Dayton, Ohio. Both the title and identifying number or symbol should be stipulated when requesting copies.)

(*Marine Corps.*—Copies of Military specifications may be obtained upon application to the Quartermaster General, Headquarters, U. S. Marine Corps, Navy Building, Washington 25, D. C. Both the title and identifying number or symbol should be stipulated when requesting copies.)

2.2 Other publications.—The following publication, of the issue in effect on the date of invitations for bid, form a part of this specification:

BUREAU OF SUPPLIES AND ACCOUNTS PUBLICATION

Navy Shipment Marking Handbook.[4]

(Copies of the Navy Shipment Marking Handbook may be obtained upon application to the Bureau of Supplies and Accounts, Navy Department, Washington 25, D. C., except that activities of the Armed Forces should make application to the Supply Officer in Command, Naval Supply Center, Norfolk 11, Va.)

2.3 Drawings.—The following drawing, of the issue in effect on the date of invitation for bids, forms a part of this specification:

ARMY ORDNANCE DEPARTMENT DRAWING

B7646909 Strap, Wrist Watch.

(Copies of Army Ordnance Department drawings may be obtained from the procuring agency or as directed by that agency.)

[1] Applicable only to Air Force purchases.
[2] Applicable only to Army purchases.
[3] Applicable only to Navy purchases.
[4] Applicable only to Navy shipments.

855948—49

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T16:03Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Material.—Material shall be as specified on Drawing B7646909.

3.1.1 The nylon material of which the strap is constructed shall not cause skin irritation or skin sensitization upon prolonged intimate contact with the skin; shall be fungi-static, and shall have sufficient porosity to permit the transmission and evaporation of moisture from the skin of the arm.

3.2 Qualification.—In all respects not specifically covered by this specification, strap material shall be equal to the bid sample furnished by the bidder and approved by the contracting officer. (See sec. 6.)

3.3 Design and construction.—The strap shall be manufactured in accordance with Drawing B7646909. It shall be of one-piece construction with integrally molded loops for the watch and buckle pins and with integrally molded keepers. Sewings, cementing, or heat sealing shall not be used in the construction of the strap.

3.4 Workmanship.—Workmanship shall be of a quality with the highest existing production standards and shall embody best practices consistent with the intended use of the item.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 General.—The watch straps shall be subjected to an acceptance inspection by authorized Government inspectors. When practicable, all inspection and tests shall be conducted at the place of manufacture, and under the supervision of the authorized Government inspector.

4.2 Acceptance or approval of material during manufacture, or the release of any design by the procuring agency, shall in no case be construed as a guarantee of the acceptance of the finished product.

4.3 Inspection.—Inspection and tests under this specification shall be for the purpose of:

a. Unit strap acceptance.

b. Acceptance of individual lots under the contract.

4.3.1 Each manufactured strap shall be inspected for compliance with the requirements for material, workmanship, color, dimensions and markings.

4.3.2 From each lot of 500 straps or fraction thereof, five straps shall be selected at random and shall be subjected to the following tests:

4.3.2.1 *Low temperature exposure.* — The strap shall be subjected to a temperature of minus 65° plus or minus 2° C. (minus 85° plus or minus 3° F.) for a period of 48 hours. The temperature shall be then raised to minus 54° plus or minus 2° C. (minus 65° plus or minus 3° F.) for a period of 24 hours. At the end of the 24 hour period the strap shall be removed from the chamber and allowed to thoroughly warm up to room temperature. It shall then be examined and shall not have become damaged in any way that would affect subsequent use.

4.3.2.2 *High temperature exposure.*—The strap shall be subjected to a temperature of 71° plus or minus 2° C. (160° plus or minus 2° F.) for a period of 24 hours. The strap shall then be removed from the chamber and allowed to thoroughly cool to room temperature where it can be examined. There shall be no damage which would affect subsequent use.

4.3.2.3 *Humidity.*—

4.3.2.3.1 *Apparatus.*—The apparatus shall consist of a test chamber capable of maintaining an internal temperature of 71° plus or minus 2° C. (160° plus or minus 3° F.) and an internal relative humidity of 95 plus or minus 5 percent. The test chamber shall be capable of being sealed so as to retain the total moisture content in the test space. The heat loss from the chamber shall be sufficient to reduce the internal temperature from the above specified operating temperature to not more than 38° C. (100° F.) within a period of 18 hours from the time of removal of the source of heat.

4.3.2.3.2 *Procedure.*—The strap shall be mounted in the test chamber with both surfaces exposed. The temperature and relative humidity shall be raised to the specified values and maintained for a period of 6 hours. At the end

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T16:03Z
Check the source to verify that this is the current version before use.

of the 6-hour period the heat shall be shut off and the chamber sealed. At the end of an additional 18-hour period, the chamber shall be unsealed and the heat again applied. This cycle shall be repeated a sufficient number of times to extend the total time of the test to 360 hours (15 cycles). At the end of the 360 hour period the strap shall be examined and shall show no physical change or damage which would affect subsequent use.

4.4 Rejections.

4.4.1 *Unit inspection.*—Straps failing to meet the requirements of paragraph 4.3.1 shall be rejected.

4.4.2 *Lot inspection.*—Failure of more than one of the five straps in a lot to meet the requirements of 4.3.2 shall be cause for rejection of the entire lot. When one of the five straps in the lot fails, ten additional straps from the same lot shall be subjected to the tests. Failure of one or more of the additional straps shall be cause for rejection of the lot.

4.5 Retests.

4.5.1 Rejected straps shall be replaced with other straps, or shall be reworked to correct the defects, after which all specified tests shall be repeated.

4.5.2 Rejected straps shall not be resubmitted for inspection without furnishing full particulars concerning previous rejection and measures taken to overcome the defects.

4.6 All parts, specimens, or assemblies destroyed in making tests required by this specification shall be in addition to the quantity specified in the contract or purchase order and shall be furnished to the procuring agency without increasing the cost of the contract.

4.7 Final acceptance.—Matériel shall be finally accepted only after it has satisfactorily undergone all inspection and tests prescribed in this and other applicable specifications, and has been prepared for shipment as prescribed in section 5 of this specification. Final acceptance shall be indicated by affixing an official Ordnance Department inspection seal to each interior package.

5. PREPARATION FOR DELIVERY

5.1 Interior packaging.—The straps shall be packaged in accordance with method IA of Specification JAN–P–116.

5.2 Exterior packing.—Interior containers shall be packed in an exterior shipping box as required for overseas shipment in accordance with Specification JAN–P–108.

5.3 Marking.

5.3.1 Interior packages.—Each interior package shall be durably and legibly marked with the following information in such a manner that the markings will not become damaged when the packages are opened:

Quantity _____
Nomenclature: Strap, Wrist Watch, Nylon_
Specification No_____
Ord. Drg. No. B7646909_____
SNL Stock No_____
Manufactured by_____
Manufacturer's Part No_____
Date of Manufacture_____

5.3.1.1 Manufacturer's part No.—The manufacturer's part number marked in the space provided in the interior carton label shall be identical with the manufacturer's engineering production drawing number including applicable dash numbers if the drawing is tabulated and covers more than one part.

5.3.2 Exterior shipping containers.—In addition to any special markings required by the contract or order, shipments for the Army shall be marked in accordance with Specification 100–2; for the Air Force, in accordance with Specification 94–40645; and for the Navy, in accordance with the Navy Shipment Marking Handbook.

6. NOTES

6.1 Use.—Nylon wrist watch straps are intended for use in connection with wrist watches for military personnel.

6.2 The following provisions should be incorporated in each inquiry or invitation for bids:

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T16:03Z
Check the source to verify that this is the current version before use.

Each bidder shall submit to the contracting officer with his bid a molded sample, or samples of the material he proposes to furnish. The sample or samples shall be of the thickness equal to that of the strap and a total of (20) twenty square inches in area. These samples will be tested in accordance with this specification to determine compliance with the specification and suitability for military use. The results of these tests will be evaluated for purposes of consideration in connection with an award of contract.

Notice.—This specification, together with specifications and drawings pertaining to it and bearing a "Notice" of similar restrictions, is intended for use only in connection with procurement by the United States Government; and shall not be reproduced either wholly or in part, except when authorized in connection with Government procurement, nor be used for any other purpose except when specifically authorized by the Chief of Ordnance.

Custodian:

Army—Ordnance Department.

Other interest:

Army—T.

Navy—Sh*MC*S.

Air Force.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T16:03Z
Check the source to verify that this is the current version before use.