MIL-C-63128 (PA)
15 February 1977

MILITARY SPECIFICATION

CARTRIDGES: 40MM, GROUND SMOKE MARKERS,
M713, M715 AND M716; BODY
PART FOR

This specification is approved for use by Picatinny Arsenal, Department of the Army and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification contains requirements not normally covered by the drawings and provides quality assurance provisions for the fabrication of one type of Body for Cartridges: 40MM, Ground Smoke Markers, M713, M715 and M716.

2.1 Issues of documents.-The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-C-5541 - Chemical Films and Chemical Film Materials for Aluminum and Aluminum Alloys
MIL-A-48078 - Ammunition, Standard QualityAssurance Provisions, General Specification For

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-1169- Packaging, Packing and Marking for Shipment of Inert Ammunition Components

DRAWINGS

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, Picatinny Arsenal, Dover, New Jersey 07801 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC: 1310

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:17Z
Check the source to verify that this is the current version before use.

PICATINNY ARSENAL

9258731 - Body

2.2 Other publications.-The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on the date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM B 117-73 - Standard Method of Salt Spray (Fog) Testing

(Application for copies should be addressed to: American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa. 19103).

3. REQUIREMENTS

3.1 Material.-Materials shall be in accordance with the applicable drawings and specifications.

3.2 Part.-The part shall comply with all requirements specified on Drawing (Dwg.) 9258731, all associated drawings, and with all requirements specified in applicable specifications.

3.3 First Article Inspection.-This specification contains technical provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

3.4 Workmanship.-All parts shall be fabricated and finished in a thorough, workmanlike manner. They shall be free of burrs, chips, sharp edges, cracks, unblended radii, surface defects, dirt, grease, rust, corrosion products, and other foreign matter. The cleaning method used shall not be injurious to any parts, nor shall the parts be contaminated by the cleaning agents. All marking and stamping shall be neat and sharply defined.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection and Standard Quality Assurance Provisions.-Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:17Z
Check the source to verify that this is the current version before use.

4.2 Classification of Inspections.-The following types of inspection shall be conducted on this item:

a. First Article Inspection
b. Quality Conformance Inspection

4.3 First Article Inspection

4.3.1 Submission.-The contractor shall submit a first article as designated by the Contracting Officer for evaluation in accordance with the provisions of 4.3.2. The first article sample shall consist of the following items in sample quantities as indicated.

Part Description	Drawings	Quantity
Body	9258731	25 (5 painted)

4.3.2 Inspections to be Performed.-See MIL-A-48078 and Table 1 herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:17Z
Check the source to verify that this is the current version before use.

TABLE I - FIRST ARTICLE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-C-63128 (PA)

PARAGRAPH	TITLE		SHEET OF		DRAWING NUMBER
	Body				see below
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Body (Dwg. 9258731)				
	Prior to painting				
	Examination for defects	20		3.2	4.4.2.1
	after painting				
	Salt spray	5		3.2	4.5.1

NOTES:

Source: https://assist.dla.mil -- Downloaded: 202610-23T02:17Z
Check the source to verify that this is the current version before use.

4.3.3 Rejection.-See MIL-A-48078.

4.4 Quality Conformance Inspection

4.4.1 Inspection Lot Formation.-Inspection lots shall comply with the lot formation provisions of MIL-A-48078.

4.4.2 Examination.-See MIL-A-48078.

a. Sampling plans.-Unless otherwise specified in the Classification of Defects and Test Tables, sampling plans for major and minor defects shall be in accordance with MIL-STD-105, Inspection Level II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:17Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-C-63128 (PA)

PARAGRAPH	TITLE	SHEET 1 OF 2	DRAWING NUMBER
4.4.2.1	Body, prior to painting		9258731
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101.	Diameter of rotating bands		0.40%	3.2	Gage
102.	Concentricity of rotating bands with bourrelet diameter		0.40%	3.2	Gage
103.	Concentricity of diameter rear of rotating bands with bourrelet diameter		0.40%	3.2	Gage
104.	Concentricity of outside diameter, counterbore end, with large inside cavity		0.40%	3.2	Gage
105.	Concentricity of rear counterbore with large inside cavity		0.40%	3.2	Gage
106.	Concentricity of hole with bourrelet diameter		0.40%	3.2	Gage
107.	Depth of base counterbore		0.40%	3.2	Gage
Minor					
201.	Diameter between rotating bands		0.65%	3.2	Gage
202.	Bourrelet diameter		0.65%	3.2	Gage
203.	Width between rotating bands		0.65%	3.2	Gage
204.	Diameter of base counterbore		0.65%	3.2	Gage
205.	Seal cavity diameter		0.65%	3.2	Gage
206.	Total length		0.65%	3.2	Gage
207.	Width of rotating bands		0.65%	3.2	Gage
208.	Distance from front end to rear rotating band		0.65%	3.2	Gage
209.	Body diameter rear of rotating bands		0.65%	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:17Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-C-63128 (PA)

PARAGRAPH	TITLE	SHEET 2 OF 2	DRAWING NUMBER
4.4.2.1	Body, prior to painting		9258731
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
210.	Diameter crimping surface		0.65%	3.2	Gage
211.	Incorrect color		0.65%	3.2	Visual
212.	Evidence of poor workmanship		0.65%	3.4	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:17Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-C-63128 (PA)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9258731
4.4.2.2	Body after painting				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101.	Salt Spray	*	*	3.2	4.5.1

NOTES: *Sampling and rejection shall be in accordance with MIL-C-5541.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:17Z
Check the source to verify that this is the current version before use.

4.4.3 Testing.-Testing is described in the First Article and Quality Conformance Inspection Tables.

4.4.4 Inspection Equipment.-The inspection equipment required to perform the examinations and tests prescribed herein is described in the Paragraph Reference/Inspection Method column in the tables starting with Paragraph 4.4.2.1. The contractor shall submit for approval inspection equipment designs in accordance with the terms of the contract. See Section 6 of MIL-A-48078 and 6.3 herein.

4.5 Test methods and procedures

4.5.1 Salt spray.-This test shall be conducted in accordance with ASTM-B 117-73. Salt solution shall be 5 percent. Parts so tested shall not be returned to the lot.

5. PACKAGING

5.1 Preservation and packaging

5.1.1 Level C.-The body shall be preserved and packaged in accordance with MIL-STD-1169.

5.2 Packing

5.2.1 Level C.-The body preserved and packaged as specified in 5.1.1, shall be packed for shipment in accordance with MIL-STD-1169.

5.3 Marking.-Marking of the carton shall comply with MIL-STD-1169.

5.4 Shipping.-When components from more than one lot are shipped as a carload, each lot shall be kept separate, and the division between lots clearly indicated to prevent mixing of the lots in transit.

6. NOTES

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:17Z
Check the source to verify that this is the current version before use.

6.1 Intended use.-The component covered by this specification is intended for use on Cartridges: 40MM, Ground Smoke Markers, M713, M715 and M716.

6.2 Ordering Data.-See MIL-A-48078.

6.3 Submission of Inspection Equipment Designs for Approval.-See MIL-A-48078. Submit equipment designs as required to Commander, ATTN: DRDAR-QAA-I, ARRADCOM, Dover, New Jersey 07801.

Custodian:
Army-PA

Preparing Activity:
Army-PA

Project Number: 1310-A-099

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:17Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:17Z
Check the source to verify that this is the current version before use.