* The documentation and process conversion measures necessary to comply with this document shall be completed by 2 September 2006.

INCH-POUND

MIL-PRF-19500/355L
2 June 2006
SUPERSEDING
MIL-PRF-19500/355K
3 July 2005

PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, UNITIZED DUAL TRANSISTOR, NPN, SILICON,
TYPES 2N2919, 2N2920, 2N2919L, 2N2920L, 2N2919U, AND 2N2920U,
JAN, JANTX, JANTXV, JANS, JANHC, AND JANKC

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for two electrically isolated, matched NPN silicon transistors as one dual unit. Four levels of product assurance are provided for each device type as specified in MIL-PRF-19500. Two levels of product assurance are provided for die.

1.2 Physical dimensions. See figure 1 (similar to TO-78), figure 2 (surface mount), figure 3 (JANHCA and JANKCA die), figure 4 (JANHCB and JANKCB die).

* 1.3 Maximum ratings, unless otherwise specified, T_C =+25°C.

Type	I_C	V_{CBO}	V_{CEO}	V_{EBO}
	mA dc	V dc	V dc	V dc
All types	30	70	60	6

P_T (1) T_A = +25°C		P_T (2) T_C = +25°C		$R_{\theta JA}$		$R_{\theta JC}$		T_J and T_{STG}
One section	Both sections	One section	Both sections	One section	Both sections	One section	Both sections	
mW	mW	mW	W	°C/W	°C/W	°C/W	°C/W	°C
200	350	300	450	875	500	583	350	-65 to +200

(1) For T_A > +25°C, derate linearly 1.143 mW/°C, one section; 2.000 mW/°C, both sections.
(2) For T_C > +25°C, derate linearly 1.714 mW/°C, one section; 2.571 mW/°C, both sections.

Comments, suggestions, or questions on this document should be addressed to Defense Supply Center, Columbus, ATTN: DSCC-VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dscc.dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at http://assist.daps.dla.mil .

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics of each individual section, unless otherwise specified, T_C =+25°C.

	h_{FE1}		$\|h_{fe}\|$	$V_{CE(SAT)}$
	V_{CE} = 5 V dc I_C = 10 μA dc		V_{CE} = 5 V dc I_C = 0.5 mA dc f = 20 MHz	I_C = 1 mA dc I_B = 100 μA dc
	2N2919 2N2919L 2N2919U	2N2920 2N2920L 2N2920U		
				V dc
Min	60	175	3.0	
Max	240	600	20	0.3

1.5 Primary electrical matching characteristics of each individual section, unless otherwise specified, T_C =+25°C.

	$\frac{h_{FE2-1}}{h_{FE2-2}}$ V_{CE} = 5 V dc I_C = 100 μA dc (1)	$\|V_{BE1} - V_{BE2}\|_1$ V_{CE} = 5 V dc I_C = 10 μA dc	$\|\Delta(V_{BE1} - V_{BE2})_{\Delta TA}\|_1$ V_{CE} = 5 V dc I_C = 100 μA dc T_A = +25°C and -55°C	$\|\Delta(V_{BE1} - V_{BE2})_{\Delta TA}\|_2$ V_{CE} = 5 V dc I_C = 100 μA dc T_A = +125°C and +25°C
		mV dc	mV dc	mV dc
Min	0.9			
Max	1.0	5	0.8	1.0

(1) The larger number will be placed in the denominator.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3, 4, or 5 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3, 4, or 5 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.


DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

(Copies of these documents are available online at http://assist.daps.dla.mil/quicksearch or http://assist.daps.dla.mil or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.




CONNECTION DIAGRAM

Symbol	Dimensions				Notes
	Inches		Millimeters		
	Min	Max	Min	Max	
CD	.335	.370	8.51	9.40	
CD_1	.305	.335	7.75	8.51	
CH	.140	.260	3.56	6.60	
HT	.009	.041	0.23	1.04	
LC	.140	.160	3.56	4.06	
LC_1	.200 TP		5.08 TP		9
LD	.016	.021	.041	0.53	10
LL	See notes 10, 11, and 12				
LU	.016	.019	0.41	0.48	10
L_1		.050		1.27	10
L_2	.250		6.35		10
P	.100		2.54		8
Q		.050		1.27	7
TL	.029	.045	0.74	1.14	5, 6
TW	.028	.034	0.71	0.86	4, 5
r		.010		0.25	
α	45°TP		45°TP		9

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. Tab shown omitted.
4. Lead numbers 4 and 8 are omitted on this variation.
5. Beyond r maximum, TW shall be held to a minimum length of .21 inch (5.33 mm).
6. TL shall be measured from maximum CD.
7. Details of outline in this zone are optional.
8. CD_1 shall not vary more than .010 inch (0.25 mm) in zone P. This zone is controlled for automatic handling.
9. Leads at gauge plane .054 - .055 inch (1.37 - 1.40 mm) below seating plane shall be within .007 inch (0.18 mm) radius of true position (TP) at a maximum material condition (MMC) relative to the tab at MMC. The device may be measured by direct methods or by the gauge and gauging procedures described on gauge drawing GS-1.
10. LU applies between L_1 and L_2. LD applies between L_2 and LL minimum. Diameter is uncontrolled in L_1 and beyond LL minimum.
11. For transistor types 2N2919 and 2N2920, LL is .500 inch (12.70 mm) minimum and .750 inch (19.05 mm) maximum.
12. For transistor type 2N2919L and 2N2920L, LL is 1.500 inches (38.10 mm) minimum and 1.750 inches (44.45 mm) maximum.
13. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 1. Physical dimensions (2N2919, 2N2919L, 2N2920, and 2N2920L).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.




Symbol	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
BL	.240	.250	6.10	6.35
BL_2		.250		6.35
BW	.165	.175	4.19	4.44
BW_2		.175		4.44
CH	.044	.080	1.12	2.03
LH	.014	.034	0.36	0.86
LL_1	.060	.070	1.52	1.78
LL_2	.082	.098	2.08	2.49
LS_1	.095	.105	2.41	2.67
LS_2	.045	.055	1.14	1.39
LW	.022	.028	0.56	0.71

Pin no.	Transistor
1	Collector no. 1
2	Base no. 1
3	Base no. 2
4	Collector no. 2
5	Emitter no. 2
6	Emitter no. 1

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 2. Physical dimensions (2N2919U and 2N2920U) surface mount.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.




NOTES:

1. Chip size ..... .015 x .019 inch ±.001 inch (0.381 x 0.4826 mm ±0.0254 mm).
2. Chip thickness ..... .010 ±.0015 inch (0.254 ±0.0381 mm).
3. Top metal ..... Aluminum 15,000Å minimum, 18,000Å nominal.
4. Back metal ..... A. Gold 2,500Å minimum, 3,000Å nominal.

   B. Eutectic Mount - No Gold.
5. Backside ..... Collector.
6. Bonding pad ..... B = .003 inch (0.0762 mm), E = .004 inch (0.1016 mm) diameter.
7. Passivation ..... Si_3N_4 (Silicon Nitride) 2 kÅ min, 2.2 kÅ nom.

FIGURE 3. Physical dimensions (JANHCA and JANKCA die).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.



NOTES:
1. Die size--------- .018 x .018 inch (0.457 mm x 0.457 mm).
2. Die thickness--- .008 ±.0016 inch (0.203 mm ±0.04 mm).
3. Base pad-------- .0025 inch diameter (0.06 mm).
4. Emitter pad----- .003 inch diameter (0.076).
5. Back metal----- Gold, 6,500 ±1,950Å.
6. Top metal------ Aluminum, 19,500 ±2,500Å.
7. Back side------ Collector.
8. Glassivation--- SiO_2, 7,500 ±1,500Å.

FIGURE 4. Physical dimensions (JANHCB and JANKCB) B version die.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500 and as follows:

h_{FE-1}/h_{FE-2}	Static forward-current-gain-ratio. The matching ratio of the static forward-current transfer ratio of each section.
$R_{\theta JA}$	Thermal resistance junction to ambient.
$R_{\theta JSP(IS)}$	Thermal resistance junction to solder pads (infinite sink mount to PCB).
$\lvert V_{BE1} - V_{BE2} \rvert$	Absolute value of base-emitter-voltage differential between the individual sections.
$\lvert \Delta V_{BE1-2}\ (T1) - \Delta V_{BE1-2}\ (T2) \rvert$	Absolute value of the algebraic difference between the base-emitter-voltage differentials between the individual sections at two different temperatures.

3.4 Interface and physical dimensions. The interface and physical dimensions shall be as specified in MIL-PRF-19500 and on figures 1, 2, 3, and 4.

3.4.1 Lead finish. Lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.5 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and 1.5.

3.6 Electrical test requirements. The electrical test requirements shall be as specified in table I.

3.7 Marking. Marking shall be in accordance with MIL-PRF-19500.

3.8 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4 and tables I and II).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

* 4.2.1 Group E qualification. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table II tests, the tests specified in table II herein that were not performed in the prior revision shall be performed on the first inspection lot of this revision to maintain qualification.

* 4.2.2.1 Group E thermal response. With extremely small junction devices such as this one, a true thermal impedance cannot be measure, only calculated. While “thermal response” has been substituted for “thermal impedance” herein, the terms, units and procedure as essentially unchanged. Each supplier shall submit a thermal response ($Z_{\theta JX}$) histogram of the entire qualification lot. The histogram data shall be taken prior to the removal of devices that are atypical for thermal response. Thermal response curves (from $Z_{\theta JX}$ test pulse time to $R_{\theta JX}$ minimum steady-state time) of the best device in the qual lot and the worst device in the qual lot (that meets the supplier proposed screening limit), or from the thermal grouping, shall be submitted. The optimal test conditions and proposed initial thermal response screening limit shall be provided in the qualification report. Data indicating how the optimal test conditions were derived for $Z_{\theta JX}$ shall also be submitted. The proposed maximum thermal response $Z_{\theta JX}$ screening limit shall be submitted. The qualifying activity may approve a different $Z_{\theta JX}$ limit for conformance inspection end-point measurements as applicable**.** Equivalent data, procedures, or statistical process control plans may be used for part, or all, of the above requirements. The approved thermal response conditions and limit for $Z_{\theta JX}$ shall be used by the supplier in screening and table I, subgroup 2. The approved thermal resistance conditions for $R_{\theta JX}$ shall be used by the supplier for conformance inspection. For product families with similar thermal characteristics based on the same physical and thermal die, package, and construction combination (thermal grouping), the supplier may use the same thermal response curves.

* 4.2.2 JANHC and JANKC die. Qualification shall be in accordance with MIL-PRF-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

* 4.3 Screening (JANS, JANTXV, and JANTX levels only). Screening shall be in accordance with table IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table IV of MIL-PRF-19500)	Measurement	
	JANS level	JANTX and JANTXV levels
(1) 3c	Thermal response, method 3131 of MIL-STD-750	Thermal response, method 3131 of MIL-STD-750
7	Optional	Optional
9	I_{CBO2}, h_{FE3}, $\frac{h_{FE2-1}}{h_{FE2-2}}$	Not applicable
10	48 hours minimum	48 hours minimum
11	I_{CBO2}, h_{FE3}, $\frac{h_{FE2-1}}{h_{FE2-2}}$ ΔI_{CBO2} = 100 percent of initial value or 1 nA dc, whichever is greater. Δh_{FE3} = ±20 percent.	I_{CBO2}, h_{FE3}, $\frac{h_{FE2-1}}{h_{FE2-2}}$
12	See 4.3.1	See 4.3.1
13	Subgroups 2 and 3 of table I herein; ΔI_{CBO2} = 100 percent of initial value or 1 nA dc, whichever is greater; Δh_{FE3} = ±25 percent.	Subgroup 2 of table I herein; ΔI_{CBO2} = 100 percent of initial value or 1 nA dc, whichever is greater; Δh_{FE3} = ±25 percent.
14	Required	Required

(1) Shall be performed anytime after temperature cycling, screen 3a; and does not need to be repeated in screening requirements.

4.3.1 Power burn-in conditions. V_{CB} = 10 - 30 Vdc. Power shall be applied to achieve T_J =135°C minimum and using a minimum P_D = 75% of P_T maximum rated as defined in 1.3. With approval of the qualifying activity and preparing activity, alternate burn-in criteria (hours, bias conditions, TJ, and mounting conditions) may be used for JANTX and JANTXV quality levels. A justification demonstrating equivalence is required. In addition, the manufacturing site's burn-in data and performance history will be essential criteria for burn-in modification approval.

* 4.3.2 Thermal response. For very small junction devices such as this, the term "thermal response" shall be used in lieu of "thermal impedance" although measurements shall be performed the same manner as thermal impedance in accordance with method 3131 of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_H, t_{SW} (V_C and V_H where appropriate). Measurement delay time (t_{MD}) = 70 μs max. See table II, group E, subgroup 4 herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

4.3.3 Screening (JANHC and JANKC). Screening of JANHC and JANKC die shall be in accordance with MIL-PRF-19500, “Discrete Semiconductor Die/Chip Lot Acceptance”. Burn-in duration for the JANKC level follows JANS requirements; the JANHC follows JANTX requirements.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500, and as specified herein. If alternate screening is being performed in accordance with MIL-PRF-19500, a sample of screened devices shall be submitted to and pass the requirements of group A1 and A2 inspection only (table VIb, group B, subgroup 1 is not required to be performed again if group B has already been satisfied in accordance with 4.4.2).

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500, and table I herein.

* 4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VIa (JANS) of MIL-PRF-19500 and 4.4.2.1 herein. Electrical measurements (end-points) and delta requirements shall be in accordance with table I, subgroup 2 and 4.5.8 herein. See 4.4.2.2 for JAN, JANTX, and JANTXV group B testing. Electrical measurements (end-points) and delta requirements for JAN, JANTX, and JANTXV shall be after each step in 4.4.2.2 and shall be in accordance with table I, subgroup 2 and 4.5.8 herein.

* 4.4.2.1 Group B inspection, table VIa (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
B4	1037	V_{CB} = 10 V dc.
B5	1027	V_{CB} = 10 V dc, $P_D \geq$ 100 percent of maximum rated P_T (see 1.3). (NOTE: If a failure occurs, resubmission shall be at the test conditions of the original sample.) Option 1: 96 hours min, sample size in accordance with table VIa of MIL-PRF-19500, adjust T_A or P_D to achieve T_J = +275°C minimum. Option 2: 216 hours min., sample size = 45, c = 0; adjust T_A to achieve T_J = +225°C minimum.

4.4.2.2 Group B inspection, (JAN, JANTX, and JANTXV). Separate samples may be used for each step. In the event of a lot failure, the resubmission requirements of MIL-PRF-19500 shall apply. In addition, all catastrophic failures during CI shall be analyzed to the extent possible to identify root cause and corrective action. Whenever a failure is identified as wafer lot or wafer processing related, the entire wafer lot and related devices assembled from the wafer lot shall be rejected unless an appropriate determined corrective action to eliminate the failures mode has been implemented and the devices from the wafer lot are screened to eliminate the failure mode.

Step	Method	Condition
1	1026	Steady-state life: 1,000 hours minimum, V_{CB} = 10 V dc, power shall be applied to achieve T_J = +150°C minimum using a minimum of P_D = 75 percent of maximum rated P_T as defined in 1.3. n = 45 devices, c = 0. The sample size may be increased and the test time decreased as long as the devices are stressed for a total of 45,000 device hours minimum, and the actual time of test is at least 340 hours.
2	1048	Blocking life, T_A = +150°C, V_{CB} = 80 percent of rated voltage, 48 hours minimum. n = 45 devices, c = 0.
3	1032	High-temperature life (non-operating), t = 340 hours, T_A = +200°C. n = 22, c = 0.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

* 4.4.2.3 Group B sample selection. Samples selected from group B inspection shall meet all of the following requirements:

a. For JAN, JANTX, and JANTXV samples shall be selected randomly from a minimum of three wafers (or from each wafer in the lot) from each wafer lot. For JANS, samples shall be selected from each inspection lot. See MIL-PRF-19500.

b. Shall be chosen from an inspection lot that has been submitted to and passed table I, subgroup 2, conformance inspection. When the final lead finish is solder or any plating prone to oxidation at high temperature, the samples for life test (subgroups B4 and B5 for JANS, and group B for JAN, JANJ, JANTX, and JANTXV) may be pulled prior to the application of final lead finish.

4.4.3 Group C inspection, Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VII of MIL-PRF-19500, and in 4.4.3.1 (JANS) and 4.4.3.2 (JAN, JANTX, and JANTXV) herein for group C testing. Electrical measurements (end-points) and delta requirements shall be in accordance with table I, subgroup 2 and 4.5.8 herein.

* 4.4.3.1 Group C inspection, table VII (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
C2	2036	Test condition E, not applicable to surface mount.
C5	3131	$R_{\theta JA}$ and $R_{\theta JC}$ only, as applicable (see 1.3) and 4.3.2.
C6	1026	1,000 hours at V_{CB} = 10 V dc; power shall be applied to achieve T_J = +150°C minimum and a minimum of P_D = 75 percent of maximum rated P_T as defined in 1.3 n = 45, c = 0. The sample size may be increased and the test time decreased as long as the devices are stressed for a total of 45,000 device hours minimum, and the actual time of test is at least 340 hours.

* 4.4.3.2 Group C inspection, table VII (JAN, JANTX, and JANTXV) of MIL-PRF-19500.

Subgroup	Method	Condition
C2	2036	Test condition E, not applicable to surface mount.
C5	3131	$R_{\theta JA}$ and $R_{\theta JC}$ only, as applicable (see 1.3) and 4.3.2.
C6		Not applicable.

4.4.3.3 Group C sample selection. Samples for subgroups in group C shall be chosen at random from any inspection lot containing the intended package type and lead finish procured to the same specification which is submitted to and passes table I tests herein for conformance inspection. When the final lead finish is solder or any plating prone to oxidation at high temperature, the samples for C6 life test may be pulled prior to the application of final lead finish. Testing of a subgroup using a single device type enclosed in the intended package type shall be considered as complying with the requirements for that subgroup.

4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table IX of MIL-PRF-19500 and as specified in table II herein. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein; delta measurements shall be in accordance with the applicable steps of 4.5.8.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

4.5.2 Testing of units. All specified electrical tests, including end-point tests, shall be performed equally on both sections of the transistor types covered herein, except where the electrical characteristic being evaluated applies to the transistor as a device entity.

4.5.3 Disposition of leads when testing characteristics of each section. During the measurement of the characteristics of each section, the leads of the section not under test shall be open-circuited.

4.5.4 Forward-current-gain ratio. The value for the forward-current-gain ratio for each individual section of a dual unit shall be measured using method 3076 of MIL-STD-750. The forward-current-gain ratio shall be calculated by dividing one of the values by the other. If possible, this ratio shall be measured directly to improve accuracy.

4.5.5 Base-emitter-voltage differential. The base-emitter-voltage differential shall be determined by connecting the emitters of the individual sections together, applying specified electrical test conditions to each individual section in accordance with method 3066 of MIL-STD-750, test condition B, and measuring the absolute value of the voltage between the bases of the individual sections of a dual unit.

4.5.6 Base-emitter-voltage differential change with temperature. The value of the base-emitter-voltage differential shall be measured at the two specified temperatures in accordance with 4.5.5 except that the polarities of the differentials and identities of the individual sections shall be maintained. The absolute value of the algebraic difference between the values at the two temperature extremes shall be calculated. A mathematical formula for this parameter is:

$$|(V_{BE1}(T_1) - V_{BE2}(T_1)) - (V_{BE1}(T_2) - V_{BE2}(T_2))|$$

4.5.7 Noise figure test. Noise figure shall be measured using Quan Tech Laboratories test set model no. 2173C/2181, or equivalent. Conditions shall be as specified in table I.

4.5.8 Delta requirements. Delta requirements shall be as specified below:

Step	Inspection	MIL-STD-750		Symbol	Limit	
		Method	Conditions		Min	Max
1	Collector-base cutoff current	3036	Bias condition D, V_{CB} = 45 V dc	ΔI_{CBO2}	100-percent of initial value or 1 nA dc, whichever is greater.	
2	Forward current transfer ratio	3076	V_{CE} = 5 V dc; I_C = 1 mA dc; pulsed, see 4.5.1	Δh_{FE3}	±25 percent change from initial reading.	

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limit		Unit
	Method	Conditions		Min	Max	
Subgroup 1 2/						
Visual and mechanical examination 3/	2071	n = 45 devices, c = 0				
Solderability 3/ 4/	2026	n = 15 leads, c = 0				
Resistance to solvents 3/ 4/ 5/	1022	n = 15 devices, c = 0				
Temp cycling 3/ 4/	1051	Test condition C, 25 cycles. n = 22 devices, c = 0				
Hermetic seal 4/ 6/ Fine leak Gross leak	1071	n = 22 devices, c = 0				
Electrical measurements 4/		Table I, subgroup 2				
Bond strength 3/ 4/	2037	Precondition T_A = +250°C at t = 24 hours or T_A = +300°C at t = 2 hours n = 11 wires, c = 0				
Decap internal visual (design verification) 4/	2075	N = 4 devices, c = 0				
Subgroup 2						
Collector to base cutoff current	3036	Bias condition D, V_{CB} = 70 V dc	I_{CBO1}		10	µA dc
Emitter to base cutoff current	3061	Bias condition D, V_{EB} = 6 V dc	I_{EBO1}		10	µA dc
Breakdown voltage, collector to emitter	3011	Bias condition D; I_C = 10 mA dc; pulsed (see 4.5.1)	$V_{(BR)CEO}$	60		V dc
Collector to base cutoff current	3036	Bias condition D; V_{CB} = 45 V dc	I_{CBO2}		2	nA dc
Collector to emitter cutoff current	3041	Bias condition D; V_{CE} = 5 V dc	I_{CEO1}		2	nA dc
Emitter to base cutoff current	3061	Bias condition D; V_{EB} = 5 V dc	I_{EBO2}		2	nA dc
Forward-current transfer ratio	3076	V_{CE} = 5 V dc; I_C = 10 µA dc	h_{FE1}			
2N2919, 2N2919L, 2N2919U 2N2920, 2N2920L, 2N2920U				60 175	240 600	
Forward-current transfer ratio	3076	V_{CE} = 5 V dc; I_C = 100 µA dc	h_{FE2}			
2N2919, 2N2919L, 2N2919U 2N2920, 2N2920L, 2N2920U				100 235	325 800	

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limit		Unit
	Method	Conditions		Min	Max	
Subgroup 2 - Continued						
Forward-current transfer ratio	3076	V_{CE} = 5 V dc; I_C = 1 mA dc;	h_{FE3}			
2N2919, 2N2919L, 2N2919U 2N2920, 2N2920L, 2N2020U				150 300	600 1,000	
Base-emitter saturation voltage	3066	Test condition A; I_C = 1.0 mA dc; I_B = 100 µA dc;	$V_{BE(sat)1}$	0.5	1.0	V dc
Collector-emitter saturation voltage	3071	I_C = 1.0 mA dc; I_B = 100 µA dc;	$V_{CE(sat)1}$		0.3	V dc
Forward-current transfer ratio (gain ratio) 6/	3076	V_{CE} = 5 V dc, I_C = 100 µA dc (see 4.5.4)	$\frac{h_{FE2-1}}{h_{FE2-2}}$	0.9	1.0	
Absolute value of base-emitter-voltage differential	3066	Test condition B; V_{CE} = 5 V dc, I_C = 10 µA dc (see 4.5.5)	$\lvert V_{BE1} - V_{BE2} \rvert_1$		5	mV dc
Absolute value of base-emitter-voltage differential	3066	Test condition B; V_{CE} = 5 V dc, I_C = 100 µA dc (see 4.5.5)	$\lvert V_{BE1} - V_{BE2} \rvert_2$		3	mV dc
Absolute value of base-emitter-voltage differential	3066	Test condition B; V_{CE} = 5 V dc, I_C = 1 mA dc (see 4.5.5)	$\lvert V_{BE1} - V_{BE2} \rvert_3$		5	mV dc
Base-emitter-voltage (nonsaturated) (absolute value of differential change with temperature) 7/	3066	Test condition B; V_{CE} = 5 V dc, I_C = 100 µA dc T_A = +25°C and -55°C (see 4.5.6)	$\lvert \Delta V_{BE1} - V_{BE2} \Delta T_A \rvert_1$		0.8	mV dc
Base-emitter-voltage (nonsaturated) (absolute value of differential change with temperature) 7/	3066	Test condition B; V_{CE} = 5 V dc, I_C = 100 µA dc T_A = +125°C and +25°C (see 4.5.6)	$\lvert \Delta V_{BE1} - V_{BE2} \Delta T_A \rvert_2$		1	mV dc
Subgroup 3						
High temperature operation		T_A = +150°C				
Collector to base cutoff current	3036	Bias condition D; V_{CB} = 45 V dc	I_{CBO3}		2.5	µA dc
Low temperature operation		T_A = -55°C				
Forward-current transfer ratio 2N2919, 2N2919L, 2N2919U 2N2920, 2N2920L, 2N2920U	3076	V_{CE} = 5 V dc; I_C = 10 µA dc	h_{FE4}	 20 50		

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limit		Unit
	Method	Conditions		Min	Max	
Subgroup 4						
Small-signal short-circuit input impedance	3201	V_{CE} = 5 V dc; I_C = 1 mA dc; f = 1 kHz	h_{ie}	3	30	kΩ
Small-signal open-circuit reverse voltage transfer ratio	3211	V_{CE} = 5 V dc; I_C = 1 mA dc; f = 1 kHz	h_{re}		1×10^{-3}	
Small-signal open-circuit output admittance	3216	V_{CE} = 5 V dc; I_C = 1 mA dc; f = 1 kHz	h_{oe}		60	μmhos
Small-signal short-circuit forward current transfer ratio (magnitude h_{fe})	3306	V_{CE} = 5 V dc; I_C = 0.5 mA dc; f = 20 MHz	$\lvert h_{fe} \rvert$	3	20	
Open circuit output capacitance	3236	V_{CB} = 5 V dc; I_E = 0 100 kHz ≤ f ≤ 1 MHz	C_{obo}		5	pF
Noise figure	3246	V_{CE} = 5 V dc, I_C = 10 μA dc R_g = 10 kΩ, (see 4.5.7)				
Test 1 Test 2 Test 3		f = 100 Hz f = 1 kHz f = 10 kHz	F1 F2 F3		5 3 3	dB dB dB
Subgroup 5						
Collector to emitter cutoff current	3041	Bias condition D; V_{CE} = 40 V dc	I_{CES}		20	nA dc
Subgroups 6 and 7						
Not required						


1/ For sampling plan see MIL-PRF-19500.
2/ For resubmission of failed test in subgroup 1 of table I, double the sample size of the failed test or sequence of tests. A failure in table I, subgroup 1 shall not require retest of the entire subgroup. Only the failed test shall be rerun upon submission.
3/ Separate samples may be used.
4/ Not required for JANS devices.
5/ Not required for laser marked devices.
6/ The larger number shall be placed in the denominator.
7/ When using table I, subgroup 2 as electrical end-points, this test is only required for JANS end-points.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

* TABLE II. Group E inspection (all quality levels) - for qualification or re-qualification only.


Inspection	MIL-STD-750		Qualification
	Method	Conditions	
Subgroup 1			12 devices c = 0
Temperature cycling (air to air)	1051	Test condition C, 500 cycles	
Hermetic seal	1071		
Fine leak Gross leak			
Electrical measurements		See table I, subgroup 2 and 4.5.8 herein.	
Subgroup 2			45 devices c = 0
Intermittent life	1037	Intermittent operation life: V_{CB} = 10 V dc, 6,000 cycles, adjust device current, or power, to achieve a minimum ΔT_J of +100°C.	
Electrical measurements		See table I, subgroup 2 and 4.5.8 herein.	
Subgroup 4			
Thermal response curves		See 4.2.2.1.	Sample size N/A
Subgroup 5			
Not applicable			
Subgroup 6			3 devices c = 0
Electrostatic discharge (ESD)	1020	Testing is not required for class 3 listing. Testing is required for a non-sensitive listing to prove capability.	
Subgroup 8			45 devices c = 0
Reverse stability	1033	Condition B.	

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.



* FIGURE 5. For each side: Thermal resistance = 875°C/W, Pt = 200mW.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.



* FIGURE 6. Both sides: Thermal resistance = 500°C/W, Pt = 350mW.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The notes specified in MIL-PRF-19500 are applicable to this specification.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead finish (see 3.4.1).

d. Product assurance level and type designator.

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from Defense Supply Center, Columbus, ATTN: DSCC/VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil.

6.4 Suppliers of JANHC die. The qualified JANHC suppliers with the applicable letter version (example JANHCA2N2919) will be identified on the QML.

JANHC and JANKC ordering information		
PIN	Manufacturer	
	43611	34156
2N2919	JANHCA2N2919 JANKCA2N2919	JANHCB2N2919, JANHCB2N2920 JANKCB2N2919, JANKCB2N2920

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.

6.5 Changes from previous issue. The margins of this specification are marked with asterisks to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - CR
Navy - EC
Air Force - 11
NASA - NA
DLA - CC

Review activities:
Army - AR, MI, SM
Navy - AS, MC
Air Force - 19, 99

Preparing activity:
DLA - CC

(Project 5961-2006-006)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil .

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:40Z
Check the source to verify that this is the current version before use.