INCH-POUND

MIL-C-70678 (AR)
AMENDMENT 3
18 February 1992
SUPERSEDING
AMENDMENT 2
31 MAY 1991

MILITARY SPECIFICATION

CASE, PROJECTILE BURSTER, XM216 (M216)

This Amendment forms a part of Military Specification MIL-C-70678 (AR), dated 14 January 1988, and is approved for use by the U.S. Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

Title: Add "(M216)" make this change wherever else the nomenclature appears in the specification.

1.1, line 3: Change "XM722" to "M722" and make this change wherever else the nomenclature appears in the specification.

PAGE 2

* 2.2, Delete "ASTM E18 ... Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials"

PAGE 4

* Add new paragraph 3.7 as follows:

"3.7 Hydrotest. Prior to air leak testing selected burster casings shall be able to withstand the hydrostatic test load specified on dwg. 9390728 without cracking, leakage, rupture or permanent deformation when tested in accordance with 4.5.5.

AMSC N/A

FSC 1310

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:50Z
Check the source to verify that this is the current version before use.

* 4.5.4 Delete in its entirety.

PAGE 12

* Add new paragraph 4.5.5 as follows:

"4.5.5 Hydrostatic test. After final machining but prior to the air leak test in 4.5.2, burster casings (manufactured from forgings only) supplied in accordance with Table I and 4.4.3.5 shall be tested using equipment capable of performing the test accurately and consistently. During the test, the pressure will be applied gradually until the required minimum pressure is reached and held for five (5) seconds, minimum. The equipment shall be calibrated prior to the start of each day's operation and at intervals of not over four (4) hours of continuous operation. It shall also be calibrated prior to restarting the operation after a layoff of three (3) hours or more. If it has been found that the equipment is out of calibration in such a direction that the pressure was actually lower than required by the test, the casings tested since the last satisfactory calibration shall be retested after the calibration error has been corrected. Casing rupture, cracking, leakage or bulging during the test (attributable to poor mechanical properties of the raw material) shall be cause for rejection of all material from the applicable heat of steel. Failure attributable to the production process shall be cause for rejection of all casings produced that day. The test fixture shall not restrict the casing from expanding longitudinally or radially under pressure. Protective barriers should be installed to shield operators from metal fragments which may come from defective casings that fail the test. Examination should be made of all hydrotest plugs after a casing is blown during testing. Badly nicked or damaged plugs may cause destruction of acceptable items. After successfully passing the hydrotest but prior to the air leak test, excess water shall be removed from the burster casings and each casing shall be dried at 250 degrees F, minimum for 20 minutes, minimum. Casings which have been hydrotested shall not be returned to the production lot."

PAGE 13

* Add new paragraph 6.7 as follows:

"6.7 Tension test specimen preparation. It is recommended that a final finish of 60 to 125 be machined on the outside diameter of the specimens for accurate test results."

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:50Z
Check the source to verify that this is the current version before use.

The margins of this amendment are marked with an asterisk or vertical lines to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity
Army-AR

(Project 1310-A505)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:50Z
Check the source to verify that this is the current version before use.