MIL-C-60607 (MU)
30 September 1966
SUPERSEDING
FA-PD-1824
7 July 1961

MILITARY SPECIFICATION

CHIPBOARD, WAD MATERIAL

1. SCOPE

1.1 This specification covers one type of chipboard used as wad material.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

SPECIFICATION

FEDERAL

UU-P-31 - Paper, General Specifications and Methods of Testing

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

FSC 8135

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:48Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Material. Chipboard shall be made of uncoated and unlined reworked scrap paper.

3.2 Thickness. Unless otherwise specified, the chipboard shall be 0.030 to 0.033 inch thick (see 4.3).

3.3 Basic weight. The basis weight in pounds per 1000 feet length, 7/16 inch width, shall be 1.2 pounds plus or minus 0.12 pound per mil, thickness, (see 4.3).

3.4 pH value. The pH of hot water extract of the chipboard shall be 6.5 plus or minus 1.5 (see 4.3).

3.5 Ash content. The ash content shall be not more than 7 percent (see 4.3).

3.6 Combustibility. The chipboard shall continue to burn after the burner is removed (see 4.4).

3.7 Punchability. There shall be no tearing or chipping at the edges of the disc, except that some fibers extending beyond the edges of the disc are permissible at the bottom of cut (see 4.5).

3.8 Width. Unless otherwise specified, the chipboard shall be 7/16 inch plus or minus 1/64 inch wide.

3.9 Color. The chipboard shall be natural (no coloring additives).

3.10 Workmanship. The chipboard shall be free from any imperfections which may impair its serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:48Z
Check the source to verify that this is the current version before use.

4.2 Sampling for lot acceptance.

4.2.1 Inspection lot. All packages or reams offered for delivery at one time shall be considered a lot for purposes of inspection.

4.2.2 Sampling for examination. A random sample of chipboard shall be selected from each lot offered in accordance with MIL-STD-105 at inspection level II. The acceptable quality level shall be 1.5 percent defective.

4.2.3 Sampling for test. A random sample of chipboard shall be selected from each lot in accordance with MIL-STD-105 at inspection level L-8.

4.3 Test procedures. Each of the sample chipboards selected in accordance with 4.2.3 shall be tested in accordance with methods specified in UU-P-31.

Tests	Methods
Thickness	173
Basic weight	110
pH	200
Ash content	202

4.4 Combustibility. A six inch sample shall be held horizontally with forceps and a Meker or Bunsen burner applied for 3 seconds, then removed and observed for compliance with 3.6.

4.5 Punchability. Discs shall be punched out from a 24 inch specimen on a Tatum #70 or similar paper punch. The discs shall be taken approximately one inch apart. Examine punched out discs under a binocular microscope (30X) for compliance with 3.7.

5. PREPARATION FOR DELIVERY

5.1 Packaging - Level C. Unless otherwise specified (see 6.2), the chipboard shall be furnished in commercial rolls, 15 inches in diameter.

5.2 Packing - Level C. Unless otherwise specified (see 6.2), the chipboard packaged as in 5.1 shall be delivered in standard commercial containers so constructed as to insure acceptance by common or other carriers for safe transportation at the lowest rate to the point of delivery.

5.3 Marking. Interior and exterior containers shall be marked in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:48Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The chipboard is intended for use as a wad material in a blank rifle grenade and small arms cartridge.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Level of packaging and packing required (see 5.1 and 5.2).

Custodian:
Army - MU

Preparing activity:
Army - MU

Project No. 8135-A030

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:48Z
Check the source to verify that this is the current version before use.

To detach this form, cut along this line

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity.

SPECIFICATION

ORGANIZATION	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD FORM 1 OCT 64 1426

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:48Z
Check the source to verify that this is the current version before use.