GG-E-916F
15 June 1987
SUPERSEDING
Int. Fed. Spec.
GG-E-00916E (DSA-DM)
April 6, 1973 and
GG-E-916D
26 August 1957

FEDERAL SPECIFICATION

EXPLORERS, DENTAL; EXPLORER-PROBE, DENTAL

This specification is approved by the Commissioner, Federal Supply Services, General Services Administration, for the use of all Federal Agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers explorers and explorer-probe combination instruments for dental use.

1.2 Classification. Dental instruments covered by this specification shall be of the following types, classes and numbers, as specified (see 6.1):

Type I. General Purpose
Class 1 - One Piece, Single-Ended
Explorer No. 6
Explorer No. 17
Explorer No. 23

Class 2 - Two Piece, Single-Ended
Explorer No. 6
Explorer No. 17
Explorer No. 23

AMSC N/A FSC 6520

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Directorate of Medical Materiel, DPSC-RST, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:53Z
Check the source to verify that this is the current version before use.

Class 3 - Three Piece, Double-Ended
Explorer No. 2

Type II. Endodontic
Class 1 - One Piece, Double-Ended
Explorer No. DG 16.

Class 3 - Three Piece, Double-Ended
Explorer No. DG 16.

Type III. Explorer-Probe Combination
Class 3 - Three Piece, Double-Ended
Explorer No. 23/Probe No. 4

2. APPLICABLE DOCUMENTS

2.1 Specifications, standards, and drawings. The following specifications, standards, and drawings of the issue in effect on the date of invitations for bid or requests for proposal, form a part of this specification to the extent specified herein:

Federal Specifications

GG-I-526	Instruments, Dental and Surgical; General Specifications.
PPP-B-566	Boxes, Folding, Paperboard.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Boxes, Shipping, Fiberboard.
PPP-B-676	Boxes, Setup

Federal Standards

FED-STD-66 - Steel, Chemical Composition and Hardenability.
FED-STD-151 - Metals; Test Methods.
FED-STD-123 - Marking for Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal specifications, standards, and commercial item descriptions as outlined under General Information in the Index of Federal Specifications, Standards and Commercial Item Descriptions. The Index, which includes cumulative bimonthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, US Government Printing Office, Washington, DC 20402.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:53Z
Check the source to verify that this is the current version before use.

(Copies of listed federal and military standards, specifications, and Commerical Item Descriptions (CIDs), listed in the Department of Defense Index of Specifications and Standards (DoDISS), should be obtained from the DoD Single Stock Point, Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120. Copies of industry association documents should be obtained from the sponsor. Copies of all other listed documents should be obtained from the contracting activity or as directed by the contracting activity.)

(Federal Government activities may obtain copies of Federal standardization documents and the Index of Federal Specifications, Standards, and Commercial Item Descriptions from established distribution points in their agencies.)

Military Specifications

MIL-P-116	Methods of Preservation.
MIL-L-10547	Liners, Case, and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible.

Military Standards

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.
MIL-STD-147	Palletized Unit Loads.
Mil-STD-794	Parts and Equipment, Procedures for Packaging of.

DRAWINGS

DEFENSE PERSONNEL SUPPORT CENTER (DPSC)

23000	Explorers, Dental, No. 2, No. 6, No. 17, and No. 23.
24332	Explorers, Dental, Endodontic DG 16.
24504	Explorer-Probe, Dental.

(Copies of specifications, standards,and drawings required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or requests for proposal shall apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:53Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

B 135	Specification for Seamless Brass Tube.
E 18	Tests for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials.
E 92	Tests for Vickers Hardness of Metallic Materials.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA. 19103.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libaries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification takes precedence. Nothing in this specification, however supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 General requirements. The instruments shall be in accordance with the applicable requirements of GG-I-526 and as specified herein.

3.1.1 Drawings. The drawings forming a part of this specification are specification control drawings. The supplier shall be responsible for preparing his own shop drawings. Where tolerances prescribed could cumulatively result in improper design, the supplier shall provide a product with dimensions within the tolerances prescribed on the drawings to insure proper design and function of the item. No deviation from the prescribed dimensions or tolerances is permissible without prior approval of the contracting officer.

3.2 Material. The instruments shall be fabricated from materials conforming to the composition as specified in Table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:53Z
Check the source to verify that this is the current version before use.

TABLE I. Materials

Type I, class 1 (One piece, single-ended)	Explorer No. 6,17,23	Class 4, 420, 440A
Type I, class 2 (Two piece, single-ended)	Explorer No. 6,17,23	
Operative end		Class 3, Type 302, or Class 5, Type 17-7PH.
Handle A		Class 3, Type 302, 303, 304 or AISI Type 430F (In accordance with FED-STD-66 for composition only).
Handle B		Class 8, Alloy 360, free cutting brass or Alloy 330 of ASTM B 135 (for composition only).
Type I, class 3 (Three piece, double-ended)	Explorer No. 2	
Operative ends		Class 3, Type 302 or Class 5, Type 17-7PH.
Handle		Class 3, Type 302, 303, 304 or Class 4, Type 416 or AISI Type 430F (In accordance with FED-STD-66 for composition only).
Type II, class 1 (One piece, double-ended)	Explorer No. DG 16	Class 4, Type 420, 440A

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:53Z
Check the source to verify that this is the current version before use.

TABLE I. Materials (continued)

Type II, class 3 (Three piece, double-ended)	Explorer No. DG 16	
Operative ends		Class 3, Type 302, or Class 5, Type 17-7 PH.
Handle A, B, C		Class 3, Type 302, 303, 304, or Class 4 Type 416, or AISI Type 430F (In accordance with FED-STD-66 for composition only).
Type III, class 3 (Three piece, Operative end double-ended)	Explorer No. 23/ Probe No. 4	
(Explorer end)		Class 3, Type 302, or Class 5, Type 17-7 PH
(Probe end)		Class 3, Type 302, 303, 304 or Class 4, Type 420.
Handle A, B, C		Class 3, Type 302, 303, 304 or Class 4, Type 416, or AISI Type 430F (In Accordance with FED-STD-66 for composition only).
Handle D		Class 8, Alloy 360, Free cutting Brass, or Alloy 330 of ASTM B 135 (for composition only).

3.3 Hardness. After proper stress relieving and passivation, the Rockwell hardness of the operative ends and shanks shall be as specified in Table II. Hardness shall be determined as specified in 4.4.2.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:53Z
Check the source to verify that this is the currenversion before use.

TABLE II. Hardness

Type I, Class 1 and Type II, Class 1 (One piece explorers)	
Operative end	C50 to C56
Shank	C40 to C50
Type I, Class 2 and Class 3, and Type II, Class 3 (Two and three piece explorers)	
Operative end and shank (Type 302)	C43 to C49
Operative end and shank (Type 17-7PH)	C43 to C49
Type III, Class 3 (Three piece explorer /probe)	
Explorer end:	
Operative end and shank (Type 302)	C43 to C49
Operative end and shank (Type 17-7PH)	C43 to C49
Probe end:	
Operative end and shank (Type 302, 303, 304)	C45 to C50
Operative end and shank (Type 420)	C45 to C50
Operative end and shank (Type 440A)	C52 to C56

3.4 Style, design, and dimensions. Type I explorers shall be general purpose dental explorers suitable for use in examining tooth structure and in exploring for periodontal pockets. Type II explorers shall be suitable for exploration and debridement of dental pulp chambers and root canals during endodontic procedures. Type III explorer/probe combination shall be a double-ended instrument having a Number 23 explorer at one end and a bin-angle periodontal probe, No. 4, at the other end. The explorer/probe shall be suitable for use in diagnosing dental caries and periodontal disease. The probe shall be suitable for use in measuring the depth of periodontal pockets and shall have dark, contrasting circumferential bands from 3 to 6 and 9 to 12 millimeters so as to graphically depict pocket depth. The instruments shall be of the type, class, and number, as specified herein. The style, design, and dimensions of the instruments shall conform to the Defense Personnel Support Center (DPSC) drawing specified in Table III for the applicable type, class, and number. Instruments shall be furnished with any of the handle designs as specified on the applicable drawing.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:53Z
Check the source to verify that this is the currentversion before use.

TABLE III. Type, Class, Number, and Drawing

Type	Class	Instrument Number	DPSC Drawing
I	1 or 2	6	23000
I	1 or 2	17	23000
I	1 or 2	23	23000
I	3	2	23000
II	1 or 3	DG 16	24332
III	3	23/4	24504

3.5 Construction. Type I explorers shall be one piece (class 1), two piece (class 2), single-ended or three piece (class 3), double-ended instruments. Type II explorers shall be one piece (class 1) or three piece (class 3), double-ended instruments. Type III instruments shall be three piece (class 3), double-ended instruments.

3.5.1 One piece instruments. The handles of one piece explorers (Type I, Class 1 or Type II, Class 1) shall be octagonal in cross-section and shall have a serrated or smooth finish, except as specified herein. Serrated handles shall have a smooth front face for identification marking purposes. Serrations shall be fillet or notched-type serrations. Handles shall be straight.

3.5.2 Two or three piece instruments. The handles of two or three piece instruments (Type I, Class 2; Type I, Class 3; Type II, Class 3; or Type III, Class 3) shall be one piece, solid or hollow construction, as specified on the applicable drawing for the particular handle style and design. The finger grip portion of the handles shall be finely serrated or fine diamond knurled. The operative ends shall be firmly and permanently secured to the handle.

3.6 Deflection. Explorer operative ends shall show no more than 1/4 degree permanent deflection following a bend of 8 degrees (minimum); no more than 2 degrees permanent deflection following a bend of 10 degrees (minimum); and no sign of rupture or fracture following a bend of 20 degrees (minimum), when tested as specified in 4.4.3.

3.7 Ductility. Explorers (operative ends) manufactured from class 3 (type 302) or class 5 (type 17-7PH) shall withstand a minimum of two 90 degree cold bends, with no signs of rupture or fracture, when tested as specified in 4.4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:53Z
Check the source to verify that this is the current version before use.

3.8 Finish.

3.8.1 Operative ends and shanks. Operative ends and shanks shall have a mirror or bright finish. The operative ends of explorers shall be properly shaped and tapered to a fine point. The millimeter (mm) markings of the probe shall be sharply defined and shall be of uniform width. The circumferential bands of the probe shall extend completely around the periphery of the operative end. The operative tip of the probe shall be rounded and polished. Operative ends shall be free of defects such as coarse grind marks, cracks, burrs, or other defects when viewed as specified in 4.3.1.

3.8.2 Handles. Smooth handles of one piece instruments shall have a bright polished finish. Serrated handles of one piece instruments and handles of two or three piece instruments (except for the finely serrated or fine knurled finger grip portion) shall have a mirror or bright polished finish. Serrated or knurled portions shall be free of barbs. Serrations or knurling shall be uniform and complete.

3.9 Corrosion resistance. One piece instruments or handles fabricated from martensitic stainless steel (Class 4, Type 440A, 420 or 416) or ferritic stainless steel (AISI Type 430F) shall meet the copper sulfate requirements of GG-I-526 when tested in accordance with 4.4.5.1. The complete instrument shall meet the boil test requirements of GG-I-526, when tested in accordance with 4.4.5.2.

3.10 Identification marking. Instruments, shall be permanently and legibly marked in accordance with GG-I-526 and as specified herein. Each instrument shall be marked with the applicable instrument number. All markings shall be on the smooth face of the handle (one piece, octagonal handle) and on the smooth portion of the handle (two and three piece, round handle). Each instrument hall be marked with the name or registered trademark of the manufacturer (and contractor, if other than the manufacturer). Each instrument of foreign manufacturer (other than the U.S.) shall be marked with the word "stainless". As an alternate to the word "stainless", the use of a registered trade name identifying the steel as stainless is acceptable provided prior approval is received from the cognizant contracting officer (see 6.1).

3.11 Workmanship. Instruments shall be uniformly and symmetrically tapered, smoothly finished, and shall be free from defects which detract from their appearance or impair their serviceability, proper functioning, and intended use. On two or three piece instruments, the interface of shanks and handles shall be smoothly blended with no crevices evident.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:53Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificates of quality. Certificates of quality, supplied by the manufacturer of the components or materials, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The Certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the NSN, the Item Identification, the name of the components or materials, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Quality conformance inspection. The examinations and tests required to assure conformance of those items or lots of items to be offered for acceptance are classified as specified in tables IV and VI (see 4.2.1 and 4.3) and table VI (see 4.2.2).

4.2.1 Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105. The inspection levels and acceptable quality levels (AQLs) shall be as indicated in table IV. The unit of product for examination purposes shall be one instrument.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:53Z
Check the source to verify that this is the current version before use.

TABLE IV. Examination Criteria

Type defect	Inspection Level	AQL (Percent Defective)
Major A	II	1.0
Major B	S-2	1.5
Minor A	II	2.5
Minor B	S-2	4.0

4.2.2 Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and table V, except that the acceptance number shall be zero for all sample sizes. The unit of product for test purposes shall be one instrument.

TABLE V. Test Criteria

Component	Characteristic	Requirement	Test procedure	Inspection level
Entire Instrument	Chemical Composition	3.2	4.4.1	see 4.2.3
Operative end and shank	Hardness	3.3	4.4.2	S-2
Explorer operative end	Deflection	3.6	4.4.2	S-2
Explorer operative end (class 3 and class 5 material)	Ductility	3.7	4.4.4	S-2
Entire instrument or handles (see 3.9)	Copper sulfate	3.9	4.4.5.1	S-2
Entire Instrument	Boil test	3.9	4.4.5.2	S-2

4.2.3 Sampling of raw materials. A sufficient quanitity of each lot of raw steel used in the fabrication of the instruments shall be selected for chemical analysis.

4.2.4 Sample unit usage. Where feasible, the same sample unit shall be used for the determination of two or more test characteristics.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:53Z
Check the source to verify that this is the current version before use.

4.3 Examination. The instruments shall be examined to determine compliance with the requirements contained in this specification. Examination shall be conducted as specified in 4.2.1 Any instrument in the sample containing one or more defects shall be rejected, and if the number of defective instruments in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected. The instruments shall be examined for defects including, but not limited to, those listed in Table VI.

TABLE VI. Classification of Defects

Categories	Defects
Critical	None defined.
Major A:	
101	Style and design not as specified for the applicable type, class and number.
102	Construction not as specified for the applicable type, class and number.
103	Operative end finish not as specified.
104	Operative end not free of coarse grind marks, cracks, burrs, or other imperfections.
105	Operative end working tip bent or not tapered to fine point for explorers, rounded end for probe.
106	Operative ends not uniformly and symmetrically tapered.
107	Circumferential bands of probe missing or not uniform, not dark or not contrasting.
Major B: 151	Operative end and shank dimensions not as specified.
Minor A:	
201	Handle finish not as specified.
202	Identification marking not present, not properly located, illegible, or incomplete.
203	Finish of handle not free of coarse grind marks.
204	Instrument not free from dirt, oil, compound, or foreign matter.
205	Handles not straight.
Minor B:	
251	Dimensions (other than 151) not as specified on applicable drawing.
252	Handle serrations or knurling not as specified.
253	Handle serrations or knurling either not uniform or not complete.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:53Z
Check the source to verify that this is the current version before use.

4.3.1 Examination under magnification. The instruments shall be examined under four power (4X) magnification for the following defects: Defects 103, 104, and 105. Examination under magnification shall include, but shall not be limited to, the defects listed herein.

4.4 Tests. Tests shall be conducted to determine compliance with the requirements of this specification.

4.4.1 Chemical composition. In the absence of certificates of quality for the metallic raw material, chemical analysis shall be conducted in accordance with method 111 or 112 of FED-STD-151. In case of dispute, method 111 shall govern.

4.4.2 Hardness. Hardness shall be determined in accordance with ASTM Designation E18 (Rockwell) or E92 (Vickers or Diamond Pyramid).

4.4.3 Deflection Tests. For Type I, class 1 and 2, Numbers 6 and 23 explorers, Type II explorers, and the explorer end of Type III explorer-probe, the first 5/32 inch of the operative end (distal end) of the explorer tip shall be clamped by means of a hemostatic forceps. For Type I, class 1 and 2, Number 17 explorer, the forceps shall grip the 105 degree bend of the operative end. The tip shall be bent back (away from the handle in the direction the tip would deflect during normal usage) 8 degrees (minimum) and then measured for permanent deflection after release. The same instrument shall then be subjected to a bend of 10 degrees (minimum) in the same manner and then measured for permanent deflection after release. The same instrument shall then be subjected to a bend of 20 degrees (minimum) in the same manner and then examined for rupture or fracture after release. Examination for rupture or fracture shall be under a minimum of 30 power (30X) magnification. Test shall be conducted at room temperature.

4.4.4 Ductility test. The first 1/4 inch of the operative end (distal end) of the instrument shall be clamped in a vise or other suitable device, the jaws of which shall be rounded to a radius of 1/16 inch. The instrument operative end shall be bent back and forth over this radius at a uniform rate. Each 90 degrees of travel shall be considered one bend. Test shall be conducted at room temperature. Examination for rupture or fracture shall be under a minimum of 30 power (30X) magnification.

4.4.5 Corrosion tests.

4.4.5.1 Copper sulfate test. The copper sulfate test shall be conducted in accordance with GG-I-526.

4.4.5.2 Boil test. The boil test shall be conducted in accordance with GG-I-526.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:53Z
Check the source to verify that this is the current version before use.

4.5 Inspection of packaging. The sampling and inspection of the preservation and interior package marking shall be in accordance with groups A and B quality conformance inspection requirements of MIL-P-116. The sampling and inspection of the packing and marking for shipment and storage shall be in accordance with the quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or C, as specified (see 6.1).

5.1.1 Level A.

5.1.1.1 Cleaning. Instruments shall be cleaned in accordance with MIL-P-116.

5.1.1.2 Drying. Instruments shall be dried in accordance with MIL-P-116.

5.1.1.3 Preservative applications. Preservatives shall not be used.

5.1.1.4 Unit package. Each instrument shall be mounted on a cardboard stiffener with the operative end inserted in a block of rigid styrofoam and the complete unit and stiffener protected with a plastic shrink wrap. The unit shall be further packaged in accordance with MIL-P-116, method IC-1. As an alternate, each instrument shall be packaged in a rigid plastic tube having a metal screw cap or a friction plastic plug type closure. The instrument shall be immobilized and cushioned within the tube in such a manner to prevent damage to the operative ends. Closure shall be as specified in the applicable box specification.

5.1.1.5 Intermediate package. Twelve instruments of one type, class and number only shall be packaged in a box conforming to PPP-B-566, PPP-B-636, class domestic or PPP-B-676. Closure shall be as specified in the applicable box specification.

5.1.2 Level C. The level C preservation for instruments shall conform to the MIL-STD-794 requirements for this level.

5.2 Packing. Packing shall be level A, B or C, as specified (see 6.1).

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:53Z
Check the source to verify that this is the currentversion before use.

5.2.1 Level A. Twelve intermediate packages containing instruments of one type, class and number only shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-601, overseas type, PPP-B-621, class 2 or PPP-B-636, class weather-resistant. Closure and strapping shall be as specified in the applicable box specification.

5.2.1.1 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall be as specified in the liner specification. Case liner shall not be required for fiberboard boxes. Each fiberboard box shall be waterproofed as specified in PPP-B-636.

5.2.2 Level B. Twelve intermediate packages containing instruments of one type, class and number only shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-601 domestic type, PPP-B-621, class 1, or PPP-B-636, class domestic. Closure shall be as specified in the applicable box specification.

5.2.3 Level C. Twleve intermediate packages containing instruments of one type, class and number only shall be packed in accordance with the requirements of MIL-STD-794 for level C.

5.2.4 Packing variation permitted. If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which will insure safe delivery to destination.

5.2.5 Unitized loads. Unitized loads, commensurate with the level of packing specified in the contract or order, shall be used whenever total quantities for shipment to one destination exceed 250 pounds or cubic feet. Loads shall be unitized on pallets conforming to MIL-STD-147. Quantities less than 20 cubic feet need not be unitized. Pallet loads including the pallet shall not exceed 54 inches in height, 48 inches in width, and 40 inches in length. Pallet shall conform to Type IV or Type V.

5.2.5.1 Levels A and B. Instruments packed as specified in 5.2.1 and 5.2.2 shall be unitized on pallets as specified in 5.2.5.

5.2.5.2 Level C. Instruments packed as specified in 5.2.3 shall be unitized as specified in MIL-STD-794.

5.3 Marking.

5.3.1 Civil agencies. Unless otherwise specified, markings for shipment shall be as specified in FED-STD-123.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:53Z
Check the source to verify that this is the currentversion before use.

5.3.2 Military requirements.

5.3.2.1 Levels A, B, and C. Each unit pack, intermediate package, exterior container and unitized load shall be marked as specified in MIL-STD-129.

5.4 General.

5.4.1 Exterior container. Exterior container (see 5.2.1, 5.2.2 and 5.2.3) shall be of minimum tare and cube consistent with the protection required and shall contain equal quantities of identical stock numbered items to the greatest extent practicable.

5.4.2 Packaging inspection. The inspection of these packaging requirements shall be in accordance with 4.5.

6. NOTES

6.1 Ordering data.

6.1.1 Acquisition requirements. Acquisition documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type, class, and number desired (see 1.2).
(c) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(d) Approval of tradename, if applicable (see 3.10).

6.2 National Stock Number (NSN) coverage. This specification covers the following items appearing in the Federal Supply Catalog:

National Stock Number	Item Identification
6520-00-083-6403	EXPLORER, DENTAL, ENDODONTIC, No. DG 16
6520-01-093-0168	EXPLORER, DENTAL, No. 2
6520-00-528-0000	EXPLORER, DENTAL, No. 6
6520-00-528-0005	EXPLORER, DENTAL, No. 17
6520-00-528-1000	EXPLORER, DENTAL, No. 23
6520-01-187-0141	EXPLORER-PROBE, DENTAL, Combination, No. 23 Explorer, Probe: Double-ended.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:53Z
Check the source to verify that this is the currentversion before use.

6.3 Subject term (key word) listing.

Dental Explorer
Endodontic Explorer No. DG-16
Explorer No. 2,6,17, 23
Periodontal Explorer-Probe

MILITARY INTERESTS:

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review Activities:
Army - MD
Navy - MS
Air Force - 03

Civil Agency Coordinating Activities:
VA-OSS
PHS
FDA-MPQAS

05379

PREPARING ACTIVITY:

DoD - MB

AGENT:

DLA-DM

Project No. 6520-1856

Location: NCR Disk #1

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:53Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS. In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE. This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 4966 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
ATTN: DPSC-ATTS
2800 South 20th Street
Philadelphia, Pennsylvania 19101-8419

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:53Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions - Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
GG-E-916F	Explorers, Dental; Explorers-Probe Dental

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil/ -- Downloaded: 2026-03-28T11:58Z
Check the source to verify that this is the correct version before use.