FEDERAL SPECIFICATION

LEATHER, CATTLEHIDE, PACKING, VEGETABLE-TANNED, CHROME-TANNED, CHROME-VEGETABLE RETANNED

This amendment, which forms a part of Federal Specification KK–L–164, dated June 23, 1964, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 1

Paragraph 1.2.1, line 2, after "tannages." Add: "and treatments." Under "Tannage III." Add: "Treatment A—Mildew resistant treated" and "Treatment B—Untreated."

PAGE 2

Paragraph 3.4, Delete first sentence in its entirety and substitute the following:

The trim of the leather shall conform with the definition of "bend" or "belting butt bend" as listed under "Definition of Terms" in KK–L–311."

Paragraph "3.5 Color": Delete in its entirety.

PAGE 3

Table III, under column headed by "Temperature":

Delete "70° C." and substitute "22±2° C."

Delete "100° C." and substitute "100±1° C."

Delete "95° C." and substitute "95±1° C."

Paragraph 3.7.1, Delete in its entirety and substitute: "3.7.1 Fungicide treatment. When treatment A leather is specified the leather shall be treated with the fungicide paranitrophenol. The leather shall contain 0.18 to 0.70 percent fungicide based on the dry weight of the leather when tested as specified in 4.3."

Paragraph 3.7.2, after title, delete paragraph in its entirety and substitute the following: "The leather shall be non-corrosive when tested as specified in 4.3."

Add the following new paragraph: "3.9 Workmanship. The finished leather shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels."

PAGE 4

Paragraph 4.2, line 3: after "STD–105" add "and KK–L–311."

Paragraph 4.2.1: Delete title and paragraph in their entirety and substitute the following: "4.2.1 Inspection of the end item. The sampling procedure for visual and dimensional examinations shall be in accordance with KK–L–311. The classification of defects found during these examinations shall be in accordance with the lists shown in 4.2.1.1 and 4.2.1.2. The sample unit for these examinations shall be one bend or belting butt bend. The lot size shall be expressed in terms of one bend or belting butt band."

Paragraph 4.2.1.2: Delete "Thickness" and all references thereto. At the end of the paragraph add the following: Under "Examine" add "Marking." Opposite "Marking" under "Defect" column, add "Omitted."

Paragraph 4.2.1.3—Delete paragraph in its entirety.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:57Z
Check the source to verify that this is the current version before use.

PAGE 5

Paragraph 4.3: Delete title and paragraph up to subparagraph "a" and substitute the following: "End item testing. The methods of testing specified in KK–L–311, wherever applicable and as listed in table V shall be followed. Sampling procedure and location from which the sample unit is to be obtained shall be in accordance with KK–L–311. All tests reports shall contain the individual values utilized in expressing the final result. The lot shall be rejected if any one of the following conditions exists."

Subparagraph "c": Delete paragraph in its entirety and substitute the following: "c. Any composite value fails to meet the specified requirement."

Table V: Under "Sample unit" opposite "Shrinkage temperature" insert "x", and delete "x" applicable to the characteristic under "Sample average." In "characteristic" column under "Tannage [1]" add "Thickness". Opposite thickness insert the following in the applicable columns: "3.6.1 1011 × —". Under "Requirement applicable to" delete "Sample average" and substitute "Composite." Under "Test Method" column, make the following changes: Delete "7011 [2]" and substitute "4.3.5"; delete "ASTM D–1611" and substitute "ASTM D–1611 [2]"; delete "6311" and substitute "6341". At the bottom of "Table V" delete footnotes "2" and "5" in their entireties and substitute the following: "5 Except that a 60 to 72 percent reagent grade perchloric acid shall be used. The chromic oxide shall be determined on the moisture free and chloroform extracted basis." "[2] The metal used in testing for corrosion shall be as specified in the end item specification (see 6.2)."

PAGE 6

Paragraph 4.3.4: Delete title and paragraph in their entireties and substitute the following: "Method for the determination of paranitrophenol. Method 6711 of KK–L–311 shall be used except that method 6341 shall be used for the extraction procedure. If the concentration of the developed paranitrophenol color is too intense for instrument readings, the 2 ml. aliquot shall be diluted until a reading can be taken. To compute the percent of paranitrophenol, use the following formula:

$$\text{Percent paranitrophenol} = \frac{\text{Milligrams paranitrophenol in aliquot} \times \text{dilution of chloroform solution}}{10 \times (\text{weight of specimen} - \text{moisture content in grams})}$$

Add the following new paragraph:

"4.3.5 Shrinkage temperature. Method 7011 of KK–L–311 shall be used except that the specimens shall be presoaked for not less than two hours at 23° C. in a solution identical to the heating medium. After the preliminary soaking period, the specimen shall be immediately immersed in the heating medium at 50°±3° C. and the heating continued from that point. Any shrinkage of the specimen at or below the required temperature shall be recorded as a failure."

PAGE 8

Paragraph 6.2, subparagraph (b): After tannage add the following:
"class and treatment required."
Add: "(f) Type of metal required (see table V)."

PAGE 9

Paragraph 6.2, subparagraph (d): Delete in its entirety.

Following paragraph 6.5. Delete information under "Military Custodians" and substitute:

CUSTODIANS:
Army—GL
Navy—SA
Air Force—11

Review activities:
Army—GL
Navy—SA, MC
Air Force—11

User activities:
Navy—SH, AS, OS, CG

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:57Z
Check the source to verify that this is the current version before use.