INCH-POUND

MIL-B-52118E
25 June 1991
SUPERSEDING
MIL-B-52118D
31 January 1975

MILITARY SPECIFICATION

BALK, DECK

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers deck balk which is a component of military bridges.

1.2 Classification. The balk shall be of the following types, as specified (see 6.2):

Type I - Short
Type II - Tapered
Type III - Normal

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: USA Belvoir Research, Development and Engineering Center, ATTN: STRBE-TSE, Fort Belvoir, VA 22060-5606 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 5420
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

PPP-B-601	-	Boxes, Wood, Cleated-Plywood.
PPP-B-636	-	Boxes, Shipping, Fiberboard.

MILITARY

MIL-T-704	-	Treatment and Painting of Materiel.
MIL-C-16173	-	Corrosion Preventive Compound, Solvent Cutback, Cold-Application.
MIL-C-46168	-	Coating, Aliphatic Polyurethane, Chemical Agent Resistant.
MIL-C-53039	-	Coating, Aliphatic, Polyurethane, Single Component, Chemical Agent Resistant (CARC), Lead and Chromate Free.

STANDARDS

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	-	Marking for Shipment and Storage.
MIL-STD-889	-	Dissimilar Metals.

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Government drawings. The following Government drawings form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those in effect on the date of the solicitation.

DRAWINGS

ME

TA13208E9880	-	Balk, Deck, Normal.
TA13208E9881	-	Balk, Deck, Short.
TA13208E9886	-	Balk, Deck, Tapered.
13217E7892	-	Balk, Deck, Short: Packing of.
13217E7893	-	Balk, Deck, Normal: Packing of.
13217E7894	-	Balk, Deck, Tapered: Packing of.

(Copies of drawings required by contractors in connection with specific acquisition functions should be obtained from the USA Belvoir Research, Development and Engineering Center, ATTN: STRBE-JBS, Fort Belvoir, VA 22060-5606.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

2.2 Non-Government publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY OF MECHANICAL ENGINEERS (ASME)

Boiler and Pressure Vessel Code, Section IX, Qualification Standard for Welding and Brazing Procedures, Welders, Brazers, and Welding and Brazing Operators.

(Application for copies should be addressed to the American Society of Mechanical Engineers, 345 East 47th Street, New York, NY 10017.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3953 - Strapping, Flat Steel and Seals.
D 4675 - Selection and Use of Flat Strapping Materials.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

AMERICAN WELDING SOCIETY (AWS)

A5.1 - Covered Carbon Steel Arc Welding Electrodes.
A5.10 - Bare Aluminum and Aluminum Alloy Welding Electrodes and Rods.
A5.18 - Carbon Steel Filler Metals for Gas Shielded Arc Welding.
D1.1 - Structural Welding Code - Steel.
D1.2 - Structural Welding Code - Aluminum.

(Application for copies should be addressed to the American Welding Society, 550 N.W. LeJeune Road, P.O. Box 35104, Miami, FL 33135.)

UNIFORM CLASSIFICATION COMMITTEE (UCC)

Uniform Freight Classification Rules.

(Application for copies should be addressed to the Uniform Classification Committee, ATTN: Tariff Publishing Officer, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC. (NMFTA)

National Motor Freight Classification Rules.

(Application for copies should be addressed to the American Trucking Associations, Inc., ATTN: Traffic Order Section, 2200 Mill Road, Alexandria, VA 22314.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

(Non-Government standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein (except for related associated detail specifications, specification sheets or MS standards), the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Description. The balks shall be as shown on TA13208E9880, TA13208E9881, and TA13208E9886 and as specified herein.

3.1.1 Drawings. The drawings forming a part of this specification are end product drawings. No deviation from the prescribed dimensions or tolerances is permissible without prior approval of the contracting officer. Where tolerances could cumulatively result in incorrect fits, the contractor shall provide tolerances within those prescribed on the drawings to insure correct fit, assembly, and operation of the balk or components. Any data (e.g. shop drawings, layouts, flow sheets, processing procedures, etc.) prepared by the contractor or obtained from a vendor to support fabrication and manufacture of the production item shall be made available, upon request, for inspection by the contracting officer or his designated representative. Dimensions shown on drawings shall be verified using parts at 68 degrees Fahrenheit (F) to 70 °F.

3.2 First article. Unless otherwise specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.3.

3.3 Material. Material shall be as specified herein and on the applicable drawings. Materials not specified shall be selected by the contractor, and shall be subject to all provisions of this specification.

3.3.1 Material deterioration prevention and control. The balk or component shall be fabricated from compatible materials, inherently corrosion resistant or treated to provide protection against the various forms of corrosion and deterioration that may be encountered in any of the applicable storage and operating environments to which the item may be exposed.

3.3.1.1 Dissimilar metals. Dissimilar metals shall not be used in intimate contact with each other unless protected against galvanic corrosion. Dissimilar metals and methods of protection are defined and detailed in MIL-STD-889.

3.3.1.2 Identification of materials and finishes. The contractor shall identify the specific material, material finish or treatment for use with components and subcomponents, and shall make information available, upon request, to the contracting officer or designated representative.

3.3.1.3 Recovered materials. For the purpose of this requirement, recovered materials are those materials which have been collected from solid

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

waste and reprocessed to become a source of raw materials, as distinguished from virgin raw materials. The components, pieces and parts incorporated in the balk may be newly fabricated from recovered materials to the maximum extent practicable, provided the balk produced meets all other requirements of this specification. Used, rebuilt or remanufactured components, pieces and parts shall not be incorporated in the balk.

3.4 Welding electrodes.

3.4.1 For steel. Welding electrodes for steel shall conform to AWS A5.1 or A5.18, classification E60 or E70 series, size as required.

3.4.2 For aluminum. Welding electrodes for aluminum shall conform to AWS A5.10, classification ER4043, size as required.

3.5 Identification marking. The balk or component, as applicable, shall be metal die stamped as shown on the applicable drawing, and markings shall be legible after all painting has been completed.

3.6 Treatment and painting. The portions of the balk normally painted, internally and external, shall be cleaned, treated, and painted in accordance with MIL-T-704, type F or G, as follows:

a. The backup plates, lugs, handles, and the balk extrusions (where the backup plates, lugs, and handles come in contact with the balk extrusions).
b. The shoe assembly of the tapered balk prior to assembling in the top and bottom balk extrusions.
c. The exterior of each completely assembled balk.
d. All components, when procured separately from balk, except threads on plugs and threads on bolts of end lug assemblies.

Unless otherwise specified (see 6.2), the top coat color shall be camouflage green 383 conforming to MIL-C-46168 or MIL-C-53039.

3.7 Stenciling. The nomenclature, National Stock Number, weight, and cube shall be stenciled on each deck balk. The letters "NET WT" shall precede the numerals in the weight and the letters "CU" shall precede the cubic displacement. Markings shall be Gothic-type capitals and Arabic numerals 3/4 inch high. Stenciling shall conform to MIL-T-704.

3.8 Balk load. When tested in accordance with 4.5.2.1, and when supported on the horizontal leg of the end lugs and a downward vertical load of 40,000 pounds is applied to one of the interior lugs, the normal deck balk shall not fail or show any visible damage such as cracks or permanent deformation in the welds, extruded sections, lugs, bolts, or base metal adjacent to the welds.

3.9 Balk leakage. When tested in accordance with 4.5.2.2, the welds on the short and normal deck balk shall not leak when subjected to an internal air pressure of 3 pounds per square inch (psi).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

3.10 Government-loaned property. Unless otherwise specified (see 6.2), the following property in the quantities indicated will be loaned by the Government (see 6.7):

ITEM	DESCRIPTION	IDENTIFICATION	QUANTITY
1.	Inspection Equipment for Balk, Deck	Quality Assurance Pamphlet, P715-107	1

3.11 Workmanship.

3.11.1 Steel fabrication. Metal used in fabrication shall be free from kinks and sharp bends. The straightening of material shall be done by methods that will not cause injury to the material. Corners shall be square and true. Flame cutting, using tips suitable for the thickness of the steel, may be employed instead of shearing or sawing. All bends shall be made with controlled means to ensure uniformity of size and shape. Precautions shall be taken to avoid overheating. Heated steel shall be allowed to cool slowly. External surfaces shall be free from burrs, sharp edges, and corners, except when sharp edges or corners are required or where they are not detrimental to safety.

3.11.2 Aluminum fabrication. Before any work or layout is done, aluminum shall be straightened. Straightening shall be done by methods that will not result in injury to the metal. Care shall be used in handling aluminum during fabrication to avoid scratching or damage to edges. Finished members shall be free from lamination, kinks, bends, scratches or winds. All bends shall be made to a radius which will not cause cracking or undue stress in the extreme outer fibers. Except for those of a minor nature, bends shall be made with metal dies or fixtures to insure uniformity of size and shape. Sharp instruments shall not be used for making bend lines. Aluminum 3/8 inch thick and over shall be cut by routing or sawing. Aluminum under 3/8 inch thick may be cut by shearing.

3.11.3 Riveting. Suitable jigs and fixtures shall be used to maintain alignment and tolerance. The types of manufactured rivets are as shown on the drawings. The driven or formed rivet heads shall be of cone point or countersunk type as specified on the drawings. Rivets shall fill the holes in the joined members. Caulking or redriving of rivet heads shall not be permitted.

3.11.4 Welders and welding.

3.11.4.1 Welders. Before assigning any welders and welding operators to welding work covered by this specification, the contractor shall obtain certification that the welder or welding operator has passed qualification tests as prescribed by one of the following listed codes for the materials joined and the type of welding operation to be performed and that such qualification is effective as defined by the particular code:

AWS D1.1 Structural Welding Code - Steel
AWS D1.2 Structural Welding Code - Aluminum
ASME Boiler and Pressure Vessel Code, Section IX

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

Contractors who only make horizontal welds need not qualify welders for all position welding. In the event of evidence of poor welds, the Government reserves the right to require retesting of any welder or welding operator. The test results shall be made available for review by the contracting officer or the contracting officer's representative.

3.11.4.2 Welding. Welding shall be in accordance with the AWS or ASME code. Prior to any welding, welding procedures shall be qualified for each joint as specified in the AWS or ASME code. Guided bend tests shall be used for procedure qualification. Welding procedures shall be available at each welding station for welder's or operator's reference. The welding procedure specifications and qualifications shall be made available for review by the contracting officer or his representative.

3.11.4.2.1 Steel welding. The surfaces of parts to be welded shall be free from rust, scale, paint, grease, mill scale and other foreign matter. Parent materials, weld filler metals, and fabrication techniques shall be as required to enable the balk to conform to the examination and test requirements specified in section 4. Parts to be joined by fillet welds shall be brought into as close contact as possible and in no event shall be separated by more that 0.188 inch unless appropriate bridging techniques are used. Procedures and sequences shall be such that distortion and shrinkage will be held to a minimum. When straightening is required, caution shall be exercised to ensure that the straightening process does not weaken the part and the complete item. Tack welds shall have the same quality requirements as the final weld. Weldments, weld beads, and tack welds shall be:

a. Homogenous in appearance.
b. Smoothly blended into the base metal without spattering or other irregularities.
c. Able to transmit stress without permanent deformation or failure when parts connected by welds are subjected to service loading.

3.11.4.2.2 Aluminum welding. Aluminum parts to be welded shall be sheared or sawed. Flame cutting shall not be used. Plasma cutting may be used on nonheatable alloys; the heat affected zone shall be machined away. The surfaces of aluminum parts to be welded shall be free from paint, grease, oxide film, and all other foreign matter, which shall be removed using a stainless steel wire brush. The welding shall be done by one of the inert gas, shielded arc methods. Welds may be ground, filed, buffed, or chipped. Welds shall not be hammered. Completed welds shall be free from discontinuities such as base metal cracks adjacent or behind welds, cracks in weld metal, undercutting of base metal, lack of fusion between weld and parent metal or between weld passes, incomplete penetration, lack of prescribed fit, or splatter.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Component and material inspection. The contractor is responsible for ensuring that components and materials used are manufactured, examined, and tested in accordance with referenced specifications, standards, and drawings.

4.1.3 Parts and components. Parts and components detailed on the drawings shall be inspected in accordance with the Quality Assurance Provisions (QAP) shown on the drawings. The drawings specify the characteristics requiring inspection, the sampling plan, and the basis for acceptance and rejection (see 6.5 and 6.6).

4.2 Classification of inspections. Inspections shall be classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).
c. Inspection of packaging (see 4.6).

4.3 First article inspection.

4.3.1 Examination. The first article or components shall be examined in accordance with 4.4.2.1. Presence of one or more defects in either deck balk or component shall be cause for rejection.

4.3.2 Tests. The first article shall be tested as specified in 4.5.2 as applicable. Failure of any test shall be cause for rejection.

4.4 Quality conformance inspection.

4.4.1 Sampling. Sampling for examination and tests shall be in accordance with MIL-STD-105. Sample size shall be determined by using MIL-STD-105, table I and table IIa. A lot shall be accepted when zero defects are found and rejected when one or more defects are found.

4.4.2 Examination.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

4.4.2.1 Individual. Each balk shall be examined for conformance to the dimensions covered by the QAP shown on the drawings under "Major-100 percent inspection" (see 6.6.1). Unless otherwise specified (see 6.2), Government-loaned inspection equipment (see 3.10) shall be used in accordance with the Government Quality Assurance Pamphlet to inspect these dimensions. Nonconformance to any of these dimensions shall constitute failure of this examination and shall be cause for rejection.

4.4.2.2 Samples. Samples selected in accordance with 4.4.1 shall be examined for the major and minor defects specified in 4.5.1. A lot shall be accepted when zero defects are found and rejected when one or more defects are found.

4.4.3 Tests. Samples of normal balk selected in accordance with 4.4.1 shall be tested as specified in 4.5.2.1 and 4.5.2.2. Samples of short balk selected in accordance with 4.4.1 shall be tested as specified in 4.5.2.2. No tests are required on the tapered balk.

4.5 Inspection procedure.

4.5.1 Examination. The balk or component, as applicable, shall be examined as specified herein for the following defects:

Major

101. All dimensions designated major on the QAP other than those under 100 percent inspection not as specified (see 3.1).
102. Radii on interior and end lugs not as specified (see 3.1.1).
103. Material not as specified (see 3.3).
104. Materials not resistant to corrosion or deterioration, or treated to be made resistant to corrosion or deterioration for the applicable storage and operating environments (see 3.3.1).
105. Dissimilar metals as defined in MIL-STD-889 are not effectively insulated from each other (see 3.3.1.1).
106. Contractor does not have documentation available for identification of material, material finishes or treatment (see 3.3.1.2).
107. Used, rebuilt or remanufactured components, pieces or parts incorporated in the balk (see 3.3.1.3).
108. Workmanship not as specified (see 3.11).
109. Riveting not as specified (see 3.11.3).
110. Weld defects such as flux inclusions, spatter, undercutting, porosity, incorrect size, or lack of fusion with parent metal (see 3.11.4).
111. Welding and welds not as specified (see 3.11.4).
112. Welders and welding operators not certified as specified (see 3.11.4.1).
113. Welding electrodes not as specified (see 3.4.1 and 3.4.2).

Minor

201. All dimensions not designated major on the QAP not as specified (see 3.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

202. Identification marking missing, incomplete, or illegible (see 3.5).
203. Treatment and painting not as specified (see 3.6).
204. Stenciling not as specified (see 3.7).

4.5.2 Tests.

4.5.2.1 Load. Support the normal deck balk on the horizontal leg of the end lugs and apply a downward vertical load of 40,000 pounds to one of the interior lugs for a minimum of 5 minutes. Nonconformance to 3.8 shall constitute failure of this test.

4.5.2.2 Leakage. Subject the normal and short deck balk to an internal air pressure of 3 psi applied through the end-plug hole and submerge the balk in water. This test shall be performed prior to final painting and after load testing of the normal deck balk. Nonconformance to 3.9 shall constitute failure of this test.

4.6 Inspection of packaging.

4.6.1 First article pack inspection.

4.6.1.1 Examination. Examine the first article pack for the defects specified in 4.6.2.3. Presence of one or more defects shall be cause for rejection.

4.6.2 Quality conformance inspection of pack.

4.6.2.1 Unit of product. For the purpose of inspection, a completed pack prepared for shipment shall be considered a unit of product.

4.6.2.2 Sampling. Sampling for examination shall be in accordance with MIL-STD-105. Sample size shall be determined by using MIL-STD-105, table I and table IIa. A lot shall be accepted when zero defects are found and rejected when one or more defects are found.

4.6.2.3 Examination. Samples selected in accordance with 4.6.2.2 shall be examined for the following defects. Presence of one or more defects shall be cause for rejection.

114. Threads of separately procured components not coated with preservative as specified (see 5.2.2).
115. Balk not bundled as shown on drawing (see 5.3.1.1).
116. Balk components of unlike description packed together (see 5.3.1.2).
117. Containers not as specified for level A or B (see 5.3.1.2 and 5.3.2.2).
118. Blocking and bracing of components within the container not adequate to prevent free movement for level A or B (see 5.3.1.2 and 5.3.2.2).
119. Strapping on containers not zinc coated for level A (see 5.3.1.2).
120. Marking missing, illegible, incorrect, or incomplete (see 5.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 First article pack. The contractor shall furnish a first article pack for examination within the time frame specified (see 6.2) to prove, prior to starting production packaging, that the applied preservation, packing, and marking comply with the preparation for delivery requirements of this specification. Examination shall be that specified in Section 4 and shall be subject to surveillance and approval by the Government (see 6.4). The first article pack may be accomplished utilizing either the first article balk or the production balk. If the first article balk is utilized, any preservation and packing shall be removed by the contractor at no expense to the Government when requested by the Government to facilitate comparison between the first article balk and the production balk.

5.2 Preservation.

5.2.1 Balk. The balk, cleaned, treated, and painted as specified shall not require additional preservation.

5.2.2 Components. When balk components are procured separately from balk, the threads on plugs and threads on bolts of end lug assemblies shall be coated with preservative conforming to MIL-C-16173, grade 1.

5.3 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.3.1 Level A.

5.3.1.1 Balk. The balk shall be prepared for shipment in bundles as shown on drawings 13217E7892, 13217E7893, or 13217E7894, as applicable.

5.3.1.2 Components. Balk components of like description, procured separately from the balk, shall be packed together in a close-fitting box conforming to PPP-B-601, overseas type, style optional. The components shall be blocked and braced within the box to prevent free movement. Box closure and strapping shall be in accordance with the appendix to the box specification. Strapping shall be in accordance with ASTM D 3953, type 1 or 2, zinc-coated, size as applicable, and ASTM D 4675.

5.3.2 Level B.

5.3.2.1 Balk. The balk shall be prepared for shipment as specified in 5.3.1.1.

5.3.2.2 Components. Balk components of like description, procured separately from the balk, shall be packed together in a close-fitting box conforming to PPP-B-601, domestic type, style optional, or PPP-B-636, V3c, style optional. The components shall be blocked and braced within the box to prevent free movement. Box closure and strapping shall be in accordance with the appendix to the applicable box specification.

5.3.3 Level C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

5.3.3.1 Balk. The balk shall be prepared for shipment as specified in 5.3.1.1.

5.3.3.2 Components. Balk components of like description, procured separately from the balk, shall be packed together in a manner to assure carrier acceptance and safe delivery to destination at lowest rating in containers complying with Uniform Freight Classification rules or National Motor Freight Classification rules.

5.4 Marking. In addition to any special marking specified by the contract or purchase order (see 6.2), marking shall be in accordance with MIL-STD-129.

6. NOTES

(This section contains information of a general or explanatory nature which is helpful, but is not mandatory).

6.1 Intended use. The balk is used as a deck component of the superstructure for floating and short fixed-span bridges.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.
b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
c. Type of deck balk required (see 1.2).
d. When a first article is required for inspection and approval, and the number of units required (see 3.2).
e. Color required (see 3.6).
f. When Government-loaned property is required (see 3.10 and 4.4.2.1).
g. Time frame required for submission of the first article pack (see 5.1).
h. Level of packing required (see 5.3).
i. Any special marking (see 5.4).

6.3 First article. When a first article inspection is required, the deck balk or separately procured components should be a preproduction model. The first article should consist of two or more of each type of deck balk or separately procured components. The contracting officer should include specific instructions in the acquisition documents regarding arrangements for examinations, approval of the first article test results and disposition of the first article. Invitation for bids should provide that the Government reserves the right to waive the requirement for samples for first article inspection to those bidders offering a product which has been previously acquired or tested by the Government, and that bidders offering such products, who wish to rely on such production or test, must furnish evidence with the bid that prior Government approval is presently appropriate for the pending contract. Bidders should not submit alternate bids unless specifically requested to do so in the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

6.4 First article pack. Any changes or deviations of production packs from the first article pack will be subject to the approval of the contracting officer. Approval of the first article pack will not relieve the contractor of his obligation to preserve, pack, and mark the balk or components in accordance with this specification.

6.5 Quality assurance provisions (QAP). The contracting officer should require the contractor to maintain records of all QAP inspections. A suggested paragraph is as follows:

"The contractor shall maintain complete records of all examinations and tests performed to verify the requirements of classified QAP characteristics. The records shall include as a minimum, lot size, sample size, drawing requirement, actual measurement, number and type of deficiencies found, quantity, quantity rejected, corrected action taken when applicable."

6.6 Definitions.

6.6.1 Quality assurance provisions (QAP). A QAP is a contractual requirement that supplements Section 4 of the specification. QAP indicates the minimum requirements which must be inspected on the product drawings to verify the design objectives of the product and assure interchangeability of repair parts.

6.7 Government-loaned property. The contracting officer should arrange to lend the property listed in 3.10, when applicable.

6.8 Subject term (key word) listing.

Balk
Deck balk
Normal balk
Short balk
Tapered balk

6.9 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodian:
Army - ME

Preparing activity:
Army - ME

Review activity:
Army - SM

Project No. 5420-0167

User activity:
Navy - MC

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:08Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-B-52118E	2. DOCUMENT DATE (YYMMDD) 910625

3. DOCUMENT TITLE
Balk, Deck

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial (703) 664-5717	(2) AUTOVON 354-5717
c. ADDRESS (Include Zip Code) US Army Belvoir RDE Center ATTN: STRBE-TSE Ft. Belvoir, VA 22060-5606	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

Source: https://assist.dla.mil -- Downloaded: 2022-08-22T12:08:07Z
Check the source to verify that this is the current version before use.