MILITARY SPECIFICATION

METAL PARTS, MINES, M718/M741 SYSTEMS

This Specification is approved for use by ARRADCOM and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification contains requirements not normally covered by the drawings and provides quality assurance provisions for the fabrication and packing of the metal parts for the M718/M741 system mines.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposals, form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-A-48078 - Ammunition, Standard Quality Assurance Provisions, General Specifications For

STANDARDS

MILITARY

MIL-STD-1169 - Packaging, Packing and Marking for Shipment of Inert Ammunition Components.

FSC: 1345

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Armament Research and Development Command, Attn. DRDAR-QA, Dover, New Jersey 07801 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

DRAWINGS

ARMAMENT RESEARCH AND DEVELOPMENT COMMAND

9276497 - Body
9277742 - Plate
9277744 - Cover
9276504 - Key
9277743 - Simulant
9277820 - Simulant, Modified
9277753 - Ring, Retainer
9277763 - Booster, Simulant
9277843 - Cup
9277846 - Cup, Closure
9277939 - Cup with collar
9277992 - Pad, Spherical
9277994 - Body & Pad Assembly
9277745 - Cover, Front
9287113 - Bushing
9287167 - Insulator Test Point
9277920 - Insulator, Lens
9277987 - Lens, Impact

(Copies of specifications, standards, drawings and publication listed above required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the Contracting Officer).

2.2 Other publications.

The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

American Society for Testing and Materials

ASTM-D792 - Specific Gravity and Density of Plastics by Displacement

(Applications for copies shall be addressed to ASTM, 1916 Race Street, Philadelphia, Pennsylvania 19103).

3. REQUIREMENTS

3.1 Material. - Materials shall be in accordance with the applicable drawings and specifications.

3.2 Parts. - The parts shall comply with all requirements specified on the Drawings and with all requirements specified in applicable specifications and standards.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

3.3 First article inspection. - This specification makes provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

3.4 Workmanship. - The parts shall be fabricated and finished in a thorough, workmanlike manner. They shall be free of burrs, chips, sharp edges, cracks, unblended radii, surface defects, dirt, grease, rust, corrosion products and other foreign matter. The cleaning method used shall not be injurious to any part, nor shall the part be contamined by the cleaning agents. All markings and stamping shall be neat and sharply defined.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection and standard quality assurance provisions. - Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification.

4.2 Classification of inspection. - The following types of inspection shall be conducted on this item.

a. First Article Inspection

b. Quality Conformance Inspection

4.3 First article inspection.

4.3.1 Submission. - The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisions of 4.3.2. The first article sample shall consist of the following items in the quantities as indicated.

PART DESCRIPTION	DRAWINGS	QUANTITY
Body	9276497	5
Plate	9277742	5
Cover	9277744	5
Cover, Front	9277745	5
Simulant	9277743	5
Simulant, Modified	9277820	5
Ring, Retainer	9277753	5
Booster, Simulant	9277763	5
Cup	9277843	5
Cup, Closure	9277846	5
Cup with collar	9277939	5
Lens, Impact	9277987	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

4.3.2 Inspections to be performed. - See MIL-A-48078 and Table I specified herein.

4.3.3 Rejection. - See MIL-A-48078.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

TABLE I - FIRST ARTICLE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-M-48261 (AR)

PARAGRAPH	TITLE		SHEET 1 OF 2		DRAWING NUMBER
	Metal Parts, Mine M718/741 Systems				See Below
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Body				
	Dwg. 9276497				
	Examination for Defects	5		3.2	4.4.2.1
	Hardness	5		3.2	4.4.3.1
	Plate				
	Dwg. 9277742				
	Examination for Defects	5		3.2	4.4.2.2
	Cover				
	Dwg. 9277744				
	Examination for Defects	5		3.2	4.4.2.3
	Simulant				
	Dwg. 9277743				
	Examination for Defedts	5		3.2	4.4.2.5
	Density improper	5		3.2	4.4.3.2
	Simulant Modified				
	Dwg. 9277820				
	Examination for Defects	5		3.2	4.4.2.6
	Density improper	5		3.2	4.4.3.2

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

TABLE I- FIRST ARTICLE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-M-48261 (AR)

PARAGRAPH	TITLE		SHEET 2 OF 2		DRAWING NUMBER
	Continuation Sheet Metal Parts, Mine M718/M741 Systems				See Below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Booster Simulant Dwg. 9277763				
	Examination for Defects	5		3.2	4.4.2.8
	Density Improper	5		3.2	4.4.3.2
	Ring, Retainer Dwg. 9277753				
	Examination for Defects	5		3.2	4.4.2.7
	Cup Dwg. 9277843				
	Examination for Defects	5		3.2	4.4.2.9
	Cup Closure Dwg. 9277846				
	Examination for Defects	5		3.2	4.4.2.10
	Cup with Collar Dwg. 9277939				
	Examination for Defects	5		3.2	4.4.2.11
	Cover, Front Dwg. 9277745				
	Examination for Defects	5		3.2	4.4.2.14
	Lens, Impact Dwg. 9277987				
	Examination for Defects	5		3.2	4.4.2.18

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection

4.4.1 Inspection lot formation. - Inspection lots shall comply with the lot formation provisions of MIL-A-48078.

4.4.2 Examination. - See MIL-A-48078 and the following "Classification of Defects & Tests" for each item. Unless otherwise specified in the classification of defects and test tables, sampling plans for major and minor defects shall be in accordance with MIL-STD-105, Inspection Level II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-M-48261 (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.1	Body				9276497
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None Defined				
Major:					
101	Outside diameter improper		0.40%	3.2	Gage
102	Inside diameter (wall) improper		0.40%	3.2	Gage
103	Inside diameter (lip) improper		0.40%	3.2	Gage
104	Minor diameter of threads, maximum improper		0.40%	3.2	Gage
105	Pitch diameter of threads, improper		0.40%	3.2	Gage
106	Height (outside) improper		0.40%	3.2	Gage
107	Thickness of lip improper		0.40%	3.2	Gage
108	Length of thread improper		0.40%	3.2	Gage
109	Parallelsim of ends improper		0.40%	3.2	Gage
110	Hardness improper		0.40%	3.2	4.4.3.1
111	Material improper		0.40%	3.2	Certification of Analysis
112	Diameter of 4 holes		0.40%	3.2	Gage
113	Depth of 4 holes		0.40%	3.2	Gage
Minor:					
201	Length of key slot improper		0.65%	3.2	Gage
202	Width of key slot improper		0.65%	3.2	Gage
203	Depth of key slot improper		0.65%	3.2	Gage
204	Evidence of poor workmanship		0.65%	3.4	Visual
205	Protective Finish Missing or Incomplete		0.65%	3.?	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET OF		DRAWING NUMBER
4.4.2.2.	Plate				9277742
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None Defined				
Major					
101	Height improper		0.40%	3.2	Gage
102	Outside diameter improper		0.40%	3.2	Gage
103	Inside diameter improper		0.40%	3.2	Gage
104	True Position I.D. to O.D. improper		0.40%	3.2	Gage
105	Location of flat improper		0.40%	3.2	Gage
106	Radius of cutout improper		0.40%	3.2	Gage
107	Length of cutcut improper		0.40%	3.2	Gage
108	Thickness improper		0.40%	3.2	Gage
109	Spherical profile improper at any point 360° around.		0.40%	3.2	Comparator/Gage
110	Material improper				Certificate of Analysis
Minor					
201	Surface finish improper		0.65%	3.2	Visual
202	Evidence of poor workmanship		0.65%	3.4	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9277744
4.4.2.3	Cover				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined.				
Major:					
101	Outside diameter improper		0.40%	3.2	Gage
102	Height improper		0.40%	3.2	Gage
103	Spherical radius (profile) improper		0.40%	3.2	Comparator/Gage
104	Length of flat at edge improper		0.40%	3.2	Gage
Minor:					
201	Thickness improper		0.65%	3.2	Gage
202	Evidence of poor workmanship		0.65%	3.4	Visual
203	Protective Finish Missing or incomplete		0.65%	3.2	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9276504
4.4.2.4	Key				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined.				
Major:					
101	Length improper		0.40%	3.2	Gage
102	Width improper		0.40%	3.2	Gage
103	Height improper		0.40%	3.2	Gage
Minor:					
201	Evidence of poor workmanship		0.65%	3.4	Visual
202	Material			3.2	Certificate of Conformance

NOTES:

SARPA-QA FORM 2567 FEB 74 4810

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-M-48261 (AR)

PARAGRAPH	TITLE			SHEET 1 OF 1	DRAWING NUMBER 9277743
4.4.2.5	Simulant				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined.				
Major:					
101	Outside diameter improper		0.40%	3.2	Gage
102	Inside diameter improper		0.40%	3.2	Gage
103	Height improper		0.40%	3.2	Gage
104	Spherical radius (two sides) improper 360° around		0.40%	3.2	Gage
105	Cracks evident		0.40%	3.2	Visual
106	Density improper	5	-	3.2	4.4.3.2
Minor:	None defined.				

NOTES:

SARPA-QA FORM 2567 FEB 74 4810

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9277820
4.4.2.6	Simulant, Modified				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined.				
Major:					
101	Width of cutout improper		0.40%	3.2	Gage
102	Depth of cutout improper		0.40%	3.2	Gage
103	Width of small slot improper		0.40%	3.2	Gage
104	Depth of small slot improper		0.40%	3.2	Gage
105	Cracks evident		0.40%	3.2	Visual
106	Density improper	5	-	3.2	4.4.3.2
Minor:	None defined.				

NOTES:

SARPA-QA FORM 2567 FEB 74 4810

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.7	Ring, Retainer				9277753
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined.				
Major:					
101	Major diameter of thread, minimum (min) improper		0.40%	3.2	Gage
102	Pitch diameter of thread, minimum (min) improper		0.40%	3.2	Gage
103	Inside diameter improper		0.40%	3.2	Gage
104	Thickness improper		0.40%	3.2	Gage
Minor:					
201	Width of notch (2) improper		0.65%	3.2	Gage
202	Depth of notch (2) improper		0.65%	3.2	Gage
203	Alignment of notches improper		0.65%	3.2	Gage
204	Inside corner (notched side) not rounded		0.65%	3.2	Visual
205	Evidence of poor workmanship		0.65%	3.4	Visual
206	Protective finish missing or incomplete		0.65%	3.2	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-M-48261 (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.8	Booster, Simulant				9277763
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical:	None defined.				
Major:					
101	Inside diameter improper		0.40%	3.2	Gage
102	Outside diameter improper		0.40%	3.2	Gage
103	Height improper		0.40%	3.2	Gage
104	Cracks evident		0.40%	3.2	Visual
105	Density improper	5	-	3.2	4.4.3.2
Minor:	None defined.				

NOTES:

SARPA-QA FORM 2567 FEB 74 4810

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9277843
4.4.2.9	Cup				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical:	None defined.				
Major:					
101	Length improper		0.40%	3.2	Gage
102	Width improper		0.40%	3.2	Gage
103	Radius of ends improper		0.40%	3.2	Gage
104	Short height improper		0.40%	3.2	Gage
105	Long height improper		0.40%	3.2	Gage
106	Location of hole improper		0.40%	3.2	Gage
107	Diameter of hole improper		0.40%	3.2	Gage
Minor:					
201	Thickness of material improper		0.65%	3.2	Gage
202	Finish missing or improper		0.65%	3.2	Visual
203	Evidence of poor workmanship		0.65%	3.4	Visual

NOTES:

SARPA-QA FORM 2567 FEB 74 4810

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9277846
4.4.2.10	Cup, Closure				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical:	None defined.				
Major:					
101	Length improper		0.40%	3.2	Gage
102	Width improper		0.40%	3.2	Gage
103	Short height improper		0.40%	3.2	Gage
104	Long height improper		0.40%	3.2	Gage
105	Location of slot improper		0.40%	3.2	Gage
106	Width of slot improper		0.40%	3.2	Gage
107	Depth of slot improper		0.40%	3.2	Gage
Minor:					
201	Thickness of material improper		0.65%	3.2	Gage
202	Evidence of poor workmanship		0.65%	3.4	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.11	Cup with collar				9277939
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined.				
Major:					
101	Cup shallow depth improper		0.40%	3.2	Gage
102	Cup deep depth improper		0.40%	3.2	Gage
103	Radius from wall to collar improper		0.40%	3.2	Gage
Minor:					
201	Cup ID minor axis improper		0.65%	3.2	Gage
202	Cup ID major axis improper		0.65%	3.2	Gage
203	Evidence of poor workmanship		0.65%	3.2	Visual
204	Thickness		0.65%	3.2	Gage
205	Protective Finish missing or incomplete		0.65%	3.2	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-M-48261 (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.12	Pad, Spherical				9277992
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical:	None defined.				
Major:	None defined.				
Minor:					
201	Diameter improper		0.65%	3.2	Gage
202	Profile improper		0.65%	3.2	Gage
203	Evidence of poor workmanship		0.65%	3.4	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-M-48261 (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9277994
4.4.2.13	Body and Pad Assembly				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical:	None defined.				
Major:	None defined.				
Minor:					
201	Absence of Pads (4)		0.65%	3.2	Visual
202	Absence of washers (4)		0.65%	3.2	Visual
203	Stake(s) Missing		0.65%	3.2	Visual
204	PAD(S) not above flush		0.65%	3.2	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET OF	DRAWING NUMBER
4.4.2.14	Cover, Front		9277745
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None Defined		0.40%	3.2	Gage
Major					
101	Large Outside Diameter		0.40%	3.2	Gage
102	Small Outside Diameter		0.40%	3.2	Gage
103	Sherical Radius		0.40%	3.2	Gage
104	Height To Flat		0.40%	3.2	Gage
105	True Position of Large O.D. To Small O.D.		0.40%	3.2	Gage
Minor					
201	Inside Radius of Curbature		0.65%	3.2	Gage
202	Thickness		0.65%	3.2	Gage
203	Evidence of Poor Workmanship		0.65%	3.4	Visual
204	Protective Finish missing or incomplete		0.65%	3.2	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET OF		DRAWING NUMBER
4.4.2.15	Bushing				9287113
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None Defined				
Major					
101	Outside Diameter		0.40%	3.2	Gage
102	True Position of I.D. To O.D.		0.40%	3.2	Gage
103	Inside Diameter		0.40%	3.2	Gage
Minor					
201	Length		0.65%	3.2	Gage
202	Evidence of Poor Workmanship		0.65%	3.4	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET OF		DRAWING NUMBER
4.4.2.16	Insulator, Test Point				9287167
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None Defined				
Major					
101	Holes or Tears Present		C.40%	3.2	Visual
Minor					
201	Length		0.65%	3.2	Gage
202	Width		0.65%	3.2	Gage
203	Radius at Ends (2 places)		0.65%	3.2	Gage
204	Thickness		0.65%	3.2	Gage

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET OF		DRAWING NUMBER
4.4.2.17	Insulator, Lens				9277920
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None Defined				
Major	None Defined				
Minor					
201	Length		0.65%	3.2	Gage
202	Width		0.65%	3.2	Gage
203	Thickness		0.65%	3.2	Gage
204	Evidence of Poor Workmanship		0.65%	3.4	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET OF		DRAWING NUMBER
4.4.2.18	Lens, Impact				9277987
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None Defined				
Major					
101	Diameter of hole		0.40%	3.2	Gage
102	Distance from edge of hole to flat		0.40%	3.2	Gage
Minor					
201	Large Spherical radius (max)		0.65%	3.2	Gage
202	Small spherical radius (min)		0.65%	3.2	Gage
203	Height to hole edge		0.65%	3.2	Gage
204	Outside diameter		0.65%	3.2	Gage
205	Evidence of poor workmanship		0.65%	3.4	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

4.4.3 Testing

4.4.3.1 Hardness (See dwg. 9276497) Major defect. - A sample of mine bodies shall be randomly selected from each lot and tested for hardness. Testing shall be performed as specified in 4.5.1 (Non-Destructive Test).

4.4.3.2 Density of the simulant (See dwgs. 9277743, 9277820, 9277763) Major defect. - A sample of five (5) each of the above parts shall be randomly selected from each lot of 200 or less parts of each type and tested for density. This test shall be performed in accordance with 4.5.2 (Non-Destructive Test).

4.4.4 Inspection equipment. - Inspection equipments required to perform the inspections prescribed in this specification are identified in 4.4.2.1 thru 4.4.2.11 and Test Method paragraphs herein. See 6.2 for details concerning responsibilities for inspection design and approval.

4.4.5 Dimensional control of molded parts. - In place of normal sampling and inspections associated with the Classification of Defects, and after a curing time for the parts has been approved (See Note 1). The Contractor may, with the approval of the Government, select a sample of three (3) parts (as molded) from each cavity to be fully inspected dimensionally to quality a new or reworked cavity for use in production. The molded parts shall carry the individual cavity identification. As a control of each cavity during production, the above quantity of parts from each cavity shall be inspected for at least the defects listed in paragraphs 4.4.2.5, 4.4.2.6 and 4.4.2.8 after continuous production of each 5,000 parts or at the end of each week, whichever occurs first. Of the three (3) samples, one (1) sample shall be the last part produced. If any defective parts are found during qualification of the cavity, the cavity producing the defective part will not be used in production. If any defective parts are found when inspection is performed for the control of the cavity, the cavity producing the defective part shall be removed from production. Further, that portion of production since the last control check shall be returned to the contractor for inspection for each separate type of defect according to MIL-STD-105, using an AQL of 0.40 percent for each major defect and an AQL of 0.65 percent for each minor defect. All cavities removed from production because of some fault, may after reworking, be returned to production providing they pass the qualification test above. The contractor may request

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

a change of inspection frequency providing he presents objective evidence to the contracting officer to substantiate the request. Contractor design of gages and test equipment required to perform the inspections listed herein shall be forwarded to Commander, ARRADCOM, Dover, New Jersey 07801, ATTN: DRDAR-QAA-I for approval prior to manufacture of equipment. The noted subparagraphs identify those items and minimum inspections subject to the requirements of this paragraph.

NOTE 1. - In establishing a curing time, dimensionally check ten (10) parts from each cavity at periodic intervals (e.g. every 30, 60, etc. mins.) until dimensional stability is attained. The curing time will be from the time the part comes out of the mold until dimensional stability is attained. The inspection data used in determining the curing time shall be sent to ARRADCOM, Dover, New Jersey 07801 ATTN: DRDAR-QAA-R. When a new cavity is substituted, an old cavity reworked, or the material or cycle time changed, a new curing time shall be established and approved.

4.5 Test methods and procedures

4.5.1 Hardness. - Hardness of the mine body shall be measured by a Rockwell "C" hardness tester. Readings shall be taken on the center of the outside wall 90° apart (total 4 readings).

4.5.2 Density of simulant. - The sample of simulant material shall be tested for density in accordance with the procedure specified in ASTM Designation D792 - "Specific Gravity and Density of Plastics by Displacement", method A-1 or an equivalent approved by DRDAR-QAA.

5. PREPARATION FOR DELIVERY

5.1 Preservation and packaging.

5.1.1 Level C. - The parts shall be preserved and packaged in accordance with MIL-STD-1169.

5.2 Packing.

5.2.1 Level C. - The parts shall be packed for shipment in accordance with MIL-STD-1169.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.

5.3 Marking. - Marking of the carton shall comply with MIL-STD-1169.

5.4 Shipping. - When parts from more than one lot are shipped as a carload, each lot shall be kept separate, and the division between lots clearly indicated to prevent mixing of the lots in transit.

6. NOTES

6.1 Ordering data. - See MIL-A-48078.

6.2 Submission of designs for approval. - See 6.2.3 of MIL-A-48078. Submit equipment designs, as required, to Commander, Armament Research and Development Command, ATTN: DRDAR-QAA-I, Dover, New Jersey 07801.

Custodian:
Army - AR

Preparing Activity
Army-(AR)

Project Number : 1345-A030

16

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:20Z
Check the source to verify that this is the current version before use.