The documentation and process conversion measures necessary to comply with this revision shall be completed by 27 March 2011.

INCH-POUND

MIL-PRF-19500/556K
27 December 2010
SUPERSEDING
MIL-PRF-19500/556J
16 June 2009

PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, FIELD EFFECT TRANSISTOR, N-CHANNEL, SILICON,
TYPES 2N6782, 2N6782U, 2N6784, 2N6784U, 2N6786, AND 2N6786U,
JAN, JANTX, JANTXV, JANS, JANHC, AND JANKC

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for an N-channel, enhancement-mode, MOSFET, power transistor. Four levels of product assurance are provided for each encapsulated device type as specified in MIL-PRF-19500. Two levels of product assurance are provided for each unencapsulated device type.

1.2 Physical dimensions. See figure 1 [similar to TO-205AF (formerly TO-39)], figure 2 (LCC), and figures 3 and 4 for JANHC and JANKC die dimensions.

1.3 Maximum ratings. Unless otherwise specified, T_A = +25°C.

Type	P_T (1) T_C = +25°C	P_T T_A = +25°C	V_{DS}	V_{DG}	V_{GS}	I_{D1} (2) (3) T_C = +25°C	I_{D2} (2) T_C = +100°C	I_S	I_{DM} (4)	T_J and T_{STG}	V_{ISO} 70,000 foot altitude
	W	W	V dc	V dc	V dc	A dc	A dc	A dc	A(pk)	°C	V dc
2N6782, U	15	0.8	100	100	±20	3.5	2.25	3.50	14.0	-55 to	
2N6784, U	15	0.8	200	200	±20	2.25	1.50	2.25	9.0	+150	
2N6786, U	15	0.8	400	400	±20	1.25	0.80	1.25	5.5		400

(1) Derate linearly 0.12 W/°C for T_C > +25°C.
(2) The following formula derives the maximum theoretical I_D limit. I_D is limited by package and internal wires and may be limited by pin diameter:

$$I_D = \sqrt{\frac{T_{JM} - T_C}{(R_{\theta JC}) \times (R_{DS}(on) \text{ at } T_{JM})}}$$

(3) See figure 5, maximum drain current graph.
(4) I_{DM} = 4 x I_{D1} as calculated in note 2.

* Comments, suggestions, or questions on this document should be addressed to DLA Land and Maritime, ATTN: VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dscc.dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.daps.dla.mil/.

AMSC N/A FSC 5961

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics at T_C = +25°C.

Type	Min $V_{(BR)DSS}$ V_{GS} = 0 I_D = 1.0 mA dc	$V_{GS(TH)}$ $V_{DS} \geq V_{GS}$ I_D = 0.25 mA dc		Max I_{DSS1} V_{GS} = 0 V_{DS} = 80 percent of rated V_{DS}	Max $r_{DS(ON)}$ (1) V_{GS} = 10 V dc		$R_{\theta JC}$ max (2)
					T_J = +25°C at I_{D2}	T_J = +150°C at I_{D2}	
	V dc	V dc		µA dc	ohm	ohm	°C/W
		Min	Max				
2N6782, U	100	2.0	4.0	25	0.60	1.20	8.33
2N6784, U	200	2.0	4.0	25	1.50	3.15	8.33
2N6786, U	400	2.0	4.0	25	3.60	9.00	8.33

(1) Pulsed (see 4.5.1).
(2) See figure 6, thermal impedance curves.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3, 4, or 5 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3, 4, or 5 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.


DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

* (Copies of these documents are available online at https://assist.daps.dla.mil/quicksearch/ or https://assist.daps.dla.mil/ or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.3 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.




Ltr	Dimensions				Notes
	Inches		Millimeters		
	Min	Max	Min	Max	
CD	.305	.335	7.75	8.51	
CH	.160	.180	4.06	4.57	
HD	.335	.370	8.51	9.40	
h	.009	.041	0.23	1.04	
J	.028	.034	0.71	0.86	2
k	.029	.045	0.74	1.14	3
LD	.016	.021	0.41	0.53	7, 8
LL	.500	.750	12.7	19.05	7, 8
LS	.200 TP		5.08 TP		6
LU	.016	.019	0.41	0.48	7, 8
L1		.050		1.27	7, 8
L2	.250		6.35		7, 8
P	.100		2.54		5
Q		.050		1.27	4
r		.010		0.25	9
α	45° TP		45° TP		6


NOTES:

1. Dimensions are in inches. Millimeters are given for general information only.
2. Beyond radius (r) maximum, J shall be held for a minimum length of .011 (0.28 mm).
3. Dimension k measured from maximum HD.
4. Outline in this zone is not controlled.
5. Dimension CD shall not vary more than .010 (0.25 mm) in zone P. This zone is controlled for automatic handling.
6. Leads at gauge plane .054 +.001, -.000 (1.37 +0.03, -0.00 mm) below seating plane shall be within .007 (0.18 mm) radius of true position (TP) at maximum material condition (MMC) relative to tab at MMC.
7. LU applies between L_1 and L_2. LD applies between L_2 and L minimum. Diameter is uncontrolled in L_1 and beyond LL minimum.
8. All three leads.
9. Radius (r) applies to both inside corners of tab.
10. Drain is electrically connected to the case.
11. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 1. Physical dimensions for TO-205AF.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.






Dimensions				
Ltr.	Inches		Millimeters	
	Min	Max	Min	Max
BL	.345	.360	8.76	9.14
BW	.280	.295	7.11	7.49
CH	.095	.115	2.41	2.92
LL1	.040	.055	1.02	1.40
LL2	.055	.065	1.40	1.65
LS	.050 BSC		1.27 BSC	
LS1	.025 BSC		0.635 BSC	
LS2	.008 BSC		0.203 BSC	
LW	.020	.030	0.51	0.76
Q1	.105 REF		2.67 REF	
Q2	.120 REF		3.05 REF	
Q3	.045	.055	1.14	1.40
TL	.070	.080	1.78	2.03
TW	.120	.130	3.05	3.30

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.
4. Ceramic package only.

FIGURE 2. Physical dimensions for LCC.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

2N6782, 2N6784, and 2N6786




Ltr	Dimensions - 2N6782				Dimensions - 2N6784				Dimensions - 2N6786			
	Inches		Millimeters		Inches		Millimeters		Inches		Millimeters	
	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max
A	0.082	0.092	2.08	2.34	0.082	0.092	2.08	2.34	0.101	0.111	2.55	2.81
B	0.059	0.069	1.48	1.74	0.062	0.072	1.57	1.83	0.071	0.081	1.81	2.07
C	0.021	0.031	0.53	0.79	0.020	0.030	0.50	0.76	0.020	0.030	0.50	0.76
D	0.020	0.030	0.50	0.76	0.019	0.029	0.47	0.73	0.019	0.029	0.47	0.73
E	0.013	0.023	0.32	0.58	0.012	0.022	0.31	0.57	0.012	0.022	0.31	0.57
F	0.014	0.024	0.34	0.60	0.013	0.023	0.32	0.58	0.013	0.023	0.32	0.58

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. Unless otherwise specified, tolerance is ±.005 inch (0.13 mm).
4. The physical characteristics of the die are: The back metals are chromium, nickel, and silver and the back contact is the drain. The top metal is aluminum.
5. Die thickness is .0187 inch (0.475 mm) ±.0050 inch (0.130 mm).

FIGURE 3. JANHCA and JANKCA die dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

2N6782 and 2N6784



Ltr	Dimensions - 2N6782 and 2N6784			
	Inches		Millimeters	
	Min	Max	Min	Max
A	.082	.089	2.08	2.26
B	.062	.066	1.58	1.68
C	.019	.021	0.48	0.53
D	.022	.024	0.56	0.61
E	.012	.014	0.30	0.36
F	.013	.015	0.33	0.38

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. Unless otherwise specified, tolerance is ±.005 inch (0.13 mm).
4. The physical characteristics of the die are: The back metals are chromium, nickel, and silver and the back contact is the drain. The top metal is aluminum.
5. Die thickness is .015 inch (0.38 mm) ±.001 inch (0.025 mm).

* FIGURE 4. JANHCB and JANKCB die dimensions (2N6782, 2N6784).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500 and as follows.

nC - nano coulomb.

* 3.4 Interface and physical dimensions. The interface and physical dimensions shall be as specified in MIL-PRF-19500 and on figures 1 (TO-205), 2 (LCC), and 3 and 4 (die) herein.

3.4.1 Lead finish. Lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4.2 Internal construction. Multiple chip construction shall not be permitted.

3.5 Marking. Marking shall be in accordance with MIL-PRF-19500.

3.6 Electrostatic discharge protection. The devices covered by this specification require electrostatic protection.

3.6.1 Handling. MOS devices must be handled with certain precautions to avoid damage due to the accumulation of static charge. However, the following handling practices are recommended (see 3.6).

a. Devices should be handled on benches with conductive handling devices.

b. Ground test equipment, tools, and personnel handling devices.

c. Do not handle devices by the leads.

d. Store devices in conductive foam or carriers.

e. Avoid use of plastic, rubber, or silk in MOS areas.

f. Maintain relative humidity above 50 percent if practical.

g. Care should be exercised during test and troubleshooting to apply not more than maximum rated voltage to any lead.

h. Gate must be terminated to source, $R \leq 100\ k\Omega$, whenever bias voltage is to be applied drain to source.

3.7 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and table I.

3.8 Electrical test requirements. The electrical test requirements shall be as specified in table I.

3.9 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.2.1 Group E qualification. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table II tests, the tests specified in table II herein that were not performed in the prior revision shall be performed on the first inspection lot of this revision to maintain qualification.

4.2.2 JANHC and JANKC die. Qualification shall be in accordance with MIL-PRF-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

4.3 Screening (JANS, JANTX and JANTXV levels only). Screening shall be in accordance with table E-IV of MIL-PRF-19500 and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table E-IV of MIL-PRF-19500) (1) (2)	Measurement	
	JANS level	JANTX and JANTXV levels
(3)	Gate stress test (see 4.3.1).	Gate stress test (see 4.3.1).
(3) (4)	Unclamped inductive switching, method 3470 of MIL-STD-750 (see 4.3.2), optional.	Unclamped inductive switching, method 3470 of MIL-STD-750 (see 4.3.2), optional.
(3) 3c	Method 3161 of MIL-STD-750 (see 4.3.3).	Method 3161 of MIL-STD-750 (see 4.3.3).
9	I_{GSSF1}, I_{GSSR1}, I_{DSS1}, subgroup 2 of table I herein.	Not applicable.
10	Method 1042 of MIL-STD-750, test condition B.	Method 1042 of MIL-STD-750, test condition B.
11	I_{GSSF1}, I_{GSSR1}, I_{DSS1}, $r_{DS(on)1}$, $V_{GS(TH)1}$, Subgroup 2 of table I herein; ΔI_{GSSF1} = ± 20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ± 20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ± 25 μA dc or ±100 percent of initial value, whichever is greater.	I_{GSSF1}, I_{GSSR1}, I_{DSS1}, $r_{DS(on)1}$, $V_{GS(TH)1}$ Subgroup 2 of table I herein.
12	Method 1042 of MIL-STD-750, test condition A, t = 240 hours.	Method 1042 of MIL-STD-750, test condition A.
13	Subgroups 2 and 3 of table I herein; ΔI_{GSSF1} = ± 20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ± 20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ± 25 μA dc or ±100 percent of initial value, whichever is greater. $\Delta r_{DS(on)1}$ = ± 20 percent of initial value. $\Delta V_{GS(TH)1}$= ± 20 percent of initial value.	Subgroup 2 of table I herein; ΔI_{GSSF1} = ± 20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ± 20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{DSS1} = ± 25 μA dc or ±100 percent of initial value, whichever is greater. $\Delta r_{DS(on)1}$ = ± 20 percent of initial value. $\Delta V_{GS(TH)1}$= ± 20 percent of initial value.

(1) At the end of the test program, I_{GSSF1}, I_{GSSR1}, and I_{DSS1} are measured.
(2) An out-of-family program to characterize I_{GSSF1}, I_{GSSR1}, I_{DSS1}, and $V_{GS(th)1}$ shall be invoked.
(3) Shall be performed anytime after temperature cycling, screen 3a; and does not need to be repeated in screening requirements.
(4) This test is optional in screening if performed in table I, subgroup 5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

4.3.1 Gate stress test. Apply V_{GS} = ±30 V minimum for t = 250 µs minimum.

4.3.2 Unclamped inductive switching.

a. Peak current (I_D)..... rated I_{D1}.

b. Peak gate voltage (V_{GS}) ..... 10 V.

c. Gate to source resistor (R_{GS})..... 25 Ω ≤ R_{GS} ≤ 200 Ω.

d. Initial case temperature (T_C)..... +25°C +10°C, -5°C.

e. Inductance (L) ..... 100 µH ±10 percent.

f. Number of pulses to be applied ..... 1 pulse minimum.

g. Pulse repetition rate ..... None.

4.3.3 Thermal impedance. The thermal impedance measurements shall be performed in accordance with method 3161 of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_H, t_{SW}, (and V_H where appropriate). Measurement delay time (t_{MD}) = 70 µs max. See table II, group E, subgroup 4 herein.

4.3.4 Screening (JANHC and JANKC). Screening of die shall be in accordance with MIL-PRF-19500. As a minimum, die shall be 100-percent probed in accordance with table I, subgroup 2, except test current shall not exceed 20 A.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500. Alternate flow is allowed for quality conformance inspection in accordance with MIL-PRF-19500.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500 and table I herein. Electrical measurements (end-points) shall be in accordance with the inspections of table I, subgroup 2 herein.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VIA (JANS) and table E-VIB (JAN, JANTX, and JANTXV) of MIL-PRF-19500 and herein. Electrical measurements (end-points) shall be in accordance with the inspections of table I, subgroup 2 herein.

4.4.2.1 Group B inspection, table E-VIA (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
B3	1051	Test condition G.
B4	1042	Intermittent operation life, test condition D; 2,000 cycles. The heating cycle shall be 1 minute minimum.
B5	1042	Accelerated steady-state operation life; test condition A, V_{DS} = rated T_A = +175°C, t = 120 hours. Read and record $V_{(BR)DSS}$ (pre and post) at 1 mA = I_D. Read and record I_{DSS} (pre and post). Deltas for $V_{(BR)DSS}$ shall not exceed 10 percent and I_{DSS} shall not exceed 25 µA. Accelerated steady-state gate bias; condition B, V_{GS} = rated, T_A = +175°C, t = 24 hours.
B5	2037	Bond strength; test condition D.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

4.4.2.2 Group B inspection, table E-VIB (JAN, JANTX, and JANTXV) of MIL-PRF-19500.

Subgroup	Method	Condition
B2	1051	Test condition G.
B3	1042	Intermittent operation life, test condition D, 2,000 cycles. The heating cycle shall be 1 minute minimum.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VII of MIL-PRF-19500 and as follows. Electrical measurements (end-points) shall be in accordance with the inspections of table I, subgroup 2 herein.

Subgroup	Method	Condition
C2	2036	Test condition E (Not required for LCC).
C5	3161	See 4.5.2, $R_{\theta JC(max)}$ = 8.33°C/W.
C6	1042	Intermittent operation life, test condition D, 6,000 cycles. The heating cycle shall be 1 minute minimum.

4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-IX of MIL-PRF-19500 and as specified in table II herein. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

4.5.2 Thermal resistance. The thermal resistance measurements shall be performed in accordance with method 3161 of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_H, t_{SW} (and V_H where appropriate). Measurement delay time (t_{MD}) = 70 μs max. See table II, group E, subgroup 4 herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical inspection	2071					
Subgroup 2						
Thermal impedance 2/	3161	See 4.3.3	$Z_{\theta JC}$			°C/W
Breakdown voltage, drain to source	3407	V_{GS} = 0 V dc, I_D = 1.0 mA dc, bias condition C	$V_{(BR)DSS}$			
2N6782, 2N6782U				100		V dc
2N6784, 2N6784U				200		V dc
2N6786, 2N6786U				400		V dc
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 0.25 mA dc	$V_{GS(TH)1}$	2.0	4.0	V dc
Gate current	3411	V_{GS} = +20 V dc, bias condition C, V_{DS} = 0	I_{GSSF1}		+100	nA dc
Gate current	3411	V_{GS} = -20 V dc, bias condition C, V_{DS} = 0	I_{GSSR1}		-100	nA dc
Drain current	3413	V_{GS} = 0 V dc, bias condition C, V_{DS} = 80 percent of rated V_{DS}	I_{DSS1}		25	µA dc
Static drain to source on-state resistance	3421	V_{GS} = 10 V dc, condition A, pulsed (see 4.5.1), I_D = I_{D2}	$r_{DS(on)1}$			
2N6782, 2N6782U					0.60	ohm
2N6784, 2N6784U					1.50	ohm
2N6786, 2N6786U					3.60	ohm
Static drain to source on-state resistance	3421	V_{GS} = 10 V dc, condition A, pulsed (see 4.5.1), I_D = I_{D1}	$r_{DS(on)2}$			
2N6782, 2N6782U					0.61	ohm
2N6784, 2N6784U					1.60	ohm
2N6786, 2N6786U					3.70	ohm
Forward voltage (source drain diode)	4011	Pulsed (see 4.5.1), I_D = I_{D1}, V_{GS} = 0 V dc	V_{SD}			
2N6782, 2N6782U					1.5	V
2N6784, 2N6784U					1.5	V
2N6786, 2N6786U					1.4	V

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 3						
High-temperature operation:		$T_C = T_J = +125°C$				
Gate current	3411	V_{GS} = +20 V dc and -20 V dc, bias condition C, V_{DS} = 0	I_{GSS2}		± 200	nA dc
Drain current	3413	V_{GS} = 0 V dc, bias condition C, V_{DS} = 80 percent of rated V_{DS}	I_{DSS2}		0.25	mA dc
Gate to source voltage (thresholds)	3403	$V_{DS} \geq V_{GS}$, I_D = 0.25 mA dc	$V_{GS(TH)2}$	1.0		V dc
Static drain to source on-state resistance	3421	V_{GS} = 10 V dc, pulsed (see 4.5.1), $I_D = I_{D2}$	$r_{DS(on)3}$			
2N6782, 2N6782U					1.08	ohm
2N6784, 2N6784U					2.81	ohm
2N6786, 2N6786U					7.92	ohm
Low-temperature operation:		$T_C = T_J = -55°C$				
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 0.25 mA dc	$V_{GS(TH)3}$		5.0	V dc
Subgroup 4						
Switching time test	3472	$I_D = I_{D1}$, V_{GS} = 10 V dc, R_G = 7.5Ω, V_{DD} = 50 percent of rated V_{DS}				
Turn-on delay time			$t_{d(on)}$			
2N6782, 2N6782U					15	ns
2N6784, 2N6784U					15	ns
2N6786, 2N6786U					15	ns

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 4 - Continued						
Rise time			t_r			
2N6782, 2N6782U					25	ns
2N6784, 2N6784U					20	ns
2N6786, 2N6786U					20	ns
Turn-off delay time			$t_{d(off)}$			
2N6782, 2N6782U					25	ns
2N6784, 2N6784U					30	ns
2N6786, 2N6786U					35	ns
Fall time			t_f			
2N6782, 2N6782U					20	ns
2N6784, 2N6784U					20	ns
2N6786, 2N6786U					30	ns
Subgroup 5						
Single pulse unclamped Inductive switching 3/	3470	See 4.3.2				
Safe operating area test	3474	See figure 7; t_p = 10 ms minimum, V_{DS} = 80 percent of maximum rated V_{DS}, ($V_{DS} \leq$ 200)				
Electrical measurements		See table I, subgroup 2 herein.				
Subgroup 6						
Not applicable						
Subgroup 7						
Gate charge	3471	Condition B				
Test 1						
On-state gate charge			$Q_{g(on)}$			
2N6782, 2N6782U					8.1	nC
2N6784, 2N6784U					8.6	nC
2N6786, 2N6786U					12	nC

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 7 - Continued						
Test 2						
Gate to source charge			Q_{gs}			
2N6782, 2N6782U					1.7	nC
2N6784, 2N6784U					1.5	nC
2N6786, 2N6786U					1.8	nC
Test 3			Q_{gd}			
Gate to drain charge						
2N6782, 2N6782U					4.5	nC
2N6784, 2N6784U					5.5	nC
2N6786, 2N6786U					7.6	nC
Reverse recovery time	3473	$d_i/ d_t \leq 100$ A/µs, $V_{DD} \leq 50$ V, $I_D = I_{D1}$	t_{rr}			
2N6782, 2N6782U		$I_F = 3.5$ A			180	ns
2N6784, 2N6784U		$I_F = 2.25$ A			350	ns
2N6786, 2N6786U		$I_F = 1.25$ A			540	ns

1/ For sampling plan, see MIL-PRF-19500.
2/ This test required for the following end-point measurements only:
Group B, subgroups 2 and 3 (JANTXV).
Group B, subgroups 3 and 4 (JANS).
Group C, subgroup 2 and 6.
Group E, subgroup 1.
3/ This test is optional if performed as a 100 percent screen.


Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

TABLE II. Group E inspection (all quality levels) for qualification or re-qualification only.


Inspection 1/	MIL-STD-750		Sample plan
	Method	Conditions	
Subgroup 1			45 devices c = 0
Temperature cycling	1051	Test condition G, 500 cycles	
Hermetic seal Fine leak Gross leak	1071		
Electrical measurements		See table I, subgroup 2	
Subgroup 2 2/			45 devices c = 0
Steady-state reverse bias	1042	Condition A, 1,000 hours	
Electrical measurements		See table I, subgroup 2	
Steady-state gate bias	1042	Condition B, 1,000 hours	
Electrical measurements		See table I, subgroup 2	
Subgroup 4			Sample size N/A
Thermal impedance curves		See MIL-PRF-19500.	
Subgroup 5			3 devices c = 0
Barometric pressure	1001	2N6786 and 2N6786U only	
Subgroup 10			22 devices c = 0
Commutating diode for safe operating area test procedure for measuring dv/dt during reverse recovery of power MOSFET transistors or insulated gate bipolar transistors	3476	Test conditions shall be derived by the manufacturer.	

1/ JANHC and JANKC devices are qualified in accordance with MIL-PRF-19500.
2/ A separate sample may be pulled for each test.


Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.



2N6782, 2N6782U



2N6784, 2N6784U



2N6786, 2N6786U

FIGURE 5. Maximum drain current versus case temperature graphs.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

2N6782, 2N6782U, 2N6784, 2N6784U, 2N6786, 2N6786U




FIGURE 6. Thermal impedance curve.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

2N6782, 2N6782U




FIGURE 7. Maximum safe operating area.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.




FIGURE 7. Maximum safe operating area - Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.




FIGURE 7. Maximum safe operating area - Continued.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead finish (see 3.4.1).

d. Product assurance level and type designator.

* e. For die acquisition, the JANHC or JANKC letter version shall be specified (see figures 3 and 4).

* 6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from DLA Land and Maritime, ATTN: VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://assist.daps.dla.mil .

6.4 Cross-reference and complement list. Parts from this specification may be used to replace the following commercial Part or Identifying Number (PIN). The term PIN is equivalent to the term part number which was previously used in this specification.

Preferred types	Commercial types
2N6782	IRFF110, IRFF111, IRFF112, IRFF113
2N6784	IRFF210, IRFF211, IRFF212, IRFF213
2N6786	IRFF310, IRFF311, IRFF312, IRFF313
2N6782U	IRFE110, IRFE111, IRFE112, IRFE113
2N6784U	IRFE210, IRFE211, IRFE212, IRFE213
2N6786U	IRFE310, IRFE311, IRFE312, IRFE313

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.

* 6.5 Suppliers of JANHC and JANKC die. The qualified die suppliers with the applicable letter version (example, JANHCA2N6786) will be identified on the QML.

JANC ordering information		
PIN	Manufacturer	
	69210	43611
2N6782	JANHCA2N6782 JANKCA2N6782	JANHCB2N6782 JANKCB2N6782
2N6784	JANHCA2N6784 JANKCA2N6784	JANHCB2N6784 JANKCB2N6784
2N6786	JANHCA2N6786 JANKCA2N6786	

6.6 Changes from previous issue. The margins of this specification are marked with asterisks to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - CR
Navy - EC
Air Force - 85
DLA - CC

Review activities:
Army - AR, MI, SM
Navy - AS, MC
Air Force - 19

Preparing activity:
DLA - CC

(Project 5961-2010-039)

* NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.daps.dla.mil/ .

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:16Z
Check the source to verify that this is the current version before use.