MILITARY SPECIFICATION

SEMICONDUCTOR DEVICE, TRANSISTOR, SILICON
TYPE 2N3906

This specification is approved for use by the Electronics Command, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the detail requirements for PNP, Silicon, Plastic encapsulated transistor, designed for general switching and amplifier applications.

1.2 Outline and Dimensions. See Figure 1 herein.

1.3 Maximum Ratings. (At T_A= +25°C, unless otherwise specified).

P_T	ΘJ-C	V_{CB}	V_{CE}	V_{EB}	I_C	T_{op} and T_{stg}
MW	MW/°C	Vdc	Vdc	Vdc	mAdc	°C
310	2.73	40	40	5	200	-55 to +150

1.4 Primary Electrical Characteristics. (At T_A= +25°C).

	h_{FE}			C_{obo}	/hfe/	NF	Switching Times	
	I_C= .1mAdc V_{CE} -1V	I_C=10mA V_{CE}-1V	I_C=50mA V_{CE}-1V	F=1MHz V_{CB}=5 IE =0 pf	f=1.0 KHZ I_C=1 MA V_{CE}=10Vdc	f=10-15.7 KHZ I_C=100uA V_{CE}=5V Rs =1kohms	V_{CC}=3.0Vdc I_C=10 mAdc IB=1 mAdc T_{on} ns	T_{off} ns
MIN	60	100	60		100			
MAX		300		4.5	400	4	70	300

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Electronics Command, ATTN: DRSEL-RD-TS-S, Fort Monmouth, NJ 07703, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 5961

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

2 APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

SPECIFICATION

MILITARY

MIL-S-19500 - Semiconductor Devices, General Specification for

STANDARDS

MIL-STD-202 - Test Methods for Electronic and Electrical Component Parts

MIL-STD-750 - Test Methods for Semiconductor Devices

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

3 REQUIREMENTS

3.1 General. Requirements shall be in accordance with MIL-S-19500, and as specified herein.

3.2 Abbreviations, symbols, and definitions. The abbreviations, symbols, and definitions used herein are defined in MIL-S-19500.

3.3 Design, construction, and physical dimensions. Transistors shall be of the design, construction, and physical dimensions shown on Figure 1. The devices covered by this specification shall be encapsulated in a plastic material which polymerizes to a rigid condition by virtue of a chemical cross-linking mechanism. Information covering the material(s) used shall be included with the qualification design data to the qualifying activity. Paragraph 3.6.1 of MIL-S-19500 does not apply to the devices covered by this specification.

3.4 Performance characteristics. Performance characteristics shall be as specified in Table I, II and III.

3.5 Marking. The following marking shall be applied:

a. Type designation and code identification

b. Manufacturer's identification and date code

4 QUALITY ASSURANCE PROVISIONS

4.1 The transistor covered by this specification (2N3906) is not intended to be certified at a higher quality level than JAN.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

4.2 Qualification and acceptance inspection shall be in accordance with MIL-S-19500 quality assurance provisions, and as otherwise specified herein. Groups A, B & C inspection shall consist of the examinations and tests specified in Table I, II & III respectively. The LTPD specified for a Subgroup in Tables I, II & III shall apply for all of the tests combined, in the subgroup. Sample units subjected to Group B, Subgroup 4 and 5 tests, shall not be delivered on the contract or order. Sample units that have been subjected to and have passed Group B, Subgroups 1, 2, 3 and 6 Tests. (These tests to be considered non destructive), may be delivered on the contract or order provided that, after Group B inspection is terminated, those sample units are subjected to and pass Group A inspection. Defective units from any sample group that may have passed group inspection shall not be delivered on the contract or order until the defect(s) has been remedied to the satisfaction of the contractor.

4.3 Particular Examination and Test Requirements:

4.3.1 All electrical test measurements shall be made at room ambient, free-air, temperature of +25° ± 3°C unless otherwise specified herein.

4.3.2 All applicable end-point test measurements shall be made, wherever possible, within four (4) hours, after the particular sample units have been subjected to the required physical-mechanical or environmental test(s). This "interval" requirement shall not be applicable to measurements specified to be made during (subjection of sample units to) a physical-mechanical or environmental test and shall not be applicable where otherwise specified for life test(s).

4.3.3. Except for intentionally deforming, mutilating, or dismembering mechanical-stress tests to which samples are subjected, there shall be no evidence of mechanical damage to any sample unit after any of the Group A, B or C tests.

4.3.4 The markings shall be legible after salt atmosphere corrosion test. There shall be no evidence (when examined with no magnification) of flaking or pitting of the finish or corrosion that will interfere with the mechanical and electrical applications of the device.

4.3.5 End-point test measurements bias moisture resistance test shall be initiated no sooner than twelve (12) hours and completed no later than forty-eight (48) hours after removal from moisture test. Prior to measurement devices must be stored in an air-conditioned room. At no greater than 25°C.

4.3.6. For the high temperature bias life test, after 1000 hours of test and prior to end-point test measurements, the devices will be allowed to cool to 25°C with the C-B voltages applied during the entire time. Within 48 hours after reaching 25°C, voltages will be removed and end-point measurements made.

4.3.7 Group A inspection shall consist of the examination and test specified in Table I. Group B inspection shall consist of the examination and test in Table II. Group C shall consist of the examination and test in Table III.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

4.3.8 For the steam pressure test, devices will be submitted to a steam pressure chamber at 15 psig ± 2 psig for 96 hours. Devices will be suspended above the water (deionized) which will be of sufficient quantity to permit 96 hours of continuous testing. Remove devices from chamber. Proceed as Para. 4.3.5.

4.3.9 External Visual: Sample shall be inspected up to 6x magnification with direct and oblique light for the following defects:

4.3.9.1 Holes or voids in the encapsulant greater than 0.025 inch in any direction.

4.3.9.2 Cracks in the encapsulant which touch any lead.

4.3.9.3 More than one sharp bend along any lead.

4.3.9.4 Flash on the body of the package greater than 0.025 inch or any protrusion which causes the device to be larger than the outline drawing dimensions.

4.3.9.5 Flash down the leads more than 0.05 inch.

4.3.9.6 Flashing of lead metallization.

4.3.9.7 Any stain, ink or encapsulant spots on the leads larger than two lead diameters.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

TABLE I - Group A Inspection

Examination or Test	Test Method per MIL-STD-750	Conditions	LTPD	SYM	Limits Min	Limits Max	Units
Subgroup 1 1/ Visual and Mechanical Examination	2071		10				
Subgroup 2 Collector-to-Base Cutoff Current	3036.1	Bias Cond. D V_{CB} = 30 Vdc I_E = 0	5	I_{CBO}	--	30	nAdc
Emitter-to-Base Cutoff Current	3061.1	Bias Cond. D V_{EB} = 3 Vdc I_C = 0		I_{EBO}	--	30	nAdc
Collector-to Base Breakdown Voltage	3001.1	Bias Cond. D I_C = 10 uAdc I_E = 0		BV_{CBO}	40	--	Vdc
Emitter-to Base Breakdown Voltage	3026.1	Bias Cond. D I_E = 10 uAdc I_C = 0		BV_{EBO}	5.0	--	Vdc
Collector-to Emitter Breakdown Voltage	3011.1	Bias Cond. D I_C = 1 mAdc 2/ I_B = 0		BV_{CEO}	40	--	Vdc
Static Forward-Current Transfer Ratio	3076.1	V_{CE} = 1.0 Vdc I_C = 0.1 mAdc 2/		h_{FE}	60	--	
Static Forward-Current Transfer Ratio	3076.1	V_{CE} = 1.0 Vdc I_C = 1.0 mAdc 2/		h_{FE}	80	--	
Static Forward Current Transfer Ratio	3076.1	V_{CE} = 1.0 Vdc I_C = 10 mAdc 2/		h_{FE}	100	300	

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

TABLE I - Group A Inspection (Cont'd)

Examination or Test	Test Method per MIL-STD-750	Conditions	LTPD	SYM	Limits Min	Limits Max	Units
Static Forward Current Transfer Ratio	3076.1	V_{CE} = 1.0 Vdc I_C = 50 mAdc 2/		h_{FE}	60	--	
Static Forward Current Transfer Ratio	3076.1	V_{CE} = 1.0 Vdc I_C = 100 mAdc 2/		h_{FE}	30	--	
Base-to-Emitter Saturation Voltage	3066.1	I_C = 10 mAdc I_B = 1.0 mAdc 2/		V_{BE}(SAT)	0.65	0.85	Vdc
Base-to-Emitter Saturation Voltage	3066.1	I_C = 50 mAdc I_B = 5.0 mAdc 2/		V_{BE}(SAT)	--	0.95	Vdc
Collector-to Emitter Saturation Voltage	3071	I_C = 10 mAdc I_B = 1.0 mAdc 2/		V_{CE}(SAT)	--	0.25	Vdc
Collector-to Emitter Saturation Voltage	3071	I_C = 50 mAdc I_B = 5.0 mAdc 2/		V_{CE}(SAT)	--	0.40	Vdc
Subgroup 3			10				
Open-Circuit Output Capacitance	3236	V_{CB} = 5.0 Vdc I_E = 0 f = 1.0 MHz		C_{obo}	--	4.5	pf
Small-Signal Short-Circuit Forward-Current Transfer Ratio	3306.2	V_{CE} = 10 Vdc I_C = 1.0 mAdc f = 1.0 kHz		h_{fe}	100	400	
Noise Figure	3246.1	V_{CE} = 5.0 Vdc I_C = 100 uAdc R_s = 1.0 k f = 10 Hz to 15.7kHz		NF	--	4.0	dB

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

TABLE I - Group A Inspection (Cont'd)

Examination or Test	Test Method per MIL-STD-750	Conditions	LTPD	SYM	Limits Min	Limits Max	Units
Extrapolated Unity Gain Frequency	3261.1	I_C = 10 mAdc V_{CE} = 20 Vdc f_C = 100 MHz		f_t	250	--	MHz
Input Capacitance	3240.1	V_{BE} = 0.5 Vdc I_C = 0 f = 1.0 MHz		C_{ibo}	--	10.0	PF
Subgroup 4 3/			15				
Delay Time	3251.1	V_{cc} = 3.0 Vdc $V_{BE(OFF)}$ = 0.5 Vdc		td	--	35	ns
Rise Time		I_C = 10 mAdc I_{B_1} = 1.0 mAdc		tr	--	35	ns
Storage Time		V_{cc} = 3.0 Vdc I_C = 10 mAdc		t_s		225	ns
Fall Time		I_{B_1} = I_{B_2} = 1.0 mAdc		t_f	--	75	ns
Subgroup 5			2				
Pulsed $V_{BE(f)}$	4011.3	I_B = 500 mAdc t = 300 us Duty Cycle 2.0%		$V_{BE(f)}$		1.45	V

1/ See Para. 4.3
2/ Pulse Test: Pulse Width 300 us Duty Cycle 2.0%
3/ Test Circuits and Procedure Per Fig. 2 herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

TABLE II - Group B Inspection

Examination or Test 1/ 2/	Test Method per MIL-STD-750	Conditions	LTPD	SYM	Limits Min	Limits Max	Units
Subgroup 1			20				
Physical Dimensions	2066						
Subgroup 2A			15				
Solderability (Omit Aging)	2026	1 Cycle					
Subgroup 2B			5				
Thermal Shock (Glass Strain)	1056.1	Test Cond. B (30 Cycles)					
Temperature Cycling	1051.1	Test Cond. F Except Low Temp -55°C					
End-Point Test							
Static forward current transfer ratio 3/ 6/	3076.1	V_{CE} = 1.0Vdc I_C = 10.0 mAdc		h_{FE}	100	300	
forward voltage	4011.3	I_B = 200 mAdc T_A = 100oC		$V_{BE(f)}$		2.0	Vdc
Subgroup 3			15				
Lead Fatigue	2036.3	Test Cond. E					
End-Point Tests Same as Subgroup 2 above							
Subgroup 4			λ = 15				
High temperature bias life 4/	1031.4	T_{stg} = 150° V_{CB} = 22.5 Vdc t = 1000 hours					
End-Point Test							
Collector-to-Base Cutoff Current 3/	3036.1	Test Cond. D V_{CB} = 30 Vdc		I_{CBO}		50	nAdc
Forward Voltage	4011.3	I_B = 200 mAdc		$V_{BE(f)}$ $\Delta V_{BE(f)}$	 7/	2.0 200	Vdc mVdc
Forward Current Transfer Ratio	3076.1	I_C = 10 mAdc V_{CE} = 1.0 Vdc		h_{FE} 7/ Δh_{FE}		± 35	%

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

TABLE II - Group B Inspection (Cont'd)

Examination or Test	Test Method per MIL-STD-750	Conditions	LTPD	SYM	Limits Min	Limits Max	Units
Subgroup 5			λ=15				
5/	1021.1	T_A = 85°C RH = 85% t = 1000 hours V_{CEO} = 15 Vdc					
End-Point Test							
Collector-to base-cutoff Current	3036.1	Test Cond. D V_{CB} = 30 Vdc		I_{CBO}	--	50	uAdc
Forward Voltage 3/	4011.3	I_B = 200 mAdc		$V_{BE}(f)$		2.0	Vdc
Forward Current Transfer Ratio	3076.1	I_C = 10 mAdc V_{CE} = 1.0 Vdc		Δh_{FE} 7/		± 35	%
Subgroup 6							
Steady State Operation Life 8/	1026.3	V_{CB} = 20 Vdc MIN P_D = 350 mW MAX T_A = 25°C T = 100 hours	λ =7				
End-Point Test Same as Subgroup 5							

1/ See Para. 4.3.2

2/ See Para. 4.3.3

3/ Pulse Test: Pulse Width ≤ 300 us
Duty Cycle ≤ 2.0%

4/ See Para. 4.3.6

5/ See Para. 4.3.5

6/ Read within 48 hours MAX

7/ Change from initial value.

8/ Test conditions to be varied within limits specified to obtain T_J = 135°C (Calculated)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

TABLE III - Group C Inspection 1/

Examination or Test	Test Method per MIL-STD-750	Conditions	LTPD	SYM	Limits Min	Limits Max	Units
Subgroup 1			7				
Steam pres-3,4/ sure		p = 15 psig +7 psig T = 121°C t = 96 hours DI Water 10MΩ					
End-Point Tests: Same as Subgroup 5, Table II							
Subgroup 2	1041	T = 72 hours	15				
Salt atmos-phere(Corrosion)							
End-Point Tests: Same as Subgroup 5, Table II							
Subgroup 3			15				
Shock	2016	1500 G, 0.5 msec, 5 Blows each, Orientations X1,Y1, Y2, Z1					
Constant acceleration	2006	20,000G					
Centrifuge							
Vibration vari- able frequency	2056	(One cycle)					
End-Point Tests: Same as Subgroup 2, Table II							
Subgroup 4			20				
Flame Test 2/							
End-Point Tests: Mechanical and Visual Inspection							

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

TABLE III - Group C Inspection (cont'd)

Examination or Test	Test Method per MIL-STD-750	Conditions	LTPD	SYM	Limits Min	Limits Max	Units
Subgroup 5 Resistance to solvents		MIL-STD 202 Test Method 215	20				
End-Point Test Visual		Markings shall have remained legible					

1/ Periodicity (Every nine (9) months)

2/ Self Extinguishing within 10 sec. per MIL-STD-202, Method III.

3/ Read within 48 hours maximum.

4/ See Paragraph 4.3.8.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.





FIG. 1

This is a TO-92 case, except the following notes apply:

Note 1; Package Height Z shall be .170" min. .185" max.

Note 2; Flash may be present on device to a height of .005" max.


Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.



DUTY CYCLE = 2%

I_C = 10 ma, I_B = 1ma, V_{BE}(OFF)=0.5V, V_{CC}= -3.0V

DELAY AND RISE TIME EQUIVALENT TEST CIRCUIT



DUTY CYCLE = 2%

I_C = 10 ma, I_{B1} = I_{B2} = 1ma, VCC= -3.0V

STORAGE AND FALL TIME EQUIVALENT TEST CIRCUIT

FIG. 2

* TOTAL SHUNT CAPACITANCE OF TEST FIXTURE AND CONNECTORS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

5. Preparation for Delivery

5.1 Preparation for Delivery. Preparation for delivery shall be in accordance with MIL-S-19500.

6. NOTES

6.1 Notes. The notes specified in MIL-S-19500 are applicable to this specification.

Custodian:
Army - ER

Preparing activity:
Army - ER

(Project 5961-A720)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY
DoD - 304

U.S.MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Cdr, US Army ERADCOM
ATTN: DELET-RP
Fort Monmouth, NJ 07703

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE: MIL-S-19500/530(ER) SEMICONDUCTOR DEVICE, TRANSISTOR, SILICON TYPE 2N3906

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:50Z
Check the source to verify that this is the current version before use.