COMMERCIAL ITEM DESCRIPTION

GASKET
(ASBESTOS)

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification HH-G-76C, type II.

This description covers metallic cloth gaskets for use with flamed joints, boiler manholes and handholes and in applications using steam, gases, air and aqueous solutions other than strong mineral acids up to 300 psi and 600° F.

Salient characteristics:

Gaskets shall be the jointed type. The cloth shall be cut on the bias and folded into required shapes and thicknesses after the ends have been securely jointed together.
Gaskets shall contain not less than 3 plies of asbestos wire-inserted cloth.
Plies of asbestos cloth shall be uniformly impregnated with friction compound. The friction compound shall be not more than 50 percent, by weight, of the finished gasket and shall not contain more than 30 percent, by weight, of rubber hydrocarbon.
Shall be of the following sizes, as specified:

3 x 4 inches I.D. (Size 1)
3-1/2 x 4-1/2 inches I.D. (Size 2)
11 x 15 inches I.D. (Size 3)

Dimensions and tolerances shall be as follows in Table I.

TABLE I. Dimensions and Tolerances

Inside Dimensions			Flange Width	Thickness	Tolerances 1/	
Minor Axis Inches	X	Major Axis Inches	Inches	Inches	Inches	Perimeter
11		15	1-1/4	1/4	1/32	1/32 on I.P. 2/ 20 inches or less.
3		4	5/8	1/4	1/32	
3-1/2		4-1/2	5/8	1/4	1/32	1/16 on I.P. more than 20 inches.

1/ No minus tolerances permissible
2/ I.P. - Inside perimeter

Each strand of the warp and filler in the cloth used in construction of the gaskets shall consist of 3 plies of asbestos yard for thicknesses, and 1 copper zinc alloy wire twisted together.
Each strand of yard shall contain not less than 18 strands per inch in the warp and not less than 9 stands per inch in the filler.
The copper zinc alloy wire used in the construction of the strands shall be 0.007 inch in diameter with a tolerance of -.001 inch, + .002 inch.
The weight of the asbestos wire-inserted cloth before insertion shall be not less than 2.75 pounds per square yard.

Workmanship. Gaskets shall be free from cracks, hardening, flowing in the friction compound and any other defects that will affect their function or serviceability.

FSC 5330

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:12Z
Check the source to verify that this is the current version before use.

Certification. The contractor shall certify that the product offered meet the salient characteristics of this description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices, and is the same product sold in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements. The manufacturer shall utilize recovered materials to the maximum extent practicable.

Packaging, packing, and marking. Packaging, packing, and marking shall be as specified in the contract or order.

MILITARY INTERESTS:

Custodians

Army - MR
Navy - SH
Air Force - 85

Review Activities

Army - MR
Navy - SH
Air Force - 85

User Activity

Army - AR

PREPARING ACTIVITY

GSA-FSS

GSA DC-01201118

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:12Z
Check the source to verify that this is the current version before use.