[INCH-POUND]
A-A-1272B
May 26, 1998
SUPERSEDING
A-A-1272A
November 1, 1991

COMMERCIAL ITEM DESCRIPTION

PLASTER, GYPSUM (SPACKLING COMPOUND)

The General Services Administration has authorized the use of this commercial item description for all Federal agencies.

1. SCOPE

1.1 Scope. This commercial item description (cid) covers spackling compound (gypsum or acrylic plaster) intended for filling small cracks, holes, dents, scars, or imperfections in drywall, or knotholes and nail holes in wood.

2. CLASSIFICATION

2.1 Classification. The spackling compound shall be of the following types and sizes.

Type I - Powder
  Size 1 - 4 to 5 pound bag or box
  Size 2 - 25 pound bag or box

Type II - Paste
  Class 1 - Normal weight (11-16 lbs./gal.)
  Class 2 - Light weight (3-6 lbs./gal.)
    Size 3 - 1 quart can
    Size 4 - 1 gallon can

3. SALIENT CHARACTERISTICS

3.1 Materials. The spackling compound (gypsum plaster) shall not contain asbestos.

3.1.1 Type I. The type I compound shall be a fine white powder of a uniform mixture of suitable filler, binders, and modifying agents that mix readily with water to form a smooth paste that dries hard in not more than 5 hours under standard operating conditions (75°F, 50% RH) and good ventilation. The size 1 shall consist of a minimum of 4 pounds of spackling compound and the size 2 shall consist of a minimum of 25 pounds of spackling compound.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: General Services Administration, Engineering Branch (7FXEE), 819 Taylor Street, Fort Worth, TX 76102.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:12Z
Check the source to verify that this is the current version before use.

3.1.2 Type II. The type II compound shall be a pre-mixed paste that dries white (in color) consisting of pigment, binder, and preservative that is not sticky or gummy when applied with trowel or broad knife. The type II compound shall be free of putrid odor. A slight acrylic/ammonia odor shall be acceptable. The size 3 shall consist of a minimum of 1 quart of spackling compound and the size 4 shall consist of a minimum of 1 gallon of spackling compound.

3.1.2.1 Class 1. The class 1 compound shall harden within eight hours after application (in voids not to exceed one-quarter inch in depth) under standard operating conditions (75°F, 50% RH) and good ventilation.

3.1.2.2 Class 2. The class 2 compound shall harden within eight hours after application (in voids not to exceed one-quarter inch in depth) under standard operating conditions (75°F, 50% RH) and good ventilation. The class 2 compound shall be capable of accepting paint after two hours. The class 2 spackling compound shall be designed for onetime use.

3.2 Performance requirements.

3.2.1 Fineness. The type I compound shall pass no less than 95 percent of dry powder through a No. 100 mesh screen.

3.2.2 Density. The type II, class 1 compound shall have a minimum density of 10.5 pounds per gallon. The type II, class 2 compound shall have a minimum density of 3.0 pounds per gallon.

3.2.3 Chalking and contraction. The type I and II compounds shall not chalk, nor sag when applied to deep narrow cracks and shall not pull away from edges of cracks.

3.3 Workmanship. Type I powder shall be smooth, uniform, and free from extraneous material. Type II paste shall be homogeneous, and free from caking, granulation, hardening, and putrid odor.

3.4 Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within tolerances specified and all other requirements of this document are met. If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch-pound units, a request should be made to the contracting officer to determine if the product is acceptable.

4. REGULATORY REQUIREMENTS

4.1 Recovered materials. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

5. QUALITY ASSURANCE PROVISIONS

5.1 Product conformance. The products provided shall meet the salient characteristics of this commercial item description, shall conform to the producer's own drawings, specifications, standards, and quality assurance practices and be the same product that has been sold in the commercial marketplace for over two years, or is the same product that has been successfully been delivered to the government on a previous contract or

Source: https://assist.dla.mil -- Downloaded: 202640-26T08:12Z
Check the source to verify that this is the current version before use.

purchase order. The Government reserves the right to require proof of such conformance prior to the first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

6. PACKAGING

6.1 Preservation, packing, and marking. Preservation, packing, and marking shall be as specified in the contract or purchase order.

7. NOTES

7.1 Part Numbering. The following part identification number procedure is for government purposes and does not constitute a requirement for the contractor.

Part Numbering System for Commercial Item Description A-A-1272

Example: AA1272-212 (AA1272-212) Example - Type II, class 1, size 2

```
          |   |||
          |   |||--- Size (1, 2, 3, or 4)
          |   ||--- Class (1 or 2)
          |   |---- Type (1 - Type I, 2 - Type II)
          |---- CID number
```

7.2 Government Document sources.

Copies of the Code of Federal Regulations (CFR) are available from the Superintendent of Documents, US Government Printing Office, Washington, DC 20402, (Internet - http://www.access.gpo.gov).

7.3 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents (if applicable).

a. Title, number, and date of this commercial item description.
b. Type, class, and size spackling compound required (see 2.1).
c. Preservation, packing and marking requirements.

7.4 National Stock Numbers (NSN's): The following is a list of NSN's assigned which correspond to this CID. The list may not be indicative of all possible NSN's associated with the CID.

Type	Size	NSN	Nomenclature	P/N
I	1	5610-00-550-6137	Plaster	AA1272-11
I	2	5610-00-171-4723	Plaster	AA1272-12
II	3	5610-00-926-4562	Plaster	AA1272-213
II	4	5610-00-926-4561	Plaster	AA1272-214

PREPARING ACTIVITY:
GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T08:12Z
Check the source to verify that this is the current version before use.