A-A-1701
October 18, 1982

COMMERCIAL ITEM DESCRIPTION

BOX, SHIPPING, CORRUGATED FIBERBOARD, HIGH COMPRESSION STRENGTH, WEATHER RESISTANT, WAX-RESIN TREATED

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification PPP-B-1163, class I.

This description covers double wall corrugated boxes or sheets (weather resistant), wax-resin treated, high compressior strength (primarily intended for shipping containers).

Salient characteristics.

Boxes or sheets shall be fabricated from unbleached kraft corrugated fiberboard which has been wax-resin treated and is low water absorbing and double wall.

Size: As specified in the solicitation (see note (1)).

Class: Weather resistant, high compression strength.

Style: As specified: RSC, OSC, HSC, HSCS, DCC (see note (2)) sheets.

Conditioning for testing: Test samples shall be in accordance with ASTM D 685.

Bursting strength: 275 or 350 pounds when tested in accordance with ASTM D 2738 (see note (3)).

Direction of flutes: Perpendicular to score lines or edge of the box opening.

Staple length: 1/2 inch ± 1/16 inch minimum.

Staple thickness: 0.020 inch with minus tolerance of 0.001 inch.

Crown size: 3/8 inch ± 1/16 inch.

Adhesive: Adhesive used to fabricate the fiberboard shall be water-resistant. Separation of components on unwaxed board shall not exceed 1/4 inch from the edge of the specimens when tested in accordance with ASTM D 1028.

Wax treatment: Wax treatment shall result in not less than 40 percent increase in basis weight when tested in accordance with ASTM D 590.

Test methods:

ASTM D 685	Conditioning Paper and Paper Board for Testing
ASTM D 590	Petroleum Wax in Paper
ASTM D 1028	Ply Separation (Wet) of Solid and Corrugated Fiberboard
ASTM D 2738	Bursting Strength of Corrugated Board

The issue of each ASTM test method in effect on the date of the solicitation shall be used to determine compliance with these requirements.

Regulatory requirements. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable.

Preservation, packaging, packing, labeling, and marking. The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.

Notes:

(1) Purchasers should specify inside dimensions (L x W x D) and fluting required.

(2) RSC = regular slotted container; OSC = overlap slotted container; HSC = half slotted container (specify with or without cover); HSCS = half slotted box with tube and cover; DCC = double cover box.

(3) Specify bursting strength.

(4) Specify minimum content of recycled materials.

(5) Specify packaging and packing required.

Copies of ASTM standards may be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

MILITARY INTERESTS:

Custodians

Army - GL
Navy - SA
Air Force - 69

Review Activities

Army - GL, SM
Navy - AS, OS, SA
Air Force - 70, 84
DSA - GL

User Activities

Army - AV, WC, EL
Navy - AS, YD, MC, EC
Air Force - 70, 84

CIVIL AGENCY COORDINATING ACTIVITIES:

HHS
AGR
INT
JUS-FPI

PREPARING ACTIVITY:

GSA-OPP

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.