A-A-2528
February 6, 1987

COMMERCIAL ITEM DESCRIPTION

LADLE, MELTING, HAND

The General Services Administration, has authorized the use of this commercial item description in preference to GGG-L-51, Type I.

This description covers double lip ladle generally used for plumbers for transporting and pouring molten metals and occasionally used for melting metals such as lead, solder, and babbitt.

Salient characteristics.


Material used in the construction of the ladle shall be grade 1008 hot rolled in accordance with the American Iron and Steel Institute (AISI) or equivalent steel, malleable iron, wrought iron, cast iron, or iron alloy passing high heat retentivity qualities. The ladle shall be provided with two lips on the top rim of the bowl. Each of the lips shall be located at a right angle to the center line of the handle. The ladle shall have a smooth, even surface in accordance with industry practice.

The ladle shall be capable of resisting thermal shock when tested as follows:

"Ladle samples shall be heated to 700 degrees F., plus or minus 20 degrees F., and quenched in water at approximately 70 degrees F., and shall be subjected to a light tap on the side of the bowl to obtain a clear resonant ring. A flat nonresonant ring indicates an invisible crack and shall be cause for rejection."

The handle of the ladle shall be either integral or attached to the bowl in such a manner to preclude it from working loose under service conditions.

See figure below.



Each ladle shall be marked in a plain and permanent manner with the manufacturer's name or with a trademark of such known character that the source of manufacture may be readily identifiable.

Dimensions. The dimensions of the ladles shall conform to the table below and when ordering, the diameter of the bowl shall be as specified in the contract or order.

National Stock Numbers	Dia. of bowl ±1/4	Depth of bowl		Thickness of bowl		Length of bowl	
		Min.	Max.	Min.	Max.	Min.	Max.
	Inches	Inches		Inches		Inches	
5120-00-288-9186	2-1/2	1	1-1/4	3/32	1/8	9	11-1/2
5120-00-242-3192	3	1-1/8	1-1/2	3/32	1/8	11	11-1/2
5120-00-222-1705	4	1-1/16	1-3/4	3/32	5/32	12	16
5120-00-221-1349	6	2-3/16	2-5/8	1/8	7/32	20	24

FSC 5120

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:23Z
Check the source to verify that this is the current version before use.

Workmanship. The ladles shall be clean and free from scale, pits, nodules, burrs, cracks, blowholes, sand inclusions, dark colored and chilled spots or any other defects which might affect appearance or serviceability.

Quality Assurance Provisions.

Inspection. Sampling for inspection shall be in accordance with MIL-STD-105, Sampling Procedures and Tables for Inspection by Attributes, except where otherwise indicated herein. The lot size shall consist of all ladles of the same size offered for acceptance at one time. The sample unit is one ladle.

Examination for visual and dimensional requirements. Each ladle shall be examined for workmanship, marking, and dimensional requirements. The inspection level shall be Special Inspection Level S-2 with an acceptable quality level (AQL) of 4.0 percent defective.

Testing for thermal shock. Each ladle shall be tested for thermal shock. The inspection level shall be Special Inspection Level S-1 with an AQL of 2.5 percent defective.

Regulatory requirements. In accordance with section 23.403 of the Federal Acquisition Regulations, the Government's policy is to acquire items composed of the highest percentage of recovered materials practicable, consistent with maintaining a satisfactory level of competition without adversely affecting performance requirements or exposing supplier's employees undue hazards from the recovered materials.

Preservation, packaging, packing, labeling, and marking. Preservation, packaging, packing, labeling, and marking shall be as specified in the contract or purchase order.

Notes. Purchasers should specify diamater of bowl, and dimensions in the contract or purchase order.

The issue of referenced documents in effect on the date of invitation for bid or request for proposals shall be used to determine compliance with the stated requirements. Sources for obtaining referenced documents may be determined by contacting the Contracting officer.

American Iron and Steel Institute, 150 East 42nd Street, New York, NY 10017.

PREPARING ACTIVITY

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 20261O-26T08:23Z
Check the source to verify that this is the current version before use.