INCH-POUND

MIL-C-70741 (AR)
AMENDMENT 1
15 February 1993

MILITARY SPECIFICATION

CONTAINER, METAL, PA117

This amendment forms a part of Military Specification MIL-C-70741 (AR), dated 27 February 1992, and is approved for use by the U.S. Army Armament, Munitions, and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.4 Painted surface. After the last sentence, add the following: "Bare spots are permissible on all bearing surfaces."

PAGE 4

3.6.1 Delete in its entirety and substitute:

"3.6.1 Air pressure of unpainted cover assembly. The unpainted cover assembly shall withstand an internal air pressure, after stabilization, of three (3) psi ± .5 psi for five (5) seconds minimum, without leakage occurring.

3.6.2 Delete in its entirety and substitute:

"3.6.2 Air pressure of unpainted body assembly. The unpainted body assembly shall withstand an internal air pressure, after stabilization, of three (3) psi ± .5 psi, for five (5) seconds minimum, without leakage occurring."

PAGE 19

4.4.2.10 Major defect 101. Under Examination of Test Section, add "(Unpainted)".

DISTRIBUTION STATEMENT A Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:56Z
Check the source to verify that this is the current version before use.

PAGE 21

4.4.2.12 Rim.

a. After Major defect 103, add "(see Note)"
b. In Notes Section, add "This inspection may be performed on the body weldments."

PAGE 24

4.4.2.15 Body.

a. After Major defect 102, add "See Note)"
b In Notes section, add "2. This inspection may be performed on the body weldments."

PAGE 28

4.4.3.1 Tensile strength of body material and weld. Delete the following (next to last) sentence: "A tensile strength test shall be performed whenever an electrode is changed or dressed."

4.4.3.2 Weld strength of rim to body. Delete the following (last) sentence: "A tensile strength test shall be performed whenever an electrode is changed or dressed."

PAGE 30

4.5.6.1 Air pressure of unpainted cover assembly and unpainted body assembly.

a. After title, delete "(Water immersion method)"
b. Delete the fifth sentence and substitute, "Observation shall be made for a pressure drop exceeding the requirement."
c. Delete the sixth sentence.

Custodian:
Army-AR

Preparing activity:
Army-AF

(Project 8140-A964)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:56Z
Check the source to verify that this is the current version before use.