INCH-POUND

MIL-P-70794(AR)
AMENDMENT 1
15 April 1990

MILITARY SPECIFICATION

PROJECTILE, 20 MILLIMETER, MULTIPURPOSE
TRACE SELF-DESTRUCT, M940
METAL PARTS

This amendment forms a part of Military Specification MIL-P-70794(AR), dated 31 March 1989 and is approved for use within the U.S. Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

2.2, Under AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM): Add, "ASTM E384 - Standard Test Method for Microhardness of Materials".

PAGE 8

4.3.3, TABLE I, Add the following under Body Projectile (Dwg 12551782), "Crimp Ability, 20, ACC-0/REJ-1, 3.2, 4.5.7".

PAGE 21

4.4.3, TABLE II, Add the following "Crimp Ability (projectile body and metering disc), 20, 7/, 3.2, 4.5.7" and "7/ If one or more of the crimped projectile bodies shows evidence of cracking on the periphery of the crimp the lot shall be rejected.".

PAGE 24

4.5.6, Delete "The method of test shall be in accordance with ASTM E18, Rockwell superficial hardness of metallic materials.".

4.5.6.1, Add the following after Nose cap. "The method of test shall be in accordance with ASTM E18.".

AMSC N/A

FSC 1305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:03Z
Check the source to verify that this is the current version before use.

4.5.6.2, Delete in its entirety and substitute the following:

"4.5.6.2 Projectile Body. The projectile body test sample (s) shall be sectioned as shown on Dwg. 12551782. Care shall be taken not to change the hardness while sectioning the projectile body. Two determinations each shall be made at the indicated positions for each sample body. The method of test for the annealed portion of the projectile body shall be in accordance with ASTM E384. A minimum indention load of 240 grams shall be used. The method of test for the unannealed portion of the projectile body shall be in accordance with ASTM E18.".

4.5.7, Add the following:

"4.5.7 Crimp ability. Insert a metering disc in each of the sample projectile bodies. Crimp the boattail over the metering disc continuously around the periphery of each sample projectile body. Visually examine the crimped periphery under 10X magnification for evidence of cracks.".

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1305-AD36)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T04:03Z
Check the source to verify that this is the current version before use.