MILITARY SPECIFICATION
PROJECTILE, 4.2 INCH, HE, M329A2
METAL PARTS ASSEMBLY

This amendment forms a part of Military Specification MIL-P-50718A(MU), dated 9 May 1973, and is approved for use by all Departments and Agencies of the Department of Defense.

Delete paragraph 3.6.3 in its entirety and substitute the following:

"3.6.3 Visual standards.-Visual standards for metal defects will be established for each contract after the first month's production or whenever requested by the procuring contracting agency. (See 6.1)"

Paragraph 4.3.2.5, under MAJOR characteristics, delete 101 through 110 in their entirety and substitute the following:

"101.	Presence, location and depth of slits	Visual (see 6.9)
102.	Material defective	Visual"

Delete paragraph 4.4.1.2.1 in its entirety and substitute the following:

"4.4.1.2.1 Yield strength and elongation.-From the samples selected in accordance with 4.3.3.1.2.1, seven tension test specimens conforming to the largest obtainable standard "R" type specimen as prescribed by ASTM Method E-8 shall be taken from each sample as follows: two longitudinal tension test specimens from the ogive area 180 degrees apart; two longitudinal tension test specimens in the body area between the ogive and zone 1, 180 degrees apart; two longitudinal tension test specimens midwall of the band seat area, with the gage length centered under the band, 180 degrees apart; and one transverse tension test specimen from the rear face of the body approximately three quarters of an inch from the centerline. The number of specimens and their location is to determine the acceptability of the mechanical properties requirements of the applicable drawing and with the approval of the procuring agency, the Government shall not be restricted from testing additional specimens at other locations to determine that the mechanical properties of the projectile conform to the drawing requirements. The criteria for performing this test shall be as prescribed by ASTM Method E-8 except that elongation shall be measured to the nearest thousandth (0.000) prior to conversion into percent elongation. Percent elongation shall be recorded to the nearest tenth. (0.0) percent.

Add paragraph 6.9 as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:35Z
Check the source to verify that this is the current version before use.

"6.9 When inspecting for slits, the obturator shall be distorted near slits in such a manner so that the slits are visible. Should the depth of the slits be in doubt as a result of visual examination, it may be measured or gaged to determine acceptability."

Custodian:

Army - MU

Preparing activity:

Army - MU

Project No. 1315 - A269

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:35Z
Check the source to verify that this is the current version before use.