MIL-F-11265A
23 JUNE 1952
SUPERSEDING
MIL-F-11265(CmlC)
11 JULY 1951

MILITARY SPECIFICATION

FIBERBOARD, FACEFORM, GAS MASK

This specification was approved by the Departments of the Army, the Navy, and the Air Force for use of procurement services of the respective Departments.

1. SCOPE

1.1 This specification covers fiberboard for use in the manufacture of gas mask faceforms.

2. APPLICABLE SPECIFICATIONS, STANDARDS, DRAWINGS, AND PUBLICATIONS

2.1 The following specifications and standards, of the issue in effect on date of invitation for bids, form a part of this specification:

SPECIFICATIONS

FEDERAL

UU-P-31 —Paper, General Specifications and Methods of Testing.
UU-T-116 —Tape, Paper, Gummed, Water-Resistant.
ZZ-R-601 —Rubber Goods; General Specifications (Methods of Physical tests and Chemical Analyses).
LLL-B-631 —Boxes, Fiber, Corrugated (For Domestic Shipment).
LLL-B-636 —Boxes, Fiber, Solid (For Domestic Shipment).

NAVY DEPARTMENT

General Specifications for Inspection of Material.

STANDARDS

MILITARY

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129—Marking of Shipments.

(Copies of specifications, standards, and drawings required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Material.—The material shall be made from cellulosic fibers and shall not contain sizing, filling, coloring, coating, or other materials which react chemically with rubber. The contractor shall furnish a statement showing the kind and amount of materials used in the manufacture of fiberboard.

3.2 Thickness.—The thickness of the fiberboard shall be .073 ± .007 inch or .093 ± .007 inch, as specified (see 6.1).

3.3 Density.—The minimum density of the dry material shall be 1.0 gram (gm.) per cubic centimeter when tested as specified in 4.4.2.

3.4 Tensile strength.—The average tensile strength of the fiberboard shall be not less than 6,000 pounds per square inch (p.s.i.) in the machine direction and 2,000 p.s.i. in the crosswise direction when tested as specified in 4.4.3.

3.5 Cohesion.—The material shall show no cracking or delamination when tested as specified in 4.4.4.

3.6 Effect on rubber.—Rubber specimens, after being subjected to the test specified in

983349—52—(683)

Source: https://assist.dla.mil -- Downloaded: 202610-17T15:48Z
Check the source to verify that this is the current version before use.

4.4.5, shall have an average tensile strength of not less than 90 percent of the average tensile strength of control specimens.

3.7 Workmanship.—All work shall be done in a neat and workmanlike manner. The surfaces of the material shall be smooth, uniform and free from sharp points, edges or cracks.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Lot.—Each shipment of material shall constitute a lot. The inspection lot within the above limitations, shall be designated by the inspector.

4.2 Sampling.

4.2.1 *For inspection.*—Sampling for nondestructive inspection shall be in accordance with Standard MIL–STD–105.

4.2.2 *For tests.*—Sampling for tests shall be in accordance with Method 160 of Specification UU–P–31.

4.3 Inspection.

4.3.1 *General.* — The samples selected as specified in 4.2.1 shall be visually inspected for compliance with 3.7.

4.3.2 *Packing and marking.*—The inspector shall inspect the packing and marking for compliance with section 5.

4.3.3 *Procedures.* — For Navy purchases, the general inspection procedures shall be in accordance with General Specifications for Inspection of Material.

4.4 Tests.

4.4.1 *Thickness.*—Five measurements shall be taken at widely scattered points on each sample board with a suitable thickness gage or micrometer accurate to a 0.001 inch.

4.4.2 *Density.*—Cut one specimen approximately 4 by 4 inches from each sample board and dry to a constant weight in an oven maintained at 212° ± 10°F. Cool in a desiccator and weigh to the nearest milligram. Determine the length and width of the specimen to the nearest .01 inch and the average thickness to the nearest .001 inch. Calculate the volume in cubic inches and convert to cubic centimeters. The density shall be calculated by dividing the weight of the specimen by its volume in cubic centimeters.

4.4.3 Tensile strength.—Test in accordance with Specification UU–P–31.

4.4.4 *Cohesion.* — One specimen approximately 2 by 6 inches shall be cut from each sample board. The 6-inch dimension shall be parallel to the machine direction of the sheet. The specimen shall be flexed over a 1-inch mandrel through a 180° arc in not less than 3 nor more than 5 seconds. The test shall be conducted at 75° ± 5°F. and the specimens examined visually for cracking or delamination.

4.4.5 *Effect on rubber.*—Cut 20 specimens approximately 1 by 6 by .075 inch from test slabs, formulated from a compound containing at least 85 percent of natural rubber by volume. The test slabs shall be known to have a minimum tensile strength of 2,600 p.s.i. Place each of 10 rubber specimens between two 1- by 6-inch strips of fiberboard and secure with paper clips. Place the 10 sandwiched specimens and 10 untreated rubber specimens (controls) in a circulating air oven maintained at 212° ± 2°F. for 24 hours, remove and condition at room temperature for not less than 16 hours. Remove fiberboard and determine the tensile strength of each of the 20 rubber specimens in accordance with the applicable sections of Specification ZZ–R–601. Compute the average tensile strength of the 10 specimens aged in contact with the fiberboard and of the 10 control specimens. Compare the average figures.

4.5 Retests.—If the material fails to conform to any requirement, the lot shall be re-

Source: https://assist.dla.mil -- Downloaded: 20260-17T15:48Z
Check the source to verify that this is the current version before use.

sampled as specified in Specification UU-P-31, Method 160, and retested for all the requirements of this specification. If, on retest, the material fails to conform to this specification, the lot shall be rejected.

5. PREPARATION FOR DELIVERY

5.1 Packing.—Fiberboard shall be packed on skids, in bundles, or in fiberboard boxes. If fiberboard boxes are used, they shall conform to Specification LLL-B-631 or LLL-B-636 and shall be sealed with gummed paper tape conforming to Specification UU-T-116.

5.2 Marking.—Shipments shall be marked in accordance with Standard MIL-STD-129.

6. NOTES

6.1 Ordering data. — Procurement documents should specify the following:

(a) Title, number, and date of this specification.

(b) Thickness and width of fiberboard desired.

6.2 Sampling and testing.—When the contractor consistently produces high-quality material and operates under a system of quality control acceptable to the Government, the Government, at its discretion, may modify, in whole or in part, the sampling and testing procedures specified herein. However, the Government reserves the right to return at any time, without previous notice to the contractor, to the sampling and testing procedures specified in this specification.

Notice.—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

Custodians:
Army—Chemical Corps
Navy—Bureau of Yards and Docks

Other interest:
Navy—ShSMd.

Source: https://assist.dla.mil -- Downloaded: 202610-17T15:48Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:48Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY

POSTAGE AND FEES PAID
NAVY DEPARTMENT

OFFICIAL BUSINESS

COMMANDING OFFICER
U. S. ARMY MUNITIONS COMMAND
ATTN: SMUFA-5500
PHILADELPHIA, PA. 19137

FOLD

Source: https://assist.dla.mil -- Downloaded: 202610-17T15:48Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof)*.

SPECIFICATION

ORGANIZATION *(Of submitter)*	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD, FORM 1 APR 63 1426 REPLACES NAVSHIPS FORM 4863, WHICH IS OBSOLETE

Source: https://assist.dla.mil -- Downloaded: 202610-17T15:48Z
Check the source to verify that this is the current version before use.