MILITARY SPECIFICATION

CORK SHEET, BULLETIN BOARD

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE AND CLASSIFICATION

1.1 Scope.- This specification covers cork sheet for facings on bulletin boards.

1.2 Classification.- Bulletin board cork facings shall be of the following types, as specified (see 6.1):

Type I - Single layer cork sheet pressed on burlap backing.

Type II - Single layer cork sheet without backing or facing.

Type III - Single layer cork backing sheet laminated to a facing of plastic film, or supported vinyl coated fabric.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

SPECIFICATIONS

FEDERAL
UU-P-271 - Paper, Wrapping, Waterproofed Kraft.
PPP-B-636 - Box, Fiberboard.
PPP-B-640 - Boxes, Fiberboard, Corrugated, Triple, Wall.

STANDARDS

MILITARY
MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications.- The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

OFFICIAL CLASSIFICATION COMMITTEE
Uniform Freight Classification Rules.

(Application for copies should be addressed to the Official Classification Committee, 1 Park Avenue at 33rd Street, New York 16, N. Y.)

3. REQUIREMENTS

3.1 Material.- The bulletin board material shall be a continuous resilient cork sheet made from soft, clean, granulated cork relatively free from hardback and dust and bonded with a binder suitable for the purpose intended.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:36Z
Check the source to verify that this is the current version before use.

3.2 Construction.-

3.2.1 Type I.- The cork sheet shall be a single layer pressed on burlap backing. The burlap backing shall be deeply imbedded and keyed to the cork sheet so as to be partially concealed in it. A pull of not less than 6 pounds (lbs.) shall be required to separate it from the cork sheet. The burlap shall not break or tear for a distance of more than 2 inches under the load of 6 pounds (see 4.3.1).

3.2.2 Type II.- The bulletin board material shall be a continuous resilient cork sheet made from soft, clean, granulated cork relatively free from hard back and dust and bonded with a binder suitable for the purpose intended. The cork sheet shall have a tensile strength of not less than 40 pounds per square inch (p.s.i.) (see 4.3.2).

3.2.3 Type III.- The cork backing sheet shall be a single layer laminated to a facing of plastic film or supported vinyl coated fabric. A pull of not less than 6 pounds shall be required to separate it from the cork backing sheet. The plastic shall not break or tear for a distance of more than 2 inches under the load of 6 pounds (see 4.3.2).

3.3 Color.-

3.3.1 Type I.- The color shall be light tan, light gray or light green, as specified (see 6.1).

3.3.2 Type II.- The color shall be light tan.

3.3.3 Type III.- The color shall be as specified (see 6.1).

3.4 Seasoning.- The material shall be thoroughly seasoned. The interior shall show no evidence of being soft or sticky (see 4.3.3).

3.5 Pliability.- The material shall show no cracks or surface breaks (see 4.3.4).

3.6 Dimensions.-

3.6.1 Width.- The sheet shall be furnished in widths of 36, 42, 48, or 72 inches, as specified (see 6.1). No minus tolerances will be permitted but an excess in width will be permitted.

3.6.2 Length.- Cork sheet shall be furnished in rolls 25 yards, ±6 inches, in length, except that no single piece shall be less than 10 feet.

3.6.3 Thickness.-

3.6.3.1 Type I.- The thickness shall be 1/8 or 1/4 inch, as specified, plus or minus 0.02 inch.

3.6.3.2 Type II.- The thickness shall be 1/16, 1/8, or 1/4 inch, as specified, plus or minus 0.02 inch.

3.6.3.3 Type III.- The thickness shall be 1/4 inch or as specified, plus or minus 0.02 inch.

3.7 Weight.-

3.7.1 Type I.- Bulletin board shall weigh not less than 4.0 pounds nor more than 9.0 pounds per square yard (see 4.3.5).

3.7.2 Type II.- The material shall weigh not less than 2.5 pounds nor more than 5.5 pounds per square yard for the 1/4 inch thickness with the weight of the other thicknesses in proportion.

3.7.3 Type III.- The material shall weigh not less than 3.5 pounds nor more than 7.5 pounds per square yard for the 1/4 inch thickness with other thicknesses in proportion.

3.8 Mounting.- The cork sheet, when suitably mounted, shall permit the ready insertion and removal of pins and thumb tacks.

Source: https://assist.dla.mil -- Downloaded: 20260-18T05:36Z
Check the source to verify that this is the current version before use.

3.9 Workmanship.-

3.9.1 Types I and II.- The wearing surface shall be as smooth as possible consistent with the coarse character of the cork, and of uniform color, free from streaks, spots, cracks, or other imperfections that would impair its usefulness or appearance.

3.9.2 Type III.- The wearing surface shall be of uniform embossed texture and of uniform dispersion of color or colors, free from streaks, spots, cracks, or other imperfections that would impair its usefulness or appearance.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.- Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Sampling for quality conformance inspection.- For purposes of sampling an inspection lot shall consist of all cork sheet of the same type, size and thickness offered for delivery at one time.

4.2.1 Inspection of the end item.-

4.2.1.1 Examination of the end item.- Examination of the end item shall be made in accordance with 4.2.1.1.1 through 4.2.1.1.3. The lot size, for purpose of determining the sample size in accordance with MIL-STD-105, shall be in units of cork sheets (see 4.2.1.1.1 and 4.2.1.1.2) and units of shipping containers (see 4.2.1.1.3).

4.2.1.1.1 Examination of the end item for defects in workmanship.- The sample unit for the following examination shall be one piece. The inspection level for determining the sample size shall be level II, with an Acceptable Quality Level (AQL) of 4.0 percent defective.

Examination	Defect
Appearance and workmanship	Cracked or damaged.
	Not smooth or uniformly embossed.
	Not uniform in color.
	Excessive streaks.
	Excessive voids.
Classification	Type not as specified.

4.2.1.1.2 Examination of the end item for defects in dimensions.- The sample unit for the following examination shall be one piece. The inspection level for determining the sample size shall be level II with an Acceptable Quality Level (AQL) of 4.0 percent defective.

Examine	Defect
Length	Not as specified.
	Single piece less than specified.
Width	Width not as specified by contract requirement.
Thickness	Not within limits or tolerance specified, or by contract requirement.

Source: https://assist.dla.mil -- Downloaded: 202610-18T05:36Z
Check the source to verify that this is the current version before use.

4.2.1.1.3 Examination of preparation for delivery.- An examination shall be made to determine that the packing and markings comply with the requirements of section 5 of this specification. The sample unit for the following examination shall be one shipping container, selected just prior to closing operation. The inspection level for determining the sample size shall be level I, within an acceptable quality level (AQL) of 4.0 percent defective. Shipping containers, fully prepared for delivery, shall be examined for closure defects.

Examine	Defect
Marking	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.
Materials	Any component missing.
	Any component damaged, affecting serviceability.
Workmanship	Inadequate application of components, such as incomplete wrapping of rolls, container flaps, loose strapping, inadequate stapling. Bulging or distortion of container.
Weight	Net weight exceeds requirements.

4.2.2 Sampling for tests.- The lot size shall be the weight of the lot in pounds. The sample size shall be the number of sets of tests, that is, the number of specimens subjected to each test (see table I).

Table I - Sampling for tests.

Lot size pounds	Sample size - Number of test specimens for each test (see 4.3.1 through 4.3.5)
Up to 200	0
201 to 500	2
501 to 1000	3
1001 to 2000	5
2001 to 5000	7
5001 and over	9

4.2.2.1 Testing of the end item.- The end item shall be tested for the applicable characteristics as shown in table II from each lot presented for examination for each type of cork sheet. The sample unit shall be one roll or sheet. Samples shall be selected throughout the lot (see table I). If any specimens fail any test, this shall be cause for rejection of the lot.

Table II - Instruction for testing.

Characteristic	Specification reference		Results reported as	
	Require-ment	Test method	Pass or fail 1/	Numerically to nearest 1/
Keying of backing	3.2	4.3.1	--	0.5 lb.
Tensile strength	3.2	4.3.2	--	p.s.i.
Seasoning	3.4	4.3.3	X	--
Pliability	3.5	4.3.4	X	--
Weight	3.7	4.3.5	--	0.2 lb.

1/ If failure is indicated, report description of failure.
2/ Test reports shall include all values on which results are based.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:36Z
Check the source to verify that this is the current version before use.

4.3 Test procedures.-

4.3.1 Keying of backing (types I and III).- Cut two specimens 3 inches wide and 6 inches long, one in the direction of the warp of the backing, and one in the direction of the filling. Break the specimen about 1 inch from the end, so as not to injure the backing. Either end shall be fastened and the backing stripped from the cork sheet specimen at a rate of approximately 12 inches per minute by steadily pulling on the other end at an angle of approximately 90 degrees. The pulling may be done in any suitable testing machine.

4.3.2 Tensile strength (type II).- Six specimens, each 2-inches wide by 10-inches long, 3 cut longitudinal and 3 cut transversely shall be used for the test. A pendulum type machine shall be used. The jaws through which the load is applied shall move at a uniform rate of 12 ± 1/2 inches per minute. The jaws shall have smooth flat faces with edges slightly rounded to prevent cutting. The specimen shall be conditioned for 2-1/2 hours at 70° to 77° F. and immediately placed symmetrically in the jaws of the machine with the long dimension parallel to and the short dimension at right angles to the direction of the load. The tensile strength shall be the average of the three specimens cut in either direction.

4.3.3 Seasoning.- Examine a clean, fresh cut, made not less than one-half inch from the edge, for any evidence of soft sticky binder.

4.3.4 Pliability.- Cut two strips 2 inches wide and 8 inches long, longitudinally, and two strips of the same size transversely of the roll, and bring to a temperature of 70° to 77° F. by exposure to these conditions for about 2-1/2 hours. Bend each strip, with the burlap or base layer on the inside, at approximately its center, over a 3-inch diameter mandrel, through an arc of 180 degrees, and at a uniform speed, in approximately 5 seconds.

4.3.5 Weight.- Cut a portion approximately 12 by 12 inches, measure accurately, and weigh to the nearest gram. Calculate the weight per square yard.

5. PREPARATION FOR DELIVERY

5.1 Packaging.- Packaging shall be level A or C, as specified (see 6.1).

5.1.1 Level A.- Each roll shall be wrapped with class 2 kraft paper conforming to UU-P-271 with ends enclosed. All seams, joints and closures shall be sealed with adhesives or other suitable materials to afford waterproofness equal to that of the wrap material itself. A minimum of 2-inch overlap shall be provided at all overlapping edges.

5.1.2 Level C.- Packaging shall be sufficient to afford adequate protection against physical damage during shipment from the supply source to the first receiving activity for immediate use. This may conform to the supplier's commercial practice when such meets the requirements of this level.

5.2 Packing.- Packing shall be level A, B, or C, as specified (see 6.1).

5.2.1 Level A.- Rolls shall be packed in containers conforming to class 2 of PPP-B-636 or PPP-B-640. All center and edge seams, and manufacturer's joints shall be waterproofed in accordance with the appendix to PPP-B-636 or PPP-B-640 (see 6.1).

5.2.2 Level B.- Rolls shall be packed in containers conforming to class 1 of PPP-B-636 or PPP-B-640. Containers shall be closed in accordance with the applicable box specification or appendix thereto.

5.2.3 Level C.- Rolls shall be packed in containers, at the lowest rates, in a manner which will insure acceptance by common carrier and will afford protection against physical damage during direct shipment from the supply source to the first receiving activity for immediate use. This level in general shall conform to the Uniform Freight Classification Rules and Regulations as applicable to the mode of transportation and may be the supplier's commercial practice.

5.3 Marking.- In addition to any special marking required by the contract or order, interior packages and exterior shipping containers shall be marked for shipment in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:36Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Ordering data.- Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Type required (see 1.2).
(c) Color required (see 3.3).
(d) Width and thickness required (see 3.6.1 and 3.6.3).
(e) Applicable level of packaging and packing required (see 5.1 and 5.2).

Custodians:
Army - GL
Navy - SH
Air Force - 69
Review activities:
Navy - SH
Air Force - 69
User activities:
Army - GL
Navy - YD

Preparing activity:
Navy - SH
(Project 9390-0009)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:36Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity.

SPECIFICATION		
ORGANIZATION		CITY AND STATE
CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT $

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD FORM 1 APR 63 1426 REPLACES NAVSHIPS FORM 4863, WHICH IS OBSOLETE

Source: https://assist.dla.mil -- Downloaded: 20261O-18T05:36Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY
BUREAU OF SHIPS
WASHINGTON, D.C. 20360

OFFICIAL BUSINESS

POSTAGE AND FEES PAID
NAVY DEPARTMENT

CHIEF, BUREAU OF SHIPS
SPECIFICATIONS AND STANDARDIZATION BRANCH
DEPARTMENT OF THE NAVY
WASHINGTON, D.C. 20360

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:36Z
Check the source to verify that this is the current version before use.