A-A-1201A
January 2, 1986
SUPERSEDING
A-A-1201
April 17, 1980

COMMERCIAL ITEM DESCRIPTION

PAPER, ABRASIVE (GARNET COATED)

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification P-P-121D, Classes 1, 2, 3, and 7.

This commercial item description covers paper sheets and rolls, coated on one surface with garnet abrasive grain.

Salient characteristics.

1. Garnet abrasive paper shall be of the following classes and grit sizes as specified.
   Class 1 - Sheets, finishing, open coat;
   Grit sizes - 280, 240, 220, 180, 150, 120, 100, 80, 60, 50, 40, and 36.
   Class 2 - Sheets, closed coat:
   Grit sizes - 220, 180, 150, 120, 100, 80, 60, 50, 40, and 36.
   Class 3 - Roll, closed coat:
   Grit sizes - 220, 180, 150, 120, 100, 80, 60, 50, 40, 36, and 24.
   Class 4 - Sheet, finishing, open coat, non-loading type.
   Grit sizes - 280, 240, 220, and 180.
2. Unless othewise specified, a sheet shall be 9 x 11 inches; rolls shall be 50 yards long, widths as specified.
3. The abrasive grain shall be crushed from clean, hard, abrasive grade garnet, graded in accordance with the requirements of ANSI Standard B74.18.
4. The backing shall be of good quality rope- or wood-fiber paper.
5. The product shall conform to the requirements of table I below:

FSC 5350

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:12Z
Check the source to verify that this is the current version before use.

TABLE I

Classes	Grit sizes	Backing weight (1)		Coated product(1)(2) Min. avg. break. strength	
		Pounds per 2880 square feet ± 5 %	Standard Industry Desig. (2)	Machine direction lbs/in.	Cross machine direction lbs/in.
1 and 4	All	40	A	25	12
2	220, 180, 150,	70	C	45	25
	120, 100	70	C	45	32
2	80, 60, 50,	90	D	55	32
	40, 36	90	D	55	32
3	All	130	E	90	45

(1) Backing weights and breaking strengths are measured after samples are in moisture equilibrium with an atmosphere of 50 ± 2 percent relative humidity at 21 ± 1 degrees C (70 ± 2 degrees F).

(2) This is an average of four tests.

The issue of ANSI B74.18 in effect on the date of the solicitation shall be used to determine compliance with stated requirements.

Workmanship. The workmanship should be equal to or be better in every respect than that which is considered good practice by industry.

Preservation, packaging, packing, labeling, and marking. The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

Notes.
The purchaser shall specify class and grit size.

ANSI standards are available from the American National Standards Institute, Inc., 1430 Broadway, New York, NY 10018.

When this commercial item description is used for procurement, the commercial item certification clause must appear in the solicitation.

The cross reference between P-P-121D and A-A-1201A classes are as follows:

P-P-121D	A-A-1201A
1	1
2	2
3	3
7	4

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:12Z
Check the source to verify that this is the current version before use.

The NSN's are as follows:

Class 1, 9 x 11 sheets

Grit size	NSN's
36	5350-00-186-8819
50	5350-00-221-0883
100	5350-00-186-8820
120	5350-00-221-0882
150	5350-00-221-0881
240	5350-00-193-7211

Class 2, 9 x 11 sheets

40	5350-00-221-0864
50	5350-00-221-0886
60	5350-00-221-0885
80	5350-00-221-0884
100	5350-00-161-9044
120	5350-00-161-9043
150	5350-00-186-8821
220	5350-00-221-0888

Class 3, 50 yard roll

40 - 12" wide	5350-00-194-7161
80 - 12" wide	5350-00-194-7140

MILITARY INTERESTS:

None: DoD has determined that no military activity has an official interest in this commercial item description.

PREPARING ACTIVITY:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:12Z
Check the source to verify that this is the current version before use.