# COMMERCIAL ITEM DESCRIPTION

## BOTTLE, VACUUM

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification RR-B-600.

This commercial item description covers stainless steel narrow mouth vacuum bottles used for maintaining liquids at or near their original temperature.

Salient characteristics:

The vacuum bottles shall be available in the following sizes:

Size 1 - 1-quart +/- 3 ounces
Size 2 - 2-quart +/- 3.5 ounces
Size 3 - 1-pint +/- 1.6 ounces

The vacuum bottles shall be constructed with stainless steel outer and inner shells joined by welding or brazing. The stainless steel shall conform to the American Society for Testing and Materials (ASTM) Standard No. A167. The space between the shells shall be insulated by vacuum or by a combination of vacuum and insulation. When filled with water at 205 +/- 2 degrees Fahrenheit the water shall not fall below 170 degrees Fahrenheit when tested as specified, except for the size 3 bottle which shall not fall below 159 degrees Fahrenheit.

The interior surface of the inner shell shall have a 2D or better finish. The exterior of the outer shell shall have a 2B or better finish, a dull frosted finish or a brushed No. 4 commercial finish. The finish numbers shall be as defined by the American Iron and Steel Institute. The outer surface of the bottle shall be permanently marked with the manufacturer's name or trademark, easily identifiable with such manufacturer.

The vacuum bottles shall have a narrow mouth of 2 inches or less inside diameter and shall be provided with a threaded removable plastic stopper and a screw-on plastic or plastic lined stainless steel cup. At the option of the manufacturer, a spigot may included within the stopper.

All plastics used as components which contact the contents of the bottles shall comply with FDA regulations covering polymers for use in contact with food for human consumption as stated in 21 CFR 177. The contractor shall furnish a certificate of compliance for this requirement.

The vacuum bottle shall be furnished with handle(s) or carrying strap(s) of the type normally furnished commercially.



Source: https://assist.dla.mil -- Downloaded: 20261O-26T08:24Z
Check the source to verify that this is the current version before use.

Workmanship: The finished vacuum bottles shall be clean and free of slivers, die marks, sharp edges, dents, scratches, pits and deformities, and other defects which may affect appearance or serviceability. The welds or brazes shall be uniform, sound and free of burn holes, cracks, undercutting, excessive metal build-up, and splatter. There shall be no evidence of scale or flux and the welds or brazes shall be finished to blend with the adjacent joined metal surfaces.

Quality Assurance:

Responsibility for inspection: Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. Inspection records of the examinations or tests shall be kept complete and available to the Government as specified in the contract or purchase order. The Government reserves the right to perform any of the inspections set forth in the Commercial Item Description where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Inspection of the end item: Sampling shall be in accordance with MIL-STD-105, Sampling Procedures and Tables for Inspection by Attributes. The inspection lot shall consist of all vacuum bottles offered for inspection at one time. The sample unit shall be one complete vacuum bottle.

Visual inspection. The visual examination of the vacuum bottles shall be for construction and workmanship defects in accordance with Table I. The inspection level shall be level II with an acceptable quality level (AQL) of 2.5 for major defects and 6.5 for total defects, expressed in terms of defects per hundred units.

Table I. Classification of Defects

| Examine | Defect | Major | Minor |
|---|---|---|---|
| Finish | Area of corrosion | X | |
| | Stain or discolored | | X |
| | Interior or exterior finish not as specified | X | |
| Construction and Workmanship | Any component fractured, split, buckled, bent, punctured or missing | X | |
| | Inner and outer shells not joined by welding or brazing | X | |
| | Deep scratch or tool mark on interior surface clearly noticeable | X | |
| | Scratched, pitted, or tool mark on exterior surfaces | | X |
| | Any sharp edge, sliver or burr | X | |
| | Functioning component inoperative or will not function as intended | X | |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.

Dimensional and test inspection. The vacuum bottles shall be sampled for the heat retention test and capacity using an inspection level of S-2 with an AQL of 2.5 defects per hundred units.

Heat retention test. The complete vacuum bottle shall be filled with water at a temperature of 205 ± 2 degrees Fahrenheit, the stopper secured and allowed to stabilize for 10 minutes. The water shall then be emptied and the bottle refilled with water at a temperature of 205 ± 2 degrees Fahrenheit and the stopper secured. Following not less than 6 hours storage in an ambient temperature of 68 to 72 degrees Fahrenheit, the temperature of the contents shall be measured and shall be 170 degrees Fahrenheit or greater for compliance for sizes 1 and 2 and 159 degrees Fahrenheit or greater for size 3.

Capacity. The capacity shall be measured by filling the bottle to stopper height with water poured from a graduated cylinder.

Inspection for preparation and delivery. An inspection shall be made to determine whether the packaging, packing, and marking comply with the requirements of the contract or purchase order. Examination for defects shall be in accordance with Table II. For examination of interior packaging, the sample unit shall be one shipping container fully prepared for delivery. Sampling shall be in accordance with MIL-STD-105. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 with an AQL of 4.0 defects per hundred units.

Table II
Preparation for delivery defects.

| Examine | Defects |
|---|---|
| Markings | Omitted; incorrect; illegible; improper size, location, sequence, or method of application. |
| Material | Any component missing, damaged, or not conforming to applicable requirements stated herein. |
| Workmanship | Inadequate application of components such as incomplete closure of container flaps, loose strapping, or distortion of container. |
| Contents | Quantity of container is more or less than required. Gross weight exceeds requirements of the box specification. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.

Regulatory requirements: In accordance with Section 23.403 of the Federal Acquisition Regulations, the Government's policy is to acquire items composed of the highest percentage of recovered materials practicable, consistent with maintaining a satisfactory level of competition without adversely affecting performance requirements or exposing suppliers' employees to undue hazards from the recovered materials.

Preservation, packaging, packing and marking (Civil Agencies): Preservation, packaging, packing, and marking shall be as specified in the contract or purchase order.

Packaging (DOD): Packaging shall be in accordance with ASTM Standard D 3951, Practice for Commercial Packaging.

Notes:

Copies of military standards may be obtained from the Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

Applications for copies of American Society for Testing and Materials (ASTM) Standards should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

MILITARY COORDINATING ACTIVITY:

Army - GL

PREPARING ACTIVITY:

GSA - FSS

Custodians:

Army - GL
Navy - SA
Air Force - 99

Review Activities:

Army - MD
Navy - MC
Air Force - 84



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.