INCH-POUND

A-A-59605
September 19, 2000

COMMERCIAL ITEM DESCRIPTION

PAN ROASTING, AND SHEET PAN: ALUMINUM, WITH NO-STICK COATED FINISH

The General Services Administrstion has authorized the use of this commercial item description (CID), for all federal agencies.

1.SCOPE

1.1 Scope. This commercial item description (CID) covers an aluminum coated roasting pan and an aluminum coated sheet pan with a no-stick coated finish.

1.2 Intended use. The pans are used for cooking, baking and roasting in field kitchens, and navy ship galleys.

2. CLASSIFICATION

2.1 Classification. The pans shall be of the following types, as specified (see 7.1).

Type I – Roasting pan
Type II – Full size sheet pan

Beneficial comments (recommendations, additions, deletions) and any data which may be of use in improving this document should be addressed to: US. Army Soldier and Biological Chemical Command, Soldier Systems Center, Natick, MA 01760-5018 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 7330

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:21Z
Check the source to verify that this is the current version before use.

3. SALIENT CHARACTERISTICS

3.1 Design and construction.

3.1.1 Type I roasting pan. The roasting pan shall be fabricated from 3004-0 anodizing quality aluminum alloy and shall have two corrosion-resistant steel strap reinforcements. The strap reinforcements shall be 1 inch wide by 0.095 inch thick. The aluminum alloys used to fabricate the pan shall conform to ASTM Standard B 209. The pan shall have a no-stick coating(see 3.3) applied to the inside surface only. The coating shall be applied from a licensed DuPont coater, and shall conform to NSF International Standard No.2 (see 5.3).

3.1.1.1 Handles. The roasting pan shall have two handles positioned in the center of the ends and shall be formed of 9/32 inch diameter wire corrosion-resistant steel rod. The handles shall be fastened securely to the pan and shall not fail or permanently deform when the pan is load tested as specified in 5.4. The outside dimensions of the roasting pan handles shall be 4 inches wide by 1-1/4 inch minimum inside opening for hand clearance.

3.1.2 Type II sheet pan. The sheet pan shall be fabricated from 3003-H25 aluminum alloy and shall have a rolled edge that is formed using a 1/4 inch zinc plated carbon steel bead wire to provide rigidity, warp and rust resistance. The pans shall be fabricated with a 0.141 inch crown or concavity at center to allow the pan to flatten when heated for even heat distribution. The aluminum alloys used to fabricate the pans shall conform to ASTM Standard B 209. The pans shall have a no-stick coating (see 3.3) applied to the inside surface only. The coating shall be applied from a licensed DuPont coater, and shall conform to NSF International Standard No. 2 (see 5.3).

3.2 Dimensions

3.2.1 Type I pan. The outside dimensions of the roasting pan shall be 24 inches by 18 inches by 4-19/32 inches high. Tolerances shall be ± 1/32 inch. Thickness of the aluminum alloy shall be 16 gauge. The corners of the roasting pan shall have a 1/2 inch inside radius.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:21Z
Check the source to verify that this is the current version before use.

3.2.2 Type II pan. The outside dimensions of the sheet pan shall be 17-26/32 inches by 25-25/32 inches by 1 inch deep. Tolerances shall be ± 1/32 inch. Thickness of the aluminum alloy shall be 16 gauge. The corners of the sheet pan shall have a 1/8 inch inside radius.

3.3 Coating. The coating shall be a DuPont process that consists of three layers: primer, midcoat, and topcoat. The total coating dry film thickness shall be 1.1 – 1.5 mils.

3.4 Workmanship. The finished pans, shall be free of cracks, dents, malformation, or deep scratches. All burrs, slivers, splinters, sharp edges, dirt, grease, and foreign matter shall be removed.

3.5 Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, provided they fall within the tolerances specified using conversion tables contained in the latest revision of ASTM E 380.

4. REGULATORY REQUIREMENTS

4.1 Contractor recovered materials. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

5. QUALITY ASSURANCE PROVISIONS

5.1 Product conformance. The pans provided shall meet the salient characteristics of this Commercial Item Description, conform to the producer’s own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial market. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:21Z
Check the source to verify that this is the current version before use.

5.2 Market acceptability. The following market acceptability criteria are necessary to document the quality of the pans to be provided under this commercial item description.

a. The company producing these pans, excluding the coating, must have been producing these pans for a least 10 years, and must have been producing coated pans for at least 2 years, to meet the requirements of this CID.

b. The company must have sold at least 2500 pans meeting the requirements of this CID in the commercial marketplace over the last 2 years.

5.3 NSF International standard compliance. Prior to approval of the first shipment contractor shall submit satisfactory evidence to the contracting officer or his authorized representive that the coating conforms to the applicable requirements of NSF International Standard No. 2. Acceptable evidence shall be a certified test report from a recognized independent testing laboratory acceptable to the medical authority of the service for which the the items are being procured, stating that the item’s coating has been tested and conforms to NSF International Standard No. 2. Acceptance of the independent testing laboratory to the medical authority shall be based on the laboratory submitting to the contracting officer a written letter from either the American Association for Laboratory Accreditation (A2LA), Gaithersburg, MD, or the American National Standards Institute (ANSI), Washington, DC stating that the independent test laboratory has been evaluated and is accredited for testing and evaluating food service equipment for conformance with applicable NSF International Standards. Accreditation of the independent testing laboratory must be completed prior to the item testing.

5.4 Load test. The type I pan shall be uniformly loaded to 130 pounds(including the weight of the pan) and lifted three times by the two end handles from floor to a table height of 36 inches, ±3 inches. The handle assembly shall be examined to determine compliance with 3.1.1.1. Any nonconformance with specified requirements shall constitute failure of this test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:21Z
Check the source to verify that this is the current version before use.

6. PACKAGING

6.1 Packaging. Preservation, packing and marking requirements shall be as specified in the contract or purchase order (see 7.1).

7. NOTES

7.1 Ordering data. Acquisition documents must specify the following:

a. Title, number and date of this CID.
b. Type required (see 2.1).
c. Packaging requirements (see 6.1).

7.2 Sources for documents

7.2.1 Sources for non-government association documents

AMERICAN SOCIETY FOR TESTING AND MATERIALS

B 209 - Standard Specification for Aluminum and Aluminum-Alloy Sheet and Plate

E 380 - Use of the International Systems of Units (SI) (the Modernized Metric System)

(Application for copies of ASTM standards should be addressed to the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959).

NSF INTERNATIONAL

NSF International Standard No.2 – Food Service Equipment and Related Products, Components and Materials

(Application for copies of NSF International Standard No. 2 should be addressed to NSF International, 3475 Plymouth Road, Ann Arbor, MI 48106).

7.3 Sources of supply. A manufacturer whose products are known to meet the requirements of this CID is listed below; however, competition is not limited to this company.

Welbilt Company
Lincoln Foodservice Products, Inc.
1111 North Hadley Road
Fort Wayne, IN 46801-1229

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:21Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

Custodians
Army – GL
Navy – SA
Air Force – 99

Review Activities
Army – MD1, QM1
Navy – MC
Air Force – 84
DLA - SS

CIVIL AGENCY
COORDINATING ACTIVITY:

GSA-FSS/7FXE

Preparing Activity:
Army - GL
DoD Project (7330-0779)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:21Z
Check the source to verify that this is the current version before use.