MILITARY SPECIFICATION

INSULATION, PANEL, VIBRATION-DAMPENING AND THERMAL-BARRIER

This specification is approved for use within the US Army Tank-Automotive Command, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers insulation with vibration-dampening and thermal-barrier properties for use on panels of military vehicles.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Standards. The following standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Tank-Automotive Command, ATTN: AMSTA-GDS, Warren, MI 48397-5000, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document, or by letter.

AMSC N/A FSC 5640

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202640-23T01:45Z
Check the source to verify that this is the currentversion before use.

STANDARDS
FEDERAL

FED-STD-595	- Colors.

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-130	- Identification Marking of US Military Property.
MIL-STD-810D	- Environmental Test Methods and Engineering Guidelines.
MIL-STD-45662	- Calibration System Requirements.

(Copies of specifications, standards, handbooks, drawings, publications, and other Government documents required by the contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following document(s) form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM C177	- Steady-State Thermal Transmission Properties by Means of the Guarded Hot Plate.
ASTM D412	- Rubber Properties in Tension.
ASTM D624	- Rubber Property - Tear Resistance.
ASTM D2240	- Rubber Property - Durometer Hardness.
ASTM E756	- Measuring Vibration - Damping Properties of Materials.

(Application for copies should be addressed to American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

SOCIETY OF AUTOMOTIVE ENGINEERS (SAE)

SAE J369	- Flammability of Automotive Interior Material - Horizontal Test Method.

Source: https://assist.dla.mil -- Downloaded: 202640-23T01:45Z
Check the source to verify that this is the currentversion before use.

(Information as to the availability of the above standard may be obtained from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. Unless otherwise specified (see 6.2), the contractor shall furnish insulation samples which shall be subjected to first article inspection (see 4.4). First article inspection samples, properly marked with identifying information, shall be a sample of the insulation to be furnished to the Government. All subsequent insulation delivered to the Government shall conform to these samples in all of their pertinent physical and performance attributes.

3.2 Materials. The materials shall be as specified herein and in referenced drawings and standards. The materials shall be free of defects and imperfections that might affect the serviceability and reliability of the finished product. The insulation shall have excellent resistance to petroleum, fuel, and alkalis, and shall have a specific gravity of 1.75 $\pm$ 10 percent. The insulation shall not contain any materials which would cause adverse effects on the health of the personnel (see 4.8.1).

3.2.1 Recycled, virgin and reclaimed materials. There are no requirements for the exclusive use of virgin materials; however, all materials shall be new and unused. The use of recycled or reclaimed (recovered) materials is acceptable provided that all other requirements of this specification are met (see 6.3.1).

3.3 Design and construction.

3.3.1 Configuration. The configuration of the insulation shall be as specified on the applicable drawing (see 4.8.2 and 6.2).

3.3.2 Thickness. The thickness of the insulation shall be as specified on the applicable drawing (see 4.8.2).

3.3.3 Weight. The weight of the insulation shall be as specified on the applicable drawing (see 4.8.2).

3.3.4 Color. The color of the insulation shall be the manufacturer's dark grey which provides the closest match to color chip number 36081 of FED-STD-595 (see 4.8.2).

Source: https://assist.dla.mil -- Downloaded: 202640-23T01:45Z
Check the source to verify that this is the currentversion before use.

3.4 Performance.

3.4.1 Vibration-dampening properties. The vibration-dampening properties of the insulation shall be not less than those shown in figures 1 through 3 (see 4.8.3).

3.4.2 Thermal conductivity. The thermal conductivity of the insulation shall be not greater than 2.1 British thermal units (Btu)/[(hour)(square foot)(degrees Fahrenheit/inch)] (see 4.8.4).

3.4.3 Indentation hardness. The indentation hardness of the insulation (using a type A durometer) shall be 85 ± 10 percent (see 4.8.5).

3.4.4 Tear resistance. The tear resistance of the insulation shall be not less than 30 pounds force per inch (ppi) (see 4.8.6).

3.4.5 Tensile strength. The tensile strength of the insulation shall be not less than 150 pounds force per square inch (psi) (see 4.8.7).

3.4.6 Flammability. The insulation shall be self-extinguishing with no burn rate (SE/NBR) when tested as specified in 4.8.8.

3.4.7 Environmental.

3.4.7.1 High temperature. The insulation shall meet the requirements of 3.4.1 in an ambient air temperature of 200 degrees Fahrenheit (°F) (see 4.8.9).

3.4.7.2 Low temperature. The insulation shall meet the requirements of 3.4.1 in an ambient air temperature of 0°F (see 4.8.10).

3.4.7.3 Water immersion. The insulation shall have not more than a 0.1-percent weight gain when immersed in water for 24 hours (see 4.8.11).

3.5 Identification marking. Identification marking shall be in accordance with MIL-STD-130 (see 4.8.2).

3.6 Workmanship. Workmanship shall be of high quality and in accordance with high-grade practices. Insulation shall be uniform in quality and free of foreign matter, cracks, tears, cuts, or any other defect that will affect its life, serviceability, or appearance. Workmanship shall be such as to ensure insulation which is in conformance to this specification (see 4.8.2).

Source: https://assist.dla.mil -- Downloaded: 202610-23T01:45Z
Check the source to verify that this is the currentversion before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order (see 6.2), the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform or witness any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply wih all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Inspection equipment. Unless otherwise specified in the contract (see 6.2), the contractor is responsible for the provision and maintenance of all inspection equipment necessary to assure that supplies and services conform to contract requirements. Inspection equipment must be capable of repetitive measurements to an accuracy of 10 percent of the measurement tolerance. Calibration of inspection equipment shall be in accordance with MIL-STD-45662.

4.2 Classification of inspection:

a. First article inspection (see 4.4).
b. Quality conformance inspections (see 4.5).
   1. Examination (see 4.5.2).
   2. Tests (see 4.5.3).
c. Control tests (see 4.6).

4.3 Inspection conditions. Unless otherwise specified (see 6.2), all inspections shall be conducted under the following conditions:

a. Air temperature 73 $\pm$ 18°F
b. Barometric pressure 28.5 + 2.0 inches mercury (Hg)
   - 0.5
c. Relative humidity 50 $\pm$ 30 percent

Source: https://assist.dla.mil -- Downloaded: 202640-23T01:45Z
Check the source to verify that this is the currentversion before use.

4.4 First article inspection. Unless otherwise specified (see 6.2), the Government shall select insulation samples produced under the production contract (see 6.2) for first article inspection. First article samples shall be inspected as specified in table I. Approval of first article samples by the Government shall not relieve the contractor of his obligation to supply insulation that is fully representative of those inspected as first article samples. Any changes or deviation of the production units from the first article samples shall be subject to the approval of the contracting officer.

4.4. First article inspection failure. Test item deficiencies during, or as a result of, first article inspection shall be cause for rejection of the items until evidence has been provided by the contractor that corrective action has been taken to eliminate the deficiency. Any deficiency found during, or as a result of, first article inspection shall be evidence that all items already produced prior to completion of first article inspection are similarly deficient unless contrary evidence satisfactory to the contracting officer is furnished by the contractor. Such deficiencies on all items shall be corrected by the contractor. The Government will not accept products until first article inspection is completed to the satisfaction of the Government.

TABLE I. Classification of inspections.

Title	Requirement	Inspection	First article	Quality conformance		Control
				Examination	Tests	
Materials	3.2	4.8.1	X		X	
Defects (see 4.5.2 and table II)	3.3.1 thru 3.3.4, 3.5 and 3.6	4.8.2	X	X		
Vibration-dampening properties	3.4.1	4.8.3	X			X
Thermal conductivity	3.4.2	4.8.4	X			X
Indentation hardness	3.4.3	4.8.5	X			X
Tear resistance	3.4.4	4.8.6	X			X
Tensile strength	3.4.5	4.8.7	X			X
Flammability	3.4.6	4.8.8	X			X
High temperature	3.4.7.1	4.8.9	X			X
Low temperature	3.4.7.2	4.8.10	X			X
Water immersion	3.4.7.3	4.8.11	X			X

Source: https://assist.dla.mil -- Downloaded: 202610-23T01:45Z
Check the source to verify that this is the currentversion before use.

4.5 Quality conformance inspections.

4.5.1 Sampling.

4.5.1.1 Lot formation. An inspection lot shall consist of all the insulation manufactured during an identifiable production period (not exceeding 24 hours), from one manufacturer, submitted at one time for acceptance.

4.5.1.2 Sampling for examination. Samples for quality conformance examination shall be selected in accordance with general inspection level II of MIL-STD-105. Before sampling may be initiated, the contractor shall establish by examination of at least 8 consecutively produced insulation samples that the process average percent defective, as defined in MIL-STD-105, is not greater than the specified AQLs.

4.5.2 Examination.

4.5.2.1 Acceptable quality level. Each sample selected in accordance with 4.5.1.2 shall be examined to determine conformance to the following acceptable quality levels (AQL) on the basis of percent defective:

Classification	AQL
Major	1.0
Minor	2.5

4.5.2.2 Classification of defects. For examination purposes, defects shall be classified as listed in table II.

TABLE II. Classification of defects.

Category	Defect	Method of examination
Critical	None	
Major	AQL 1.0% Defective	
101	Dimensions, out of tolerance (see 3.3.1).	SIE 1/
102	Thickness, out of tolerance (see 3.3.2).	SIE
103	Weight, out of tolerance (see 3.3.3).	SIE
104	Identification marking, improper (see 3.5).	Visual
105	Faulty workmanship affecting performance (see 3.6).	Visual
Minor	AQL 2.5% Defective	
201	Color not as specified (see 3.3.4).	Visual
202	Faulty workmanship affecting appearance (see 3.6).	Visual

1/ SIE = Standard Inspection Equipment.

Source: https://assist.dla.mil -- Downloaded: 202640-23T01:45Z
Check the source to verify that this is the currentversion before use.

4.5.3 Tests. Each insulation sample shall be subjected to the quality conformance tests specified in table I.

4.6 Control tests. Control tests shall be conducted on 1 insulation sample from each lot of 200 units consecutively produced, except that not more than 1 test shall be performed in a 3-month period, nor less than 1 test in a 6-month period. The insulation shall be subjected to the tests specified in table I.

4.7 Failure. Failure of any sample to pass any of the specified quality conformance or control tests shall be cause for the Government to refuse acceptance of the production quantity represented, until action taken by the contractor to correct defects and prevent recurrence has been approved by the Government.

4.8 Methods of inspection.

4.8.1 Materials. Conformance to 3.2 shall be determined by inspection of contractor records providing proof or certification that materials conform to requirements. Applicable records shall include drawings, specifications, design data, receiving inspection records, processing and quality control standards, vendor catalogs and certifications, industry standards, test reports, and rating data.

4.8.2 Defects. Conformance to 3.3.1 through 3.3.4, 3.5, and 3.6 shall be determined by examination for the defects listed in table II. Examination shall be visual, tactile, or by measurement with standard inspection equipment.

4.8.3 Vibration-dampening properties. To determine conformance to 3.4.1, the insulation shall be tested as specified in ASTM E756.

4.8.4 Thermal conductivity. To determine conformance to 3.4.2, the insulation shall be tested as specified in ASTM C177.

4.8.5 Identation hardness. To determine conformance to 3.4.3, the insulation shall be tested as specified in ASTM D2240.

4.8.6 Tear resistance. To determine conformance to 3.4.4, the insulation shall be tested as specified in ASTM D624, die C.

4.8.7 Tensile strength. To determine conformance to 3.4.5, the insulation shall be tested as specified in ASTM D412, die A.

4.8.8 Flammability. To determine conformance to 3.4.6, the insulation shall be tested as specified in SAE J369.

Source: https://assist.dla.mil -- Downloaded: 202640-23T01:45Z
Check the source to verify that this is the current version before use.

4.8.9 High temperature. To determine conformance to 3.4.7.1, the insulation shall be tested as specified in MIL-STD-810D, method 501.2, procedure II, at 200°F. When the insulation has stabilized at 200°F, the insulation shall be tested as specified in 4.8.3.

4.8.10 Low temperature. To determine conformance to 3.4.7.2, the insulation shall be tested as specified in MIL-STD-810D, method 502.2, procedure II, at 0°F. When the insulation has stabilized at 0°F, the insulation shall be tested as specified in 4.8.3.

4.8.11 Water immersion. To determine conformance to 3.4.7.3, a 4- by 14-inch specimen of insulation shall be immersed for 24 hours in water. After the immersion, the insulation specimen shall be allowed to dry for 48 hours. The insulation specimen shall be weighed before the immersion and after the drying period to determine the weight gain.

5. PACKAGING

5.1 Preservation, packaging, packing, and marking. Preservation, packaging, packing, and marking for the desired level shall be in accordance with the applicable packaging standard or packaging data sheet specified by the contracting authority (see 6.2).

6. NOTES

6.1 Intended use. This insulation is intended to be used as panel insulation in military vehicles.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this specification.
b. If first article samples are not required (see 3.1).
c. Title, number, and date of applicable drawing (see 3.3.1).
d. If responsibility for inspection shall be other than as specified (see 4.1).
e. If responsibility for inspection equipment shall be other than as specified (see 4.1.2).
f. If inspection conditions shall be other than as specified (see 4.3).
g. If first article inspection is not required (see 4.4).
h. Number of samples to be selected for first article inspection (see 4.4).
i. Selection of applicable level and packaging standard or packaging data sheet (see 5.1).

Source: https://assist.dla.mil -- Downloaded: 202640-23T01:45Z
Check the source to verify that this is the currentversion before use.

6.3 Definitions.

6.3.1 Recovered materials. "Recovered materials" means materials that have been collected or recovered from solid waste (see 6.3.2).

6.3.2 Solid waste. "Solid waste" means (a) any garbage, refuse, or sludge from a waste treatment plant, water supply treatment plant, or air pollution control facility; and (b) other discarded material, including solid, liquid, semisolid, or contained gaseous material resulting from industrial, commercial, mining, and agricultural operations, and from community activities. It does not include solid or dissolved material in domestic sewage, or solid or dissolved material in irrigation return flows or industrial discharges which are point sources subject to permits under section 402 of the Clean Water Act, (33 U.S.C. 1342 et seq.), or source, special nuclear, or byproduct material as defined by the Atomic Energy Act of 1954 (42 U.S.C. 2011 et seq.) (Source: Federal Acquisition Regulations, section 23.402).

6.4 Subject term (key word) listing.

Insulation
Panel insulation
Thermal barrier
Vibration dampening


6.5 Supersession data. This military specification supersedes AM General Corporation specification AMG 194, revision C, dated 5 March 1985.

Custodian:
Army - AT

Preparing activity:
Army - AT

(Project No. 5640-A446)

Source: https://assist.dla.mil -- Downloaded: 202610-23T01:45Z
Check the source to verify that this is the currentversion before use.




NOTE:

1. FREQUENCY = 200 HERTZ.

FIGURE 1. Loss factor versus thickness ratio.

Source: https://assist.dla.mil -- Downloaded: 202640-23T01:45Z
Check the source to verify that this is the current version before use.




NOTE:

1. THICKNESS RATIO OF INSULATION TO METAL IS 2:1.

FIGURE 2. Loss factor versus frequency.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:45Z
Check the source to verify that this is the current version before use.



NOTES:

1. THICKNESS RATIO OF INSULATION TO STEEL IS 2:1.
2. FREQUENCY = 200 HERTZ.

FIGURE 3. Loss factor versus temperature.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:45Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:45Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Test and Evaluation Command
ATTN: DRSTE-AD-M
Aberdeen Proving Ground, MD 21005

Source: https://assist.dla.mil -- Downloaded: 202640-23T01:45Z
Check the source to verify that this is the current version before use.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE

Source: https://assist.dla.mil -- Downloaded: 202640-23T01:45Z
Check the source to verify that this is the current version before use.