MIL-C-43247B
AMENDMENT-1
3 August 1977

MILITARY SPECIFICATION

CLOTH, KNITTED, NYLON, TUBULAR,

STRETCH TYPE

This amendment forms a part of Military Specification MIL-C-43247B, dated 16 September 1970, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 1

1.2: Delete in its entirety and substitute:

"1.2 Classification. The cloth shall be of the following classes, as specified (see 6.2):

Class 1 - 6.5 - 8.0 ounces per square yard (interlock)

Class 2 - 9.0 - 10.0 ounces per square yard (interlock)

Class 3 - 10.0 - 11.5 ounces per square yard (1 x 1 rib knit)".

PAGE 2

3.3.3, lines 1 and 2: Delete "natural (north sky) daylight or".

PAGE 3

Table I: Delete in its entirety and substitute:

"TABLE I. Physical requirements

Class	Knit type	Weight oz/sq. yd. (min)	Weight oz/sq. yd. (max)	Wales per inch (min)	Courses per inch (min)	Bursting strength pounds (min)	Elongation length (wales) (min)	Elongation length (wales) (max)	Percentage width (courses) (min)	Percentage width (courses) (max)
1	Interlock	6.5	8.0	30	35	165	65	130	115	180
2	Interlock	9.0	10.0	28	40	200	55	80	75	100
3	1 x 1 rib	10.0	11.5	15	28	-	60	90	200	300"

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:59Z
Check the source to verify that this is the current version before use.

3.6 and Table II: Delete in their entirety and substitute:

"3.6 Dimensional stability (classes 1 and 2). The finished cloth shall not shrink or elongate more than 3.0 percent (maximum) in the length (wales) or width (courses) direction, when tested as specified in 4.4."

Custodians:

Army - GL
Navy - SA
Air Force - 11

Preparing activity:

Army - GL

Project No. 8305-0163

Review activities:

Army - MD
Air Force - 99
DLA - CT

User activity:

Navy - SH

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:59Z
Check the source to verify that this is the current version before use.