INCH-POUND

MS16627C
14 March 2012
SUPERSEDING
MS16627B
14 May 1990

DETAIL SPECIFICATION SHEET

RING, RETAINING, INTERNAL, INVERTED
(TAPERED SECTION TYPE)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and procurement specification MIL-R-21248.




FIGURE 1. RING, RETAINING.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:59Z
Check the source to verify that this is the current version before use.

TABLE I DIMENSIONS.

ØH HOUSING (REF)		ØD FREE		E LARGE SECTION HEIGHT		J SMALL SECTION HEIGHT		T 1/ THICKNESS		ØG RECOMMENDED GROOVE (REF)		W WIDTH		K 3/	ØC 4/	R 5/ OF RETAINED PART (REF)	CH 5/
INCH	MM	BASIC	TOL.	BASIC	TOL.	BASIC	TOL.	BASIC	TOL.	BASIC	TOL.	BASIC	TOL.	MIN.		MAX.	MAX.
											±.002 .004						
.750	19.0	.808		.085	±.004	.042	±.004	.035		.796	FIM 2/	.040		.165	.560	.050	.031
.812	20.6	.877	+.010	.092		.044		.042		.862		.047	+.003	.180	.620	.054	.034
.875	22.2	.944	-.005	.099		.047		.042		.931	±.003	.047	-.000	.190	.650	.057	.036
.938	23.8	1.015		.106	±.005	.051	±.005	.042		1.000	.004	.047		.220	.700	.060	.038
1.000	25.4	1.081		.113		.054		.042		1.066	FIM 2/	.047		.235	.750	.064	.040
1.062	27.0	1.150		.120		.057		.050		1.130		.056		.220	.800	.069	.041
1.125	28.6	1.217		.123		.059		.050		1.197		.056		.245	.860	.070	.044
1.188	30.2	1.283	+.015	.126	±.006	.060	±.006	.050	±.002	1.262	±.004	.056		.260	.910	.071	.045
1.250	31.7	1.351	-.010	.129		.061		.050		1,330	.005	.056		.280	.970	.071	.045
1.312	33.3	1.418		.132		.063		.050		1.396	FIM 2/	.056		.290	1.020	.072	.045
1.375	34.9	1.486		.135		.065		.050		1.461		.056		.330	1.080	.074	.046
1.438	36.5	1.552		.144		.069		.050		1.528		.056	+.004	.350	1.130	.079	.050
1.500	38.1	1.622		.148		.070		.050		1.594		.056	-.000	.330	1.180	.081	.051
1.562	39.7	1.688		.158		.074		.062		1.658		.068		.360	1.210	.088	.055
1.625	41.3	1.756		.162		.077		.062		1.725		.068		.385	1.270	.090	.056
1.688	42.9	1.823		.166		.079		.062		1.792	±.005	.068		.405	1.320	.091	.057
1.750	44.4	1.891	+.020	.170		.082		.062		1.858	.005	.068		.420	1.380	.093	.058
1.875	47.6	2.025	-.013	.188	±.007	.090	±.007	.062	±.003	1.989	FIM 2/	.068		.440	1.470	.105	.066
2.000	50.8	2.160		.208		.100		.062		2.122		.068		.480	1.550	.118	.074
2.062	52.4	2.224	+.025 -.015	.218		.106		.078		2.186	±.006 .006 FIM 2/	.086	+.005 -.000	.485	1.590	.125	.078

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:59Z
Check the source to verify that this is the current version before use.

TABLE I. DIMENSIONS - Continued

ØH HOUSING (REF)		ØD FREE		E LARGE SECTION HEIGHT		J SMALL SECTION HEIGHT		T 1/ THICKNESS		ØG RECOMMENDED GROOVE (REF)		W WIDTH RECOMMENDED GROOVE (REF)		K 3/	ØC 4/	R 5/ OF RETAINED PART (REF)	CH 5/ OF RETAINED PART (REF)
INCH	MM	BASIC	TOL.	BASIC	TOL.	BASIC	TOL.	BASIC	TOL.	BASIC	TOL.	BASIC	TOL.	MIN.		MAX.	MAX.
2.125	54.0	2.295		.223		.108		.078		2.251		.086		.490	1.650	.128	.080
2.375	60.3	2.567	+.025 -.015	.243		.115		.078		2.517		.086		.550	1.860	.138	.086
2.438	61.9	2.634		.248		.117		.078		2.584		.086		.570	1.910	.141	.088
2.500	63.5	2.700		.254		.120		.078		2.648		.086		.590	1.960	.144	.090
2.625	66.7	2.840		.266		.128		.093		2.781		.103		.600	2.060	.150	.094
2.750	69.8	2.975		.278		.134		.093		2.914		.103		.630	2.160	.157	.098
2.812	71.4	3.063	+.030 -.020	.286	±.007	.139	±.007	.093	±.003	2.980		.103		.610	2.210	.162	.102
2.835	72.0	3.063		.286		.139		.093		3.006	±.006	.103	+.005	.670	2.230	.162	.102
3.000	76.2	3.245		.302		.143		.093		3.182	.006	.103	-.000	.705	2.360	.169	.106
3.156	80.2	3.408		.314		.149		.109		3.348	FIM 2/	.120		.760	2.500	.174	.109
3.346	85.0	3.611		.321		.155		.109		3.546		.120		.810	2.670	.177	.111
3.500	88.9	3.780		.324	±.008	.154	±.008	.109		3.710		.120		.840	2.820	.175	.110
3.562	90.5	3.850		.326		.155		.109		3.776		.120		.860	2.880	.175	.110
4.000	100.6	4.350		.338		.161		.109		4.240		.120		.930	3.290	.175	.110

1/ T - THICKNESS "T" APPLIES TO UNPLATED RINGS. FOR CORROSION RESISTANT STEEL AND PLATED RINGS, +.002 SHOULD BE ADDED TO THE MAXIMUM TOLERANCE, i.e. ±.002 SHOULD BE +.004/-.002.

2/ FIM - (FULL INDICATOR MOVEMENT) IS THE MAXIMUM ALLOWABLE DEVIATION OF CONCENTRICITY BETWEEN THE GROOVE AND THE HOUSING.

3/ K - MINIMUM DIMENSION WHEN THE RING IS PROPERLY SEATED IN THE GROOVE. (DESIGN REFERENCE DIMENSION).

4/ C - ACTUAL CLEARANCE DIAMETER WHEN THE RING IS SPRUNG INTO THE HOUSING, PRIOR TO INSTALLATION INTO THE GROOVE. (DESIGN REFERENCE DIMENSION).

5/ R AND CH - RADII OR CHAMFERS ALLOWABLE ON PARTS TO BE RETAINED BY THE RING. THRUST LOADS OF RINGS, RETAINING PARTS WITH CORNER RADII OR CHAMFERS ARE TABULATED ON PAGE 7.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:59Z
Check the source to verify that this is the current version before use.

REQUIREMENTS:

1. CLASSIFICATION: RETAINING RINGS FURNISHED UNDER THIS STANDARD SHALL BE TYPE 1, CLASS 3 OF THE PROCUREMENT SPECIFICATION.

2. MATERIAL: CARBON SPRING STEEL,GRADE 1060 THRU 1095 (UNS G10600 THRU G10950) IN ACCORDANCE WITH ASTM A568/A568M OR ASTM A684/A684M.
CORROSION RESISTANT STEEL IN ACCORDANCE WITH AMS 5520 (UNS S15700).
BERYLLIUM COPPER, ALLOY NUMBER 170 (UNS C17000) OR ALLOY NUMBER 172 (UNS C17200) IN ACCORDANCE WITH ASTM B194.

3. HARDNESS

TABLE II. HARDNESS.

ØHOUSING (REF)	CARBON STEEL	CORROSION RESISTANT STEEL	BERYLLIUM COPPER
.750	85.5 -88 HR15N (50-55 HRC EQUIV) 1/	82.5-86 HR15N (44-51 HRC EQUIV) 1/	79-82 HR15N (37-43 HRC EQUIV) 1/
.812 & .875	66.5 -71 HR30N (48-53 HRC EQUIV) 1/	63-69.5 HR30N (44-51 HRC EQUIV) 1/	56.5 -62 HR30N (37-43 HRC EQUIV) 1/
938 TO 1.500 INCL	52.5 -58.5 HR45N (48-53 HRC EQUIV) 1/	48-56 HR45N (41-51 HRC EQUIV) 1/	39.5-47 HR45N (37-43 HRC EQUIV) 1/
1.562 TO 2.000 INCL	46-51 HRC	44-51 HRC	37-43 HRC
2.062 TO 3.000 INCL	46-51 HRC	44-51 HRC	
3.156 TO 4.000 INCL	44-49 HRC	44-51 HRC	

1/ USE HIGHEST SCALE TO PROVIDE SECTION WIDTH EQUAL TO OR GREATER THAN 5 TIMES THE BRAILE IMPRESSION DIAMETER.

4. PROTECTIVE FINISH OR TREATMENT:

   a. CARBON STEEL – SHALL BE AS SPECIFIED (SEE TABLE III OR IV):

      1. CADMIUM PLATE IN ACCORDANCE WITH SAE AMS-QQ-P-416, TYPE II, CLASS 3 OR ASTM B696, TYPE II, CLASS 5.

      2. ZINC COAT IN ACCORDANCE WITH ASTM B633, TYPE II, CLASS Fe/Zn 5 OR ASTM B695, TYPE II, CLASS 5.

      3. PHOSPHATE COAT IN ACCORDANCE WITH MIL-DTL-16232, TYPE Z, CLASS II.

   b. CORROSION RESISTANT STEEL – SHALL BE CLEANED, DESCALED AND PASSIVATED IN ACCORDANCE WITH SAE AMS2700.

5. PART NUMBER: THE BASIC MS PART NUMBER IS FOLLOWED BY A DASH NUMBER TAKEN FROM TABLE III OR IV.

   EXAMPLE: MS16627-1100 IS THE PART NUMBER FOR A CARBON STEEL, CADMIUM PLATED, INTERNAL, INVERTED RETAINING RING FOR USE IN A 1.000 HOUSING DIAMETER.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:59Z
Check the source to verify that this is the current version before use.

TABLE III. DASH NUMBERS FOR MS16627.

ØH HOUSING (REF)	1/ CARBON STEEL CADMIUM PLATE	1/ CARBON STEEL ZINC COAT	1/ CARBON STEEL PHOSPHATE COAT	STEEL CORROSION RESISTANT	1/ BERYLLIUM COPPER
	DASH NO.	DASH NO.	DASH NO.	DASH NO.	DASH NO
.750	-1075	-2075	-3075	-4075	-5075
.812	-1081	-2081	-3081	-4081	-5081
.875	-1087	-2087	-3087	-4087	-5087
.938	-1093	-2093	-3093	-4093	-5093
1.000	-1100	-2100	-3100	-4100	-5100
1.062	-1106	-2106	-3106	-4106	-5106
1.125	-1112	-2112	-3112	-4112	-5112
1.188	-1118	-2118	-3118	-4118	-5118
1.250	-1125	-2125	-3125	-4125	-5125
1.312	-1131	-2131	-3131	-4131	-5131
1.375	-1137	-2137	-3137	-4137	-5137
1.438	-1143	-2143	-3143	-4143	-5143
1.500	-1150	-2150	-3150	-4150	-5150
1.562	-1156	-2156	-3156	-4156	-5156
1.625	-1162	-2162	-3162	-4162	-5162
1.688	-1168	-2168	-3168	-4168	-5168
1.750	-1175	-2175	-3175	-4175	-5175
1.875	-1187	-2187	-3187	-4187	-5187
2.000	-1200	-2200	-3200	-4200	-5200
2.062	-1206	-2206	-3206	-4206	
2.125	-1212	-2212	-3212	-4212	
2.375	-1237	-2237	-3237	-4237	
2.438	-1243	-2243	-3243	-4243	
2.500	-1250	-2250	-3250	-4250	
2.625	-1262	-2262	-3262	-4262	
2.750	-1275	-2275	-3275	-4275	
2.812	-1283 2/	-2283 2/	-3283 2/	-4283 2/	
2.835	-1283 2/	-2283 2/	-3283 2/	-4283 2/	
3.000	-1300	-2300	-3300	-4300	
3.156	-1315	-2315	-3315	-4315	
3.346	-1334	-2334	-3334	-4334	
3.500	-1350	-2350	-3350	-4350	
3.562	-1356	-2356	-3356	-4356	
4.000	-1400	-2400	-3400	-4400	

1/ SUBSTITUTE CORROSION RESISTANT STEEL WHEN USED IN FOOD PROCESSING MACHINERY, OR IN FUEL OR LUBRICATION SYSTEMS, OR WHEN USED AT TEMPERATURES OVER 450°F (233°C).

2/ SAME DASH NUMBERS SUITABLE FOR EITHER HOUSING DIAMTER (INCH OR MM).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:59Z
Check the source to verify that this is the current version before use.

TABLE IV. SUBSTITUTION TABLE (CROSS REFERENCE OF PART NUMBERS).

	INACTIVE	SUBSTITUTE	SUBSTITUTE	SUBSTITUTE
ØH HOUSING (REF)	CARBON STEEL	1/ CARBON STEEL CADMIUM PLATE	1/ CARBON STEEL ZINC COAT	1/ CARBON STEEL PHOSPHATE COAT
	MS16627	MS16627	MS16627	MS16627
.750	-75	-1075	-2075	-3075
.812	-81	-1081	-2081	-3081
.875	-87	-1087	-2087	-3087
.938	-93	-1093	-2093	-3093
1.000	-100	-1100	-2100	-3100
1.062	-106	-1106	-2106	-3106
1.125	-112	-1112	-2112	-3112
1.188	-118	-1118	-2118	-3118
1.250	-125	-1125	-2125	-3125
1.312	-131	-1131	-2131	-3131
1.375	-137	-1137	-2137	-3137
1.438	-143	-1143	-2143	-3143
1.500	-150	-1150	-2150	-3150
1.562	-156	-1156	-2156	-3156
1.625	-162	-1162	-2162	-3162
1.688	-168	-1168	-2168	-3168
1.750	-175	-1175	-2175	-3175
1.875	-187	-1187	-2187	-3187
2.000	-200	-1200	-2200	-3200
2.062	-206	-1206	-2206	-3206
2.125	-212	-1212	-2212	-3212
2.375	-237	-1237	-2237	-3237
2.438	-243	-1243	-2243	-3243
2.500	-250	-1250	-2250	-3250
2.625	-262	-1262	-2262	-3262
2.750	-275	-1275	-2275	-3275
2.812	-281	-1283	-2283	-3283
2.835	-283	-1283	-2283	-3283
3.000	-300	-1300	-2300	-3300
3.156	-315	-1315	-2315	-3315
3.346	-334	-1334	-2334	-3334
3.500	-350	-1350	-2350	-3350
3.562	-356	-1356	-2356	-3356

1/ SUBSTITUTE CORROSION RESISTANT STEEL WHEN USED IN FOOD PROCESSING MACHINERY, OR IN FUEL OR LUBRICATION SYSTEMS, OR WHEN USED AT TEMPERATURES OVER 450°F (233°C).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:59Z
Check the source to verify that this is the current version before use.

NOTES:

1. DIMENSIONS IN INCHES, UNLESS OTHERWISE SPECIFIED.

2. IN THE EVENT OF A CONFLICT BETWEEN THE TEXT OF THIS STANDARD AND THE REFERENCES CITED HEREIN, THE TEXT OF THIS STANDARD SHALL TAKE PRECEDENCE.

3. RECOMMENDED DESIGN LIMITATIONS AND USAGE:

(a) INTENDED USE- TO PROVIDE UNIFORM PROTRUDING SHOULDERS FOR POSITIONING AND RETAINING MACHINE COMPONENTS IN HOUSINGS (BORES). TAPERED DESIGN PRINCIPLE PERMITS RINGS TO MAINTAIN PRACTICTICALLY CONSTANT CIRCULARITY, AND FIT SECURELY AGAINST BOTTOM OF GROOVE. ESPECIALLY SUITED FOR LOCATING AND RETAINING MACHINE PARTS HAVING CURVED ABUTTING SURFACES. THE USE OF THE FOLLOWING FORMULAS ARE BASED ON THE FACT THAT THE RING MATERIAL WILL NOT FAIL IN COMPRESSION.

LIMITATION ON USE – THE FOLLOWING FORMULAS ARE NOT TO BE USED FOR BRITTLE MATERIALS SUCH AS CAST IRON, ETC.

WARNING: RINGS SHOULD NOT BE EXCESSIVELY CONTRACTED DURING INSTALLATION SINCE THIS WILL LEAD TO RING FAILURE. IF RING HAS PLAY BETWEEN THE GROOVE DIAMETER AND THE OUTSIDE RING DIAMETER THIS INDICATES THAT THE RING HAS BEEN EXCESSIVELY CONTRACTED, (PROVIDING THE GROOVE DIAMETER HAS BEEN MACHINED TO RECOMMENDED DIMENSIONS).

(b) ALLOWABLE THRUST LOAD CAPACITY OF THE RINGS. (ABUTTING COMPONENTS TO HAVE SHARP CORNERS).

$$P = \frac{2}{3}\frac{\pi HTX}{F}$$

WHERE:

P = ALLOWABLE THRUST LOAD (POUNDS)
H = HOUSING DIAMETER (INCHES)
T = RING, THICKNESS (INCHES)
X = ULTIMATE SHEAR STRENGTH OF THE RING MATERIAL (PSI) 1/
F = FACTOR OF SAFETY

A FACTOR OF SAFETY, F=4, IS RECOMMENDED, SINCE THE RING UNDER LOAD IS SUBJECTED NOT ONLY TO PURE SHEAR STRESSES BUT ALSO TO BENDING STRESSES

(c) ALLOWABLE LOAD CAPACITY OF GROOVE WALL =

$$P = \frac{1}{2}\frac{\pi HdY}{F}.$$

WHERE:

P = ALLOWABLE COMPRESSION LOAD (POUNDS)
H = HOUSING DIAMETER (INCHES)
d = GROOVE DEPTH (INCHES)
Y = YIELD STRENGTH IN COMPRESSION OF THE GROOVE MATERIAL (PSI)
F = FACTOR OF SAFETY

TO INSURE A SAFE WORKING LOAD A SAFETY FACTOR, F = 2, IS RECOMMENDED

(d) MINIMUM DISTANCE BETWEEN OUTER GROOVE WALL AND END OF HOUSING =

$$Z = 3d$$

WHERE:

Z = MINIMUM DISTANCE BETWEEN OUTER GROOVE WALL AND END OF HOUSING (INCHES)
d = GROOVE DEPTH (INCHES)

(e) DIFFERENTIAL ROTATION=

THE CONDITIONS UNDER WHICH A RETAINING RING MAY BE USED WHEN ADJACENT PARTS ROTATE RELATIVE TO IT, FALL INTO TWO CATEGORIES:

(1) WHERE NO THRUST IS EXERTED BY ADJACENT PART: IN THIS CASE, DIFFERENTIAL ROTATION OF RING AND ADJACENT PART CREATES NO ELEMENT OF RISK IN THE APPLICATION OF THE RINGS BECAUSE NO FRICTIONAL TORQUE IS EXERTED BY THE MACHINE PART ON THE RING.

(2) CONSIDERATION MUST BE GIVEN TO THE MAGNITUDE OF THE THRUST INVOLVED. THE FRICTION MOMENT MAY NOT EXCEED THE BENDING MOMENT, WHICH THE RING CAN TOLERATE WITHOUT RELEASING ITS PRESSURE AGAINST THE BOTTOM OF THE GROOVE, FORMULATED AS FOLLOWS:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:59Z
Check the source to verify that this is the current version before use.

$$fPN \leq \frac{sTE^2}{18}$$ OR $$P \leq \frac{sTE^2}{f18N}$$

WHERE:

P = ALLOWABLE THRUST LOAD EXERTED BY ADJACENT PART (POUNDS)
f = COEFFICIENT OF FRICTION
s = WORKING STRESS OF RING UNDER MAXIMUM CONTRACTION (PSI) 2/
T = RING THICKNESS (INCHES)
E = GREATEST WIDTH SECTION OF RING (INCHES)
N = NEUTRAL RING DIAMETER (INCHES) = FREE DIAMETER MINUS 3/4 E DIMENSION

IN SUCH CASES WHERE DIFFERENTIAL ROTATION OCCURS, THE CALCULATION SHOULD BE BASED ON THE MAXIMUM POSSIBLE VALUE OF THE COEFFICIENT OF FRICTION.

1/ X = 150,000 PSI ULTIMATE SHEAR STRENGTH FOR RINGS OF CARBON STEEL OR CORROSION RESISTANT STEEL.
X = 110,000 PSI ULTIMATE SHEAR STRENGTH FOR RINGS OF BERYLLIUM COPPER.
2/ S = 250,000 PSI WORKING STRESS FOR RINGS OF CARBON STEEL OR CORROSION RESISTANT STEEL.
S = 180,000 PSI WORKING STRESS FOR RINGS OF BERYLLIUM COPPER.

(f) IMPACT CAPACITY OF RING OR GROOVE WALL=

$$I_R = \frac{PT}{2}$$ FOR THE RING (INCH POUNDS) ABUTTING COMPONENTS TO HAVE SHARP CORNERS

$$I_G = \frac{Pd}{2}$$ FOR THE GROOVE (INCH POUNDS).

WHERE:

P = ALLOWABLE THRUST LOAD OF RING OR GROOVE (POUNDS)
T = RING THICKNESS (INCHES)
I_G = IMPACT CAPACITY OF GROOVE WALL (INCH POUNDS)
d = GROOVE DEPTH (INCHES)
I_R = IMPACT CAPACITY OF RING (INCH POUNDS)

(g) LOAD CAPACITY, WITH THE RETAINED PART RADIUSED OR CHAMFERED =

WHEN THE RADIUS OR CHAMFER OF THE RETAINED PART DOES NOT EXCEED THE MAXIMUM RADIUS ALLOWED FOR THE BOTIOM OF THE RING GROOVE, THE LESSER LOAD CAPACITY COMPUTED FROM THE FORMULAS ON PAGE 7 WILL APPLY. THE CORNER RADII AND CHAMFERS LISTED ON TABLE I WERE CHOSEN AS LARGE AS POSSIBLE FOR THE RING SIZES INVOLVED AND ARE RELATED TO THE MAXIMUM THRUST LOADS LISTED IN TABLE V.

IF THE CORNER RADII OR CHAMFERS ARE SMALLER THAN THOSE LISTED, THEN THE THRUST LOADS INCREASE PROPORTIONALLY, IN ACCORDANCE WITH THE FOLLOWING FORMULAS:

$$P^1 = \frac{PCH}{CH^1}$$ OR $$P^1 = \frac{PR}{R^1}$$

WHERE:

P^1 = NEW ALLOWABLE THRUST LOAD
P = LISTED ALLOWABLE THRUST LOAD
CH^1 = NEW (SMALLER) CHAMFER
CH = LISTED CHAMFER
R^1 = NEW (SMALLER) CORNER RADIUS
R = LISTED CORNER RADIUS

LIMIT LOADS LISTED IN TABLE V ARE BASED ON RINGS OF STEEL (WORKING STRESS = 250,000 PSI) AND OF BERYLLIUM COPPER (WORKING STRESS = 180,000 PSI). IF THE ALLOWABLE GROOVE CAPACITY LOADS, AS CALCULATED BY USING THE FORMULA ON PAGE 7 ARE LESS THEN THEY SHOULD BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:59Z
Check the source to verify that this is the current version before use.

TABLE V. LIMIT LOADS.

NOMINAL RING SIZE		ALLOWABLE THRUST LOAD FOR RING ASSEMBLIES WITH PARTS HAVING MAXIMUM CORNER RADII OR CHAMFERS.	
FROM	TO	CARBON STEEL OR CORROSION RESISTANT STEEL	BERYLLIUM COPPER
.750		850 LB	610 LB
.812	1.000	1250 LB	900 LB
1.063	1.500	1800 LB	1300 LB
1.562	2.000	2900 LB	2000 LB
2.062	2.500	4600 LB	
2.625	3.000	6700 LB	
3.156	4.000	9000 LB	

4. CHANGES FROM PREVIOUS ISSUE. MARGINAL NOTATIONS ARE NOT USED IN THIS REVISION TO IDENTIFY CHANGES WITH RESPECT TO THE PREVIOUS ISSUE DUE TO THE EXTENT OF THE CHANGES.

MILITARY INTEREST

Custodians:
Army - AR
Navy - OS
Air Force - 99

Preparing activity:
DLA - IS

(Project 5325-2011-008)

Review activities:
Army – AT, AV, CR4, MI

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:59Z
Check the source to verify that this is the current version before use.